INCH-POUND

MIL-C-24640/11C
26 June 1995
SUPERSEDING
MIL-C-24640/11B
31 July 1989

MILITARY SPECIFICATION SHEET

CABLE, ELECTRIC, 600 VOLTS, LIGHT WEIGHT, MULTI TRIAD AWG 18, TYPE 3XS (INCLUDING VARIATION TYPE 3XSA)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation: MIL-C-24640.

CONSTRUCTION
(Non-Watertight)

FIRST - 19 strand copper conductor in accordance with ASTM B-286, tinned strands in accordance with ASTM B-33. AWG size 18 maximum diameter 0.052 inch.

SECOND - Component wires shall be MIL-W-81044/12 and shall be tested in accordance with the component wire ratings and requirements listed in this slash sheet. Quality conformance testing shall be in accordance with Table VI of MIL-C-24640.

THIRD - Three conductors, one black, one white and one red, twisted together. The pitch shall be 2" ± ½" (inch).

FOURTH - Binder tape applied helically over each triad with overlap, at manufacturer's option.

FIFTH - Braided shield of # 38 AWG tin coated copper strands. Braid coverage shall be no less than 90% determined in accordance with MIL-C-27500.

SIXTH - Shield insulation of two polyester tapes or polyester tape and extruded jacket. Identification codes applied using Method 2.

AMSC N/A FSC 6145

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited

Source: https://assist.dla.mil -- Downloaded: 202610-19T23:43Z
Check the source to verify that this is the current version before use.

SEVENTH - The required number of shielded, twisted triads shall be cabled together. Cabling sequence shall be consecutive, starting with number 1 from center outward. Fillers may be used as necessary, to form a round cable.

Eighth - Binder tape applied helically with overlap.

CONSTRUCTION VARIANT FOR TYPE 3XS

NINTH - Crosslinked polyolefin jacket. (See Table I for thickness).

CONSTRUCTION VARIANT FOR TYPE 3XSA

NINTH - Crosslinked polyolefin jacket. (See Table II for thickness).

TENTH - Braided metal armor, dimensions in accordance with Table II.

* TABLE I. Construction details - unarmored.

PIN M24640/11	Type number	Number of triads	Jacket thickness (inch) (minimum)	Cable diameter (inch) min	Cable diameter (inch) max	Cable weight (pounds per 1000 feet) (max)
-01UN	3XS-7	3	0.044	0.601	0.647	315.0

TABLE II. Construction details - armored.

PIN M24640/11	Type number	Number of triads	Jacket thickness (inch) (minimum)	Cable diameter (inch) min	Cable diameter (inch) max	Cable weight (pounds per 1000 feet) (max)
-01AN	3XSA-7	7	0.044	0.651	0.697	350.0

REQUIREMENTS:

Qualification required.
Construction details: See tables I, and II.

Component wire:

For the component wire the following additional tests shall be applicable in accordance with MIL-W-81044:

Source: https://assist.dla.mil -- Downloaded: 202610-19T23:43Z
Check the source to verify that this is the current version before use.

WIRE, RATINGS AND ADDITIONAL REQUIREMENTS:

Temperature rating: 150°C (302°F) maximum conductor temperature
Voltage rating: 600 volts (rms) at sea level.
Accelerated aging: Oven temperature, 300± 2°C (572± 3.6°F) for 6 hours.
Blocking: 150± 2°C (302± 3.6°F)
Flammability: 30 seconds (max); 3.0 inches (max); no flaming of tissue paper.
Humidity resistance: 5000 megohms for 1000 feet, minimum insulation resistance after humidity exposure.
Impulse dielectric test:
  Primary insulation (when tested in lieu of spark test): 6.0 kilovolts (peak) 100 percent test.
  Finished wire: 8.0 kilovolts (peak), or 3 Khz spark test 5.5KV, 100 percent test.
Insulation resistance: 5000 megohms for 1000 feet (min).
Life cycle: Oven temperature, 200± 2°C (392± 3.6°F) for 168 hours.
Physical properties of primary insulation:
  Tensile strength, 2500 lb/in^2 (min).
  Elongation, 150 percent (min).
Shrinkage: 0.125 inch maximum at 300± 2°C (572± 3.6°F).
Spark test primary insulation: 1500 volts (rms), 60 Hz, 100 percent test.
Surface resistance: 500 megohms inches (min), initial and final readings.
Thermal shock: Oven temperature, 150± 2°C (302± 3.6°F).
  Maximum change in measurement: 0.060 inch.
Wet dielectric test: 2500 volts (rms).
Wrap test: Mandrel wrap test required.

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor Resistance - ohms/1000 feet at 25°C, maximum	6.67
Voltage withstand - volts, root mean square, minimum	
* Conductor to conductor and shield	1000
* Component shield to shield	200
* Insulation resistance - megohms/1000 feet, minimum	
Conductor to conductor	2500
Shield to shield (component shield only)	100
Shield to shield (component shield to overall shield)	Not applicable
Conductor and shield continuity	No failure
Jacket flaws	Not applicable
Group A:	
Visual and dimensional	No failure
Capacitance:	
Mutual capacitance - at 1 MHz, picofarads/foot (pF/ft), maximum	55
Capacitance unbalance - percent, maximum	15

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

	Characteristic impedance - at 1 MHz, ohms	Not applicable
	Watertightness (see table XI of MIL-C-24640 for limits of water leakage)	Not applicable
	Weight	No failure
	Group B:	
	Cold bending	No failure
	Drip	Not applicable
*	Cross-link proof test (percent maximum)	
	Jacket	50
	Tear - pounds per inch thickness, minimum	35
	Physicals (unaged)	
	Jacket	
	Tensile strength - lb/in^2, minimum	1300
	Elongation - percent, minimum	160
	Attenuation - at 3 MHz, dB/100 feet, maximum	Not applicable
	Gas flame (1 hour)	Not applicable
	Group C:	
	Physicals (aged)	
	Jacket	
	Air oven	
	Tensile strength - percent of unaged, minimum	60
	Elongation - percent of unaged, minimum	60
	Hot oil immersion	
*	Tensile strength - percent of unaged, minimum	50
*	Elongation - percent of unaged minimum	50
*	Permanence of printing (conductor) - cycles, minimum	25
*	Permanence of printing (jacket) - cycles, minimum	125
	Armor - (type 3XSA only) conformance to material, construction and coverage	No failure
	Shield - conformance to material, construction and coverage	No failure
	Heat distortion - percent of unaged, maximum	30
*	Cable sealant removability	Not applicable
	Shrinkage	No failure
	Mutual inductance - dB/1000 feet, maximum	Not applicable
	Surface transfer impedance	
	Milliohms per meter, maximum	Not applicable
	EMP response, dB, minimum	Not applicable
	Pulse response time - ms/500 feet	
	Rise time, maximum	Not applicable
	Decay time, maximum	Not applicable
*	**Group D**	
	Flame propagation	No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B, C and D, plus the following:

Aging and compatibility (cable)	No failure
Acid gas equivalent - percent, maximum	
Jacket	2
Fillers	2
Insulation	18
Halogen content - percent, maximum	
Jacket	0.2
Fillers	0.2
Immersion	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged minimum	50
* Smoke index, maximum	
Jacket	25
Fillers	45
Insulation	10
Toxicity index, maximum	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - (type A) hardness, minimum	80
Weathering (jacket)	No failure
Fungus Resistance	No failure
Abrasion resistance	No failure
Gas Flame (3 hour)	Not applicable
Component wire	No failure

Unit ordering length: 500 feet nominal.

NOTE: The margins of this specification are marked with asterisks to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - MI
Navy - SH

Review Activities:
Army - AV, CR, ER, MB, AR, AL
Navy - EC, CG
DLA - IS

Preparing Activity:
Navy - SH

Agent:
DLA-IS

(Project No. 6145-2105-11)

Source: https://assist.dla.mil Downloaded: 2026-10-19T23:43Z
Check the source to verify that this is the current version before use.