INCH-POUND

MIL-DTL-24640/17D
22 August 2002
SUPERSEDING
MIL-C-24640/17C
26 June 1995

DETAIL SPECIFICATION SHEET

CABLE, ELECTRIC, 600 VOLTS, LIGHT-WEIGHT, MULTI-PAIR, AWG 26, TYPE 2XOW

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of MIL-DTL-24640 listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation.

Construction (Watertight)

First - 7-strand, tin-coated copper conductor, AWG size and dimensions in accordance with Table I.

Second - Insulation material and basic construction requirements shall be in accordance with MIL-W-81044/12 and tested in accordance with the component wire ratings and requirements listed on this slash sheet. Quality conformance testing shall be in accordance with MIL-W-81044, prior to cabling.

Third - Two conductors twisted together. Identification codes applied using Method 3 (telephone color code) or twisted pair identification, one black and one white conductor, applied using method 6. Pair lay length in accordance with Table III.

Fourth - The required number of twisted pairs shall be cabled together. Cabling sequence shall be consecutive, starting with number 1 from center outward. Fillers may be used as necessary, to form a round cable.

Fifth - Binder tape applied helically with overlap.

Sixth - Braided shield, tin coated copper strands. Braid must be constructed to meet Surface Transfer Impedance requirements as listed herein.

Seventh - Binder tape applied helically with overlap.

Eighth - Cross-linked polyolefin jacket. (See Table II for thickness).

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.

TABLE I. Component wire details

Watertight conductor			Finished wire			
Wire size (AWG)	Stranding (no. x AWG)	Diameter nominal (inches)	Diameter (inches)	Test load life cycle accelerated aging tests (lbs. ± 3%)	Low temp. at -40° C	
					Mandrel diameter (inches)	Test load (lbs)
26	7 x 34	0.019	0.034 ± 0.003	0.125	0.50	0.50

TABLE II. Construction details.

PIN M24640/17	Type number	Number of pairs	Diameter over shield (inch) (nom)	Jacket thickness (inch) (min)	Cable diameter (inch) min	max	Cable weight (pounds per 1000 feet) (max)
-01UO	2XOW-6	6	0.229	0.038	0.336	0.363	181.6
-02UO	2XOW-18	18	.374	.041	.468	.504	201.0
-03UO	2XOW-24	24	.447	.044	.546	.588	266.0
-04UO	2XOW-42	42	.567	.044	.646	.686	380.0
-05UO	2XOW-60	60	.661	.047	.744	.802	485.0
-06UO	2XOW-77	77	.770	.047	.840	.906	615.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.

TABLE III. Pair lay.[1/]

Pair no.	Pair lay (inches)	Pair no.	Pair lay (inches)	Pair no.	Pair lay (inches)
1	1.5	27	1.0	53	2.5
2	1.0	28	2.0	54	3.0
3	2.0	29	3.0	55	4.5
4	3.0	30	4.5	56	5.5
5	4.5	31	1.0	57	1.0
6	1.0	32	2.0	58	1.5
7	2.0	33	3.0	59	2.0
8	3.0	34	4.5	60	2.5
9	1.5	35	1.0	61	3.0
10	2.5	36	2.0	62	4.5
11	5.5	37	3.0	63	5.5
12	1.5	38	4.5	64	1.0
13	2.5	39	1.0	65	1.5
14	3.7	40	2.0	66	2.0
15	5.5	41	3.0	67	2.5
16	1.5	42	4.5	68	3.0
17	2.5	43	1.0	69	4.5
18	3.7	44	1.5	70	5.5
19	1.5	45	2.0	71	1.0
20	2.5	46	2.5	72	1.5
21	3.7	47	3.0	73	2.0
22	5.5	48	4.5	74	2.5
23	1.0	49	5.5	75	3.0
24	2.0	50	1.0	76	4.5
25	3.0	51	1.5	77	5.5
26	4.5	52	2.0		

1/ All lays are left handed.

TABLE IV. Assembly.

		Assembly			
Type Number	Core	Layer 1	Layer 2	Layer 3	Layer 4
2XOW-6	- - -	Pairs 1-6			
2XOW-18	Pair 1	Pairs 2-6	Pairs 7-18		
2XOW-24	Pairs 1-2	Pairs 3-10	Pairs 11-24		
2XOW-42	- - -	Pairs 1-8	Pairs 9-22	Pairs 23-42	
2XOW-60	Pair 1	Pairs 2-7	Pairs 8-19	Pairs 20-36	Pairs 37-60
2XOW-77	Pairs 1-3	Pairs 4-12	Pairs 13-27	Pairs 28-49	Pairs 50-77

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

Qualification required.
Construction details: See Tables I, II, III and IV.

Component wire: The component wire shall be per MIL-W-81044 and shall be tested in accordance with the following wire ratings and additional requirements.

Temperature rating: 135°C (275°F) maximum conductor temperature
Voltage rating: 600 volts (rms) at sea level.
Accelerated aging: Oven temperature, 250 ± 2°C (482 ± 3.6°F) for 6 hours.
Low temp.-cold bend: -40°C (-40°F) for 4 hours
Blocking: 150 ± 2°C (302 ± 3.6°F)
Color: In accordance with MIL-STD-104, class 1; white preferred
Flammability: 30 seconds (max); 3.0 inches (max); no flaming of tissue paper.
Humidity resistance: 5000 megohms for 1000 feet, minimum insulation resistance after humidity exposure.
Identification, striping or banding durability: 125 cycles (250 strokes) (min), 500 gram weight.
Impulse dielectric test:
    Primary insulation (when tested in lieu of spark test):
        6.0 kilovolts (peak) 100 percent test.
    Finished wire: 8.0 kilovolts (peak), or 3 kHz spark test
    5.5 kV, 100 percent test.
Insulation resistance: 5000 megohms for 1000 feet (min).
Life cycle: Oven temperature, 200 ± 2°C (392 ± 3.6°F) for 120 hours.
Physical properties of primary insulation:
    Tensile strength, 2500 lb/in^2 (min).
    Elongation, 150 percent (min).
Shrinkage: 0.125 inch maximum at 250 ± 2°C (482 ± 2°F).
Spark test primary insulation: 1500 volts (rms), 60 Hz or 3 kHz, 100 percent test.
Surface resistance: 500 megohms inches (min), initial and final readings.
Thermal shock: Oven temperature, 150 ± 2°C (302 ± 3.6°F).
    Maximum change in measurement: 0.060 inch.
Wet dielectric test: 2500 volts (rms).
Wrap test: Mandrel wrap test required.

EXAMINATION AND TESTS:

Basic electrical:	Requirements:
Conductor Resistance - ohms/1000 feet at 25°C, maximum	46.01
Voltage withstand - volts, root mean square, minimum	
Conductor to conductor and shield	1000
Component Shield to Component Shield	NA
Component Shield to overall shield	NA
Insulation resistance - megohms-1000 feet, minimum	

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.

Conductor to conductor and shield 2500
Shield to shield (component shield only) 100
Shield to shield (component shield to overall shield) 100
Conductor and shield continuity ..... No failure
Jacket flaws ..... No failure

Group A:
Visual and dimensional ..... No failure
Capacitance:
Mutual capacitance - at 1 MHz, picofarads/foot (pF/ft), maximum 60
Capacitance unbalance - percent, maximum 15
Characteristic impedance - at 1 MHz, ohms ..... 70 min, 105 max
Watertightness (see Table IX of MIL-DTL-24640 for limits of water leakage) ..... No failure
Weight ..... No failure

Group B:
Cold bending ..... No failure
Drip ..... No failure
Cross link proof test (percent maximum)
Jacket 50
Tear - pounds per inch thickness, minimum 35
Physicals (unaged)
Jacket
Tensile strength - lb/in^2, minimum 1300
Elongation - percent, minimum 160
Attenuation - at 3 MHz, dB/100 feet, maximum 3
Gas flame (1 hour) ..... Not applicable

Group C:
Physicals (aged)
Jacket
Air oven
Tensile strength - percent of unaged, minimum 60
Elongation - percent of unaged, minimum 60
Permanence of printing (conductor) - Method 6 only cycles, minimum 25
Permanence of printing (jacket) - cycles, minimum 125
Shield - conformance to material, construction and coverage ..... No failure
Heat distortion - percent of unaged, maximum 30
Cable sealant removability ..... No failure
Shrinkage ..... No failure
Mutual inductance - dB/1000 feet, maximum ..... Not applicable
Surface transfer impedance
Milliohms per meter, maximum 700
EMP response, dB, minimum 60
Pulse response time - ms/500 feet

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.

Rise time, maximum .....Not applicable
Decay time, maximum .....Not applicable

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B, C and D, plus the following:

Aging and compatibility (cable) .....No failure
Acid gas equivalent - percent, maximum
Jacket 2
Fillers 2
Insulation 18
Halogen content - percent, maximum
Jacket 0.2
Fillers 0.2
Flame propagation .....No failure
Hot oil immersion
Tensile strength - percent of unaged, minimum 50
Elongation - percent of unaged, minimum 50
Smoke index, maximum
Jacket 25
Fillers 45
Insulation 10
Toxicity index, maximum
Jacket 5
Fillers 5
Insulation 1.5
Durometer (jacket) - (type A) hardness, minimum.....80
Weathering (jacket).....No failure
Fungus Resistance.....No failure
Abrasion resistance .....No failure
Gas Flame (3 hour) .....Not applicable
Component wire.....No failure

Unit ordering length: 6 & 18 500 feet nominal.
24 - 77 250 feet nominal.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.

Custodians:
Army - MI
Navy - SH

Preparing Activity:
Navy - SH
(Project 6145-2307-017)

Review Activities:
Army - AR, AV, CR, CR4
Navy - CG, EC
DLA - IS

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.