INCH-POUND

MIL-DTL-24640/18D
22 August 2002
SUPERSEDING
MIL-C-24640/18C
26 June 1995

DETAIL SPECIFICATION SHEET

CABLE, ELECTRIC, 600 VOLTS, LIGHT-WEIGHT, MULTI-TRIAD, AWG 18, TYPE 3XSW (INCLUDING VARIATION TYPE 3XSOW)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of MIL-DTL-24640 listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation.

Construction (Watertight)

First – 7-strand, tin-coated copper conductor, AWG size and dimensions in accordance with Table I.

Second - Insulation material and basic construction requirements shall be in accordance with MIL-W-81044/12 and tested in accordance with the component wire ratings and requirements listed on this slash sheet. Quality conformance testing shall be in accordance with MIL-W-81044, prior to cabling.

Third - Three conductors, one black, one white and one red, twisted together. The pitch shall be 2 ± ¼ inch.

Fourth - Binder tape applied helically over each triad with overlap, at manufacturer's option.

Fifth - Braided shield of No. 38 AWG tin coated copper strands. Braid coverage shall be no less than 90 percent determined in accordance with WC 27500.

Sixth - Shield insulation of two polyester tapes or polyester tape and extruded jacket. Identification codes applied using Method 2.

Seventh - The required number of shielded, twisted triads shall be cabled together. Cabling sequence shall be consecutive, starting with number 1 from center outward. Fillers may be used as necessary, to form a round cable.

Eighth - Binder tape applied helically with overlap.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.

CONSTRUCTION VARIANT FOR TYPE 3XSW

Ninth - Crosslinked polyolefin jacket. (See Table II for thickness).

CONSTRUCTION VARIANT FOR TYPE 3XSOW

Ninth - Braided shield, tin coated copper strands. Braid must be constructed to meet Surface Transfer Impedance requirements as listed herein.
Tenth - Binder tape applied helically with overlap.
Eleventh - Crosslinked polyolefin jacket. (See Table III for thickness).

TABLE I. Component wire details.

Watertight conductor			Finished wire			
Wire size (AWG)	Stranding (no. x AWG)	Diameter nominal (inches)	Diameter (inches)	Test load life cycle accelerated aging tests (lbs. ± 3%)	Low temp. at -40° C.	
					Mandrel diameter (inches)	Test load (lbs)
18	7 x 26	0.048	0.065 ± 0.003	0.250	1.0	1.0

TABLE II. Construction details.

PIN M24640/18	Type number	Number of triads	Jacket thickness (inch) (min)	Cable diameter (inch) (min)	(max)	Cable weight (pounds per 1000 feet) (max)
-01UN	3XSW-3	3	0.041	0.472	0.508	205.0
-02UN	3XSW-7	7	.044	.620	.668	390.0
-03UN	3XSW-10	10	.047	.803	.865	625.0
-04UN	3XSW-14	14	.047	.873	.941	775.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.

TABLE III. Construction details - overall shield.

PIN M24640/18	Type number	Number of triads	Diameter over shield (inch) (nom)	Jacket thickness (inch) (min)	Cable diameter (inch) (min)	(max)	Cable weight (pounds per 1000 feet) (max)
-01UO	3XSOW-3	3	0.398	0.044	0.519	0.559	271.0
-02UO	3XSOW-7	7	.547	.044	.659	.711	475.0
-03UO	3XSOW-10	10	.721	.047	.835	.901	730.0
-04UO	3XSOW-14	14	.800	.047	.898	.968	880.0
-05UO	3XSOW-19	19	.909	.050	1.010	1.090	1150.0
-06UO	3XSOW-24	24	1.080	.057	1.200	1.300	1607.0

REQUIREMENTS:

Qualification required.
Construction details: See Tables I, II, and III

Component wire: The component wire shall be per MIL-W-81044 and shall be tested in accordance with the following wire ratings and additional requirements.
Temperature rating: 135°C (275°F) maximum conductor temperature.
Voltage rating: 600 volts (rms) at sea level.
Accelerated aging: Oven temperature, 250 ± 2°C (482 ± 3.6°F) for 6 hours.
Low temp.-cold bend: -40°C (-40°F) for 4 hours
Blocking: 150 ± 2°C (302 ± 3.6°F).
Color: In accordance with MIL-STD-104, class 1.
Flammability: 30 seconds (max); 3.0 inches (max); no flaming of tissue paper.
Humidity resistance: 5000 megohms for 1000 feet, minimum insulation resistance after humidity exposure.
Identification, striping or banding durability: 125 cycles (250 strokes) (min), 500 gram weight.
Impulse dielectric test:
Primary insulation (when tested in lieu of spark test):
6.0 kilovolts (peak) 100 percent test.
Finished wire: 8.0 kilovolts (peak), or 3 kHz spark test
5.5 kV, 100 percent test.
Insulation resistance: 5000 megohms for 1000 feet (min).
Life cycle: Oven temperature, 200 ± 2°C (392 ± 3.6°F) for 120 hours.
Physical properties of primary insulation:
Tensile strength, 2500 lb/in^2 (min).
Elongation, 150 percent (min).
Shrinkage: 0.125 inch maximum at 250 ± 2°C (482 ± 2°F).
Spark test primary insulation: 1500 volts (rms), 60 Hz or 3 kHz, 100 percent test.
Surface resistance: 500 megohms inches (min), initial and final readings.
Thermal shock: Oven temperature, 150 ± 2°C (302 ± 3.6°F).
Maximum change in measurement: 0.060 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.

Wet dielectric test: 2500 volts (rms).
Wrap test: Mandrel wrap test required.

EXAMINATION AND TESTS:

Basic electrical:	Requirements:
Conductor Resistance - ohms/1000 feet at 25°C, maximum	7.11
Voltage withstand - volts, root mean square, minimum	
Conductor to conductor and shield	1000
Component Shield to Component Shield	200
Component Shield to overall shield (3XSOW only)	500
Insulation resistance - megohms-1000 feet, minimum	
Conductor to conductor and shield	2500
Shield to shield (component shield only)	100
Shield to shield (component shield to overall shield) (Type 3XSOW only)	100
Conductor and shield continuity	No failure
Jacket flaws (type 3XSOW only)	No failure

Group A:	
Visual and dimensional	No failure
Capacitance:	
Mutual capacitance - at 1 MHz, picofarads/foot (pF/ft), maximum	65
Capacitance unbalance - percent, maximum	15
Characteristic impedance - at 1 MHz, ohms	Not applicable
Watertightness (see Table IX of MIL-DTL-24640 for limits of water leakage)	No failure
Weight	No failure

Group B:	
Cold bending	No failure
Drip	No failure
Cross link proof test (percent maximum)	
Jacket	50
Tear - pounds per inch thickness, minimum	35
Physicals (unaged)	
Jacket	
Tensile strength - lb/in^2, minimum	1300
Elongation - percent, minimum	160
Attenuation - at 3 MHz, dB/100 feet, maximum	Not applicable
Gas flame (1 hour)	Not applicable

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.

Group C:

Physicals (aged)
Jacket
Air oven
Tensile strength - percent of unaged, minimum 60
Elongation - percent of unaged, minimum 60
Permanence of printing (conductor) - cycles, minimum .....Not applicable
Permanence of printing (jacket) - cycles, minimum.....125
Shield - conformance to material, construction and coverage .....No failure
Heat distortion - percent of unaged, maximum 30
Cable sealant removability .....No failure
Shrinkage .....No failure
Mutual inductance - dB/1000 feet, maximum .....Not applicable
Surface transfer impedance (type 3XSOW only)
Milliohms per meter, maximum 700
EMP response, dB, minimum 60
Pulse response time - ms/500 feet
Rise time, maximum .....Not applicable
Decay time, maximum .....Not applicable

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B, C and D, plus the following:

Flame propagation .....No failure
Aging and compatibility (cable) .....No failure
Acid gas equivalent - percent, maximum
Jacket 2
Fillers 2
Insulation 18
Halogen content - percent, maximum
Jacket 0.2
Fillers 0.2
Hot oil immersion
Tensile strength - percent of unaged, minimum 50
Elongation - percent of unaged minimum 50
Smoke index, maximum
Jacket 25
Fillers 45
Insulation 10
Toxicity index, maximum
Jacket 5
Fillers 5

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.

Insulation	1.5
Durometer (jacket) - (type A) hardness, minimum	80
Weathering (jacket)	No failure
Fungus Resistance	No failure
Abrasion resistance	No failure
Gas Flame (3 hour)	Not applicable
Component wire	No failure

Unit ordering length: 3 - 10 500 feet nominal.
14 - 24 250 feet nominal.

Custodians:
Army - MI
Navy - SH

Preparing Activity:
Navy - SH
(Project 6145-2307-018)

Review Activities:
Army - AR, AV, CR, CR4
Navy - CG, EC
DLA - IS

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:45Z
Check the source to verify that this is the current version before use.