INCH-POUND

MIL-C-24640/20C
26 June 1995
SUPERSEDING
MIL-C-24640/20B
31 July 1989

MILITARY SPECIFICATION SHEET

CABLE, ELECTRIC, 600 VOLTS, LIGHT WEIGHT, THREE CONDUCTOR, POWER, TYPE TXW (INCLUDING VARIATION TYPES TXOW AND TXWA)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation: MIL-C-24640.

CONSTRUCTION
(Watertight)

FIRST - Copper conductor, uncoated in accordance with ASTM B-8, 7 strands (watertight). AWG size and dimensions in accordance with tables I, II or III for the applicable type.

SECOND - Mica glass tape insulation 0.0029 ±.0002 inch (50 percent overlap maximum and minimum overlap of 45 percent).

THIRD - Opaque-pigmented polyimide tape .001 inch (50 percent overlap minimum).

FOURTH - Opaque-pigmented polyimide tape .001 inch with 0.0001 inch Fluorinated Ethylene Propylene [FEP] (50 percent overlap minimum).

FIFTH - Modified aromatic polyimide resin coating 0.0005 inch minimum (.001 inch nominal). Identification codes applied using Method 1 or 3.

SIXTH - Three component wires shall be cabled together. Fillers may be used as necessary, to form a round cable.

SEVENTH - Binder tape applied helically with overlap.

AMSC N/A FSC 6145
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-19T23:46Z
Check the source to verify that this is the current version before use.

CONSTRUCTION VARIANT FOR TYPE TXW

EIGHTH - Crosslinked polyolefin jacket. (See Table I for thickness).

CONSTRUCTION VARIANT FOR TYPE TXWA

EIGHTH - Crosslinked polyolefin jacket. (See Table II for thickness).

NINTH - Braided metal armor. Dimensions in accordance with Table II.

CONSTRUCTION VARIANT FOR TYPE TXOW

EIGHTH - Braided shield, tin coated copper strands. Braid must be constructed to meet Surface Transfer Impedance requirements as listed herein.

NINTH - Binder tape applied helically with overlap.

TENTH - Crosslinked polyolefin jacket. (See Table IV for thickness).

TABLE I. Construction details - unarmored.

Pin M24640/20	Type Number	AWG size	Conductor diameter (inch) (nominal)	Component wire diameter (inch) (min)	(max)	Jacket thickness (inch) (minimum)	Cable diameter (inch) (min)	(max)	Cable weight (pounds per 1000 feet) (max)	Conductor resistance per 1000 feet (ohms)
-01UN	TXW-3	16	0.058	0.075	0.081	0.034	0.246	0.266	65.2	4.35
-02UN	TXW-4	14	.073	.091	.097	.038	.292	.314	99.1	2.88

TABLE II. Construction details - armored.

Pin M24640/20	Type Number	AWG size	Conductor diameter (inch) (nominal)	Component wire diameter (inch) (min)	(max)	Jacket thickness (inch) (minimum)	Cable diameter (inch) (min)	(max)	Cable weight (pounds per 1000 feet) (max)	Conductor resistance per 1000 feet (ohms)
-01AN	TXWA-3	16	0.058	0.075	0.081	0.034	0.296	0.316	95.6	4.35
-02AN	TXWA-4	14	.073	.091	.097	.038	.342	.364	125.3	2.88

TABLE III. Construction details - overall shield.

Pin M24640/20	Type Number	AWG size	Conductor diameter (inch) (nominal)	Component wire diameter (inch) (min)	(max)	Diameter over shield (inch) (nom)	Jacket thickness (inch) (minimum)	Cable diameter (inch) (min) (max)		Cable weight (pounds per 1000 feet) (max)	Conductor resistance per 1000 feet (ohms)
-01UO	TXOW-3	16	0.058	0.075	0.081	0.225	0.034	0.305	0.329	113.5	4.35
-02UO	TXOW-4	14	.073	.091	.097	.250	.038	.343	.369	147.5	2.88

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:46Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

Qualification required.
Construction details: See tables I, II and III.

Component wire:

For polyimide tape constructions, the following additional tests shall be applicable in accordance with MIL-W-81381:

Temperature rating: 150°C (302°F) maximum conductor temperature
Voltage rating: 600 volts (rms) at sea level.
Blocking: Oven temperature, 200± 2°C (392± 3.6°F) no sticking of conductors
Flammability: 3 seconds (max) after flame.
3.0 inches (max) flame travel.
No flaming of tissue paper.
Humidity resistance: 5 megohms for 1000 feet, minimum insulation resistance after humidity exposure.
Impulse dielectric test: 100 percent test. Impulse voltage at 8.0 kV.
Insulation resistance: 2500 megohms for 1000 feet (min).
Polyimide cure test: No cracking.
Shrinkage: 0.062 inch maximum at 180°C
Surface resistance: 5 megohms inches (min), initial and final readings.
Thermal shock: Oven temperature, 150± 2°C (302± 3.6°F). Maximum change in measurement: 0.031 inch.
Wet dielectric test: 2500 volts (rms).

EXAMINATION AND TESTS:

Basic electrical:	Requirements
Conductor Resistance - ohms/1000 feet at 25°C, maximum	See tables I, II and III
Voltage withstand - volts, root mean square, minimum	
Conductor to conductor	2000
Conductor to shield (TXOW Only)	1000
Shield to shield	Not applicable
Insulation resistance - megohms/1000 feet, minimum	
Conductor to conductor	2500
Conductor to overall shield	2500
Shield to shield (component shield only)	Not applicable
Shield to shield (component shield to overall shield	Not applicable
Conductor and shield continuity	No failure
Jacket flaws (TXOW only)	No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:46Z
Check the source to verify that this is the current version before use.

	Group A:	
	Visual and dimensional	No failure
	Capacitance:	
	Mutual capacitance - at 1 MHz, picofarads/foot (pF/ft), maximum	Not applicable
	Capacitance unbalance - percent, maximum	Not applicable
	Characteristic impedance - at 1 MHz, ohms	Not applicable
	Watertightness (see table XI of MIL-C-24640 for limits of water leakage)	No failure
	Weight	No failure
	Group B:	
	Cold bending	No failure
	Drip	No failure
*	Cross link proof test (percent maximum)	
	Jacket	50
	Tear - pounds per inch thickness, minimum	35
	Physicals (unaged)	
	Jacket	
	Tensile strength - lb/in^2, minimum	1300
	Elongation - percent, minimum	160
	Attenuation - at 3 MHz, dB/100 feet, maximum	Not applicable
*	Gas flame (1 hour)	No failure
	Group C:	
	Physicals (aged)	
	Jacket	
	Air oven	
	Tensile strength - percent of unaged, minimum	60
	Elongation - percent of unaged, minimum	60
	Hot oil immersion	
*	Tensile strength - percent of unaged, minimum	50
*	Elongation - percent of unaged minimum	50
*	Permanence of printing (conductor) - Method 1 only cycles, minimum	25
*	Permanence of printing (jacket) - cycles, minimum	125
	Armor - conformance to material, (type TXWA only) construction and coverage	No failure
	Shield - conformance to material, construction and coverage (type TXOW only)	No failure
	Heat distortion - percent of unaged, maximum	30
*	Cable sealant removability	No failure
	Shrinkage	No failure
	Mutual inductance - dB/1000 feet, maximum	Not applicable
*	Surface transfer impedance (type TXOW only)	
	Milliohms per meter, maximum	700
	EMP response, dB, minimum	60
	Pulse response time - ms/500 feet	
	Rise time, maximum	Not applicable
	Decay time, maximum	Not applicable

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:46Z
Check the source to verify that this is the current version before use.

* Group D

Flame propagation	No Failure

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B, C and D, plus the following:

Aging and compatibility (cable)	No failure
Acid gas equivalent - percent, maximum	
Jacket	2
Fillers	2
Insulation	18
Halogen content - percent, maximum	
Jacket	0.2
Fillers	0.2
Immersion	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50
Smoke index, maximum	
Jacket	25
Fillers	45
Insulation	10
Toxicity index, maximum	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - (type A) hardness, minimum	80
Weathering (jacket)	No failure
Fungus Resistance	No failure
Abrasion resistance	No failure
* Gas Flame (3 hour)	No failure
Component wire	No failure

Unit ordering length: 500 feet nominal

NOTE: The margins of this specification are marked with asterisks to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - MI
Navy - SH

Review Activities:
Army - AV, CR, ER, ME, AR, AL
Navy - EC, CG
DLA - IS

Preparing Activity:
Navy - SH

Agent:
DLA - IS

(Project No. 6145-2105-20)

Source: https://assist.dla.mil -- Downloaded: 202640-19T23:46Z
Check the source to verify that this is the current version before use.