INCH-POUND
MIL-DTL-24640/23E
8 November 2011
SUPERSEDING
MIL-DTL-24640/23D
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRIC, -20 TO +105 °C, 600 VOLTS, LIGHTWEIGHT, MULTI-CONDUCTOR, 18 AWG, TYPE MXCW (INCLUDING VARIATION TYPE MXCOW)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24640.

Construction (Watertight)

First	-	Copper conductor, coated or uncoated 18 AWG, 7 strands, in accordance with ASTM B8.
Second	-	Mica glass tape insulation 0.0029±0.0002 inch (50 percent overlap maximum and minimum overlap of 45 percent). Conformance testing shall be in accordance with MIL-DTL-81381 prior to cabling.
Third	-	Opaque-pigmented polyimide tape 0.001 inch (50 percent overlap minimum).
Fourth	-	Opaque-pigmented polyimide tape 0.001 inch with 0.0001 inch Fluorinated Ethylene Propylene (FEP) (50 percent overlap minimum).
Fifth	-	Modified aromatic polyimide resin coating 0.0005 inch minimum (0.001 inch nominal). Identification codes applied using Method 1 or 3.
Sixth	-	The required number of component wires shall be cabled together. Cabling sequence shall be consecutive, starting with number 1 from center outward. Fillers may be used, as necessary, to form a round cable.
Seventh	-	Optional binder tape.

Construction Variant for Type MXCW

Eighth	-	Cross-linked polyolefin jacket (see table I for thickness). NOTE: Manufacturer's identification tape or thread is required (see 3.7.3).

Construction Variant for Type MXCOW

Eighth	-	Braided shield, tin-coated copper strands. Braid must be constructed to meet surface transfer impedance requirements as listed herein.
Ninth	-	Optional binder tape.
Tenth	-	Cross-linked polyolefin jacket (see table II for thickness). NOTE: Manufacturer's identification tape or thread is required (see 3.7.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:47Z
Check the source to verify that this is the current version before use.

TABLE I. Construction details.

PIN M24640/23	Type number	Number of conductors	Jacket thickness (inch) (min.)	Cable diameter (inch)		Cable weight (pounds per 1000 feet) (max.)
				(min.)	(max.)	
-01UN	MXCW-7	7	0.038	0.295	0.319	90.0
-02UN	MXCW-10	10	0.041	0.375	0.405	139.0
-03UN	MXCW-14	14	0.041	0.402	0.434	173.0
-04UN	MXCW-19	19	0.041	0.440	0.474	215.0
-05UN	MXCW-24	24	0.044	0.520	0.560	295.0
-06UN	MXCW-30	30	0.044	0.547	0.589	340.0
-07UN	MXCW-37	37	0.044	0.584	0.630	398.0
-08UN	MXCW-44	44	0.044	0.656	0.708	492.0
-09UN	MXCW-61	61	0.047	0.729	0.785	640.0

TABLE II. Construction details - overall shield.

PIN M24640/23	Type number	Number of conductors	Jacket thickness (inch) (min.)	Cable diameter (inch)		Cable weight (pounds per 1000 feet) (max.)
				(min.)	(max.)	
-01UO	MXCOW-7	7	0.038	0.340	0.366	140.0
-02UO	MXCOW-10	10	0.041	0.415	0.447	185.0
-03UO	MXCOW-14	14	0.041	0.440	0.474	225.0
-04UO	MXCOW-19	19	0.041	0.477	0.515	280.0
-05UO	MXCOW-24	24	0.044	0.557	0.601	362.0
-06UO	MXCOW-30	30	0.044	0.584	0.630	399.0
-07UO	MXCOW-37	37	0.044	0.622	0.670	466.0
-08UO	MXCOW-44	44	0.047	0.697	0.751	574.0
-09UO	MXCOW-61	61	0.047	0.757	0.817	715.0

REQUIREMENTS:

Qualification required.

Construction details: See tables I and II.

Finished wire: For polyimide tape constructions, the following additional tests shall be applicable in accordance with MIL-DTL-81381.

Temperature rating	150 °C (302 °F) (max.) conductor temperature
Voltage rating	600 volts (root mean square) at sea level
Blocking	Oven temperature, 150±2 °C (302±3.6 °F) no sticking of conductors
Flammability	3 seconds (max.) after flame
	3.0 inches (max.) flame travel
	No flaming of tissue paper

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:47Z
Check the source to verify that this is the current version before use.

Humidity resistance	5 megohms for 1000 feet (min.) insulation resistance after humidity exposure
Impulse dielectric test	8.0 kV, 100 percent impulse test
Insulation resistance	2500 megohms for 1000 feet (min.)
Polyimide cure test	No cracking
Shrinkage	0.062 inch (max.) at 180 °C
Surface resistance	5 megohms inches (min.), initial and final readings
Thermal shock	Oven temperature, 150±2 °C (302±3.6 °F)
Maximum change in measurement	0.031 inch
Wet dielectric test	2500 volts (root mean square)

INSPECTION:

Basic electricals:

Conductor resistance (ohms/1000 feet at 25 °C, max.)	7.07
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	2000
Conductor to shield (MXCOW only)	1000
Shield to shield	Not applicable
Insulation resistance (megohms/1000 feet, min.)	
Conductor to conductor	2500
Conductor to overall shield (MXCOW only)	2500
Shield to shield (component shield only)	Not applicable
Shield to shield (component shield to overall shield)	Not applicable
Conductor and shield continuity (Type MXCOW only)	No failure
Jacket flaws (Type MXCOW only)	No failure

Group A:

Visual and dimensional	No failure
Capacitance:	
Mutual capacitance (at 1 MHz, picofarads/foot (pF/ft), max.)	Not applicable
Capacitance unbalance (percent, max.)	Not applicable
Characteristic impedance (at 1 MHz, ohms)	Not applicable
Watertightness (see table IX of MIL-DTL-24640 for limits of water leakage)	No failure
Weight	No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:47Z
Check the source to verify that this is the current version before use.

Group B	
Cold bending	No failure
Drip	No failure
Cross-link proof test (percent, max.)	
Jacket	50
Tear (pounds per inch thickness, min.)	35
Physicals (unaged)	
Jacket	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160
Attenuation (at 3 MHz, dB/100 feet, max.)	Not applicable
Gas flame (1 hour)	No failure
Group C:	
Physicals (aged), air oven	
Jacket	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (conductor insulation, cycles, Method 1 only, min.)	25
Permanence of printing (jacket, cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Cable sealant removability	No failure
Shrinkage	No failure
Surface transfer impedance (Type MXCOW only)	
Milliohms per meter (max.)	700
EMP response (dB, min.)	60
Group D:	
Flame propagation	No failure

Qualification Inspection:

Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:

Aging and compatibility (cable)	No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:47Z
Check the source to verify that this is the current version before use.

Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	10
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Fungus resistance	No failure
Abrasion resistance	No failure
Gas flame (3 hour)	No failure
Component wire	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)	
MXCW-7, MXCW-10, MXCW-14, MXCW-19, MXCW-24, MXCW-30, MXCW-37, MXCW-44, MXCW-61, MXCOW-7, MXCOW-10, MXCOW-14, MXCOW-19, MXCOW-24, MXCOW-30, MXCOW-37, MXCOW-44, MXCOW-61	7 - 19	500
	24 - 61	250

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:47Z
Check the source to verify that this is the current version before use.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2009-098)

Review Activities:
Army – AR, AV, CR, CR4
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:47Z
Check the source to verify that this is the current version before use.