INCH-POUND

MIL-C-50704A (AR)
AMENDMENT 1
01 May 1995

MILITARY SPECIFICATION

CARTRIDGE, 7.62MM: DIM TRACER, XM276

This amendment forms a part of MIL-C-50704A, dated 20 September 1991, and is approved for use by the US Army Armaments, Research, Development and Engineering Center, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 4

3.8.1 Add the following:

"If velocity is measured using the EPVAT system, the chamber pressure measurement must be performed using the EPVAT system as well."

PAGE 5

3.8.1.5 Delete paragraph "3.8.1.5" in its entirety.

3.8.1.6 Delete paragraph "3.8.1.6" in its entirety.

3.8.1.7 Delete paragraph "3.8.1.7" in its entirety.

Add the following paragraphs:

"3.8.2 Velocity. The velocity test may be performed using a velocity test barrel or the EPVAT method. The test method employed shall be recorded on the test results.

3.8.2.1 Velocity measurement by velocity test barrel. The average velocity of the sample cartridges conditioned at 70°F shall be 2,750 ± 30 ft/sec for gilding metal clad steel jacketed bullets or 2,680 ± 30 ft/sec for gilding metal jacketed bullets at 78 feet from the muzzle of the weapon. The standard deviation of the velocities shall not exceed 32 ft/sec.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:34Z
Check the source to verify that this is the current version before use.

3.8.2.2 Velocity measurement by EPVAT test method. The average velocity of the sample cartridges conditioned at 70°F shall be 2,735 ± 30 ft/sec for gilding metal clad steel jacketed bullets or 2,665 ± 30 ft/sec for gilding metal jacketed bullets at 78 feet from the muzzle of the weapon. The standard deviation of the velocities shall not exceed 32 ft/sec.

3.8.2.3 Velocity at 125°F and -65°F. The average velocity of the sample cartridge subjected to 125°F and -65°F storage conditions shall not vary from the average velocity of the sample cartridges of the same lot conditioned at 70°F by more than +150 or -250 ft/sec.

3.8.3 Function and casualty. The sample cartridges subjected to 70°F, 125°F and -65°F shall function without casualty."

3.10 Delete paragraph 3.10 in its entirety and substitute the following:

"3.10 Port Pressure. The port pressure measurement may be performed by either the copper-crush cylinder or EPVAT test method. If velocity is measured using the EPVAT system, the port pressure measurement must be performed using the EPVAT system as well. The average port pressure of the sample cartridges when conditioned for not less than 2 hours at 68° to 72°F and fired at that temperature shall be as noted in the applicable sub-paragraphs:"

PAGE 9

In Table I, under requirement paragraph for velocity, delete:

"3.8.1.5, 3.8.1.6 and 3.8.1.6" and substitute "3.8.2, 3.8.2.3 and 3.8.2.3" respectively.

PAGE 10

In Table I, under requirement paragraph, delete "3.8.1.7" wherever it appears and substitute "3.8.3".

PAGE 11

In Table I, under requirement paragraph, delete "3.8.1.7" wherever it appears and substitute "3.8.3".

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:34Z
Check the source to verify that this is the current version before use.

PAGE 21

In Table V, under requirement paragraph for Function and Casualty, delete "3.8.1.7" and substitute "3.8.3".

PAGE 22

In Table V, under requirement paragraph for Velocity Measurement by Copper-Crush Cylinder, delete "3.8.1.5, 3.8.1.6" and substitute "3.8.2.1, 3.8.2.3".

In Table V, under requirement paragraph for Velocity Measurement by EPVAT, delete "3.8.1.5, 3.8.1.6" and substitute "3.8.2.2, 3.8.2.3".

Custodian:
Army-AR

Preparing Activity:
Army-AR

(Project 1305-0121)

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:34Z
Check the source to verify that this is the current version before use.