INCH–POUND

MIL–P–51433A(EA)
AMENDMENT 2
25 September 1990
SUPERSEDING
AMENDMENT 1
16 January 1990

MILITARY SPECIFICATION

PLASTIC TUBE, POLYETHYLENE COPOLYMER

This amendment forms a part of MIL–P–51433A(EA), dated 31 August 1988, and is approved for use by the U.S. Army Chemical Research, Development and Engineering Center, Department of the Army and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.6: Delete paragraph in its entirety and substitute the following:

"**3.6 Workmanship.** The plastic tube shall have a smooth finish and shall be free of ripples, waves, cracks, streaks, blisters, bubbles, discoloration, craze, foreign material, pitting, and scratches that form definite indentations and other defects that affect appearance or could affect serviceability."

PAGE 4

Table I: Change requirement for flow rate characteristic from "2.0" to "**" in two places and add the following note below table I: "**The tube produced is allowed to increase in flow rate a maximum of 100 percent from pelletized resin to extruded sheet, or to a maximum value of 3.0 grams per 10 minutes, whichever is less."

AMSC N/A FSC 9330

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:00Z
Check the source to verify that this is the current version before use.

Custodian:

Army - EA

Preparing activity:

Army - EA

Project No. 9330-A040

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:00Z
Check the source to verify that this is the current version before use.