METRIC
A-A-60000
May 14, 2019

COMMERCIAL ITEM DESCRIPTION

STRIPPER, FLOOR

The General Services Administration has authorized the use of this commercial item description for all federal agencies.

1. SCOPE. This commercial item description (CID) covers a concentrated floor stripper compound, that removes water emulsion floor finish and floor wax from impermeable floor surfaces.

2. SALIENT CHARACTERISTICS.

2.1 General. The in-use stripper shall be a homogeneous, free-flowing liquid. Upon application, it shall form a uniform layer or sheet of liquid without beading or puddling.

2.2 Prohibited materials. The stripper shall not contain any materials above the threshold for trace amount that have a severity category of either catastrophic or critical in the prohibited and restricted chemicals tables in the Naval Sea Systems Command (NAVSEA) List of Targeted Chemicals (N-LTC) appendix of T9070-AL-DPC-020/077-2, NAVSEA Hazardous Material Avoidance Process. The threshold for trace amount is defined as less than 1 percent for non-carcinogenic compounds and less than 0.1 percent for carcinogenic compounds.

2.3 Volatile organic compound (VOC) levels. VOC levels of the stripper shall be stated as a percent of VOCs by weight when prepared in the dilution ratio as directed on the manufacturer's label and shall not exceed the California Air Resources Board (CARB) 17 CCR § 94509 VOC standard for floor wax strippers.

2.4 pH. The pH of an un-diluted solution shall be a minimum of 6.0 and a maximum of 13.5 when tested in accordance with ASTM E70.

2.5 Flash point. The flash point shall be greater than 93.3 °C (200 °F) when tested in accordance with ASTM D56.

2.6 Eutrophication and phosphate. The stripper shall comply with the U.S. Environmental Protection Agency (EPA) Safer Choice Standard eutrophication and phosphate criteria.

2.7 Aquatic toxicity. The stripper, when used as directed on the label in a use-dilution solution, shall not be harmful to aquatic life in accordance with the United Nations Economic Commission for Europe (UNECE) Globally Harmonized System of Classification and Labelling of Chemicals (GHS) criteria for acute and chronic aquatic toxicity.

2.8 Removal efficiency. The stripper shall completely remove the standard floor finish and the standard floor wax when tested in accordance with ASTM D1792, or other equivalent or comparable test methods, with the following exceptions:

a. The compound, in a 1:12 solution with distilled water, shall be used in place of the stripper solution.
b. The diluted compound shall have a 5-minute presoak on the substrate.
c. The total number of oscillations required for complete removal shall be not more than 50.
d. The substrate shall be coated with the standard floor finish and wax.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: Commander, Naval Sea Systems Command, ATTN: SEA 05S, 1333 Isaac Hull Avenue, SE, Stop 5160, Washington Navy Yard DC 20376-5160 or emailed to CommandStandards@navy.mil, with the subject line "Document Comment". Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

FSC 7930

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:32Z
Check the source to verify that this is the current version before use.

2.9 Ammonia. The stripper shall contain no volatile ammonia when tested as follows, or following other equivalent or comparable test methods: Mix 2 milliliters of floor stripper concentrate with 10 milliliters of 10 percent sodium hydroxide. Distill and catch the distillate (1-2 milliliters) in a tube containing 5 milliliters of ammonia-free distilled water. Add a few milliliters of Nessler's reagent to the tube containing the distillate. A brown color indicates ammonia. Yellow or white colors indicate volatile amines and are not cause for rejection.

2.10 Deleterious effects. The stripper, when used as directed on the label in a use-dilution solution, shall have no deleterious action on epoxy coatings, epoxy and polyurethane seal coats, rubber electrical grade sheeting, unglazed ceramic tile, vinyl, or vinyl-composition flooring when tested as follows, or following other equivalent or comparable test methods: Prepare 5.08 by 10.16 by 0.032-centimeter (2 by 4 by ⅛-inch) test coupons from asphalt and vinyl asbestos tile. Place coupons in separate 250-milliliter beakers and add 150 milliliters of compound, in a 1:12 solution to each beaker. Prepare the 1:12 solution by adding 50 milliliters of compound to 600 milliliters of distilled water. Allow to stand for 4 hours at room temperature, 22 to 26 °C (71.6 to 78.8 °F), rinse thoroughly with distilled water, and allow to dry for 1 hour at room temperature. Examine the dry coupons and residual solution for evidence of deleterious action.

3. REGULATORY REQUIREMENTS. The offeror/contractor is encouraged to use recovered materials or biobased materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

4. PRODUCT CONFORMANCE PROVISIONS. The products provided shall meet the salient characteristics of this Commercial Item Description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance.

5. PACKAGING. Preservation, packing, and marking shall be as specified in the contract or order.

6. NOTES.

6.1 Source of documents.

6.1.1 ASTM International. ASTM standards are available from ASTM International, 100 Barr Harbor Dr., P.O. Box C700, West Conshohocken, PA 19428-2959 or online at www.astm.org.

6.1.2 California Code of Regulations (CCR). The CCR may be obtained online at https://oal.ca.gov/publications/ccr/.

6.1.3 EPA. The U.S. EPA Safer Choice Standard may be obtained from the Environmental Protection Agency, Ariel Rios Building, 1200 Pennsylvania Avenue, N.W., Washington, DC 20460 or online at https://www.epa.gov/saferchoice/standard.

6.1.4 FAR. The FAR may be obtained from the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402 or online at https://www.acquisition.gov/far.

6.1.5 GHS. The UNECE GHS may be obtained online at http://www.unece.org/trans/danger/publi/ghs/ghs_rev06/06files_e.html.

6.1.6 NAVSEA publications. Copies of T9070-AL-DPC-020/077-2 are available online via Technical Data Management Information System (TDMIS) at https://mercury.tdmis.navy.mil/ by searching for the TMIN without the suffix. Refer questions, inquiries, or problems to: DSN 296-0669, Commercial (805) 228-0669. T9070-AL-DPC-020/077-2 is available for ordering (hard copy) via the Naval Logistics Library https://nll.navsup.navy.mil. For questions regarding the NLL, contact the NLL Customer Service at nllhelpdesk@navy.mil, (866) 817-3130, or (215) 697-2626/DSN 442-2626.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:32Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. The contract or order should specify the following:

a. CID document number and revision letter.

b. Quantity required.

c. Product conformance provisions.

d. Packaging requirements.

6.3 Key words.

Floor cleaner

CONCLUDING MATERIAL

MILITARY INTERESTS:

Custodians:
Army – MI
Navy – SH

Review Activities:
Army – AV, GL
Navy – AS, CG, MC

CIVIL AGENCY COORDINATING ACTIVITY:
GSA – FAS

Preparing Activity:
Navy – SH
(Project 7930-2019-003)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:32Z
Check the source to verify that this is the current version before use.