MIL-A-83462(USAF)
AMENDMENT 1
l7 March 1976

MILITARY SPECIFICATION

ARTIC CUSHION - CLOTHING, CHU-10/P AND CHU-11/P

This amendment forms a part of Military Specification MIL-A-83462 (USAF) dated 27 May 1975.

Page 1, paragraph 2.1: Add "MIL-C-83391 Cloth, Duck, Aromatic Polyamide, Non-Melting"

Page 2, paragraph 3.4.1: Delete and substitute:

3.4.1 Basic fabric for cover. The basic fabric for the cover shall be duck cloth that has been coated on one side and shall be USAF color shade No. 1565 (see 6.3). The duck cloth shall conform to MIL-C-83391. The coating shall be fluorinated chloroprene rubber. The finished coated duck cloth shall conform to the following:

Weight, ounces per square yard	12.0 (plus minus 1.0)
Breaking strength, pounds, minimum , Initial	
Warp	150
Filling	150
After accelerated weathering	
Warp	1/
Filling	1/
Tearing strength, pounds, minimum	
Warp	20
Filling	20
Coating adhesion, pounds per 2-inch Width, minimum	12.0
Resistance to blocking	scale rating 2 (no blocking: cloth surfaces adhere slightly)
Resistance to accelerated aging	2/
Hydrostatic resistance	
Initial	no leakage of water
After abrasion	no leakage of water

FSC 1660

Source: https://assist.dla.mil -- Downloaded: 202610-23T08:14Z
Check the source to verify that this is the current version before use.

Resistance to accelerated weathering	3/
Resistance to low temperature	no cracking or flaking
Resistance to high temperature	no tackiness, no blistering, and no softening

1/ The specimen shall retain not less than 80 percent of its initial breaking strength.
2/ The specimens that have been exposed to accelerated aging, when compared to unexposed specimens from the same unit of product, shall not have become stiff, brittle, soft, or tacky.
3/ When folded sharply upon itself, there shall be no cracking, no crazing, no chalking, and no blooming."

Page 7: Add:

"4.5.1.1 Coated duck cloth. The finished coated cloth shall be subjected to sampling inspection, to determine conformance to the requirements specified herein, as follows: The coated side of the finished cloth shall be examined as described in the paragraph entitled "Yard by yard examination" in MIL-C-20696 to determine conformance to the requirements specified in 3.4.1 of this specification. The finished coated cloth shall be tested as specified for type III, class 5 coated cloth in the paragraph entitled "Testing of the end item" in MIL-C-20696 to determine conformance to the requirements specified in 3.4.1 of this specification."

Custodian:
Air Force - 11

Reviewer:
Air Force 71

Preparing activity
Air Force - 11

Project No. 1660-F134

Source: https://assist.dla.mil -- Downloaded: 202610-23T08:14Z
Check the source to verify that this is the current version before use.