MILITARY SPECIFICATION

CLOTH, SERGE, POLYESTER, TEXTURIZED

This amendment forms a part of Military Specification MIL-G-83448(USAF), dated 26 July 1974, and is approved for use by the Department of the Air Force and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

Paragraph 3.3.1: Add "The yarns shall be of the modified cross section anti-glitter type."

Paragraph 3.4: Delete "1578" and substitute "1598".

Paragraph 3.4.2: Add "The light exposure time for "good" fastness shall be 40 standard fading hours. Tests shall be as specified in 4.5."

TABLE I, fourth column, Shrinkage percent (maximum): Under "Warp" delete "2.5" and substitute "2.0".

PAGE 3

Paragraph 3.6: Delete "The cloth shall be given an anti-snag treatment." Substitute: "The finished cloth shall show the character of finish and hand exhibited by the standard sample."

Paragraph 3.7, line 2: Delete "1.0" and substitute "2.0".

Add the following:
"3.10. Dimensional stability.

"3.10.1 Dimensional stability to washing. The finished cloth shall not shrink more than 2.0 percent or elongate more than 1.0 percent in either the length or width direction after five launderings when tested as specified in 4.4.

"3.10.2 Dimensional stability to dry cleaning. The finished cloth shall not shrink more than 2.0 percent or elongate more than 1.0 percent in length or width direction after one cycle of dry cleaning when tested as specified in 4.4."

Paragraph 3.10: Delete "3.10" and substitute "3.11".

Paragraph 3.11: Delete "3.11" and substitute "3.12".

Paragraph 3.12: Delete "3.12" and substitute "3.13".

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T08:13Z
Check the source to verify that this is the current version before use.

PAGE 4

TABLE II, Requirement paragraph, entire column: Delete "2." in 3.2.1 and substitute "3."

PAGE 8

TABLE III: Delete "Finish, 3.6, 1/".

TABLE III: After "Pilling" line delete "1/" in its entirety and add the following:

"Non-fibrous material	3.7	2611
Color fastness (as applicable):		
Light	3.4.2	5660
Wet-dry cleaning	3.4.2	5622
Perspiration	3.4.2	5680
Crocking	3.4.2	5651
Dimensional stability to:		
Dry cleaning (1 cycle)	3.10	5580
Washing (5 cycles)	3.10.1	1/

1/ AATCC test method 135-1973, Dimensional Changes in Automatic Home Laundering of Durable Press, Woven or Knit Fabrics - machine wash conditions method II (120 ±5°F), dry procedures B (tumble)."

PAGE 9

Paragraph 6.1, line 2: Delete "and functional clothing".

Custodian:
Air Force: 20

Preparing activity:
Air Force: 20

(Project No.: 8305-F912)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T08:13Z
Check the source to verify that this is the current version before use.