MILITARY SPECIFICATION

CLOTH, TWILL, NYLON WARP, RAYON FILLING

This amendment forms a part of Military Specification MIL-C-83453(USAF), dated 29 November 1975.

PAGE 1

1.1 Line 1: Delete "one type" and substitute "two types".

1.2 Add new paragraph:

"1.2 Classification. The cloth shall be of the following types, as specified (see 6.2):

Type I - Durable water repellent face finish.
Type II - Durable water repellent face finish polyurethane coating on reverse.

PAGE 2

Table I, yarns per inch, warp and filling, delete minimum requirements "138" and "44" and replace with "134" and "42" respectively. Breaking strength, warp and filling, delete minimum requirements "340" and "290" and replace with "375" and "170" respectively.

PAGE 3

3.6 Add the following to the end of the paragraph: "The type II fabric shall be given a 3/4 oz./sq. yd. polyurethane coating on the reverse side."

3.7, line 2, delete "1.0" and substitute "4.0".

PAGE 5

4.4.1.1, line 1, page 5: Delete "10.0" and substitute "75.0".

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T08:13Z
Check the source to verify that this is the current version before use.

6.2 Add new sub-paragraph:

"g. Type required."

Custodian:
Air Force - 11

Preparing Activity:
Air Force - 11

Project No. 8305-F696

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T08:13Z
Check the source to verify that this is the current version before use.