MIL-B-40092D
27 March 1987
SUPERSEDING
MIL-B-40092C
16 August 1972

MILITARY SPECIFICATION

BRAID, TEXTILE, CORD-EDGE, POLYESTER

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers polyester cord-edge braid.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Documents. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

A-A-203	- Paper, Kraft, Untreated
V-T-285	- Thread, Polyester
PPP-B-636	- Boxes, Shipping, Fiberboard

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8315

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-L-35078	- Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification For

STANDARDS

FEDERAL

FED-STD-191	- Textile Test Methods

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	- Marking for Shipment and Storage
MIL-STD-147	- Palletized Unit Loads
MIL-STD-731	- Quality of Wood Members for Containers and Pallets

(Copies of documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.1.2 Other Government documents. The following other Government documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

FEDERAL TRADE COMMISSION

Rules and Regulations Under the Textile Fiber Products Identification Act

(Application for copies should be addressed to the Federal Trade Commission, Pennsylvania Avenue at Sixth Street, N.W., Washington, DC 20580.)

2.2 Other publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

* 2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence. Nothing in this document, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Standard sample. The finished braid shall match the standard sample for shade and appearance and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.2 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.4).

3.3 Materials.

3.3.1 Polyester yarns. The yarns for the braided cover of cord section and flat braid section shall be multifilament, polyester, 70 denier, 3 ply (letter size A) yarns. The yarns for the core of the cord section shall be multifilament, polyester, 220 denier, 3 ply, plied 3 times (number size 3). These yarns shall conform to type I, class 1 of V-T-285.

* 3.3.1.1 Preshrinking. Preliminary to braiding the yarn for piece-dyed braid, the yarn shall be preshrunk by autoclaving at appropriate times and temperatures to impart dimensional stability to the yarn resulting in a finished dyed braid that has the cord-edge and sewn-edge as uniform in appearance and quality as that of the standard sample and that also conforms to all other requirements of this document.

3.3.2 Cotton yarn. The flat section reinforcement cotton yarn shall be 60/4 ply or 30/2 ply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.

* 3.4 Dyeing. The braid shall be either yarn dyed or piece dyed using the pressure dyeing system (see 6.6).

* 3.4.1 Color. The color of the braid shall be as specified (see 6.2). The single reinforcement end (cotton yarn) need not meet the color requirements for the braid (see 6.7).

* 3.4.2 Matching. The color of the dyed and finished braid shall match the standard sample when viewed under filtered tungsten lamps that approximate artificial daylight and that have a correlated color temperature of 7500 ± 200 K, with illumination of 100 ± 20 foot candles, and shall be a good, approximation to the standard sample under incandescent lamplight at 2300 ± 200 K.

* 3.4.3 Colorfastness. The piece- or yarn-dyed braid shall show fastness to laundering, perspiration, crocking, light, and sublimation equal to or better than the standard sample or shall show good fastness to laundering, perspiration, crocking, light, and sublimation when tested as specified in 4.4.3.

3.5 Construction. The flat braid section and the cord section shall be braided together in one operation on a cord-edge braider.

3.5.1 Cord section. The cord section shall consist of a cover braided around a core of stuffer yarns (see 3.3.1). The cover shall conform to the requirements of table I.

3.5.2 Core. The core shall consist of five polyester stuffer yarns (see 3.3.1).

3.5.3 Flat-braid section. The flat braid section shall conform to the requirements of table I, and the edge reinforcement yarn shall be as specified in 3.3.2.

* 3.5.4 Dimensional stability. The finished cord-edge braid shall not shrink or elongate more than 5 percent in length, nor shall the sewn edge be distorted when tested as specified in 4.4.3.

Source: https://assist.dla.mil -- Downloaded: 202610-21T19:14Z
Check the source to verify that this is the current version before use.

any inspection requirement in the document shall not relieve the absence o

TABLE I. Physical requirements for cord-edge braid

	Width (inches)		Weight per gross (144) yards (ounces)	No. of carriers		Ends per carrier	Picks per inch	Braid type
	Min.	Max.	Min.	Min.	Max.	Min.	Min.	
Cord-braided cover	3/32	1/8	-	19	-	3	25	2/2
Flat braid section	1/4	3/8	-	21	25	4	25	2/2
Finished cord-edge braid	-	-	29.0	-	-	-	-	-

3.6 Put-up and length. Unless otherwise specified (6.2), the braid shall be put-up on double-headed spools as specified in 5.1.1 containing 144 ± 10 yards. There shall be not more than three lengths per spool and no single length shall be less than 5 yards.

3.7 Fiber identification. Each spool shall be labeled, ticketed, or invoiced for fiber content in accordance with the Textile Fiber Products Identification Act (see 2.1.2).

3.8 Marking. Each spool shall have firmly attached, a white paper label printed in black with the following information:

Stock number
Item description
Document number
Name of contractor
Number and date of contract
Name of contracting agency
Total yards

3.9 Workmanship. The finished cord-edge braid shall conform to the quality of product established by this document and the occurrence of defects shall not exceed the applicable acceptable quality levels.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirement in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Certificates of compliance. When certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.2 and tested for the defects specified in 4.4.3. The presence of any defect or failure to pass any test shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.

4.4.1.1 Component testing. The component materials listed in table II shall be accepted on the basis of the contractor's certificate of compliance with requirements specified for said characteristics.

TABLE II. Component testing

Component material	Characteristics	Requirement reference
Polyester yarn (Cord cover and flat braid)	Material identification	3.3.1
	Yarn size-denier	3.3.1
	Ply	3.3.1
Polyester yarn (Core-stuffer yarns)	Material identification	3.3.1
	Yarn size-denier	3.3.1
	Ply	3.3.1
Cotton yarn (Flat braid reinforcement yarn)	Material identification	3.3.2
	Yarn number	3.3.2
	Ply	3.3.2

4.4.2 End item examination.

4.4.2.1 Yard-by-yard examination. The braid shall be examined at normal inspection distance (3 feet) for the defects listed in table IV. All defects listed shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The lot size shall be expressed in yards. The sample unit shall be 1 yard of braid. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 1.5 for major defects and 4.0 for total (major and minor combined) defects. The number of spools from which the sample is to be selected shall be in accordance with table III. The sample yardage shall be apportioned equally among the selected spools.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.

TABLE III. Sampling size and acceptance criteria

Lot size (yards)	Sample size (spools)	Acceptance number 1/
Up to and including 1200 2/	3 spools	0
1,201 up to and including 3,200	5 spools	0
3,201 up to and including 8,000	7 spools	0
8,001 up to and including 22,000	10 spools	0
22,001 up to and including 110,000	15 spools	1
110,001 or over	25 spools	1

1/ Applicable to overall examination (see 4.4.2.2)

2/ If a lot contains fewer than 3 spools, each spool shall be examined.

TABLE IV. End item visual defects

Examine	Defects	Classification	
		Major	Minor
Braid	Abrasion mark		X
	Any cut, hole, or tear	X	
	Broken or missing yarn	X	
	Core not completely covered	X	
	Uneven tension, resulting in thick and thin places	X	
	Tight or loose yarns, causing distortions or loopiness		X
	Spot, stain, or streak		X
	Width (cord cover section) exceeding limits		X
	Width (flat braid section) exceeding limits		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.

* 4.4.2.2 Overall examination. The braid shall be examined for the defects listed below. The sample shall consist of the applicable number of spools indicated in table III. The lot shall be rejected if the total number of defects in the sample exceeds the acceptance number specified in table III.

Defects
Not clean throughout
Objectionable odor
Identification marking missing, illegible, or incorrect
Not ticketed or labeled in accordance with the Textile Fiber Products Identification Act
Improperly or insecurely wound on spools, tangled, and does not unwind properly

* 4.4.2.3 Length examination. The braid shall be examined for the defects listed below. The sample shall consist of the applicable number of spools indicated in table III. The presence of any defect shall be cause for rejection of the lot.

Defect
Length less than specified minimum or more than specified length
Length more than 2 yards less than length marked on spool
Any spool containing more than the maximum allowable number of pieces
Any individual length less than 5 yards
Total of the actual lengths on the spools is less than the total of the lengths marked on the spools

* 4.4.2.4 Shade and appearance examination. The braid shall be examined for the defects listed below. The sample shall consist of the applicable number of spools indicated in table III. The presence of any defect shall be cause for rejection of the lot.

Defects
Shaded end to end
Does not match the standard sample for shade and appearance
Mottled or uneven color

* 4.4.3 End item testing. The end item shall be tested as indicated in table V. The methods of testing specified in FED-STD-191, wherever applicable, and as listed in table V shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test methods except for the weight characteristic. The lot size shall be expressed in

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.

units of yards. The sample unit for test purposes shall be 6 yards of the finished braid. The lot shall be unacceptable if one or more sample units fail to meet any requirements specified, except for the weight characteristic the lot average of all sample units shall apply. All physical tests shall be performed in accordance with Standard Conditions as defined in FED-STD-191. The sample size for each characteristic shall be as follows:

Lot size (yards)	Sample size (sample unit)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE V. End item tests

Characteristics	Requirement reference	Test methods
Colorfastness to:		
Laundering	3.4.3	5614
Perspiration	3.4.3	5680
Crocking	3.4.3	5651 1/
Light	3.4.3	5660
Sublimation	3.4.3	5642 2/
Flat braid section:		
Autoclaving	3.3.1.1	3/
No. of carriers	Table I	Visual 4/
Ends per carrier	Table I	Visual 4/
Picks per inch	Table I	Visual 5/
Braid type	Table I	Visual 6/
Cord section:		
No. of carriers	Table I	Visual 1/
Ends per carrier	Table I	Visual 1/
Picks per inch	Table I	Visual 2/
Braid type	Table I	Visual 3/
No. stuffer yarns (core)	3.5.2	Visual 1/
Weight (oz/gross yards)	Table I	4.5.1
Dimensional stability	3.5.4	5552

Source: https://assist.dla.mil -- Downloaded: 202610-21T19:14Z
Check the source to verify that this is the current version before use.

1/ Method 5651 shall be followed except that the lengths of cord-edge braid shall be laid so that the cord portions are side by side, presenting the same continuous height.

2/ The sample shall be tested at a temperature of 376° ± 6°C.

3/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirements.

4/ One determination per sample unit and results reported as "actual count".

5/ Three determinations per sample unit and results reported as average of 3 determinations to nearest whole number.

6/ One determination per sample unit and results reported as "pass or fail".

4.4.4 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling Bulged or distorted container
Content	Number of spools per container is more or less than required

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.

* 4.4.5 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1, and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Interlocking of loads not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

4.5 Methods of inspection.

4.5.1 Weight. Six specimens in excess of one yard each shall be selected at random from different spools in the sample. The six specimens of braid in the relaxed state shall then be cut to exactly one yard each. While in a Standard Condition as defined in FED-STD-191, each yard shall be weighed separated on a balance or scale accurate to 0.01 ounce (a scale or balance graduated in grams may be used and results converted to ounces). The weight of the six specimens shall be averaged and this average value multiplied by 144 to determine the ounces per gross (144) yards to the nearest 0.5 ounce.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial, as specified (see 6.2).

* 5.1.1 Level A. Braid, put-up in the yardage specified in 3.6, shall be neatly wound on a 6-inch spool consisting of a chipboard tube approximately 3/4 inch outside diameter by 1/8 inch wall, mechanically attached to 5-1/2 inch diameter by 1/8 inch thick circular ends. Each spool shall be wrapped with a band of transparent plastic film or within minimum 30-pound kraft paper conforming to A-A-203. The wrap shall completely enclose the braid on the spool and shall be secured with gummed or pressure-sensitive tape.

Source: https://assist.dla.mil -- Downloaded: 202640-21T19:14Z
Check the source to verify that this is the current version before use.

* 5.1.2 Commercial. Braid shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial, as specified (see 6.2).

* 5.2.1 Level A packing. Twenty-four spools of braid of one color only, preserved as specified in 5.1, shall be packed in a fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. Level A unit packs shall be packed on the circular ends, four in length, three in width, and two in depth within a shipping container. Inside dimensions of the container shall be approximately 22 1/2 inches in length, 17 inches in width, and 12 1/2 inches in depth. Approximate dimensions are furnished as a guide only. The top and bottom of the contents of each container shall be covered with a sheet of 30-pound minimum basis weight kraft paper conforming to A-A-203. Each shipping container shall be closed, waterproofed, and reinforced in accordance with the appendix of PPP-B-636. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.2.2 Level B packing. Twenty-four spools of braid of one color only, preserved as specified in 5.1, shall be packed in a fiberboard shipping container conforming to style RSC, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. Level A unit packs shall be packed on the circular ends, four in length, three in width, and two in depth within a shipping container. Inside dimensions of the container shall approximately 22 1/2 inches in length, 17 inches in width, and 12 1/2 inches in depth. Approximate dimensions are furnished as a guide only. The top and bottom of the contents of each container shall be covered with a sheet of 30-pound minimum basis weight kraft paper conforming to A-A-203. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

5.2.2.1 Weather-resistant shipping container. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of PPP-B-636.

* 5.2.3 Commercial packing. Braid, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

* 5.3 Palletization. When specified (see 6.2), braid, packed as specified in 5.2.2 and 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Pallet type shall be type I (4-way entry), type IV or type V in accordance with MIL-STD-147. Each prepared load

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.

shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet pattern shall be number 3 in accordance with appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

* 5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers, unit packs, and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. The braid is intended for use as piping on clothing.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. When a first article is required (see 3.2, 4.3, and 6.4).
c. Color required (see 3.4.1).
d. Put-up if other than specified (see 3.6).
e. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
f. Type and class of unit load required (see 5.2.1).
j. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
h. When palletization is required (see 5.3).

6.3 Standard sample. For access to samples, address the contracting activity issuing the invitation for bids.

6.4 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

6.5 Scouring. For industry guidance, the braid should be thoroughly scoured in order to remove surface dye.

Source: https://assist.dla.mil -- Downloaded: 202610-21T19:14Z
Check the source to verify that this is the current version before use.

* 6.6 Dye and formulations. Suggested dye formulations for the following colors are as follows:

Marine Corps Green 2220	Army Green 260
Disperse Blue - 73	Disperse Navy Blue - SWG
Disperse Orange - 41	Disperse Yellow - 92
Disperse Yellow - 42	Disperse Brown - 1

6.7 Reinforcement end color. Shade of the single reinforcement end (cotton yarn) is inconsequential. The single reinforcement end (cotton yarn) need not be dyed to match the color of the braid.

* 6.8 Subject term (key word) listing.

Braid, polyester
Clothing
Piping

6.9 Changes from previous issue. The margins of this document are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only, and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content, as written, irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - NU
Air Force - 11

Preparing activity:

Army - GL

Project No. 8315-0325

Review activities:

Army - MD
Air Force - 82, 99
DLA - CT

User activity:

Navy - MC

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS. In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY
US Army Natick Research and Development Center
Natick, Massachusetts 01760

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D C
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development Center
ATTN: STRNC-ES
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 202610-21T19:14Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions - Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-B-40092D	Braid, Textile, Cord-Edge, Polyester

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)* _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* - Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* - Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* - Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATIONAL Apr 94

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:14Z
Check the source to verify that this is the current version before use.