MIL-R-40075C
17 August 1982
SUPERSEDING
MIL-R-40075B
8 November 1967

MILITARY SPECIFICATION

REFLECTOR, LIGHT, GASOLINE LANTERN

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers a gasoline lantern light reflector.

2. APPLICABLE DOCUMENTS

2.1 Government documents. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

SPECIFICATIONS

FEDERAL

TT-E-529	-	Enamel Alkyd, Semi-Gloss.
TT-P-1757	-	Primer Coating, Zinc Chromate, Low-Moisture-Sensitivity.
PPP-B-636	-	Boxes, Fiberboard.

STANDARDS

FEDERAL

FED-STD-151	-	Metals; Test Methods.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Natick Research and Development Laboratories, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 6260

2310

Source: https://assist.dla.mil -- Downloaded: 20261O-21T19:12Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-1188 - Commercial Packaging of Supplies and Equipment.

DRAWING

US ARMY NATICK RESEARCH AND DEVELOPMENT LABORATORIES

5-13-1884 - Reflector, Light, Gasoline Lantern.

(Copies of documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

2.2 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence.

3. REQUIREMENTS

3.1 Materials and components. The materials and components shall be as specified herein and on the applicable drawings. Materials and components not definitely specified shall be of the quality normally used by the manufacturer provided the completed item complies with all the provisions of this document (see 6.4).

3.1.1 Aluminum. The aluminum shall conform to alloys 5252, temper H25; 5257, temper H25; 5457, temper 0 or temper 25; 5557, temper 0 or 5657, temper H25. The aluminum shall be analyzed in accordance with Method 111 or 112 of FED-STD-151.

3.1.2 Primer. The primer shall conform to composition G or L, color Y of TT-P-1757.

3.1.3 Enamel. The enamel shall conform to class A, composition G or L, Olive Drab color No. 24087 of TT-E-529.

3.2 Design and construction. The design and construction of the reflector shall be as specified herein and as shown on Drawing 5-13-1884. The reflector may be fabricated with a lock seam or may be spun in one piece from any one of the aluminum alloys specified in 3.1.1.

2310

Source: https://assist.dla.mil -- Downloaded: 202610-21T19:12Z
Check the source to verify that this is the current version before use.

3.3 Finish. After fabrication, the interior surface shall be buffed, chemically bright dipped, and followed by anodizing in accordance with industry practice in such a manner as to produce a uniform bright natural finish; or electropolished (see 6.3). After anodizing, or electropolishing; the exterior surface shall be coated with primer specified in 3.1.2. After primer has thoroughly dried, the exterior surface shall be coated with enamel specified in 3.1.3. The enamel finish shall level out to produce a smooth and uniform surface.

3.4 Marking identification. The reflectors shall be marked with the manufacturer's name or readily identifiable trademark.

3.5 Workmanship. The light reflector shall be free from burrs or sharp edges. If applicable, the lock seam shall be free from any malformations. The interior reflector finish shall be free from discoloration, abrasions, whitening or blemishes. The exterior finish shall be free from runs, wrinkles or areas of no film, orange peel, foreign matter, or separation of color (flooding or floating).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.2.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified or qualified in this document or applicable purchase document.

4.2.1.1 Certification. The contractor shall furnish a certificate of compliance that the applicable material conforms to the aluminum requirements of 3.1.1.

4.2.2 End item examination. The end item shall be examined in accordance with 4.2.2.1 and 4.2.2.2. A lot shall consist of all reflectors offered for inspection at one time. The sample unit for visual and dimensional examination shall be one completely fabricated reflector.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:12Z
Check the source to verify that this is the current version before use.

4.2.2.1 Visual examination. Examination shall be made of the end item and shall be examined in accordance with the defects in table I. The inspection level shall be level II and the acceptable quality level (AQL) shall be 2.5 for major defects and 6.5 for total (major and minor combined) defects per hundred units.

TABLE I. Visual examination

Examine	Defect	Classification Major	Minor
Finish	Not as specified		X
Exterior (topside)	Not free from runs, wrinkles, orange peel, foreign matter, or separation of color (loading or floating) or area of no film		X
Interior (reflecting inside)	Not reflective finished as specified, i.e. Not uniform bright natural finish or electropolished (ALZAK)	X	
Design, construction, and workmanship	Not as specified	X	
	Lock seam, if applicable, not free from malformation		X
	Not free from burrs or sharp edges		X
Identification marking	Missing, incomplete, illegible, or incorrect		X

4.2.2.2 Dimensional examination. The end item shall be examined for conformance to the specified dimensions. Any measurement deviating from the specified dimension shall be classified as a defect. The inspection level shall be S-2 and the AQL shall be 4.0 defects per hundred units.

4.4.3 Packaging inspection. An examination shall be made to determine that preservation, packing, and marking comply with section 5. Defects shall be scored in accordance with table II. The sample unit shall be one shipping container fully packaged. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:12Z
Check the source to verify that this is the current version before use.

TABLE II. Packaging defects

Examine	Defect
Marking (interior and exterior)	Omitted; incomplete; incorrect, illegible; of improper size, location, sequence, or method of application.
Materials	Component missing or damaged.
Contents	More or less than required.

5. PACKAGING

5.1 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.1.1 Level A packing. Fifty reflectors shall be packed, with a wide opening down, in a snug-fitting fiberboard shipping container conforming to style RSC-L, grade V2s or PPP-B-636. The reflectors shall be nested, fifty in depth, with a sheet of 15-pound minimum basis weight kraft paper placed between each reflector. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V and reinforced as specified in the appendix of PPP-B-636.

5.1.2 Level B packing. Fifty reflectors shall be packed, with the wide opening down, in a snug-fitting fiberboard shipping container conforming to style RSC-L, type CF, (variety SW), or type SF, class domestic, grade 275 of PPP-B-636. The reflectors shall be nested, fifty in depth, with a sheet of 15-pound minimum basis weight kraft paper placed between each reflector. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Closure shall be in accordance with method II of the appendix of PPP-B-636.

5.1.2.1 Weather-resistant fiberboard container. When specified (see 6.2), the shipping container shall be a V3c, V3s or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636.

5.1.3 Commercial packing. Reflectors shall be packed in accordance with MIL-STD-1188.

5.2 Marking. In addition to any special marking required by the contract or purchase order shipping containers shall be marked in accordance with MIL-STD-129 or MIL-STD-1188, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:12Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The reflector is intended to confine and reflect a portion of the light rays from the lantern into a downward area of direction when used with the military gasoline field lantern.

6.2 Ordering data. Acquisition documents should specify the following data:

(a) Title, number and date of this document.
(b) Selection of applicable level of packing (see 5.1).
(c) When V3c, V3s or V4s fiberboard is required for level B pack (see 5.1.2.1).

6.3 Finish electro brightening or electropolishing processes. The ALZAK process is developed by the Aluminum Company of America. Other commercial processes include fluroberic acid, sodium carbonate and sulfuric-phosphoric-chromic acid treatments. Other trade names are Battelle and Baytal processes.

6.4 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the document (see 3.1).

6.5 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - MC
Air Force - 82

Preparing activity:

Army - GL

Project No. 6260-0049

Review activities:

Army - MD
DLA - GS

Source: https://assist.dla.mil -- Downloaded: 202610-21T19:12Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-R-40075C Reflector, Light, Gasoline Lantern

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1 OCT 76 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T19:12Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY CARD

FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development
Laboratories
ATTN: DRDNA-ES
Natick, MA 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 202640-21T19:12Z
Check the source to verify that this is the current version before use.