MIL-C-10113C(EA)
AMENDMENT 1
18 July 1986

MILITARY SPECIFICATION

COVER, OUTLET VALVE (FOR C15 OUTLET VALVE)

This amendment forms a part of MIL-C-10113C(EA), dated 16 September 1974, and is approved for use within the Chemical Research, Development and Engineering Center, Department of the Army and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

Replace paragraph 3.2.2 "Test Slabs" with the following:

"3.2.2 Test slabs and equivalent cure. Test slabs shall be molded from stock representative of the formulation used for preproduction sample and from each sublet during regular production of outlet valve covers *in* accordance with ASTM D 3182. The slabs shall have a cure equivalent to that of regular production outlet valve covers. Equivalent cure is established when physical properties are in conformance with table I at a given cure time and temperature and that the percent free sulfur of the slab and the part are equivalent. Objective evidence shall be submitted in accordance with 4.1.2.3. Once cure time and cure temperature are established, they may not change during production."

PAGE 4

Add the following new paragraph 4.1.2.3:

"4.1.2.3 Equivalent cure. After date of award of contract, and prior to submission of preproduction, and without additional cost to the Government, the contractor shall submit the information listed below which will constitute evidence for establishing equivalent cure for a given formulation at optimal cure time and cure temperature for each mold used in the contract. The information relating to the cure may be classified as "company confidential" and this information will be so treated by the Government.

(a) Different combinations of cure time and temperature for slabs and parts, approaching and surpassing optimum cure shall be finished

(b) percent free sulfur for slabs and parts shall be furnished for each time/temperatue combinations.

FSC 4240

DISTRIBUTION STATEMENT A, Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:33Z
Check the source to verify that this is the current version before use.

(c) All physical property data from table I shall be generated for slabs and shall be furnished for each time/temperature combinations. In addition, any physical property data from table I which can be generated for outlet valve covers shall be furnished for each time/temperature combination.

(d) Any other information and data which substantiates the equivalency of cure at the established cure time and cure temperature."

Custodian:

Army - EA

Preparing activity:

Army-EA

Project No. 4240-A852

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:33Z
Check the source to verify that this is the current version before use.