MILITARY SPECIFICATION

BATTERY, DRY FOR XM122 FIRING DEVICE

This specification is approved for use by the U.S. Army Armament Research and Development Command and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers requirements, quality assurance provisions, preparation for delivery, the fabrication, manufacture of one type of battery for the XM122 Firing Device Transmitter. The battery is composed of electrochemical cells of the zinc-potassium hydroxide-manganese dioxide type.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposals, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-A-48078 - Ammunition, Standard Quality Assurance Provisions, General Specification For

MIL-W-76 - Wire and Cable, Hook-up, Electrical Insulated

MIL-W-6858 - Welding, Resistance: Aluminum, Magnesium, Non-Hardening Steels or Alloys, Nickel Alloys, Heat-Resisting Aloys, and Titanium Alloys; Spot and Seam

MIL-B-55521 - Battery, Dry Packaging and Packing

FEDERAL

L-P-513 - Plastic Sheet, Laminated, Thermosetting, Paper-Base, Phenolic-Resin

QQ-N-290 - Nickel Plating (Electrodeposited)

QQ-S-571 - Solder: Lead Alloy, Tin Lead Alloy and Tin Alloy; Flux Cored Ribbon and Solid Form

FSC: 1375

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Armament Research and Development Command, Attn. DRDAR-QA, Dover, New Jersey 07801 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED. STD. No. 595 - Colors

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

MIL-STD-143 - Specification and Standard Order of Precedence for the Selection of

DRAWINGS

U.S. ARMY ARMAMENT RESEARCH AND DEVELOPMENT COMMAND

9296723 - Battery 18 Volt

3. REQUIREMENTS

3.1 Selection of specifications and standards. - Specifications and standards for necessary commodities and services not specified herein shall be selected in accordance with MIL-STD-143.

3.2 Components and assembly. - The components and assembly shall comply with all requirements of specification drawing 9296723 and associated drawings and with all requirements specified in applicable specifications and drawings. When a definite material or component is specified, it shall be in accordance with the applicable specification or requirement. When deemed necessary by the Government, certification from the source of the material or component will be required. In the absence of certification from the source, a certificate of analysis or certified inspection data will be required.

3.3 Metals. - All metals which do not enter into the basic electrochemical reaction of the cell shall resist or be treated to resist corrosion when subjected to any test or storage conditions specified herein.

3.4 Dissimilar metals. - When dissimilar metals which would adversely affect battery performance are used in intimate contact with each other, protection against electrolysis and corrosion shall be provided.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

3.5 Electrolyte leakage. - There shall be no evidence of electrolyte leakage on the external surfaces of the jacket at any time prior to or during the performance of test specified in 4.8.7 or any other tests specified herein. Electrolyte leakage shall be considered to have occurred when a drop of phenolphthalein solution placed on the battery turns pink or red.

3.6 Design and construction. - Batteries shall be of the design, construction, physical dimensions, weight, and polarity specified. (See 3.2)

3.6.1 Battery voltage.

3.6.1.1 Open-circuit voltage. - The open circuit voltage shall be a maximum of eighteen volts plus two and seven tenths volts (18 V + 2.7 V).

3.6.1.2 Closed-circuit voltage. - The closed-circuit voltage shall be greater than sixteen and forty hundredths volts (16.40 V) when measured across a twenty five plus or minus five per cent (25 ± 5%) ohm resistive load.

3.6.2 Insulating, impregnating, potting and sealing compounds. - The insulating, impregnating, potting and sealing compounds shall exclude moisture from insulating material without impairing its electrical characteristics. When tested as specified in 4.8.1.1, the potting and sealing compounds shall not flow at high temperature (160°F) nor crack or draw away from the sides of a container at low temperature (-40°F) or during any temperature change between +160°F and -40°F sufficiently to impair electrical connections.

3.6.3 Filler or padding. - Filler or padding if used shall be a cushioning electrically nonconducting material which maintains its insulating characteristics under adverse environmental conditions.

3.6.4 Cell-block container. - Cell-block containers shall be an insulating material that surround a group or a stack of individual cells.

3.6.5 Intercell separation. - A separator shall be placed between cells in series connected multicell batteries. The separator shall be an insulating material.

3.6.6 Intercell connections. - Intercell connections shall be spot welded in accordance with MIL-W-6858, class B, or soldered depending upon the applicable terminal. Connections between cell blocks and between cell block and terminal shall be so insulated or positioned as to avoid contact with other conducting material or jacket of the battery. When insulated wire is soldered to terminal lugs, it shall not be bared more than 3/32 inch from the lug nor shall it extend more than 3/32 inch beyond the lug.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

3.6.7 Age of Cells. - The minimum age of cells, from the time of their fabrication to the time of their presentation for acceptance inspection as batteries, shall be 5 days. The maximum age of cells, from the time of their fabrication to the time of their shipping date shall be 90 days. Batteries shall be submitted for acceptance inspection not more than 30 days prior to the shipping date.

3.6.8 Socket.

3.6.8.1 Socket Components. - Contact components, of socket terminals shall be made of phosphor bronze, berylium copper, spring brass or steel suitably plated to resist wear and corrosion. Sockets shall be designed and constructed so that there will not be contact of any of the pins of the mating plug to any socket terminal other than those for which such pins are intended and there shall be no contact between the mating plug and any conducting surface of a cell or bare wires connecting the cells without using undue force. Insulating materials shall be plastic. The pinhole-spacing tolerances shall be ± .005 inch.

3.6.8.2 Socket Mounting. - The socket shall be so supported and mounted that the top surface of the socket shall not protrude above the adjacent surface of the jacket and shall be not more than 1/16 inch below the surface of the jacket, initially, during, and after subsequent insertions of the mating plug. The socket pin-circle center shall be located as specified, and the jacket opening shall be positioned so that its center is within 3/32 inch diameter circle whose center coincides with the socket pin-circle center, initially, during and after insertions of the mating plug. The angular orientation of the socket shall be within 5° of the battery centerlines or other lines of orientation as specified.

3.6.8.3 Contact resistance. - Contact resistance between each socket insert and the applicable pin of the mating-plug when tested in accordance with 4.8.2.1.1 shall not exceed .005 ohm.

3.6.9 Jacket. - The jacket shall consist of nonmetallic materials. The cells shall fit snugly enough to minimize movement.

3.6.9.1 Jacket Coating. - If a wax coating is used on the jacket, micro-crystalling wax or equal shall be used. All excess wax shall be removed from the external surfaces of the jacket.

3.6.9.2 Waterproofing of jacket (WOJ). - The jacket shall not fall apart and the seams shall remain intact when tested as specified in 4.8.3.1.

3.6.9.3 Color of Jackets. - The color of exposed surfaces of jackets shall match one of the following lusterless greens 34079, 34086, 34087, 34096, 34102, 34127, and 34128 per Federal Standard No. 595.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

3.7 Capacity. - When the battery is tested for capacity as specified in 4.8.6 the discharge time period to termination of test as specified in 4.8.6.5 shall be not less than the minimum time specified below:

Test	Storage Period	Temperature	Minimum Svce Req'd (Hrs)
I (Initial 70 F)	48 Hrs Min.	70 F	40
LT (0 F)	16 Hrs Min.	0 F	8
HT (160 F)	7 Days plus	160 F	
	48 Hrs Min.	70 F	35

The battery shall be discharged through 200 ± 0.5% ohms continuously to an end voltage of 10.8 volts.

3.8 Vibration. - After the batteries have been tested as specified in 4.8.9 they shall meet the visual and mechanical, dimensional, closed circuit voltage and terminal requirements.

3.9 Mechanical shock. - After the batteries have been tested as specified in 4.8.10 they shall meet the visual and mechanical, dimensional, closed circuit voltage and terminal requirements.

3.10 Insulation resistance. - The insulation resistance between all terminals and the container of the battery, shall be not less than 5 megohms when tested as specified in 4.8.8.

3.11 Labeling and marking. - All labeling and marking shall be clear and legible throughout all of the tests specified herein.

3.12 Workmanship. - Batteries shall be processed in such a manner as to be uniform in quality and shall be free from defects that will affect their life, serviceability, or appearance.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection and standard quality assurance provisions. - Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this specification.

4.1.1 Instrument accuracy.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

4.1.1.1 Voltmeters and ammeters. - All voltmeters and ammeters used in testing the batteries shall be accurate within 1 percent of the full-scale value. The voltmeter and ammeter ranges shall be such that all readings are taken on the upper half of the scale. The sensitivity of voltmeters shall be not less than 1,000 ohms per volt.

4.1.1.2 Resistor tolerances. - During all tests involving discharge through a resistance, such resistance shall be accurate within 0.5 percent. In determining the resistance used as a test load, the resistance of all continuously operating voltmeters shall be considered as part of the specified load.

4.1.1.3 Timing. - Timing equipment shall be accurate within 0.5 percent.

4.2 Classification of inspection. - The examination and testing of batteries shall be classified as follows:

(a) Materials and components inspection. (See 4.4)

(b) First Article inspection. (See 4.5)

(c) Quality conformance inspection.

(1) Inspection of product for delivery. (See 4.6.1)

(2) Inspection of preparation for delivery. (See 4.6.2)

4.3 Inspection conditions. - Except as otherwise specified herein, all examinations and tests shall be performed at a temperature of 80° ± 20°F. (26.7° ± 11.1°C), ambient atmospheric pressure, and relative humidity.

4.4 Materials and components inspection. - Materials and components inspection shall consist of verification by certification from the source that the materials and components used in fabricating the batteries are in accordance with applicable requirements prior to such fabrication. In the absence of certification from the source a certificate of analysis or certified inspection data shall be required as proof of conformance to applicable requirements.

4.5 First Article Inspection.

4.5.1 Submission. - The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.5.2. The first article sample shall consist of ninety five (95) batteries, part number 9296723.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

4.5.2 Inspections to be performed. - See MIL-A-48078 and Table I specified herein.

TABLE I - First Article Inspection

Group	No. of Batteries	Examination & Test	Req. Par.	Method of Test Par.
I	25	Visual-Mechanical (External)	3.6	4.8.1
		Battery voltage	3.6.1	4.8.5
		Dimensions and weight	3.2	4.8.4
		Vibration	3.8	4.8.9
		Mechanical Shock	3.9	4.8.10
		Insulation Resistance	3.10	4.8.8
		Capacity Discharge I	3.7	4.8.6.1.1
		Contact Resistance	3.6.8.3	4.8.2.1.1
II	20	(15) Electrolyte leakage	3.5	4.8.7
		(3) WOJ	3.6.9.2	4.8.3.1
		(2) Visual-Mechanical (Internal)	3.6	4.8.1
III	25	Visual-Mechanical (External)	3.6	4.8.1
		Battery voltage	3.6.1	4.8.5
		Capacity Discharge HT	3.7	4.8.6.1.2
IV	25	Visual-Mechanical (External)	3.6	4.8.1
		Battery Voltage	3.6.1	4.8.5
		Capacity Discharge LT	3.7	4.8.6.1.5

4.5.3 Rejection. - See MIL-A-48078.

4.6 Quality conformance inspection.

4.6.1 Inspection lot formation. - Inspection lots shall comply with the lot formation provisions of MIL-A-48078.

4.6.2 Group A inspection. Each unit on contract or purchase order shall be inspected for conformance to the inspections specified in Table II . Discrete lots shall be formed from units that pass this inspection. Factors of lot composition not defined herein, or in the contract or purchase order, shall be in accordance with MIL-STD-105. Each lot shall be subject to sampling inspection, utilizing the procedures of MIL-STD-105, using the general inspection levels, and AQL's indicated in Table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

TABLE II - Group A Inspection

Examination and Test	Requirement Paragraph	Method of Test Para.	AQL Major	AQL Minor	Insp. Level
Visual-Mechanical (External)	3.6	4.8.1	1.0%	4.0	II
Battery Voltage	3.6.1	4.8.6	1.0%	-	II

4.6.3 Group B_1 inspection. - This inspection, including sampling, shall conform to Table III and to special procedures for small-sample inspection of MIL-STD-105. Group B_1 inspection shall be performed in the order listed in Table III on the same sample batteries and shall normally be performed on inspection lots that have passed group A inspection and on samples selected from units that have been subjected to and met the group A inspection with the exception that the WOJ test can at the option of the manufacturer be performed on any batteries representing the inspection lot.

TABLE III - Group B_1 Inspection

Examination and Test	Requirement Paragraph	Method of Test Para.	AQL	Insp. Level
Dimensions & weight	3.2	4.8.4	1.0%	S-1
Insulation Resistance	3.10	4.8.8	1.0%	S-1
Vibration	3.8	4.8.9	2.5%	S-1
Mechanical Shock	3.9	4.8.10	2.5%	S-1
Battery Voltage	3.6.1	4.8.5	2.5%	S-1
Visual-Mechanical (External)	3.6	4.8.1	2.5%	S-1
WOJ		4.8.3.1	2.5%	S-1
Electrolyte Leakage	3.5	4.8.7	1.5%	S-4

4.6.4 Group B_2 Inspection. - This inspection, including sampling, shall conform to Table IV and to special procedures for small-sample inspection of MIL-STD-105. Group B_2 inspection shall be performed on separate samples for each sub-group and shall normally be performed on inspection lots that have passed group A inspection and on samples selected from units that have been subjected to and met the group A inspection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

TABLE IV - Group B_2 Inspection

Examination and Test	Requirement Paragraph	Method of Test Para.	AQL	Insp. Level
Subgroup I:				
HT	3.7	4.8.6.1.2	4.0%	S-3
Subgroup II:				
LT	3.7	4.8.6.1.3	4.0%	S-3

4.6.5 DELETED

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

4.6.6 Determination of Compliance. - The entire contract lot shall be considered as complying when the test results of the Group A, B_1 and B_2 tests show compliance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

4.6.7 Deleted

4.6.8 Packing. - The unit packages shall be packed in a shipping container in accordance with Specification MIL-B-55521 for Level C Packing (See 5.1). Maximum gross weight of shipping containers for these samples shall be sixty (60) pounds.

4.7 Inspection of preparation for delivery. - Inspection of preparation for delivery shall be accomplished in accordance with the quality assurance provisions of Military Specification MIL-B-55521.

4.8 Methods of examination and tests.

4.8.1 Visual and mechanical examination. - Batteries shall be examined to determine compliance with all applicable requirements and characteristics listed in Table VII. When internal examination is necessary it shall be performed either during fabrication of the battery, or by dismantling the finished battery.

4.8.1.1 Potting. - The manufacturer shall determine the minimum weight of an adequately potted battery, and shall not present for acceptance any batteries failing to meet this minimum weight requirement. This shall be done by determining the minimum weight of a battery filled with a sufficient quantity of potting material to withstand the vibration and mechanical-shock tests specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

TABLE VII - Visual and Mechanical Examination

Requirement	Requirement Paragraphs
External	
Design and construction 1/	3.6
Sockets	3.6.8
Jacket	3.6.9
Internal	
Dissimilar metals	3.4
Filler or padding	3.6.3
Cell-Block container	3.6.4
Intercell separation	3.6.5
Intercell Connections	3.6.6
Age of cells	3.6.7
Insulating, impregnating Potting and sealing compounds	3.6.2

1/ With exception of dimensions and weight shall be performed in group B_1 inspection.

4.8.1.1.1 Flow or shrinking. - Potting and sealing compounds, when used, shall be placed in a container, approximately 3 inches wide by 6 inches long by 3/4 inch high, to within 1/4 inch of the top. The temperature of the compound within the container shall be raised to 160° ± 5°F. (71.1° ± 2.8°C.) and the container shall be held in an inverted position for 24 hours. Then the temperature of the compound shall be lowered to -40° ± 5°F. (-40° ± 2.80°C.) The flow, cracking or shrinking of the compound from the sides of the container shall be noted and the batteries shall be examined to determine that there is no impairment of electrical contact. If flow is noted at 160° ± 5°F. (77.1° ± 2.8°C.) five batteries of type involved shall be exposed to 160° ± 5°F. (77.1° ± 2.8°C.) storage for 24 hours with terminals resting in lowest possible position. At the end of this exposure period batteries shall be examined to determine that there is no impairment of electrical contact. (See 3.6.2)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

4.8.2.1 Socket terminals.

4.8.2.1.1 Contact resistance. - Contact resistance between each socket insert and the applicable pin of the mating-plug shall be measured after insertions No. 1, 10, 11, and 20 while a current of 5 amperes is flowing through the point of contact.

4.8.3 Jacket.

4.8.3.1 Waterproofing of jackets (WOJ). - All multicell batteries and paper jacketed single cell batteries shall be immersed to within 1/4 inch of the top of the jacket in water maintained at a temperature of 160° ± 5°F. (71.1° ± 2.8°C.) for a period of 48 hours. In case of multicell metallic jacketed batteries the metal containers without covers may be subjected to this test in place of assembled batteries. In the case of nonmetallic jacketed batteries the jackets may be applied to dummy batteries in place of actual batteries. Condition of the jacket and its seams shall be observed.

4.8.4 Dimensions and weight. - Batteries shall be examined by gaging or measuring and by weighing to determine conformance.

4.8.4.1 Dimensions. - All dimensions shall include any coating which may be used, and shall remain within the specified tolerances throughout the required tests. When box gages are used, the batteries shall be loaded with a weight of five (5) pounds. The batteries shall pass freely through the applicable gage openings. The inside dimensions of the box gage shall be the specified maximum outside dimensions of the battery.

4.8.5 Battery Voltage.

4.8.5.1 Open-circuit voltage. - A direct current voltmeter of proper range and sensitivity shall be used to measure the open-circuit voltage.

4.8.5.2 Closed-circuit voltage. - A direct current voltmeter of proper range and sensitivity shall be used to measure the closed circuit voltage utilizing resistance specified.

4.8.6 Capacity.

4.8.6.1 Capacity Tests. - Sample batteries selected for capacity tests shall be stored and discharged, as applicable, in accordance with 4.8.6.1.1 through 4.8.6.5.

4.8.6.1.1 Capacity Test I. - Discharge at 70°F without previous storage specified in 4.8.6.3.

4.8.6.1.2 Capacity Test HT. - Discharge at 70°F after one week (7 days) storage at 160°F.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

4.8.6.1.3 Capacity Test LT. - Discharge at 0°F after storage at 0°F for a minimum of sixteen (16) hours.

4.8.6.2 Ambient storage and discharge conditions. - The ambient conditions specified in Table VIII shall prevail during storage and discharge periods. Normal conditions shall be maintained insofar as possible. Deviations from normal conditions are permitted, provided that: (1) the extreme conditions specified in Table VIII do not exist for more than five percent (cumulative) of the specified storage or discharge periods; and (2) that at no time are the extreme conditions exceeded.

4.8.6.3 Storage. - Sample batteries (packaged per contract) shall be stored at applicable storage conditions for the specified period. (See 3.7) The storage period shall be considered to have started from the date the batteries are actually placed in storage.

4.8.6.4 Stabilization preceding discharge. - Following storage, and conditioning, when applicable, the batteries shall be further stored for 48 hours at ambient discharge conditions specified in Table VIII. Prior to initiation of discharge, LT samples shall be stored at 0°F for a minimum of sixteen (16) hours.

4.8.6.5 Discharge - Following stabilization the batteries shall be discharged at the ambient discharge conditions specified in Table VIII. The discharge shall be terminated when any one of the following conditions occur:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

TABLE VIII - AMBIENT STORAGE AND DISCHARGE CONDITIONS

Kind of Storage or Discharge	Normal Conditions		Extreme Conditions	
	Temperature	Relative Humidity	Temperature	Relative Humidity
HT Storage	160° + 3°F - 7°F (71.1° + 1.7°C) - 3.9°C)	NA	140°F (60°C) thru 153°F (67.2°C) and 163°F (72.8°C) thru 165°F (73.9°C)	NA
LT Storage and discharge	0°F ± 2°F. (-17.7°C. ± 1.1°C)	NA	-5°F (20.5°C) thru -2°F. (18.8°C) and +2°F.(-16.6°C) thru +5°F(-15°C)	NA

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

(a) The battery voltage falls below the specified test-end voltage.

(b) The battery dimensions exceed the maximum specified. (See 3.2)

(c) Electrolyte leakage becomes apparent on the exterior surface of the battery.

4.8.7 Electrolyte leakage. - Sample batteries shall be discharged as specified in 3.7 and then stored for 15 days. Fifty percent of the batteries shall be stored in an inverted position. The storage and discharge shall be performed at inspection conditions specified in 4.3. During the 15-day storage period, each battery shall be examined daily for evidence of electrolyte leakage on the external surfaces of the jacket. (See 3.5).

4.8.8 Insulation resistance. - Insulation-resistance test shall be performed. Batteries shall be stored for a period of 48 hours at 70° ± 5°F. (21.1° ± 2.8°C) and a relative humidity of 50 ± 15 percent. After storage and while at these conditions, the insulation resistance shall be measured by applying a direct-current potential of 500 ± 20 volts between any two terminals not electrically connected and between all ungrounded terminals and the container of the battery. The insulation resistance of batteries having a nonmetallic container shall be measured by the use of a 1 inch-square copper plate making physical contact with the container. The plate shall be placed with the broad surface against any area of any surface of the jacket other than that on which the battery terminals are located.

4.8.9 Vibration. - Vibration test shall be performed. Each battery shall be rigidly clamped to the platform of a vibration machine in a manner approximating as closely as practicable the manner in which the batteries are clamped when in use. A simple harmonic motion shall be applied having an amplitude of 0.03 inch (0.06 - inch total maximum excursion). The frequency shall be varied at the rate of 1 cycle per second per minute between the limits of 10 and 55 cycles per second. The entire range of frequencies and return shall be traversed in 95 ± 5 minutes for each mounting position, (direction of vibration) of the battery. The batteries shall be vibrated in three equal periods in mutually perpendicular directions, one of which shall be perpendicular to the terminal face of the battery. Open-circuit voltage shall be observed for 30 seconds during the last quarter of each of the three vibration periods.

4.8.10 Mechanical shock. - Mechanical shock test shall be performed except as otherwise specified. Each battery shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of the battery. Each battery shall be subjected to a total of three shocks of equal

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.

magnitude. The shocks shall be applied in each of three mutually perpendicular directions. Each shock shall be supplied in a direction normal to a face of the battery. The faces of the battery are identified by their position in relation to the front face (the face which bears the label). For each shock, the battery shall be accelerated in such a manner that during the first 3 milliseconds the minimum average acceleration is 75 gravity units (G). The peak acceleration shall be between 125 to 175 G.

5. PREPARATION FOR DELIVERY

5.1 Preservation, packaging, packing and marking. - Preservation, packaging, packing and marking shall be in accordance with Military Specification MIL-B-55521. Preservation and packaging shall be level A or C with each unit packaging containing one battery, and packing shall be level A, B, or C, as specified in contract or order.

6. NOTES

6.1 Intended use. - The components and assemblies covered by this specification are intended for use as the battery for the XM122 firing device transmitter. This specification is to be used only as a guideline in establishing an updated version of this device.

6.2 Ordering data. - See Section 6.1 and 6.2 of MIL-A-48078.

6.3 Submission of inspection equipment designs for approval (See MIL-A-48078). Submit equipment designs as required to:

Commander
ARRADCOM
Dover, New Jersey 07801
ATTN: DRDAR-QAA-I

6.4 Distribution of ammunition data cards, inspection results and test data. - Distribution of ammunition data cards, inspection and test results shall be submitted to:

Commander
ARRADCOM
Dover, New Jersey 07801
ATTN: DRDAR-QAA-Q

Custodian:

Preparing Activity:
Project Number:1375-A-195

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T02:15Z
Check the source to verify that this is the current version before use.