INCH-POUND
A-A-50067B
January 13, 2026
SUPERSEDING
A-A-50067A
February 27, 1995

COMMERCIAL ITEM DESCRIPTION

CLOTH, FLANNEL, WOOL

The General Services Administration has authorized the use of the Commercial Item Description (CID) by all federal agencies.

1. SCOPE. This CID covers the one (1) type of cloth, flannel, wool used as a facing for the underside of the collar of uniform coats and overcoats.

2. CLASSIFICATION. The cloth shall be of one (1) type in one of the following classes:

2.1 Classes.

Class 1 - Heavy weight, 4.3 ounces per square yard
Class 2 - Medium weight, 2.9 ounces per square yard
Class 3 - Light weight, 2.2 ounces per square yard
Class 4 - Light weight, 2.4 ounces per square yard
Class 5 - Medium weight, 3.0 ounces per square yard
Class 6 - Medium to heavy weight, 3.6 ounce per square yard

3. SALIENT CHARACTERISTICS.

3.1 Material requirements. The cloth shall be plain; weave wool or wool blend evenly sheared containing up to 20 percent nylon and mothproofed with an approved treatment. Unless otherwise specified, a certificate may be submitted and will be acceptable for the stated requirement. The minimum beneficial width of the cloth shall be a minimum of 60 inches.

Beneficial comments, recommendations, additions, deletions, clarifications, and suggestions, or questions on this document should be sent to trpsptctstandardiz@dla.mil. Since contact information can change, verify the currency of the address information using ASSIST online database https://assist.dla.mil.

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.
Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

TABLE I. Physical and colorfastness requirements.

Characteristic	Requirement	Test method
Fiber identification, percentage 1/ Nylon Wool	 ≤ 20 ≥ 80	AATCC TM20A
Weight, oz./yd^2 minimum	(see 2.1)	ASTM D3776/D3776M Opt C
Yarns per inch, minimum Warp Filling	 26 23	ASTM D3775
Breaking strength, lbs., minimum Warp Filling	 24 19	ASTM D1682 Section 16

1/ No other fiber is permitted.

3.1.1 Color. The color shall be specified in the contract or procurement document. The finished cloth shall match the standard sample for shade and appearance and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced. (See 7.5).

3.1.1.1 Visual shade matching. The color and appearance of the Cloth, Flannel, Wool shall match the standard sample when viewed using the AATCC EP 9, Option C, (see 7.4.1) with a primary light source simulating the spectral quality of average daylight, CIE Illuminant D65, with a color temperature of 6500 (± 200) Kelvin (K) illumination of 100 (± 20) foot candles. Alternatively, the color and appearance of the cloth shall match the standard sample with a primary light source simulating artificial daylight, CIE Illuminant D75, with a color temperature of 7500K (± 200) illumination of 100 (± 20) foot candles in lieu of D65 (see 7.4.2). The cloth shall also be a good match to the standard sample with a secondary source simulating the spectral quality of incandescent lamplight, CIE Illuminant A, with a color temperature of 2856K (± 200).

3.3 Length and put-up. The cloth shall be furnished in rolls of continuous length, and each length shall be not less than 40 yards. Each roll shall weigh not more than 250 pounds.

3.4 Fiber identification. Each roll of finished cloth shall be labeled or ticketed for fiber content in accordance with the Title 16 CFR Part 303, Rules and Regulations under the Textile Fiber Products Identification Act. (See 7.1.2).

3.4.1 Wool identification. The finished cloth containing wool shall be labeled in accordance with Wool Products Labeling Act. (See 6.1 and 7.1.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

3.5 Toxicity. Unless otherwise specified in the contract or procurement documents the finished cloth shall not present a health hazard and shall show compatibility with prolonged, direct skin contact when tested as specified in 3.5.1.

3.5.1 Toxicity test. When the toxicity requirement (see 3.5) can be demonstrated with historical use data on the finishing treatments used, toxicity testing may not be required (see 7.1.6 and 7.6).

3.6 Workmanship. The finished cloth shall conform to the quality of the product established in this document. The cloth shall be free from defects which would affect its serviceability, appearance, uniformity and quality assurance standards defined by the technical data in the procurement documents.

4. REGULATORY REQUIREMENTS. Unless otherwise specified, the offeror/contractor is encouraged to use recovered, recycled, bio based, and environmentally preferable materials to the maximum extent practicable, in accordance with paragraph 23.403, 23.404(b) of the Federal Acquisition Regulation FAR, or the sustainable acquisition of EO 13834; as applicable (see 7.1.4).

5. PRODUCT CONFORMANCE PROVISIONS.

5.1 Product conformance. The cloth flannel wool shall meet the salient characteristics of this CID and associated procurement documents (see 7.6), conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance.

5.2 Market acceptability. The finished cloth flannel offered must have been sold to the government or commercial market.

5.3 Inspection procedures. Sampling for inspection shall be conducted in accordance with ASQ/ANSI Z1.4 - Sampling Procedures and Tables for Inspection of Attributes (see 7.2.2).

5.4 Visual examination. The finished cloth shall be examined for the defects listed below as defined in ASTM D3990.

TABLE II. Visual examination defects.

Material defects: Any spot, or stain more than 1-inch in its longest dimension; any hole, cut or tear; missing end or pick, thick or thin areas; width less than specified; overall uncleanliness; crease or hard crease; slubs, slugs or gout; shade bar, streaks or uneven dying.
Label: Label missing, incorrect, or illegible. Required information missing or not in accordance with the contract or procurement documents.
Packaging: Not packaged in accordance with the contract or procurement documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

5.5 Acceptance criteria. Acceptance criteria shall be as specified in the contract or procurement document (see 7.6).
5.5.1 Mothproofing treatment. Mothproofing of the wool fabric shall be in accordance with MIL-DTL-43665.

6. PACKAGING. The preservation, packing, and marking shall be as specified in the contract or order (see 7.6).

6.1 Label/tag. Each roll shall be individually bar-coded with the Type VII or VIII, Class 17 label/tag of MIL-DTL-32075. This label/tag shall be located so that it is completely visible on each roll and causes no damage to the roll. Fiber information for labeling should be in accordance with 3.4.

7. NOTES

7.1 Source of Government documents:

7.1.1 Copies of Government documents are available online at https://quicksearch.dla.mil.

7.1.2 Title 16 CFR Part 300; Rules And Regulations Under the Wool Products Labeling Act of 1939 and Title 16 CFR Part 303, Rules and Regulations under the Textile Fiber Products Identification Act (Copies of these documents are available online at https://www.ecfr.gov.)

7.1 EPA information is available online at https://www.epa.gov and EO 13834 information is available online at https://www.fedcenter.gov/.

7.1.4 United States Standards for Grades of Wool are available online at https://ams.usda.gov.

7.1.5 Federal Acquisition Regulations (FAR) are available online at https://acquisition.gov.

7.1.6 Toxicity testing. If dermal toxicity testing is required, it will be conducted using Title 40, Protection of Environment, Code of Federal Regulations current edition and applicable sections, which are also consistent with the following OECD tests:

Skin Sensitization 406 and Dermal Irritation 404 (https://www.oecd-ilibrary.org/environment/oecd-guidelines-for-the-testing-of-chemicals-section-4-health-effects_20745788?page=1).

Dermal Sensitization (https://www.law.cornell.edu/cfr/text/40/798.4100).
Dermal Toxicity (https://www.law.cornell.edu/cfr/text/40/798.2250).

7.2 Source of non-Government documents.

7.2.1 AATCC Test Methods are available for purchase online at https://aatcc.org.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

7.2.2 ASQ/ANSI Z1.4 – Sampling Procedures are available online at https://asq.org.

7.2.3 ASTM Standards are available for purchase online at https://www.astm.org.

7.3 Intended use. This cloth is intended to be used as pocketing, waistband and lining for dress and service clothing items.

7.4 Standard samples. For access to standard shade samples of the cloth address the contracting activity issuing the invitation for bids or request for proposal.

7.4.1 Visual shade matching. In 2017, Option A of AATCC EP9 was changed to Option C. NOTE: In case of confusion, the viewing geometry should be "The specimen plane and illumination source will be parallel to each other and aligned so that the light flux is incident at the center of the specimen plane, which is set at a 35 (± 5º) angle relative to the horizontal. The observer will view the specimens at a 90º angle, relative to the plane of the specimens."

7.4.2 In 2022, the U.S. Military (All Services) accepted D65 as the new preferred light source for visual shade matching due to the supply chain issues with D75. DD1222's should reflect which light source is used. If the light source is not indicated on the DD1222, D65 will be assumed by the Government Shade Laboratory.

7.5 Certificate of compliance. The contracting activity may select to accept a certificate of compliance for a stated requirement.

7.6 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this CID.
b. Class required (see 2.1).
c. Color required (see 3.1.1).
d. When toxicity testing is required (see 3.5).
e. Product conformance provisions (see 5.1).
f. Acceptance criteria (see 5.5).
g. Packaging requirements (see 6).

7.7 Key words.

Clothing
Lining
Pocketing

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

CIVIL COORDINATING AGENCY
GSA-FAS

Custodians:
Army - GL
Navy - NU

Preparing Activity:
DLA-CT

(Project: 8305-2026-001)

Review activities:
Army - MD
Navy - MC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using ASSIST Online database at https://assist.dla.mil/.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:38Z
Check the source to verify that this is the current version before use.