MILITARY SPECIFICATION

CASE, CARTRIDGE, 105MM, M201

This specification is approved for use by the US Army Armament Research and Development Command, and is available for use by all Departments, and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification contains requirements not covered by the drawings and provides quality assurance provisions for the fabrication of parts and packing for one type of cartridge case, M201.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-A-48078	-	Ammunition, Standard Quality Assurance Provisions, General Specification for
MIL-C-46487	-	Cleaning, Preparation and Organic Coating of Steel Cartridge Cases

STANDARDS

MILITARY

MIL-STD-1167	-	Ammunition Data Card
MIL-STD-1169	-	Packaging, Packing and Marking for Shipment of Inert Ammunition Components

FSC: 1315

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Armament Research and Development Command, Attn. DRDAR-QA, Dover, New Jersey 07801 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

DRAWINGS

US ARMY ARMAMENT RESEARCH AND DEVELOPMENT COMMAND (ARRADCOM)

7548320	-	Cartons, Ammunition for Interplant Shipment of Brass, Aluminum and Spirally Wrapped Steel Cartridge Cases, Empty 75MM to 120MM Inclusive
8647258	-	Chamber Gage
11820669	-	Case, Cartridge, 105MM, M201

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer).

2.2 Other publications.-The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

ANSI-B46.1 Surface Texture

(Application for copies should be addressed to the American National Standards Institute, (ANSI), 1430 Broadway, New York, NY 10018).

ASTM	-	American Society for Testing and Materials
B117	-	Salt Spray (Fog) Test
E18	-	Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials, Test for

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Phila, Pa. 19103).

3. REQUIREMENTS

3.1 General.-The cartridge case shall comply with the requirements of the applicable drawings, referenced specifications and the following:

3.2 Protective coating.-Protective coating as specified on the applicable drawings and referenced specifications shall apply to all surfaces of the cartridge case regardless of contour configuration and shall be uniform and continuous.

3.3 Material.-The supplier shall be responsible for selecting from the classification list contained in the raw material specification, the surface and physical condition of the raw material intended for use in manufacture.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

3.4 Mechanical properties.-The mechanical properties specified on the applicable drawing and referenced specifications shall be uniform throughout each section.

3.5 Maximum profile and alignment.-Maximum profile and alignment of the cartridge case shall comply with the requirements of the applicable drawing.

3.6 First article inspection.-This specification contains technical provisions for First Article Inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

3.7 Functional.-The cartridge case shall be subjected to a functional test in the following phases:

Excess Pressure Phase
Cold Temperature Phase
Excess, Excess Pressure Phase (For Information Only)

3.7.1 Obturation.-The cartridge case shall effectively seal the breech of the weapon against leakage of gases generated during firing.

3.7.2 Soundness.-After firing, the cartridge case shall be free of cracks, or splits, except as permitted by Table II.

3.7.3 Ejection.-After firing, the cartridge case shall be ejected by the service extractors when the weapon is operated in the normal manner (see 6.2).

3.7.4 Primer retention.-The cartridge case shall retain its primer during firing and ejection.

3.8 Crimp integrity.-After crimping of the cartridge case to the projectile there shall be no evidence of wrinkles, bumps or folds around the cartridge case mouth (see 6.1).

3.9 Workmanship

3.9.1 General.-The requirements for workmanship are as specified on the applicable drawings, referenced specifications and the following:

3.9.2 Metal defects.-Prior to firing, the cartridge case shall be free from cracks, blisters, seams, laminations, deep scratches or porosity.

3.9.3 Threads.-Threads shall be full and undamaged for the entire minimum length or depth as required by the applicable drawings and specifications.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

3.9.4 Burr.-No cartridge case shall have a burr.

3.9.5 Foreign matter.-No cartridge case shall contain chips, dirt, grease, oil, rust, corrosion or other foreign matter.

3.9.6 Body/Base/Collar interface.-There shall be no evidence of interference between the collar and body in the region beyond the body seat groove.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.-Unless otherwise specified in the contract or herein, the provision of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

4.2 Classification of inspections.-The following types of inspection shall be conducted on this item:

a. First Article Inspection
b. Quality Conformance Inspection

4.3 First article inspection

4.3.1 Submission.-The contractor shall submit a First Article sample as designated by the Contracting Officer for evaluation in accordance with the provisions of 4.3.2. The First Article sample shall consist of the following items in sample quantities as indicated.

Part Description	Drawings	Quantity
Cartridge Case, Coated	11820669	270
Cartridge Case, Components Coated and Unassembled	11820669	4
Body, Uncoated	11820734	10
Base, Uncoated	11820733	10
Collar, Uncoated	8595384	10
Test Panels	See MIL-C-46487	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

250 of the above coated cartridge cases shall be forwarded to a designated proving ground for ballistic testing. The sample shall be manufactured using the same materials, equipment, processes, and procedures as will be used in regular production. All parts and materials, including packaging shall be the same as used in regular production and shall be obtained from the same source of supply. A first article sample or portion thereof, as directed by the procuring agency, shall also be submitted whenever there is a lapse in production for a period of 90 days or whenever a change occurs in manufacturing processes, materials used, drawings, specification, or source of supply, such as to significantly affect product uniformity as determined by the responsible technical agency.

4.3.2 Inspections to be performed.-The first article parts submitted in accordance with paragraph 4.3.1 will be subjected by the Government to any or all of the examinations and tests specified in the Item Detail Specification and to any or all the requirements of the applicable drawings and to the inspection of Table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

TABLE I - FIRST ARTICLE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-63209 (AR)

PARAGRAPH	TITLE	SHEET 1 OF 2	DRAWING NUMBER
	Case, Cartridge, 105MM, M201		See below
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Cartridge Case, Coated (Dwg. 11820669)				
	Examination for defects	270		3.1	4.4.4
	Examination of Body/Base/Collar interface	2		3.9.6	4.5.5
	Crimp integrity	250		3.8	4.5.6
	Ballistic test				
	a. Excess, Excess Pressure (Info only)	100		3.7	4.5.4.1
	b. Excess Pressure	100		3.7	4.5.4.2
	c. Cold Temperature	50		3.7	4.5.4.3
	Cartridge Case Components, Coated and Unassembled (Dwg. 11820669)				
	Thickness of coating	4		3.1	4.5.3
	Salt Spray	2		3.1	4.5.3.1
	Body, Uncoated (Dwg. 11820734)				
	Examination for defects	10		3.1	4.4.4.3
	Hardness	10		3.4	4.5.1
	Base, Uncoated (Dwg. 11820733)				
	Examination for defects	10		3.1	4.4.4.2
	Hardness	10		3.4	

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

TABLE I - FIRST ARTICLE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS MIL-C-63209 (AR)

PARAGRAPH	TITLE		SHEET 2 OF 2		DRAWING NUMBER
	Case, Cartridge, 105MM, M201				See below
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Collar, Uncoated (Dwg. 8595384)				
	Examination for defects	10		3.1	4.4.4.1
	Hardness	10		3.4.1	4.5.1
	Test Panels (See MIL-C-46487)				
	Weight of coating	2		3.1	See MIL-C-46487
	Flexibility test	2		3.1	See MIL-C-46487

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

4.3.3 Rejection.-See MIL-A-48078.

4.4 Quality conformance inspection

4.4.1 Inspection lot formation.-Inspection lots shall comply with the lot formation provisions of MIL-A-48078.

4.4.2 Examination.-See MIL-A-48078.

Unless otherwise specified in the classification of defects and test tables, sampling plans for major and minor defects shall be in accordance with MIL-STD-105, Inspection Level II.

4.4.3 Tool control dimensions.-Dimensions marked tool control shall be gaged during First Article testing and after each 250 items produced on each machine in operation and prior to any tooling change. Where destruction of components is necessary to inspect these dimensions, measurements of the tool may be substituted provided the contractor has established correlation between the tool dimensions and the component dimensions prior to the start of production. The contractor shall be responsible for maintaining adequate surveillance to assure that drawing requirements are being met throughout the life of the tool. Corrective action will immediately be instituted by the contractor whenever a defective tool control dimension is found. All material produced prior to periodic inspection will be rejected and screened whenever a defective tool control dimension is found.

4.4.4 Classification of defects

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS MIL-C-63209 (AR)

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.4.1	Collar, Prior to Coating		8595384
			NEXT HIGHER ASSEMBLY
			11820669

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	True position of large outside diameter to small outside diameter		0.40%	3.1	Gage
102	Small outside diameter		0.40%	3.1	Gage
103	Distance from rear face to flange, max.		0.40%	3.1	Gage
104	Total length		0.40%	3.1	Gage
105	Distance from rear face to forward inside angle		0.40%	3.1	Gage
106	Thickness of flange		0.40%	3.1	Gage
107	Width of rear surface		0.40%	3.1	Gage
108	Depth of groove		0.40%	3.1	Gage
109	Width of groove wall		0.40%	3.1	Gage
110	Metal defective		0.40%	3.1	Visual
111	Crack in weld zone (if applicable)		0.40%	3.1	Visual
Minor					
201	Large outside diameter		0.65%	3.1	Gage
202	Angle of the forward face		0.65%	3.1	Gage
203	Radii or chamfers, missing or incorrect		0.65%	3.1	Visual
204	Foreign matter		0.65%	3.9.5	Visual
205	Burr		0.65%	3.9.4	Visual

NOTES:

Standards Store https://assist.dla.mil - Downloaded: 2025-04-26T04:26Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

MIL-C-63209(AR)

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET 1 OF 2	DRAWING NUMBER
4.4.4.2	Base, prior to coating		11820733
			NEXT HIGHER ASSEMBLY
			11820669

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	True position of collar groove with forward outside diameter		0.40%	3.1	Gage
102	True position of primer hole counterbore diameter with minor diameter		0.40%	3.1	Gage
103	True position of the minor diameter with the forward outside diameter		0.40%	3.1	Gage
104	Runout of rear outside diameter		0.40%	3.1	Gage
105	Rear outside diameter		0.40%	3.1	Gage
106	Forward outside diameter		0.40%	3.1	Gage
107	Diameter of outside edge of collar groove		0.40%	3.1	Gage
108	Width of collar groove openings		0.40%	3.1	Gage
109	Pitch diameter of primer threads, max.		0.40%	3.1	Gage
110	Minor diameter of primer threads, max.		0.40%	3.1	Gage
111	Angle of collar groove sidewall (both sides)		0.40%	3.1	Gage
112	Metal defective		0.40%	3.9.2	Visual
Minor					
201	Diameter of counterbore		0.65%	3.1	Gage
202	Depth of counterbore		0.65%	3.1	Gage
203	Depth of collar groove		0.65%	3.1	Gage
204	Depth of recess of body seat		0.65%	3.1	Gage

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-63209 (AR)

PARAGRAPH	TITLE		SHEET 2 OF 2		DRAWING NUMBER
4.4.4.2	Base, prior to coating				11820733
					NEXT HIGHER ASSEMBLY 11820669
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
205	Diameter of raised surface (if applicable)		0.65%	3.1	Gage
206	Length of collar groove protrusion, max. (if applicable)		0.65%	3.1	Gage
207	Thickness through base at raised surface (if applicable)		0.65%	3.1	Gage
208	Thickness through base below raised surface		0.65%	3.1	Gage
209	Thickness of flange		0.65%	3.1	Gage
210	Width of collar groove protrusion, max. (if applicable)		0.65%	3.1	Gage
211	Width of flat in the recess		0.65%	3.1	Gage
212	Maximum offset of the diameter of the outside surface of the collar groove		0.65%	3.1	Gage
213	Maximum offset of the diameter of the inside surface of the collar groove		0.65%	3.1	Gage
214	Surface finish improper		0.65%	3.1	Visual
215	Foreign matter		0.65%	3.9.5	Visual
216	Burr		0.65%	3.9.4	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-63209 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 11820734
4.4.4.3	Body, Prior to Coating				NEXT HIGHER ASSEMBLY 11820669
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Thickness, blanked steel		0.40%	3.1	Gage
102	Outside Radius (at rear)		0.40%	3.1	Gage

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-63209 (AR)

PARAGRAPH	TITLE		SHEET 1 OF		DRAWING NUMBER
4.4.4.4	Cartridge Case				11820669
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Inside diameter of the mouth		100%	3.1	Gage (see Note 1)
102	Maximum profile and alignment		100%	3.5	Gage (4.5.2)
103	Collar cracked in weld area (if applicable)		0.40%	3.1	Visual
104	Number of wraps		0.40%	3.1	Visual
105	Evidence of poor workmanship		0.40%	3.9	Visual
106	Metal defective		0.40%	3.9.2	Visual
107	Hardness	10		3.4	4.5.1 (see 6.5)
108	Body/Base/Collar interface	4.4.5.4		3.9	4.5.5
109	Excess pressure ballistic test	4.4.5.2.1		3.7	4.5.4.2
110	Crimp integrity	4.4.5.2.1		3.8	4.5.6
Minor					
201	Length to forward datum diameter, min.		0.65%	3.1	Gage
202	Length to rear datum diameter, min.		0.65%	3.1	Gage
203	Total length		0.65%	3.1	Gage
204	Protective coating inadequate or damaged		0.65%	3.2	Visual
205	Varnish in primer hole		0.65%	3.1	Visual
206	Compound missing in primer hole		0.65%	3.1	Visual
207	Marking missing, incorrect or illegible		0.65%	3.1	Visual
208	Foreign matter		0.65%	3.9.5	Visual
209	Burr		0.65%	3.9.4	Visual

NOTES: 1. Minimum I.D. of the mouth (including ovality) will be determined by a plug (4.101 dia) in the bottom of the max. profile gage.

ARMY Acquisition Process Data.mil -- Downloaded: 2026-01-20T04:26Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-C-63209 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.4.5	Packing, Carton, Prior to Sealing				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major	None defined				
Minor					
201	Improper assembly		0.65%	3.1	Visual
202	Incorrect number of cartridge cases in carton		0.65%	3.1	Visual
203	Separation missing or damaged		0.65%	3.1	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS MIL-C-63209 (AR)

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.4.6	Carton, Packed and Sealed				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major	None defined				
Minor					
201	Carton damaged, cut or gouged through all layers		0.65%	3.1	Visual
202	Carton improperly sealed		0.65%	3.1	Visual
203	Contents loose		0.65%	3.1	Visual/Manual
204	Marking missing, incorrect or illegible		0.65%	3.1	Visual

NOTES:

DRDAR-QA Form 160 Jul 77 Replaces SARPA-QA Form 2567 Feb 74 Which is Obsolete

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

4.4.5 Inspection testing.-The following test shall be performed in accordance with the provisions of 4.5.

4.4.5.1 Protective coating.-The samples to be used for the specified tests shall be coated components, for example base, collar and body. The sample size and acceptance criteria shall be as specified in MIL-C-46487. Failure to comply with the requirements shall be cause for taking the corrective action prescribed herein.

4.4.5.2 Functional.-The following proving ground functional tests will be performed by the Government.

4.4.5.2.1 Production lot sample.-One hundred cartridge cases from each production lot of 25,000 or less, will be ballistically tested in the excess pressure phase. When lots exceed 25,000 cartridge cases, 4 additional cartridge will be tested for every 1,000 or fraction thereof, above 25,000. Acceptance and rejection criteria shall be in accordance with Table II. The lot shall be considered eligible for retest, using double the number of samples, provided that after firing, no cartridge case contains cracks or splits within one caliber of the head, and the rejection criteria of Table II has not been attained.

TABLE II

Defect	Characteristic	First Sample Accept	First Sample Reject	Cumulative Sample Accept	Cumulative Sample Reject
1.	Obturation	0	2	1	2
2.	Splits or cracks through all layers within 1 caliber of head	0	1	not permitted	
3.	Splits or cracks in sidewall more than 1 caliber from head*	1	3	2	3
4.	Ejection	0	2	1	2
5.	Primer retention	0	2	1	2
6.	Loose assembly	0	1	not permitted	
7.	Crimp integrity	0	2	1	2

*Splits or cracks within one caliber of the head that do not extend through all layers of metal shall be considered the same as defect characteristic 3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

4.4.5.3 Inspection equipment.-The inspection equipment required to perform the examinations and tests prescribed herein is described in the "Paragraph Reference/Inspection Method" column in the tables starting with paragraph 4.4.4.1. The contractor shall submit for approval inspection equipment designs in accordance with the terms of the contract. See Section 6 of the MIL-A-48078 and 6.5 herein.

4.4.5.4 Body/Base/Collar interface.-In order to determine the integrity of the body/collar crimp two samples shall be inspected from each shifts production as per 4.5.5. The samples shall be one from the middle of the work shift and one from the end of the work shift. An additional sample shall be taken, if any change to the process is made, directly after the change is made. Failure of any sample to comply with the requirements shall be cause for rejection of the product produced subsequent to the last inspection.

4.5 Test methods and procedures

4.5.1 Hardness.-Samples selected in accordance with 4.4.4.4 will be tested as follows: The body shall be removed from the base by cutting through the body approximately one inch from the rear face of the base. The bottom portion of the body and the collar shall be removed from the base. Seven hardness values shall be taken across the center of the rear face of the base on both sides of the primer hole at approximately 1/4 inch intervals. Four hardness values shall be taken on the underside of the flange of the collar approximately 90 degrees apart. The large portion of the body shall be hand straightened to permit hardness values to be taken, both vertically and horizontally at approximately 2 inch intervals, through the center of the length and width of the piece. All hardness values shall be taken on bare metal, and in accordance with the procedures prescribed by ASTM E-18.

4.5.2 Maximum profile and alignment gage.-The cartridge case, after application of the protective coating shall freely enter the maximum profile gage described on drawing 8647259. The gate of the gage shall close without interference with the cartridge case head.

4.5.3 Protective coating.-The methods and procedures for performing these tests will be in accordance with the requirements of MIL-C-46487.

4.5.3.1 Salt spray.-The salt spray test shall be performed using a 20 percent sodium chloride solution with the equipment and criteria prescribed by ASTM Method B117.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

4.5.4 Functional

4.5.4.1 Excess, excess pressure phase.-The cartridge case shall be assembled into a complete round in the same manner as required for service firing. The propellant charge will be such as to produce a chamber pressure of 45,600 psi (314.4 MPa) to 46,800 psi (322.7 MPa). The complete round will be temperature conditioned at plus 70°F ± 5°F (21.1°C ± 2.8°C) and fired in a serviceable weapon for which the round is standard. The weapon will be operated in the service manner.

4.5.4.2 Excess pressure phase.-The cartridge case shall be assembled into a complete round in the same manner as required for service firing. The propellant charge will be such as to produce a chamber pressure of 42,500 psi (293.0 MPa) to 45,600 psi (314.4 MPa). The complete round will be conditioned at plus 70°F ± 5°F (21.1°C ± 2.8°C) and fired in a serviceable weapon for which the round is standard. The weapon will be operated in the service manner.

4.5.4.3 Cold temperature phase.-The cartridge case shall be assembled into a complete round in the same manner as required for service firing. The propellant charge will be such as to produce a chamber pressure of 35,000 psi (241.3 MPa) to 38,000 (262.0 MPAa). The complete round will be temperature conditioned at minus 35°F (-37.2°C) to minus 45°F (-42.8°C) and fired in a serviceable weapon for which the round is standard. The weapon will be operated in the service manner.

4.5.5 Body/Base/Collar interface.-The samples taken in accordance with 4.4.5.4 shall be cut along a center line of the cartridge case and inspected for the following characteristics:

a. Distance from outside wall of base to a single ply of the body----------Gage

b. Metal defects----------Visual (see 3.9.2)

c. Poor Workmanship----------Visual (see 3.9)

All inspections shall be on the same sectioned part and shall be gaged on the same half of the part.

4.5.6 Crimp integrity.-The samples selected in accordance with para. 4.4.5.2.1 and Table I shall be inspected for crimp integrity (see 3.8) by means of both a visual and ring gage inspection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Preservation and packing

5.1.1 Level C-minimum military pack.-The cartridge cases shall be packed in accordance with requirements of drawing 7548235.

5.2 Labeling and marking.-Labeling and marking for shipment shall be in accordance with MIL-STD-1169.

5.3 Data card.-Data card information shall be in accordance with MIL-STD-1167.

6. NOTES

6.1 Prior to fabrication of a first article sample the contractor upon approval of the contracting officer may make and submit for evaluation up to five (5) process control lots. These process control lots shall consist of not less than ten (10) nor more than twenty-five (25) cartridge cases each. The contractor shall furnish all information pertaining to the manufacture of the lots to the contracting officer. All costs for testing these process control lots will be borne by the Government.

6.2 The term "ejected" shall mean that the cartridge case is thrown free of the breech of the weapon to permit loading of the subsequent round.

6.3 Visual examination qualification.-When compliance with the applicable requirements is in doubt as a result of visual examination, this characteristic may be measured or gaged to determine acceptability.

6.4 Ordering data.-See MIL-A-48078.

6.5 Mechanical properties.-The number of specimens and their location are for the convenience of the contractor and government and shall not restrict the contractor or government from testing additional specimens at other locations to determine that properties of the components conform to drawing requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

6.6 Submission of inspection equipment designs for approval.-See MIL-A-48078.-Submit equipment designs, as required to:

Commander
US Army Armament Research and Development Command
ATTN: DRDAR-QAR-I
Dover, NJ 07801

6.7 Drawings.-Drawings listed in Section 2 of this specification under the heading US Army Armament Research and Development Command (ARRADCOM) may also include drawings prepared by, and identified as Edgewood Arsenal, Frankford Arsenal, Rock Island Arsenal, or Picatinny Arsenal drawings. Technical data originally prepared by these activities is now under the cognizance of ARRADCOM.

6.8 Submission of test data and ammunition data cards.-In addition to the normal distribution of records when the projectile is procured by the Army Armament Material Readiness Command, one copy of all ballistic test data and ammunition data cards shall be forwarded to each of the following: Commander, ARRADCOM, ATTN: DRDAR-LCU-M and DRDAR-QAR-E, Dover, N.J. 07801; and Commander, ARRCOM, ATTN: DRSAR-QAM, Rock Island, Ill. 61201.

Custodian:
Army-AR

Preparing Activity
Army-AR

Project Number: 1315-A144

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

CASE, CARTRIDGE, 105MM, M201 MIL-C-63209

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1 OCT 76 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:26Z
Check the source to verify that this is the current version before use.