PPP-C-26B
AMENDMENT-1
December 29, 1977

FEDERAL SPECIFICATION

CANNED BAKED, CANNED STEAMED, AND CANNED STEAMED AND

RETORTED SUBSISTENCE ITEMS, PACKAGING AND PACKING OF

This amendment, which forms a part of Federal Specification PPP-C-26B, dated January 20, 1976, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 4

Table I, under Fruitcake column. Delete "5 oz. (141.7g)" and substitute "4-3/4 oz. (134.7g)".

PAGE 5

Table II, for Product "Chocolate Nut Roll" under Baking column. Delete "320°F (160°C) and substitute "375°F (191°C)"; for Product "Orange Nut Roll" under Baking column. Delete "325°F (163°C)" and substitute "375°F (191°C)".

PAGE 8

3.5.1.1. Delete the second, third & fourth sentences & substitute "For canned baked items, except fruit cake, a code indicating an 8 hour production shift, and day of production shall be included on one end or on the body of the can."

PAGE 9

3.5.2.1. Delete the second and third sentences and substitute "In addition, the date of pack (day, month, and year) shall be shown on one end or the body of the can."

PAGE 13

Table X, end of title. Add "and embossing defects (4.4.4)"; in table under Category, Major B column. Add "153" and on the same line under Defects column. Add "Evidence of discoloration in embossing."

PAGE 15

Add new paragraph as follows: "4.4.4 Copper sulphate metal exposure test for embossing defects. Components in test solution and the test procedures with this solution are as follows:

Test solution - (acid copper sulphate solution):

Copper sulphate crystals - 20 percent by weight.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:49Z
Check the source to verify that this is the current version before use.

Concentrated (37%) hydrochloric acid - 10 percent by weight.
Distilled water - 70 percent by weight.

Test procedures:

Immerse embossed lids or cans in acid copper sulphate solution. At the end of five minutes remove lids or cans and rinse with running tap water.

Examine the embossed digits and letters (as applicable) for discoloration. Any discoloration due to bare metal exposure within the digits or letters shall be cause for rejection.

NOTE: Can and lid samples for the test procedures may be the same as those used in vacuum determination."

Military Custodians:

Army - GL
Navy - SA
Air Force - 45

Civil Agency Coordinating Activities:

AGRI - AMS, APS
GSA - FSS
VA - DMS

Review Activities:

Army - SM, MD
Navy - MC
DP - SS

Preparing Activity:

Army - GL

Project No. 8920-0369

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:49Z
Check the source to verify that this is the current version before use.