PPP-P-1150
July 9, 1973
SUPERSEDING
Fed. Spec. PPP-P-115C
December 14, 1964

FEDERAL SPECIFICATION

PADS, PAPER, MACERATED

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies

1 SCOPE AND CLASSIFICATION

1.1 Scope This specification covers macerated paper pads made of two sheets of kraft paper separated by an evenly distributed cushioning medium.

1.2 Classification

1.2.1 Types Pads covered by this specification shall be of the following types as specified.

Type I - Pads consisting of two sheets of kraft paper separated by cushioning material.

Type II - Pads consisting of two sheets of kraft paper separated by cushioning material with an additional facing sheet of tissue paper to provide abrasion protection. Pads will be a minimum of 18 inches wide.

1.2.2 Sizes Macerated paper pads may range from 6 to 60 inches in width and 12 to 180 inches in length.

2 APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications

UU-P-268 - Paper, Kraft, Untreated, Wrapping.
PPP-B-636 - Boxes, Shipping, Fiberboard.

Federal Standard

Fed Std No 123 - Marking for Domestic Shipment (Civil Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U S Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:49Z
Check the source to verify that this is the current version before use.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

National Motor Freight Traffic Association, Incorporated, Agent

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Associations, Inc., Tariff Order Section, 1616 P Street N.W., Washington, DC 20036.)

Uniform Classification Committee, Agent

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Materials

3.1.1 Liners. Liners shall be kraft paper which meets or exceeds minimum requirements of grade B of UU-P-268, and shall have a minimum 40 pound basis weight (24 by 36 - 500).

3.1.2 Facing sheet. Facing sheets shall be tissue having a minimum basis weight of 13 pounds single ply and 10 pounds double ply. The sheet shall be of such quality and texture that it will not abrade or mar finish surfaces of articles it is protecting.

3.1.3 Liner coating. The inside face of the liner shall be coated with a thermoplastic adhesive which enables the pads to meet the requirements of 3.2.

3.1.4 Cushioning material. The cushioning material shall be macerated paper.

3.1.5 Adhesive. The adhesive shall be a commercial type which shall affectively bind the tissue facing to the kraft liner.

3.2 Construction

3.2.1 Pad. The sealed edges at the sides and ends of the pads shall be uncushioned, a minimum of 1/2 inch and a maximum of 2 inches. The walls of the pad shall consist of a ply of kraft paper on each side of cushioning material. If tissue facing is specified it shall be sealed at the sides of the pad with a commercial adhesive.

3.2.2 Cushioning binder. Thermoplastic coating on the kraft sheets shall serve to bind the cushioning material in place. It shall be applied so as to prevent shifting or lumping of the cushioning material when tested in accordance with 4.4.1.

3.2.3 Cushioning material. Cushioning material shall be evenly distributed between the exterior liners of the pad at a thickness of between 1/8 and 3/16 inch. Compression properties of the cushioning material shall be determined according to 4.4.2.

3.2.4 Adhesion. The thermoplastic coating shall adhere to and seal the liners at all edges.

3.2.5 Bleeding. Pads shall show no evidence of bleeding when tested as described in 4.4.3.

3.3 Workmanship. Overall dimensions shall be accurate to within 1/4 inch and the workmanship shall be first class in every respect.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:49Z
Check the source to verify that this is the current version before use.

...ility as submitted to ...e per ...mance of the inspection requirements specified herein, unless ...s waived by ...e Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. When certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Sampling for inspection, testing and acceptance. Sampling for inspection, testing, and acceptance shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated. The lot size shall be the number of pads offered for delivery at one time, and shall consist of pads of the same size and type.

4.3 Inspection for defects. An inspection shall be made to determine that the pads meet the requirements set forth in this specification. Defects shall be scored as specified in table I. The inspection level shall be S-2 with an AQL of 6.5 defects per hundred units.

TABLE I

Examine	Defects
Material	Any component missing or damaged. Liners not kraft or do not meet requirements (see 3.1.1) Facing sheet not tissue or is wrong basis weight (see 3.1.2). Liner coating is not a thermoplastic type (see 3.1.3). Cushioning material is not macerated paper (see 3.1.4)
Construction	The edges are cushioned or do not meet the minimum or maximum dimensions (see 3.2.1). Any undue pad distortion (see 3.2.2) Thickness of cushioning material does not meet requirements (see 3.2.3). The thermoplastic coating does not adhere to or seal the liner at all edges (see 3.2.4)
Workmanship	Rips on exterior or interior surfaces of the pad Work not of good quality or not uniform Overall dimension not accurate within 1/4 inch (see 3.3)

4.4 Testing. The following tests shall be performed to determine structural defects in the pads. Failure of any test shall be counted as one major defect. The inspection level shall be S-2 with an AQL of 4.0 defects per hundred units.

4.4.1 Cushioning shifting test. Test pad samples shall be attached rigidly in a vertical position to a conventional vibrating machine and vibrated at an amplitude of 1/2 inch and a frequency of 300 c.p.m. for a period of 1 hour. At the end of this test, there shall be no noticeable shifting or lumping of the cushioning material within the pad.

4.4.2 Compression set test. Each sample consisting of 10 stacked pads, shall be subjected to a force of 0.2 pounds per square inch (p.s.i.) evenly distributed over the surface of the pads. The thickness of the pads under this pressure shall be considered the initial uncompressed thickness and maintained at this thickness for a period of 5 minutes. The pads shall then be released from all pressure for a period of 2 minutes and finally resubjected to the original force of 0.2 p.s.i. The difference between the original thickness of the 10 pads under a force of 0.2 p.s.i. (before compression) and the final thickness considered the compression set of the 10 pads. Compression set shall not exceed 20% of the measured initial uncompressed thickness. The test pad should be allowed to condition without any compression, for a period of 24 hours at 73.4° ± 3.6°F. and 50 ± 2 percent relative humidity before testing.

4.4.3 Bleeding test. The sample pads shall be placed in an oven for 3 hours at a temperature of 120° ± 5°F. There shall be no evidence of bleeding on the pad surface at the end of the test.

5 PREPARATION FOR DELIVERY

5.1 Packing. Packing shall be level A, B or C, and specified (see 6.2).

5.1.1 Level A. Pads of like size and type shall be packed in quantities as specified (see 6.2) ...ts fitting box conforming to PPP-B-636, class weather resistant, style RSC-L. Boxes shall ...closed, sealed, and reinforced in accordance with method V of the appendix to PPP-B-636.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:49Z
Check the source to verify that this is the current version before use.

5 1 2 Level B Pads of like size and type shall be packed in quantities as specified (see 6.2) in a close-fitting box conforming to PPP-B-636, class domestic, style RSC L Boxes shall be closed and reinforced in accordance with method II of the appendix to PPP-B-636

5 1 3 Level C Pads shall be packed to insure protection during shipment and safe delivery to destination in compliance with National Motor Freight Classification rules or the Uniform Freight Classification rules, as applicable

5 2 Marking. In addition to any special markings required by the contract or order, all marking shall be in accordance with 5.2.1 or 5.2.2 as specified (see 6.2).

5 2 1 Civil agencies All marking shall be in accordance with Fed Std. No. 123

5 2 2 Military agencies. All marking shall be in accordance with MIL-STD-129.

6 NOTES

6 1 Intended uses.

6 1 1 Macerated pads provide cushioned resilient protection to items, surfaces and finishes to prevent breakage or damage from marring, scratching or abrasion. Pads are useful in protecting such items as furniture, household goods, ceramics and mechanical assemblies

6 2 Ordering data Purchasers should select the preferred options permitted herein and include the following information in procurement documents

(a) Title, number, and date of this specification.
(b) Type (1 2 1)
(c) Size required
(d) Quantity
(e) Level of packing required (5 1)
(f) Whether civil or military marking is required (see 5 2)

Preparing Activity.

GSA-FSS

U. S. GOVERNMENT PRINTING OFFICE 1973 O - 544-600/1252

Orders for this publication are to be placed with the General Services Administration, acting as an agent for the Superintendent of Documents See section 2 of this specification to obtain extra copies and other documents referenced herein Price 10 cents each

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:49Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER

2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION

4. TYPE OF ORGANIZATION (Mark one)

- ☐ VENDOR
- ☐ USER
- ☐ MANUFACTURER
- ☐ OTHER (Specify)

b. ADDRESS (Street, City, State, ZIP Code)

5. PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER (Last, First, MI) – Optional

b. WORK TELEPHONE NUMBER (Include Area Code) – Optional

c. MAILING ADDRESS (Street, City, State, ZIP Code) – Optional

8. DATE OF SUBMISSION (YYMMDD)

DD FORM 1426 PREVIOUS EDITION IS OBSOLETE

FOLD ON THIS LINE

FOLD ON THIS LINE

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:49Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 5 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development
Laboratories
ATTN: ORDNA-SS (Mr. D. Juppino)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:49Z
Check the source to verify that this is the current version before use.