PPP-S-30D
AMENDMENT-4
November 22, 1976
SUPERSEDING
AMENDMENT-3
MARCH 30, 1976

FEDERAL SPECIFICATION

SACKS, SHIPPING, PAPER (CUSHIONED)

This amendment, which forms a part of Federal Specification PPP-S-30D, dated September 27, 1974, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 1

2.1, under Federal Standard, delete "Domestic" from title.

PAGE 2

3.1.1, Delete and substitute the following:

3.1.1 Liners. The paper used in the fabrication of the sacks shall be bleached or unbleached kraft, as specified (see 6.2). Unbleached kraft shall conform to the requirements of UU-B-268, grade B. Bleached kraft requirements shall be 65 pounds (24 x 36 - 500 basis weight) having a 38 pound minimum Mullen burst strength. Liners for each type sack shall be as follows:

Type I - 60 pound outer liner and 40 pound inner liner (24 x 36 - 500 basis weight).

Type II - 65 pound minimum outer liner (24 x 36 - 500 basis weight) 38 pound Mullen burst strength minimum.

Type III - 60 pound outer liner and 40 pound inner liner (24 x 36 - 500 basis weight).

Type IV - 60 pound outer liner and 40 pound inner liner (24 x 36 - 500 basis weight).

3.1.2.2, delete and substitute the following:

3.1.2.2 Type II. The cushioning material shall be closed cell plastic film conforming to PPP-C-795, class 1; have a nominal thickness of 3/16 inch and a maximum corresponding weight as shown in table IV. For self sealing sacks, add 0.2502 (see table IV and 6.2).

PAGE 3

3.1.3.3 Second line, after "seams", add, "and bottom folds".

Add the following in proper sequence:

3.1.4 Seam strength, type II. The sides, center and bottom seam strength shall be determined in accordance with 4.4.2.

3.1.5 Leakage, type II. The sacks shall show no evidence of leaking when subjected to the static leak test in 4.4.8.

3.2.2, At the end of paragraph, add, "alternatively, sacks may be fabricated from preformed tubular material, having a center seam, an open end and a heat-sealed bottom reinforced with a flat seam chain stitch".

FSC 8105

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:49Z
Check the source to verify that this is the current version before use.

PAGE 3 (con.)

3.2.2.2, third line, delete "4.4.6" and substitute "4.4.7"; fourth line, delete "Type IV".

3.3 Delete and substitute the following:

3.3 Dimensions. Dimensions of the sack shall be outside measurements, exclusive of flaps when provided (see 3.2.1 and 3.2.2.2), expressed as width by length. Dimensions shall be accurate to within 1/8 inch in width and 1/4 inch in length. Unless otherwise specified (see 6.2), sacks shall be furnished as specified in table IV.

PAGE 5

After first paragraph, insert "4.4.4 Seam strength test."

Second paragraph, first line, delete "4.4.4 Seam strength test" and substitute "4.4.4.1 Type I, III, and IV".

4.4.4.1 Last sentence, delete and substitute: "In all cases, the strength of the side seams, center and bottom seam or fold shall exceed the burst strength of the sack (see 3.1.3.3)".

Add new subparagraph "4.4.4.2 in proper sequence as follows:

4.4.4.2 Type II. Test specimen shall consist of a 3-inch wide strip cut from a side, center and bottom seam. The strip shall be placed in the grips of the testing machine of the constant rate-of-jaw separation type, equipped with a device for recording tensile load and rate of separation. The grips shall be moved apart at a uniform rate of 1.2 inches per minute until the seam breaks. Minimum strength of each side, center and bottom shall be 10 pounds per inch of seam width (see 3.1.4)".

Delete 4.4.8 in its entirety and substitute the following new paragraph:

4.4.8 Static leak test, type II. The sacks shall be filled to one half of the total length above the bottom with water and observed for 5 minutes. No leakage shall occur.

Add the following in proper sequence:

4.4.9 Examination of preparation for delivery. An examination shall be made to determine that packing and marking as required by section 5 are complied with. Defects shall be as specified in table II. The sample unit shall be one shipping container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 with an AQL of 2.5, expressed in terms of defects per hundred units.

TABLE II. Examination of preparation for delivery

Examine	Defect
Marking	Missing; incorrect; illegible; of improper size, location sequence, or method of application.
Materials	Components missing, damaged, or otherwise defective.
Contents	Number of components per container is more or less than required.

4.4.9.1 Examination of shipping containers. When shipping containers are required to be in accordance with PPP-B-636, examination for defects in closure, waterproofing and strapping shall be in accordance with PPP-B-636.

4.4.9.2 Examination of palletization. An examination shall be made to determine whether palletization as required by section 5 is complied with. Defects shall be as specified in table III. The sample unit shall be one palletized unit load ready for shipment. The lot shall be the number of palletized unit loads submitted for inspection at one time. The inspection level shall be S-1 with an AQL of 6.5, expressed in terms of defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:49Z
Check the source to verify that this is the currentversion before use.

PAGE 6

TABLE IV

Dimensions	Type I No. sacks per box	Type II No. sacks per box	Type II Max. sack weight	Type III No. sacks per box	Type IV No. sacks per box
4 x 8	500	500	.4 oz.	500	500
5 x 10	250	500	.6 oz.	500	500
6 x 10	250	500	.7 oz.	500	500
7-1/4 x 12	100	500	.9 oz.	200	250
8-1/2 x 12	100	250	1.0 oz.	200	250
8-1/2 x 14-1/2	100	250	1.3 oz.	200	250
9-1/2 x 14-1/2	100	250	1.4 oz.	200	250
10-1/2 x 16	100	250	1.7 oz.	100	250
12-1/2 x 19	50	100	2.3 oz.	100	125
14-1/4 x 20	50	100	2.7 oz.	100	125

6.1.1, delete last sentence beginning with "In" and ending with "breakage".

PAGE 7

6.2, delete options and substitute the following:

(a) Title, number, and date of this specification.
(b) Type, dimensions, and quantiy required (see 1.2 and table IV).
(c) State whether bleached or unbleached (see 3.1.1).
(d) With or without pressure-activated adhesive closure (see 3.2.2.2).
(e) Level of packing required (see 5.1).
(f) When palletization is not required (see 5.2).

Add new paragraph as follows:

6.3 Closures. Closures may be effected by heat-sealing, pressure-activated adhesive (see 3.2.2.2), or by stapling. Staples, when used, shall be spaced not less than 1 inch apart and not less than 1/4 inch form all edges.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:49Z
Check the source to verify that this is the current version before use.