PPP-T-70A
February 5, 1974
SUPERSEDING
Int. Fed. Spec. PPP-T-0070(GSA-FSS)
January 17, 1964

FEDERAL SPECIFICATION

TAPE, PACKAGING, PLASTIC FILM

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers a plastic film backed adhesive tape designed for use in packaging and packing applications and those applications where the properties of a thin, tough film are required.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specification:

PPP-T-680 - Tape, Pressure-Sensitive Adhesive: Packaging and Packing of.

Federal Standard:

Federal Test Method Std. 147 - Tapes, Pressure-Sensitive and Gummed; Methods of Inspection, Sampling and Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which included cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Backing. The backing material shall consist of a transparent plastic film.

3.1.2 Adhesive. The backing shall be coated on one side with a water insoluble adhesive requiring no moisture, heat, or other preparation prior to application to clean dry surfaces.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:49Z
Check the source to verify that this is the current version before use.

3.2 Physical properties.

3.2.1 General. The adhesive shall be such that the tape will adhere immediately and firmly to clean, dry surfaces to which it is applied (see 4.4.3). When the roll is unwound, the backing shall not tear, and the adhesive shall not transfer or split from the face of the tape to the back of the adjacent layer.

3.2.2 Physical tests. The test values must meet the requirements of table I.

3.2.3 Transparency. The tape shall be transparent enough to allow easy reading of 10 point type when tape is applied directly over it.

3.3 Finished tape.

3.3.1 Rolls. The tape shall be wound in rolls, adhesive side in, on cores made of paper-fiber or plastic. The core shall have sufficient rigidity to prevent distortion of the roll under normal conditions of transportation, storage, and use. The core shall have an inside diameter of 3 inches -0, +1/16 inches.

3.3.2 Length and width. The width shall be as specified in the contract or order. A width tolerance of ±1/32 inch will be allowed. The length shall be 72 yards or multiples thereof, as specified.

3.3.3 Splices. A maximum of 3 splices shall be allowed per each 72 yards of roll length. Any splices shall be such that it will not separate when the tape is unwound in test or application.

3.3.4 Weathering. After testing as described in 4.4.4 for 96 hours, the tape shall have an adhesion value as specified in table I and shall show no evidence of lifting or buckling that would impair the tapes serviceability.

TABLE I.

Property	Value	Test paragraph
Adhesion, oz/in. width, min.		
Initial	20	4.4.3
After accelerated aging	18	4.4.5
After accelerated weathering	30	4.4.4
Holding power, hours, min.	24	4.4.6
Tensile breaking strength, lbs/in.		
Dry	20	4.4.3
Wet	20	4.4.7
Elongation at break %, min.		
Dry	30	4.4.3
Wet	30	4.4.7
Bursting strength, lbs/sq. in. min.		
Dry	35	4.4.3
Wet	35	4.4.8
Water penetration rate, gm/100 sq. in. 24 hrs. max.	2.0	4.4.3

3.4 Workmanship. Workmanship shall be first class throughout. The tape shall be free from defects which detract from its appearance or impair its serviceability. The adhesive shall be a smooth, uniform coating, covering the entire area of one side of the tape. The edges of the tape shall be straight, true, and unbroken.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:49Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptance to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 End item examination. Sampling and examination of the end item shall be as specified in section 7 of Federal Test Method Std. No. 147.

4.3 End item testing. Sampling and examination for end item testing shall be as specified in section 7 of Federal Test Method Std. No. 147 at an Acceptable Quality Level (AQL) of 4 percent.

4.4 Tests. Tests for acceptance of individual lots shall consist of tests for all requirements specified in section 3.

4.4.1 Specimen. The specimen shall be selected and prepared as described in Method 4.1 of Federal Test Method Std. No. 147.

4.4.2 Conditioning. Condition the rolls as specified in Method 1.1 of Federal Test Method Std. No. 147.

4.4.3 Test methods. The following tests shall be conducted as described in Federal Test Method Std. No. 147, except that one specimen per sample shall be tested:

Adhesion	Method 10.2
Tensile strength	Method 30.2
Elongation at break	Method 30.2
Bursting strength	Method 44.2
Water penetration rate	Method 72.2

4.4.4 Accelerated weathering. One specimen per sample unit shall be tested as described in Method 63.2 of Federal Test Method Std. No. 147. Exposure shall be for 96 hours on a standard steel panel. Examine for conformance to 3.3.4. Test for adhesion as described in Method 10.2, 4.4.3, except do not remove the tape from the test pannel after weathering.

4.4.5 Accelerated aging. One specimen per sample unit shall be tested as described in Method 61.1 of Federal Test Method Std. No. 147, except that the exposure temperature shall be 120 $\pm 5^{\circ}$ F. and 80 ± 2 percent relative humidity. Exposure shall be 30 hours. Cool for 4 hours. Examine for adhesive transfer when separating the test strips and test for adhesion as described in Method 10.2, 4.4.3.

4.4.6 Holding power. Test one specimen per sample unit for holding power as described in Method 20.2, Federal Test Method Std. No. 147. Test at 73° F. only. Tape shall not slip more than 1/8 inch in 24 hours.

4.4.7 Wet tensile and elongation. Soak one specimen per sample unit in distilled water for 6 hours. Test immediately for tensile and elongation as described in Method 30.2, 4.4.3.

4.4.8 Wet bursting strength. Soak one specimen per sample unit in distilled water for 6 hours. Test immediately for bursting strength as described in Method 44.2, 4.4.3.

5. PREPARATION FOR DELIVERY

5.1 Packaging and packing. Packaging and packing shall be in accordance with the requirements of PPP-T-680. The levels of packaging and packing shall be A, B, or C as specified in the contract or order.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:49Z
Check the source to verify that this is the currentversion before use.

5.2 Marking. Containers of tape shall be marked in accordance with the requirements of PPP-T-680. When specified, the core of each roll of tape shall be marked on the inside or on the edge with numerals or letters indicating the month and year of manufacture and specification number. In addition, the manufacturer's name and designation of the product shall be marked on the core.

6. NOTES

6.1 Intended uses. The tape is intended for the closure and sealing of interior and exterior domestic containers. Printed on the adhesive side in appropriate manner and supplied on a liner it may be used as a packing list enclosure. It also is intended for label attaching and as a label covering material to protect labels from moisture and weathering. It is ideal for miscellaneous holding and sealing applications where a transparent, water-resistant, weather-resistant material is desired.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Width of tape required (see 3.3.2).
(c) Selection of applicable levels of packaging and packing (see 5.1).
(d) Marking required (see 5.2).

6.3 Storage. The tape should be stored in the original container in a cool location. It should not be stored in close proximity to steam pipes, radiators, or other sources of heat, or in a location where it may be exposed to direct rays of sun.

MILITARY CUSTODIANS:

Army - GL (MCA)
Navy - SA
Air Force - 84

Preparing activity:

GSA-FSS

Review activity:

Army - SM

Orders for this publication are to be placed with the General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 10 cents each.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:49Z
Check the source to verify that this is the current version before use.