INCH-POUND

MIL-C-43992B
28 June 1989
SUPERSEDING
MIL-C-43992A
10 May 1985

MILITARY SPECIFICATION

CLOTH, BROADCLOTH, POLYESTER/COTTON, DURABLE PRESS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers polyester/cotton broadcloth treated with a durable press finish.

* 1.2 Classification. The cloth shall be of the following classes as specified (see 6.2).

Class 1	-	3.5 to 4 oz	- Blue 1550
Class 2	-	3.5 to 4 oz	- White 3060
Class 3	-	3.8 to 4.3 oz	- Blue 1550
Class 4	-	3.8 to 4.3 oz	- Blue 1550
Class 5	-	3.8 to 4.3 oz	- Green 415
Class 6	-	3.5 to 4.0 oz	- Blue 3379

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

PPP-P-1134 - Packaging of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics)

MILITARY

MIL-T-43548 - Thread, Polyester Core: Cotton-, Rayon-, or Polyester-Covered

STANDARDS

FEDERAL

FED-STD-4 - Glossary of Fabric Imperfections
FED-STD-191 - Textile Test Methods

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Naval Publications and Forms Center, (ATTN: NPODS), 5801 Tabor Avenue, Philadelphia, PA 19120-5099.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies are available from the Federal Trade Commission, Correspondence Branch, Pennsylvania Avenue at Sixth Street, N.W., Washington, DC 20580-0001.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

Chromatic Transference Scale

Method 124 - Appearance of Durable Press Fabrics After Repeated Home Launderings

(Application for copies should be addressed to the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709-2215.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 1424 - Tear Resistance of Woven Fabrics by Falling-Pendulum (Elmendorf) Apparatus (DoD adopted)

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.

3.2 Standard sample. The finished cloth shall match the standard sample for shade and appearance and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.4).

3.3 Material. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

3.3.1 Fibers.

3.3.1.1 Polyester fiber. The fiber shall be polyethylene glycol terephthalate.

3.3.1.2 Cotton. The cotton shall be carded and combed.

3.3.2 Yarns. All yarns shall be a blend of polyester and cotton, drawn and spun into single yarns for both warp and filling. The finished cloth shall contain 65 ± 5 percent polyester and the remaining percentage cotton, based on the dry weight of the desized specimen. Tests shall be made as specified in 4.4.3.

* 3.4 Color. The color of the dyed and finished cloth shall be as follows:

Class 1, 3, or 4	Blue 1550
Class 2	White 3060
Class 5	Green 415
Class 6	Blue 3379

The color for classes 1, 3, 4, 5, and 6 shall be obtained by weaving with dyed and white yarns (see 3.5.2).

3.4.1 Labile sulfur. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dye stuff shall be chosen and applied so that the dyed and finished cloth shall contain no more labile sulfur than shown by the standard sample when tested as specified in 4.4.3. When a standard sample is not available, the dyed and finished cloth shall show no more than a slight trace of labile sulfur when tested as specified in 4.4.3.

* 3.4.2 Matching. The color of the finished cloth shall match the standard sample when viewed under filtered tungsten lamps that approximate artificial daylight and that have a correlated color temperature of 7500 ± 200K, with illumination of 100 ± 20 foot candles and shall be a good match to the standard sample under incandescent lamplight at 2300 ± 200K.

* 3.4.3 Colorfastness. The dyed and finished cloth shall show fastness to laundering (after 3 cycles), perspiration, light, and dry heat equal to or better than the standard sample or equal to or better than a rating of "good." The dyed and finished cloth shall show fastness to crocking equal to or better than the standard sample or shall have an AATCC Chromatic Transference Scale rating for crocking not lower than 3.5. Testing shall be as specified in 4.4.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

* 3.5 Physical requirements. The finished cloth shall conform to the requirements specified in table I when tested as specified in 4.4.3.

TABLE I. Physical requirements

Classes	Weight per sq yd, ounces		Yarns per inch, minimum		Breaking strength pounds, minimum		Tearing strength pounds, minimum	
	Min	Max	Warp	Filling	Warp	Filling	Warp	Filling
1	3.5	4.0	100	64	70	52	4.0	3.0
2	3.5	4.0	100	64	70	52	4.0	3.0
3	3.8	4.3	101	65	72	90	4.0	5.0
4	3.8	4.3	100	62	85	55	5.0	3.0
5	3.8	4.3	100	62	95	55	4.5	3.0
6	3.5	4.0	100	64	70	52	4.0	3.0

3.5.1 Weave. The weave shall be a plain weave.

* 3.5.2 Construction. Classes 1, 3, 4, 5, and 6 cloth shall be of an end-and-end construction with alternate dyed and white warp yarns and with an all white filling. The class 2 cloth shall be woven with all white yarns.

3.5.3 Width. The width of the cloth shall be as specified (see 6.2) and shall be the minimum acceptable width inclusive of selvages when fly shuttle looms are used, and exclusive of selvages and fringe when shuttleless looms are used.

3.6 Finish. The cloth shall be scoured, singed, stabilized, mercerized, and bleached when required to result in a smooth and lustrous finish equal in character to that of the standard sample. In addition, the cloth shall be given an approved durable press treatment (see 6.6) and shall be processed and cured to meet the requirements of this document.

3.7 Nonfibrous material. The starch and protein content, including chloroform-soluble and water-soluble material, prior to application of the durable press treatment shall not exceed 2.0 percent when tested as specified in 4.4.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

3.8 Appearance rating. The finished cloth shall have an appearance rating of not less than 3.5 when tested after five launderings as specified in 4.4.3.

3.9 Dimensional stability. The finished and cured cloth shall have dimensional changes of not more than 2.0 percent in either the warp or filling direction when tested as specified in 4.4.3. The preshrinking process used shall not be identified by name or trademark either on the cloth, ticket, or package.

3.10 pH. The pH value of the water extract of the finished cloth shall be no less than 5.0 nor more than 8.5 when tested as specified in 4.4.3.

3.11 Seam efficiency. The finished cloth shall have a seam efficiency of not less than 85 percent when tested as specified in 4.4.3.

3.12 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 40 yards. Each length shall be put-up on full width rolls as specified in 5.1.

3.13 Fiber identification. Each roll of cloth shall be labeled or ticketed for fiber content in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act.

3.13.1 Marking. The face side of the cloth shall be identified by applying a stamping on that side of the cloth with the word "FACE" at each end of the piece.

3.14 Workmanship. The finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards, when calculated as specified in section 4, shall not exceed the established maximum point value.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

* 4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Certificates of compliance. When certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

* 4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

* 4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.2.1 through 4.4.2.4 and tested as specified in 4.4.3.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.2 End item examination.

4.4.2.1 Yard-by-yard examination. Each roll in the sample shall be examined on the face side only. When the total yardage in the roll does not exceed 100 yards, the entire yardage in the roll shall be examined. When the total yardage in the roll exceeds 100 yards, only 100 yards shall be examined. All defects as defined in Section 1 of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet), shall be scored and assigned demerit points as listed in 4.4.2.1.1 except that only those slubs and knots which exceed the limits shown on Sears Fabric Defect Scales (see 6.5), E for slubs and B for knots, shall be scored. No linear yards (increments of 1 yard on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than four points. The sample size shall be 20 rolls selected from 20 containers. The lot shall be unacceptable if the points per 100 square yards of the total yardage examined exceeds 30.0 points.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

The lot shall be unacceptable if the points per 100 square yards of two or more individual rolls exceeds 45.0 points. If one roll exceeds 45.0 points per 100 square yards, a second sample of 20 rolls shall be examined only for individual roll quality. The lot shall be unacceptable if one or more rolls in the second sample exceeds the point level. Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample X 3600}}{\text{Contracted width of cloth (inches) X Total yards inspected}} = \text{Points per 100 square yards}$$

4.4.2.1.1 Demerit points. Demerit points shall be assigned as follows:

For defects 3 inches or less in any dimension	- one point
For defects exceeding 3 inches but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

NOTE: The following defects, when present, shall be scored four points for each yard in which they occur:

Holes, cuts, or tears
Baggy, ridgy, or wavy cloth
Width less than minimum specified
Poor dye penetration, mottled, streaky, or cloudy
Excessive neppiness

4.4.2.2 Length examination. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than 2 yards less than the length marked on the ticket shall be considered a length defect. The lot shall be rejected if two or more rolls in the sample are defective with respect to length or if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the roll tickets.

4.4.2.3 Shade and appearance examination. During the yard-by-yard examination, each roll in the sample shall be examined for shade and appearance. Any roll in the sample off shade; shaded side to side, side to center, or end to end; or not having the same appearance as the standard sample shall be cause for rejection of the entire lot represented by the sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

4.4.2.4 Roll identification examination. During the yard-by-yard examination, each roll in the sample shall be examined for defects listed below. The lot shall be unacceptable if two or more of the following defects are present in the sample:

Preshrinkage process identified by name or trademark on cloth or ticket
Face stamping missing from either or both ends
Not labeled or ticketed in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act

4.4.3 End item testing. The cloth shall be tested for the characteristics listed in table II. The methods of testing specified in FED-STD-191, wherever applicable, and as listed in table II shall be followed. The physical and chemical values specified in section 3 apply to the average result of the determinations made on a sample unit for test purposes as specified in the applicable test methods. All test reports shall contain the individual values used in expressing the final results. The sample unit shall be 4 continuous yards full width of the finished cloth and 1/4 yard of the cloth prior to application of the durable press treatment. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. The sample size shall be in accordance with the following:

Lot size (yards)	Sample size (sample units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE II. End item tests

Characteristic	Requirement paragraph	Test method
Polyester identification	3.3.1.1	1/
Cotton identification	3.3.1.2	1200 1/
Cotton, combed	3.3.1.2	1/
Fiber content	3.3.2	2535 1/
Yarn (single)	3.3.2	Visual 1/
Labile sulfur	3.4.1	2020
Colorfastness to:		
Laundering (after 3 cycles)	3.4.3	5610 2/
Perspiration	3.4.3	5680
Light	3.4.3	5660 3/
Dry heat 4/	3.4.3	5642
Crocking	3.4.3	5651
Weight	3.5	5041
Yarns per inch	3.5	5050
Breaking strength	3.5	5100

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

TABLE II. End item tests (cont'd)

Characteristic	Requirement paragraph	Test method
Tearing strength	3.5	ASTM D 1424
Weave	3.5.1	Visual 5/
Mercerization	3.6	1/
Approved durable press treatment	3.6	1/
Nonfibrous material	3.7	2611
Appearance rating	3.8	4.5.1
Dimensional stability	3.9	4.5.1
pH	3.10	2811
Seam efficiency	3.11	5110 6/

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

2/ The specimens shall be dried after each of the three laundering cycles.

3/ The exposure time shall be 40 hours for classes 1, 3, 4, and 6 and 80 hours for classes 2 and 5.

4/ A temperature of 376° ± 6°F shall be used to perform the test.

5/ One determination shall be made from each sample unit and the result reported as "pass" or "fail".

6/ The needle shall measure 0.36 ± 0.001 inch across the blade at the eye. The polyester/cotton wrapped thread shall conform to MIL-T-43548. The thread shall be ticket No. 70, 2 ply for the needle, and the thread shall be ticket No. 80, 2 ply for the looper.

4.4.4 Packaging inspection. The sampling and inspection of the preservation, packaging, and container marking shall be in accordance with the requirements of PPP-P-1134.

4.5 Methods of inspection.

4.5.1 Appearance and dimensional stability after laundering testing.

4.5.1.1 Apparatus and materials. Apparatus and materials shall be as specified in AATCC Technical Manual, method 124.

4.5.1.2 Preparation of specimens. Three specimens, 22 by 22 inches measured parallel to the warp and filling, shall be cut from a portion of the cloth sample. One specimen shall be cut from each side of the sample unit to within 3 inches of the selvages, and the third specimen shall be taken from the center.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

No two specimens shall contain the same filling yarns. The specimens shall be conditioned to equilibrium under standard conditions in accordance with FED-STD-191. The conditioned specimens shall be laid without tension on a flat surface, care being taken that the cloth is free from wrinkles or creases. Three distances, each a minimum of 18 inches, shall be measured and marked off parallel to each of the warp and filling directions of the specimen. Each pair of markings shall be a minimum of 6 inches from each other and not closer than 1 inch to the edges of the specimen. The distance may be marked with indelible ink and a fine pointed pen, or by sewing fine threads into the cloth, or by stamping. The samples shall then be laundered in accordance with 4.5.1.3.

4.5.1.3 Laundering. Place the three 22 by 22 inch specimens in the washer. The washing load shall be 4 pounds ± 1/4 pound. Dummy pieces shall be added to the machine, along with the specimens to make up the 4 pounds ± 1/4 pound load. Fill to the full water level of the washer with water of a hardness not to exceed 50 parts per million and at a temperature of 120° ± 5°F. The rinse temperature shall be 80° ± 5°F. Add 140 grams ± 1 gram of detergent. Set the washer for a 12-minute cycle on the "Permanent Press" setting. Allow the washing to proceed automatically through the final spin cycle. Remove the specimens immediately at the completion of the final spin, and separate from the dummy pieces and each other if tangled. Place the complete washed load (4 pounds ± 1/4 pound) in the dryer and dry at the "Permanent Press" setting with a 10-minute cool down cycle. Operate the dryer until the load is dry and continue tumbling 5 minutes with the heat turned off (cool down cycle). Remove the load immediately after the machine stops. Repeat the wash and dry cycles for five complete cycles. Remove all the specimens and condition to equilibrium under standard conditions in accordance with FED-STD-191.

4.5.1.4 Appearance evaluation. Three trained observers shall evaluate each sample unit for appearance characteristics. The observers shall make their evaluations independent of each other. Each observer shall evaluate each specimen for appearance as it hangs on the viewing board while standing in front of the viewing board and 4 feet back from it. The overhead lighting shall be used. Mount each 22 by 22 inch specimen on the viewing board with the center of the specimen 5 feet from the floor. Place three dimensional plastic replicas on each side of the specimen with the centers 5 feet from the floor, to facilitate comparative rating. The specimen shall be rated according to the appearance on the plastic replica that most nearly matches the appearance of the cloth. No estimated rating falling between the approved replicas shall be given. The average of the rating values assigned for appearance of the cloth by the observers rounded off to the nearest 0.1 rating shall be the rating for the specimen. Each rating value given by the observers for the appearance of the cloth shall also be reported.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

4.5.1.5 Dimensional stability. After evaluation for appearance is made, the three 22 by 22 inch specimens shall be laid out without tension on a flat surface in the standard atmosphere. Care shall be taken that the specimens are free from wrinkles and creases. The previously measured distance marked on the specimens shall be measured in both the warp and filling directions. The dimensional stability of the specimens shall be calculated as follows:

$$\text{Dimensional change, percent} = \frac{A-B}{A} \times 100$$

Where A = Average of initial measurements (3 specimens)
B = Average measurements after laundering (3 specimens)

The dimensional change of the sample unit in the warp and filling directions shall be the average of the specimens tested in each direction respectively and shall be reported separately to the nearest 0.1 percent. The individual values used to calculate the average shall also be reported.

5. PACKAGING

5.1 Put-up and preservation. Put-up and preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Levels A and Commercial. The cloth shall be put-up and preserved in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Levels A, B, and Commercial. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required by the contract or purchase order, shipments shall be marked in accordance with the requirements of PPP-P-1134.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The cloth is intended for use in the manufacture of shirts worn by the Department of Defense personnel.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Class of cloth required (see 1.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

c. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
d. When a first article is required (see 3.1, 4.3, and 6.3).
e. Width of cloth required (see 3.5.3).
f. Minimum length if other than specified (see 3.12).
g. Levels of preservation and packing (see 5.1 and 5.2).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4 Standard sample. For access to samples, address the contracting activity issuing the invitation for bids or request for proposal.

6.5 Fabric defect scales. Fabric Defect Replica Kits are available from Sears, Roebuck and Company, Department 817 (ATTN: BSC 23-29), Sears Tower, Chicago, IL 60684.

6.6 Durable press resin treatment. Approval of the durable resin for utilization under this document is the responsibility of the U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 and is based on extensive tests, including those for toxicity which are not set forth in this document. Because of the time necessary to conduct a full evaluation (approximately 6 months), only those treatments approved and so listed in the invitation for bids or request for proposals shall be considered acceptable for the related procurement.

6.7 Yarn number. The class 5 cloth has been satisfactorily manufactured using 30's cotton count, warp, and filling.

* 6.8 Subject term (key word) listing.

Material
Material, perma-press
Shirt

6.9 Cross-reference. Cancellation of MIL-C-83314A necessitated redesignation of classifications in MIL-C-43992A. MIL-C-43992(GL) and MIL-C-83314A designations and corresponding current designations in MIL-C-43992B are shown below.

MIL-C-83314A, class 1	MIL-C-43992B, class 1
MIL-C-83314A, class 2	MIL-C-43992B, class 2
MIL-C-83314A, class 3	MIL-C-43992B, class 3
MIL-C-83314A, class 4	MIL-C-43992B, class 4
MIL-C-43992(GL), (no class designation)	MIL-C-43992B, class 5

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

6.10 Changes from previous issue. The margins of this specification are marked with asterisks to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - NU
Air Force - 11

Review activities:

Army - MD
Navy - MC, CG
Air Force - 82, 99
DLA - CT

Preparing activity:

Army - GL

(Project 8305-0288)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

instructions. In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE. This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

US Army Natick Research, Development, and
Engineering Center
Natick, MA 01760-5014

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON D C
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research, Development,
and Engineering Center
ATTN: STRNC-ES
Box 14A
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1 DOCUMENT NUMBER	2 DOCUMENT TITLE
MIL-C-43992B	Cloth, Broadcloth, Polyester/Cotton, Durable Press

3a. NAME OF SUBMITTING ORGANIZATION	4 TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)* _____

5 PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6 REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.