INCH-POUND

MIL-DTL-43992C
23 September 2002
SUPERSEDING
MIL-C-43992B
28 June 1989

DETAIL SPECIFICATION

CLOTH, BROADCLOTH, POLYESTER/COTTON, DURABLE PRESS

This specification is approved for use by all Departments and Agencies of the Department of Defense

1. SCOPE

1.1 Scope. This document covers polyester/cotton broadcloth treated with a durable press finish.

1.2 Classification. The cloth should be of the following classes, as specified (see 6.2).

Class 1	-	3.5 to 4 oz.	-	Blue 1550
Class 2	-	3.5 to 4 oz.	-	White 3060
Class 3	-	3.8 to 4.3 oz.	-	Blue 1550
Class 4	-	3.8 to 4.3 oz.	-	Blue 1550
Class 5	-	3.8 to 4.3 oz.	-	Green 415
Class 6	-	3.5 to 4.0 oz.	-	Blue 3379

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Supply Center Philadelphia, Clothing and Textile Directorate, ATTN: DSCP-CRDD, 700 Robbins Avenue, Bldg. 6D, Philadelphia, PA 19111-5092) by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section is specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure completeness of this list, document users are cautioned that they must meet all the specified requirements documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

A-A-50199	-	Thread, Polyester Core, Cotton or Polyester Covered

STANDARDS

FEDERAL

FED-STD-4	-	Glossary of Fabric Imperfections

(Unless otherwise indicated, copies of the above specifications, standards, and handbooks are available from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.2.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies are available from the Federal Trade Commission, Correspondence Branch, Pennsylvania Avenue at Sixth Street, NW, Washington, DC 20580-0001.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

ENVIRONMENTAL PROTECTION AGENCY

Office of Prevention, Pesticides and Toxic Substances

870.1200 (Acute Dermal Toxicity)

(Copies are available from the US Government Printing Office, Washington, DC 20402, or from the Environmental Protection Agency at 800-490-9198).

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the document which are DoD adopted are those listed in the issue of the DoDISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DoDISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR QUALITY CONTROL

ASQC Z1.4	-	Sampling Procedures and Tables for Inspection by Attributes

(Application for copies should be addressed to the American Society for Quality Control (ASQC), P.O. Box 3005, 611 East. Wisconsin Avenue, Milwaukee, WI 53201-4606.)

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS

Chromatic Transference Scale

AATCC 8	-	Colorfastness to Crocking: AATCC Crockmeter Method
AATCC 15	-	Colorfastness to Perspiration
AATCC 16	-	Colorfastness to Light
AATCC 61	-	Colorfastness to Laundering, Home and Commercial: Accelerated
AATCC 81	-	pH of the Water-Extract from Bleached Textiles
AATCC 117	-	Colorfastness to Heat: Dry (Excluding Pressing)
AATCC 124	-	Appearance of Fabrics After Repeated Home Launderings.
AATCC 135	-	Dimensional Changes in Automatic Home Laundering of Woven and Knit Fabrics

(Application for copies should be addressed to the American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Research Triangle Park, NC 27705-2215.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

ASTM INTERNATIONAL

ASTM-D-276	-	Identification of Fibers in Textiles
ASTM-D-629	-	Quantitative Analysis of Textiles
ASTM-D-1424	-	Tearing Strength of Fabrics by Falling-Pendulum Type (Elmendorf) Apparatus
ASTM-D-1683	-	Failure in Seams of Woven Fabrics
ASTM-D-3775	-	Fabric Count of Woven Fabrics
ASTM-D-3776	-	Mass Per Unit Area (Weight) of Fabric
ASTM-D-5034	-	Breaking Strength and Elongation of Textile Fabrics (Grab Test)

(Application for copies should be addressed to ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.)

2.4 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to the first article inspection (see 6.3) in accordance with 4.3.

3.2 Standard sample. The finished cloth shall match the standard sample for shade and appearance and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.4).

3.3 Recycled, recovered, or environmentally preferable materials. Recycled, recovered, or environmentally preferable materials should be used to the maximum extent possible provided that the material meets or exceeds the operational and maintenance requirements, and promotes economically advantageous life cycle costs. The use of recycled fiber in the production of this fabric is prohibited.

3.3.1 Fibers.

3.3.1.1 Polyester fiber. The fiber shall be an environmentally acceptable polyethylene terephthalate.

3.3.1.2 Cotton. The cotton shall be carded and combed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

3.3.2 Yarns. All yarns shall be a blend of polyester and cotton, drawn and spun in single yarns for both warp and filling. The finished cloth shall contain 65 percent ± 5 percent polyester and the remaining percentage cotton, based on the dry weight of the desized specimen. Tests shall be made as specified in 4.3.3.

3.4 Color. The color of the dyed and finished cloth shall be as follows:

Class 1, 3, or 4	Blue 1550
Class 2	White 3060
Class 3	Green 415
Class 6	Blue 3379

The color for classes 1, 3, 4, 5, and 6 shall be obtained by weaving with dyed and white yarns (see 3.5.2.)

3.4.1 Labile sulfur. The use of dyes and components containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyestuff shall be chosen and applied so that the dyed and finished cloth shall contain no more labile sulfur than shown by the standard sample when tested as specified in 4.3.3. When a standard sample is not available, the dyed and finished cloth shall show no more than a slight trace of labile sulfur when tested as specified in 4.3.3.

3.4.2 Matching. The color of the finished cloth shall match the standard sample when viewed under filtered tungsten lamps that approximate artificial daylight and that have a correlated color temperature of 7500 ± 200K (Kelvin), with illumination of 100 ± 20 foot-candles and shall be a good match to the standard sample under incandescent lamp at 2300 ± 200K.

3.4.3 Colorfastness. The dyed and finished cloth shall show fastness to laundering (after 3 cycles), perspiration, light, and dry heat equal to or better than the standard sample or equal to or better than a rating of 3.0. The dyed and finished cloth shall show fastness to crocking equal to or better than the standard sample or shall have an AATCC Chromatic Transference Scale rating for crocking not lower than 3.5. Testing shall be as specified in 4.3.3.

3.5 Physical requirements. The finished cloth shall conform to the requirements specified in Table I when tested as specified in 4.3.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

TABLE I. Physical requirements

Classes	Weight per square, yard, ounces		Yarns per inch , minimum		Breaking strength pounds, minimum		Tearing strength, pounds, minimum	
	Min.	Max.	Warp	Filling	Warp	Filling	Warp	Filling
1	3.5	4.0	100	64	70	52	4.0	3.0
2	3.5	4.0	100	64	70	52	4.0	3.0
3	3.8	4.3	101	65	72	90	4.0	5.0
4	3.8	4.3	100	62	85	55	5.0	3.0
5	3.8	4.3	100	62	95	55	4.5	3.0
6	3.5	4.0	100	64	70	52	4.0	3.0

3.5.1 Weave. The weave shall be a plain weave.

3.5.2 Construction. Classes 1, 3, 4, 5, and 6 cloth shall be of an end-and-end construction with alternate dyed and white warp yarns and with an all white filling. The Class 2 cloth shall be woven with all white yarns.

3.5.3 Width. The width of the cloth shall be as specified (see 6.2), and shall be the minimum acceptable width inclusive of selvages when fly shuttle looms are used, and exclusive of selvages and fringe when shuttleless looms are used.

3.6 Finish. The cloth shall be scoured, singed, stabilized, mercerized, and bleached when required to result in a smooth and lustrous finish equal in character to that of the standard sample. In addition, the cloth shall be given an approved durable press treatment (see 6.2), and shall be processed and cured to meet the requirements of this document.

3.7 Nonfibrous material. The starch and protein content, prior to application of the durable press treatment shall not exceed 2.0 percent when tested as specified in 4.3.3.

3.8 Appearance rating. The finished cloth shall have an appearance rating of not less than 3.5 when tested after five launderings as specified in 4.3.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

3.9 Dimensional stability. The finished and cured cloth shall have dimensional changes of not more than 2.0 percent in either the warp or filling direction when tested as specified in 4.3.3. The preshrinking process used shall not be identified by name or trademark either on the cloth, ticket, or package.

3.10 pH. The pH value of the water extract of the finished cloth shall be no less than 5.0 nor more than 8.5 when tested as specified in 4.3.3.

3.11 Seam efficiency. The finished cloth shall have a seam efficiency of not less than 85 percent when tested as specified in 4.3.3.

3.12 Length and put-up. Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 40 yards. Each length shall be put-on on full width rolls as specified in 5.1.

3.13 Fiber identification. Each roll of cloth shall be labeled or ticketed for fiber content in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act.

3.13.1 Marking. The face side of the cloth shall be identified by applying a stamping on that side of the cloth with the word “FACE” at each end of the piece.

3.14 Workmanship. The finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards, when calculated as specified in Section 4 shall not exceed the established maximum point value.

4. VERIFICATION

4.1 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.2)

b. Conformance inspection (see 4.3.)

4.2 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.3.

4.3 Conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with ASQC Z1.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

4.3.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.3.2 End item examination.

4.3.2.1 Yard-by-yard examination. Each roll in the sample shall be examined on the face side only. When the total yardage in the roll does not exceed 100 yards, the entire yardage in the roll shall be examined. When the total yardage in the roll exceeds 100 yards, only 100 yards shall be examined. All defects are defined in Section 1 of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet), shall be scored and assigned demerit points as listed in 4.3.2 except that only those slubs and knots which exceed the limits shown on Sears Fabric Defect Scales (see 6.5), E for slubs and B for knots, shall be scored. No linear yards (increments of 1 yard on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than four points. The sample size shall be 20 rolls selected from 20 containers. The lot shall be unacceptable if the points per square yards of the total yardage examined exceeds 20.0 points. The lot shall be unacceptable if the points per square yards of two or more individual rolls exceeds 30.0 points. If one roll exceeds 30.0 points per square yards, a second sample of 20 rolls shall be examined only for individual roll quality. The lot shall be unacceptable if one or more rolls in the second sample exceeds the point level. Point computation for lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{Total yards inspected}} = \text{Points per 100 square yards}$$

4.3.2.1.1 Demerit points. Demerit points shall be assigned as follows:

For defects 3 inches or less in any dimension	- one point
For defects exceeding 3 inches but not exceeding 6 inches in any dimension	-two points
For defects exceeding 6 inches but not exceeding 9 inches in any dimension	-three points
For defects exceeding 9 inches in any dimension	-four points

NOTE: The following defects, when present, shall be scored four points for each yard in which they occur:

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

Holes, cuts, or tears
Baggy, ridgy, or wavy cloth
Width less than minimum specified
Poor dye penetration, mottled, streaky, or cloudy
Excessive neppiness

4.3.2.2 Length examination. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than 2 yards less than the length marked on the ticket shall be considered a length defect. The lot shall be rejected if two or more rolls in the sample are defective with respect to length or if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the roll tickets.

4.3.2.3 Shade and appearance examination. During the yard-by-yard examination, each roll in the sample shall be examined for shade and appearance. Any roll in the sample off shade; shaded side to side, side to center, or end to end; or not having the same appearance as the standards sample shall be cause for rejection of the entire lot represented by the sample.

4.3.2.4 Roll identification examination. During the yard-by-yard examination, each roll in the sample shall be examined for defects listed below. The lot shall be unacceptable if two or more of the following defects are present in the sample:

Preshrinkage process identified by name or trademark on cloth or ticket
Face stamping missing from either or both ends
Not labeled or ticketed in accordance with the Rules and Regulations under the Textile Fiber Products Identification Act

4.3.3 End item testing. The cloth shall be tested for the characteristics listed in Table II. The methods of testing specified in Table II shall be followed. The physical and chemical values specified in Section 3 apply to the average result of the determinations made on a sample unit for test purposes as specified in the applicable test methods. All test reports shall contain the individual values used in expressing the final results. The sample unit shall be 4 continuous yards full width of the finished cloth and 1/4 yard of the cloth prior to application of the durable press treatment. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. The sample size shall be in accordance with the following:

Lot size (yards)	Sample size (sample units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

TABLE II. End item tests

Characteristic	Requirement paragraph	Test method
Polyester identification	3.3.1.1	Visual 1/
Cotton identification	3.3.1.2	ASTM-D-276
Cotton, combed	3.3.1.2	Visual 1/
Fiber content	3.3.2	ASTM-D-629
Yarn (single)	3.3.2	Visual 1/
Labile sulfur	3.4.1	4.4.1
Colorfastness to:		
Laundering (after 3 cycles)	3.4.3	AATCC 61 2/
Perspiration	3.4.3	AATCC 15
Light	3.4.3	AATCC 16 3/
Dry heat 4/	3.4.3	AATCC 117
Crocking	3.4.3	AATCC 8
Weight	3.5	ASTM-D-3776
Yarns per inch	3.5	ASTM-D-3775
Breaking strength	3.5	ASTM-D-5034
Tearing strength	3.5	ASTM-D-1424
Weave	3.5.1	Visual 5/
Mercerization	3.6	Visual
Approved durable press treatment	3.6	Visual
Nonfibrous material	3.7	ASTM-D-629
Appearance rating	3.8	AATCC 124 7/
Dimensional stability	3.9	AATCC 135 7/
pH	3.10	ASTM-D-2165
Seam efficiency	3.11	ASTM-D-1683 6/

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

2/ The specimen shall be dried after each of the three laundering cycles and only the polyester and cotton in the multifiber test cloth shall be rated for staining.

3/ The exposure time shall be 40 hours for classes 1, 3, 4, and 6 and 80 hours for classes 2 and 5.

4/ A temperature of $376^{o} \pm 6^{o}$F shall be used to perform the test.

5/ One determination shall be made from each sample unit and the result reported as "pass" or "fail".

6/ The needle shall measure 0.36 inch $\pm$ 0.001 inch across the blade at the eye. The polyester/cotton wrapped thread shall conform to A-A-50199. The thread shall be Tex 31-35, 2-ply for the needle and Tex 31-35 for the looper.

7/ Permanent press machine cycle, 120 $\pm$ 5 degrees F wash temperature. Tumble dry, permanent press cycle.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

4.4 Methods of inspection.

4.4.1 Presence of labile sulfur. In the determination of labile sulfur in textile materials with lead acetate, two 1.50 gram ± 0.01 gram samples from each material submitted for evaluation shall be tested. Each of the two samples shall be cut into very small pieces and placed into separate test tubes. The samples shall be submersed in a stannous chloride solution that contains 100 grams of stannous chloride crystals ACS in 100 milliliters of hydrochloric acid ACS (35 percent concentration) and 50 milliliters of distilled water. A filter paper wet out with a 5.0 percent lead acetate solution contains 5.0 grams of lead acetate CP reagent grade and enough distilled water to make up a 100-milliliter solution; if the solution is not clear, add a few drops (one at a time) of glacial acetic acid until the solution is clear. The test over a low flame until the solution is boiling. The solution should not be heated for more than 15 seconds. A brown to black stain on the filter paper should be evaluated as follows:

Free	-	The filter paper shows no discoloration or staining of any kind.
Slight	-	The filter paper shows a light tan to light brown discoloration stain.
Moderate	-	The filter paper shows a dark brown discoloration stain.
Severe	-	The filter paper shows a black color stain.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When actual packaging of material is to be performed by DoD personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activity within the Military Department or Defense Agency, or within the Military Department's System Command. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature which may be helpful but is not mandatory.)

6.1 Intended use. The cloth is intended for use in the manufacture of shirts worn by the Armed Forces.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Class of cloth required (see 1.2).
c. Issue of DoDISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
d. When a first article is required (see 3.1, 4.3, and 6.3).
e. Width of cloth required (see 3.5.2).
f. Minimum length of other than specified (see 3.12).
g. Packaging (see 5.1).

6.3 First article. When a first article is required, it should be inspected and approved under the appropriate provision of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4 Standard sample. For access to samples, address the contracting activity issuing the invitation for bids or request for proposal.

6.5 Fabric defect scale. Fabric Defect Replica Kits are available from Sears, Roebuck and Company, Department 817, ATTN: BSC 23-29, Sears Tower, Chicago, IL 60684.)

6.6 Durable press resin treatment. Approval of the durable resin for utilization under this document is the responsibility of the US Army Natick Soldier Systems Center, Natick, MA 01760-5014 and is based on extensive tests. Because of the time necessary to conduct a full evaluation (approximately 6 months), only those treatments approved and listed in the invitation for bids or request for proposals should be considered acceptable for the related procurement.

6.7 Yarn number. The Class 5 cloth has been successfully manufactured using 30's cotton count, warp and filling.

6.8 Subject term (key word) listing.

Fabric
Material
Material, perma-press
Shirt

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

Custodians:

Army - GL
Air Force - 11

Review activities:

Navy - MC, CG

Preparing activity:

DLA - CT

(Project 8305-0808)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7 and send to preparing activity.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	**1. DOCUMENT NUMBER** MIL-DTL-43992C	**2. DOCUMENT DATE** ***(YYYYMMDD)*** 20020923

3. DOCUMENT TITLE
CLOTH, BROADCLOTH, POLYESTER/COTTON, DURABLE PRESS

3. **NATURE OF CHANGE** *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME *(Last, First, Middle Initial)*	b. ORGANIZATION	
c. ADDRESS *(Include Zip Code)*	d. TELEPHONE *(Include Area Code)* (1) Commercial (2) DSN *(If applicable)*	7. DATE SUBMITTED *(YYYYMMDD)*

8. PREPARING ACTIVITY

a. NAME DEFENSE SUPPLY CENTER PHILADELPHIA DSCP-CRDD (BLDG 6D)	b. TELEPHONE *(Include Area Code)* (1) Commercial (2) DSN (215) 737- 3085 444-3085
c. ADDRESS *(Include Zip Code)* 700 Robbins Ave (Bldg 6, C&T) PHILADELPHIA, PA 19111-5092	**IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:** Defense Standardization Program Office (DLSC-LM) 8725 John J. Kingman Road, Suite 2533 Fort Belvoir, Virginia 22060-6221 Telephone (703) 767-6888 DSN 427-6888

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.