MILITARY SPECIFICATION

SWEATBAND, HEADWEAR: ARTIFICIAL LEATHER

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers one type of sweatband.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

A-A-203	- Paper, Kraft, Untreated
PPP-B-636	- Boxes, Shipping, Fiberboard

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8405

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-L-35078 - Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification For

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods
FED-STD-311 - Leather, Methods of Sampling and Testing

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads
MIL-STD-731 - Quality of Wood Members for Containers and Pallets

(Copies of specifications, standards, and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

* 2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

Chromatic Transference Scale

(Copies should be obtained from the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709-2215.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 2209 - Tensile Strength of Leather
D 3951 - Standard Practice for Commercial Packaging

(Copies should be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Standard sample. The finished sweatband shall match the standard sample for color, appearance, and gloss and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

* 3.2 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.4).

3.3 Material (see 6.5). The material for the sweatbands shall be composed of a non-woven synthetic substrate impregnated with an elastomeric binder. The top surface of the substrate shall be coated with an abrasive resistant finish.

3.3.1 Toxicity. The material used shall not produce skin irritation or sensitization reaction under simulated conditions of use when tested as specified in 4.4.1.

3.3.2 Color and finish. Unless otherwise specified (see 6.2), the color of the finished surface shall be Brown 424. The material shall match the standard sample for color, appearance, and gloss.

3.4 Physical requirements.

3.4.1 Thickness. The thickness of the material shall be 0.8 mm (-0.1 mm +0.2 mm) when tested as specified in 4.4.1.

3.4.2 Tearing strength, slot tear. The slot tearing strength of the material shall be greater than 15 pounds in the machine direction and greater than 10 pounds in the cross direction when tested as specified in 4.4.1.

* 3.4.3 Breaking strength and elongation. The breaking strength and elongation at break of the material shall conform to the requirements specified in table I when tested as specified in 4.4.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

TABLE I. Breaking strength requirements

	Breaking strength pounds, minimum		Elongation at break percent, minimum	
	Machine direction	Cross direction	Machine direction	Cross direction
Initial	25	20	50	30
After exposure to dry cleaning solvent	22	17.5	50	30
After accelerated aging	22	17.5	50	30

3.4.4 Hydrolytic stability. The material shall not change in dimensions by more than 1/16 inch, or have a noticeable change in stiffness, color, gloss, or appearance of finished surface when tested as specified in 4.4.1.

3.4.5 Blocking. The material shall separate with ease, show no evidence of tackiness, peeling, or separation of the finish from the substrate and shall show no change in appearance of the finished side when tested as specified in 4.4.1.

* 3.4.6 Colorfastness. The material shall be tested on the finished side for resistance to dry and wet crocking in accordance with 4.4.1 and staining of the wet and dry crock cloths shall be not lower than expanded AATCC value 4.

3.4.7 Abrasion resistance. The material shall have a weight loss no greater than 0.1 gram after being subjected to 100 cycles on the finished surface when tested for abrasion resistance as specified in 4.4.1.

* 3.4.8 Resistance to dry cleaning solvent. The material shall not change by more than 1/16 inch in dimensions, twist, curl, or have a noticeable change in color, gloss, or appearance of finished surface when tested for resistance to dry cleaning solvent as specified in 4.4.1. A slight upward bowing of the ends of the sample not exceeding 1/2 inch from the surface on which they are resting is permissible in the machine direction only.

3.4.9 Wrinkle pattern. The wrinkle pattern formed on the finished surface of the material shall be no coarser than the wrinkle pattern represented by number 4 on the Satra Break and Pipeyness Scale (see 6.6) when tested as specified in 4.4.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

3.4.10 Stiffness.

3.4.10.1 Initial. The maximum initial stiffness values of the sweatband material shall be 375 degrees in the machine direction and 400 degrees in the cross direction when tested as specified in 4.4.1.

3.4.10.2 After exposure to dry cleaning solvent. The stiffness of the material shall not increase more than 5 percent in either direction or decrease more than 10 percent in either direction from the initial stiffness when tested as specified in 4.4.1.

3.4.10.3 After accelerated aging. The stiffness of the material shall not increase more than 12 percent in the machine direction or increase more than 5 percent in the cross direction from the initial stiffness when tested as specified in 4.4.1.

3.4.10.4 After exposure to alcohol. The stiffness of the material shall not increase at all and shall not decrease more than 10 percent in either direction from the initial stiffness when tested as specified in 4.4.1.

3.4.10.5 After exposure to perspiration. The stiffness of the material shall not increase more than 5 percent in either direction from the initial stiffness when tested as specified in 4.4.1.

3.5 Construction. The sweatbands shall be cut from material conforming to the requirements specified in 3.3 through 3.4.10. The width, length, and tolerance of the sweatbands shall be as specified (see 6.2). The long dimension of the sweatband shall be cut perpendicular to the machine direction of the material.

3.6 Workmanship. The finished sweatbands shall conform to the quality of product established by this document and the occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

* 4.1.1 Responsiblity for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirement in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Certificates of compliance. When certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

* 4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

* 4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.2 and 4.4.3 and tested for the characteristics specified in 4.4.1.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents, unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document. In addition, inspection shall be performed on the non-woven material for the characteristics specified in table II. The sample unit shall be an 18 inch by 18 inch piece of the artificial leather. The sample size shall be as indicated below. All requirements are applicable to the sample unit. The lot shall be rejected if any sample unit fails to meet any requirement specified.

Lot size (yards)	Sample size (sample units)
800 or less	2
801 up to and including 22,000	3
22,001 and more	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

TABLE II. Material tests

Characteristic	Requirement paragraph	Test method 1/
Material identification	3.3	2/
Toxicity	3.3.1	2/
Thickness	3.4.1	1011 3/
Tearing strength (slot tear)	3.4.2	2161 4/
Breaking strength and elongation:		
Initial	3.4.3	ASTM D 2209 4/
After exposure to dry cleaning solvent	3.4.3	4.5.1 and ASTM D 2209 4/
After accelerated aging	3.4.3	4.5.2 and ASTM D 2209 4/
Hydrolytic stability	3.4.4	4.5.3
Blocking	3.4.5	3121
Colorfastness	3.4.6	3031
Abrasion resistance	3.4.7	4.5.4
Resistance to drycleaning solvent	3.4.8	4.5.5
Wrinkle pattern	3.4.9	4.5.6
Stiffness:		
Initial	3.4.10.1	4214 4/
After exposure to dry cleaning solvent	3.4.10.2	4.5.1 and 4212 4/
After accelerated aging	3.4.10.3	4.5.2 and 4212 4/
After exposure to alcohol	3.4.10.4	4.5.7 and 4212 4/
After exposure to perspiration	3.4.10.5	4.5.8 and 4212 4/

1/ Unless otherwise indicated, test methods are in accordance with FED-STD-311.

2/ A certificate of compliance shall be submitted and will be acceptable for the stated requirements.

3/ Use spring type gage and measure five locations 1/2 to 1 inch from edge of material. The specimen shall be an 18 inch by 18 inch piece of material. Make one determination per sample unit.

4/ Exception to methods 2161, 4212, ASTM D 2209: Two specimens shall be cut from each sample unit. One specimen shall be cut with the long dimension in the machine direction and the other shall be cut with the long dimension in the cross direction.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

4.4.2 End item visual examination. The end item shall be examined for the defects listed below. The lot size shall be expressed in units of sweatbands. The sample unit shall be one sweatband. The inspection level shall be I and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 4.0.

Examine	Defect
Quality of material	Hole, cut, or tear Crease or wrinkle that cannot be corrected by manual pressure Spot, stain, or streak Objectionable odor Any edge not straight Folded edge Edge not cleanly cut (e.g., ragged edge) Finished side does not match standard sample for appearance and gloss
Color	Color not Brown 424 per standard sample (or not as specified)
Finish	Unfinished area Blister or delamination Lump or heavily finished area Uneven finish

4.4.3 End item dimensional examination. The end item shall be examined for conformance to the length and width dimensions specified in 3.4. Any dimension that is not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of sweatbands. The sample size shall be one sweatband. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

* 4.4.4 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and unit packs)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

Workmanship	Inadequate application of components, such as: incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling Bulged or distorted container
Weight	Weight of contents exceeds requirement
Content	Number of sweatbands per unit is more or less than required 1/

1/ For this defect, one unit pack from each shipping container in the sample shall be examined.

* 4.4.5 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Interlocking of loads not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

4.5 Methods of inspection.

4.5.1 Exposure to dry cleaning solvent procedure. Submerge two cut specimens in perchloroethylene in a suitable glass container. Then place the container in a ventilating hood at 23° ± 2°C for 4 hours. Stir the solution several times during this 4 hour period. At the end of 4 hours, remove the specimens from the solution and air dry under the ventilating hood for 4 hours.

4.5.2 Accelerated aging procedure. Place the two cut specimens in a circulating air oven for 100 hours at 80° ± 2°C. At the end of 100 hours, remove the specimens from the oven and allow them to equilibrate to 23° ± 2°C room temperature for 4 hours.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

4.5.3 Hydrolytic stability test. Test two 2 inch by 2-inch specimens from each sample unit. Measure the four sides of each specimen for length to the nearest 1/32 inch on the finished surface 1/4 inch in from the edges. Mark the finished surface to indicate the location of the measurements. Average the four values and record the average value as D 1. Place each specimen finish side up in a petri dish. Add a sufficient amount of a 1/2 g/L solution of urea to completely cover the specimen. Cover the petri dish with specimen to prevent evaporation and then place in an oven maintained at 75°C ± 2°C. The petri dish with specimen shall remain in the heated oven for 20 hours. At the end of 20 hours, remove the specimen from the oven, rinse in deionized or distilled water then air dry for a minimum of 12 hours. Then examine the specimen for change in color, gloss, and appearance of finished surface. Record any change in these characteristics. Remeasure the four sides of the specimen as indicated above along the marked locations and record the average value as D 2. Determine the difference between the value of D 1 and D 2 and record the value as D 3. Any specimen having a D 3 value greater than 1/16 inch shall be a test failure. Finally fold the specimen back to back finished side out and record any change in stiffness or evidence of cracking of the finish.

4.5.4 Abrasion resistance test. Method 5306 of FED-STD-191 shall be used with the following exceptions:

a. One 5-inch diameter specimen shall be tested from each sample unit.

b. The specimen shall be weighed to the nearest 0.001 gram before being abraded. While being abraded, the specimen shall be vacuumed to remove loose particles, then weighed again to the nearest 0.001 gram. The difference in weight between the two weighings shall be recorded as the weight loss.

c. The specimen shall be abraded on the finished surface using an H-18 abrading wheel and a 1000-gram load on the wheel.

4.5.5 Resistance to dry cleaning solvent test. Test two 2 inch by 2-inch specimens from each sample unit. Measure and mark the specimens and record the average of the measurements for each specimen in accordance with the procedures used for measuring and marking specimens for hydrolytic stability tests (see 4.5.3). Place the specimens in a 400 mL beaker containing 50 mL of perchloroethylene for each specimen. Place the beaker with specimens in a ventilating hood at 23° ± 2°C for 4 hours. Stir the solution several times during this 4 hour period. At the end of 4 hours, remove the specimens from the beaker and air dry under the ventilating hood for 4 hours. Then, examine the specimens for change in color, gloss, and appearance of finished surface. Remeasure the specimens as indicated in 4.5.3 and record the average value for each specimen. Record the difference between the average measurement values obtained before and after soaking in the solvent as D 3. Any specimen having a D 3 value greater than 1/16 inch shall be a test failure. Fold the specimens back to back, grain side out and record any evidence of cracking of the finish.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

4.5.6 Wrinkle pattern test. Test two 2 inch by 2 inch specimens from each sample unit. Gently fold each specimen in half, with the finished surface on the inside of fold, until the surfaces touch, then unfold specimen. Fold and unfold each specimen five times along the same fold line. Do not apply excess pressure along the apex of the fold. Fold one specimen from each sample unit so the fold line is parallel to the machine direction of the material. Fold the second specimen so the fold line is perpendicular to the machine direction. After folding and unfolding the specimens, they shall be formed, finished side in, to the same concaved curvature as the Satra Scale. While the test specimens are in the curved position, compare the wrinkle pattern on the concaved surfaces of the test specimens to the wrinkled patterns on the Satra Scale. Record the number of the wrinkle pattern of the Satra Scale that is comparable or closest to the wrinkle pattern on the finished surface of the test specimen. Any test specimen with a wrinkle pattern greater than 4 shall be a test failure.

4.5.7 Exposure to alcohol procedure. Immerse the two cut specimens in a solution of 50 percent ethyl alcohol (add 598 mL (482g) of 95 percent undenatured ethyl alcohol to 435 mL of water) and allow to remain for 4 hours at 23° ± 2°C. Stir the solution several times during the 4-hour period. At the end of the 4 hours, remove the specimens from the solution and allow to dry for a minimum of 4 hours.

4.5.8 Exposure to perspiration procedure. Immerse the two cut specimens in an artificial perspiration solution for a period of 4 hours at 23° ± 2°C. The perspiration solution shall be prepared as follows:

Sodium chloride, grams	9.0
Urea, grams	1.67
Sodium lactate (60% solution), grams	86.0
Disodium phosphate ($NA_2HP04.12H_20$) grams	0.165
Distilled water to make up 1 liter of solution	

After 4 hours, remove the specimens, rinse with distilled water, and allow to air dry at 23° ± 2°C. After drying, condition the specimens for 4 hours at 23° ± 2°C.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Seventy-two sweatbands of one length and width only shall be bundled to form a unit pack. Each unit pack shall be secured with cotton tape or twine approximately 4 inches from each end.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

5.1.2 Commercial packaging. Sweatbands shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

* 5.2.1 Level A packing. Sweatbands of one length and width only, preserved as specified in 5.1, shall be packed in a fiberboard shipping container conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Each shipping container shall have the contents completely covered on the top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to A-A-203. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636, except that inspection shall be in accordance with 4.4.4. The weight of contents of each shipping container shall not exceed 65 pounds. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). When unit loads are strapped, strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

* 5.2.2 Level B packing. Sweatbands of one length and width only, preserved as specified in 5.1, shall be packed in a fiberboard shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Each container shall have the contents completely covered on the top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to A-A-203. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that inspection shall be in accordance with 4.4.4. The weight of contents of each shipping container shall not exceed 65 pounds.

5.2.2.1 Weather-resistant fiberboard container. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.4.

5.2.3 Commercial packing. Sweatbands, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

* 5.3 Palletization. When specified (see 6.2), sweatbands, packed as specified in 5.2.2 and 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV or type V in accordance with MIL-STD-147. Pallets shall

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet pattern shall be number 3 in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

5.4 Marking. In addition to any special marking required by the contract or purchase order, unit packs, shipping containers, and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. The sweatbands are intended for use in various types of military headwear.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. When a first article is required (see 3.1, 4.3, and 6.4).
c. Color required if other than Brown 424 (see 3.3.2).
d. Length, width, and tolerances required (see 3.5).
e. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
f. Type and class of unit load required (see 5.2.1).
g. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
h. When palletization is required (see 5.3).

6.3 Standard samples. For access to samples, address the contracting activity issuing the invitation for bids.

* 6.4 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

6.5 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of this document (see 3.3).

6.6 Satra Scale. The Satra Break and Pipeyness Scale may be obtained from the British Shoe and Allied Trade Research Association, Satra House, Kettering, Northants, England or from the Satra House North American Agent, Bata Engineering, Batawa, Ontario, Canada.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

* 6.7 Subject term (key word) listing.

Headwear
Leather, artificial
Sweatband

6.8 Changes from previous issue. The margins of this document are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only, and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content, as written, irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Air Force - 11

Review activities:

Army - MD
Air Force - 82, 99
DLA - CT

Preparing activity:

Army - GL

Project No. 8405-0046

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS. In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was uncompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE. This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

US Army Natick Research, Development, and
Engineering Center
Natick, MA 01760-5014

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON D C
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research, Development,
and Engineering Center
ATTN: STRNC-ES
Box 14A
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1 DOCUMENT NUMBER	2 DOCUMENT TITLE
MIL-S-43993C	Sweatband, Headwear: Artificial Leather

3a. NAME OF SUBMITTING ORGANIZATION	4 TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)* _____
b ADDRESS *(Street, City, State, ZIP Code)*	

5 PROBLEM AREAS

a. Paragraph Number and Wording

b Recommended Wording

c Reason/Rationale for Recommendation

6 REMARKS

7a NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 1426 82 MAR PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil - Downloaded: 2026-10-21T23:18Z
Check the source to verify that this is the current version before use.