INCH-POUND
A-A-60066
April 3, 2025

COMMERCIAL ITEM DESCRIPTION

SHELTER, COMBAT, IMPROVED, GEN II

The General Services Administration has authorized the use of this commercial item description (CID) by all federal agencies.

1. SCOPE. This commercial item description covers the technical requirements for one (1) style of a single storage vestibule, one-person size, double-walled, free-standing, improved combat shelter capable of setup in at least two (2) configurations used by the Army.

2. CLASSIFICATION. The Improved Combat Shelter (ICS) GEN II shall be of one (1) type.

3. SALIENT CHARACTERISTICS

3.1 Description. The improved combat shelter shall consist of a shelter body, an attachable rain fly (providing shelter waterproofness and forming a shelter storage vestibule; it also shall function separately as a hooch), support poles, and ground stakes. The shelter body contains insect screening protection, entry/exit through both lengthwise sidewalls, and an attached, tub floor. A shelter system carry bag, and a field expedient repair kit are also included.

The improved combat shelter is designed for use in its standard configuration consisting of as a minimum; the stand-alone, pole-supported shelter body, the attachable (pole- supported) rain fly, ground stakes and guy line cords (for use in high wind conditions). The shelter provides protection from rain, wind, and snow and from ground wetness; it has a means for ventilation and for resisting the entry of insects (i.e., insect screening in ventilation panels and in shelter entry/exit). The shelter is made with flame resistant materials meeting, as a minimum, commercial standards for flame resistance of tentage. With the pole-supported rain fly assembled and affixed to the shelter, the shelter provides a storage vestibule formed by the rain fly; the storage vestibule can be accessed from either outside the shelter via a slide fastener closure in the rain f1y or from the inside the shelter through a sidewall slide fastener closure. The complete shelter system weighs no more than 6.5 pounds.

Comments, suggestions, or questions on this document should be sent to trpsptctstandardiz@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST online database at https://assist.dla.mil.

AMSC N/A FSC 8340

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

3.2 Operational environment. The combat shelter is a versatile, man-portable, shelter system for one (1) Soldier with capabilities to be carried/used as a 'minimum' configuration shelter which is compact and easy to carry or as a 'standard' configuration shelter which is stand-alone, pole-supported, and has additional room for equipment stowage.

Key features are the following:

a. Provide shelter from rain, wind, and snow in climates ranging from basic cold through hot without leaking or collapsing.
b. Be capable of multiple configurations including at least the following: Minimum configuration using available vegetation and terrain to provide a canopy or lean-to. Standard configuration that provides one-person a stand-alone, pole-supported (objective) or pin and pole-supported (threshold) shelter. Combined configuration that allows additional room for extended operations. All configurations will minimize visual signature and profile.
c. System shall weigh no more than 6.5 pounds (threshold). The minimum configuration shall be capable of being carried in the Modular, Lightweight, Load Carry Equipment (MOLLE) rucksack outer pouch.
d. Provide room for the 95 percent male soldier to lie down and simultaneously house a rucksack.
e. Include ventilation, insect protection, Operational Camouflage Pattern (OCP), and waterproof ground protection as objective requirements.
f. Have a service life of 120 combat days.
g. Interface with the Soldier's load carry system for portability.

3.3 Improved combat shelter components.

3.3.1 Shelter basic body. The shelter basic body shall be made flame resistant, with a breathable, insect proof mesh net canopy. The mesh shall compose the front and rear wall, left and right entry doors and be integral to the waterproof tub floor. The mesh shall be black in color and the integrated waterproof tub shall be Tan 499 or color as specified in the contract. The integral, waterproof floor shall have corner ground straps (with grommets/devices for shelter pole anchor, rain fly attachment and ground staking). The shelter shall contain a means for ventilation (i.e., air and moisture vapor permeable fabric, or mesh fabric vents, or combination of both). The shelter basic shall be pole-supported bowed on its exterior and secured at the base of the shelter at diagonally opposite corners at corner ground straps; the shelter shall be secured to the bowed poles using either pole "J" clips, webbing loops or pole tunnels along the joining seam of the sidewalls and end walls.

The shelter shall have internal floor dimensions of not less than 84-inches long by 72-inches wide the internal height at the center point shall be 36-48 inches. The vestibule area shall be a minimum 8.5 square feet.

3.3.2 Rain fly. The rain fly shall be made with flame resistant, waterproof, and the color shall be OCP, or color as specified in the contract. The rain fly shall be easily assembled with a lightweight, interlocking sectional, shock-corded aluminum or composite pole in a pole sleeve or pole clip on symmetric center of the rain fly and attached to the shelter

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

basic to form the standard configuration shelter. The rain fly shall be attached to the shelter with adjustable buckles at the corner points of the shelter basic. The rain fly shall form an overhang/awning or vestibule on the shelter front or rear, for storage and shall extend down on the end walls to shingle over the waterproof tub floor seam. The vestibule area shall be 8-1/2 square feet (minimum). The rain fly shall have a slide fastener closure for external access into the vestibule and hem reinforced grommets along its perimeter to facilitate staking when used in the standard shelter configuration, and tie-down/staking when used in the minimum configuration as a hooch. The slide fastener closure shall operate from shelter center top to ground and permits opening the vestibule to access gear storage vestibule. All seams, except the hem seam, shall be waterproof and shall show no leakage to water when tested in accordance with 5.3.3.

3.3.3 Poles.

3.3.3.1 Shelter poles. The pole system shall be lightweight, interlocking segment, with shock-cording, aluminum/composite or carbon fiber poles with locking tip ends.

3.3.4 Ground stakes. The ground stake shall be an aluminum stake with anodized Black finish and a cord loop for extraction.

3.3.5 Carry bags. Carry bags shall be provided for the complete shelter system and repair kit, as a minimum, and shall be OCP, or other color as specified in the contract. Separate carry bags for the poles and ground stakes may also be provided but must all fit into a single carry bag for the complete system.

3.3.6 Repair kit. The repair kit shall consist of the following, as a minimum, and carried in a repair kit carry bag: 1 ounce tube of seam sealant (See 7.5), 70 feet of 3 millimeter diameter cordage, Coyote 498, Tan 499, or other color as specified in the contract, nylon cord (for guy lines)(see 7.5).

3.4 Materials.

3.4.1 Shelter floor, canopy top, rain fly and carry bag material. The shelter floor and canopy top fabric shall be OCP, Coyote 498, Tan 499, or other color as specified in the contract, shall be a 70 Denier, nylon ripstop, The shelter floor shall meet the requirements in Table IA when tested as specified in Table IA. The shelter rain fly and carry bag, shall be a 30 Denier nylon ripstop and made using the camouflage pattern OCP, or other color as specified in the contract, and the fabric shall meet the requirements in Table IB when tested as specified in Table IB and the spectral reflectance requirements of Table II when tested as specified in 3.4.1.1.

THIS SPACE LEFT INTENTIONALLY BLANK

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

TABLE IA. Physical requirements for water-resistant shelter floor.

Characteristics, units	Requirements	Test Method
Weight, oz./sq. yd. (max.)	3.1	ASTM D3776/D3776M, Option C
Breaking strength, lbs. Initial: Warp and Fill (min.) After Weathering: Warp and Fill (min.)	 50 35	 ASTM D5035 5.3.2 and ASTM D5035
Tearing Strength, grams. Initial Warp and fill (min.) After Weathering Warp and fill (min.)	 600 400	 ASTM D1424 5.3.2 and ASTM D1424
Adhesion of coating, lbs./2-inch width Dry (min.)	 7.0	 ASTM D751 1/
Spray Rating (min.)	80, 80, 80	AATCC TM22 2/
Hydrostatic resistance, psi: Initial (min.) After flexing, 100 cycles (min.) After abrasion, (min.) After strength of coating (min.) After high humidity (min.)	 125 35 35 35 40	 ASTM D751 3/ ASTM F392 4/ and ASTM D751 3/ ASTM D3886 5/ and ASTM D751 3/ ASTM D751 3/, 6/ 7/ and ASTM D751 3/
Water permeability Initial After cold crack, -25°F After accelerated weathering 100kJ	 Pass Pass Pass	 ASTM D751 8/ ASTM D751 8// and 9/ 5.3.2 and ASTM D751 8/
Flame resistance After flame, seconds: (max.) Initial Warp and Fill After Weathering 100kJ Warp and Fill Char length, inches Initial Warp and Fill After Weathering 100kJ Warp and Fill	 2.0 Average 4.0 Individual 2.0 Average 4.0 Individual 7.5 Average 10.0 Individual 7.5 Average 10.0 Individual	 ASTM F3431 5.3.2 and ASTM F3431 ASTM F3431 10/ 5.3.2 and ASTM F3431 10/

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

TABLE IA. Physical requirements for water-resistant shelter floor. - Continued

Characteristics, units	Requirements	Test Method
Melt Drip Initial After Weathering 100kJ	 No flaming or Molten Drips No flaming or Molten Drips	 ASTM F3431 10/ 5.3.2 and ASTM F3431 10/
Flame resistance After flame, seconds: (max.) Initial Warp and Fill After Weathering 100kJ Warp and Fill Char length, inches Initial Warp and Fill After Weathering 100kJ Warp and Fill Melt Drip Initial After Weathering 100kJ	 2.0 Average 4.0 Individual 2.0 Average 4.0 Individual 7.5 Average 10.0 Individual 7.5 Average 10.0 Individual No flaming or Molten Drips No flaming or Molten Drips	 ASTM F3431 5.3.2 and ASTM F3431 ASTM F3431 10/ 5.3.2 and ASTM F3431 10/ ASTM F3431 10/ 5.3.2 and ASTM F3431 10/
Flexibility (warp only), cm: Initial (max.) At -25°F (max.)	 10 15	 ASTM D1388 Option A 11/ ASTM D1388 Option A 11/
Blocking, scale rating (max.)	3	5.3.3 ASTM D751
Mildew resistance	No Growth No Growth	AATCC TM 30 AATCC TM147
Colorfastness: Rating (min.) After accelerated weathering After high humidity	 3 12/ 3 12/	 5.3.2 and AATCC TM107 13/, 14/ 7/ and AATCC TM107 13/, 14/

1/ ASTM D751, Adhesion of Coating except with 2-inch wide reinforced coating adhesion specimens, cyanoacrylate (solventless) adhesive and pulling clamp speed of 5 millimeters per second. Three (3) specimens shall be tested by adhering the film/coating sides of the fabric to itself. The adhesion of the specimen shall be the average of the five (5) highest load peaks of resistance.

2/ The water shall be applied to the uncoated side of fabric.

3/ ASTM D751, Hydrostatic Resistance, Procedure A (Pressure Application by Mullen Type Hydrostatic Tester), Procedure 1 with water pressure applied to the uncoated side of the fabric.

4/ Test specimens shall be conditioned and tested as specified in ASTM F392 except that the specimens shall not be aged, the short edges shall not be heat sealed or otherwise joined, and the specimen shall be flexed for 100 flex cycles.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

5/ The coated side of the coated fabric shall be abraded 1,000 multi-directional cycles using the coated side of the coated fabric as the abradant.
6/ Except that the load shall be 20 lbs.
7/ Three (3), 4-inch by 4-inch specimens shall be laid flat, coated side up on supporting plate, and the assembly placed in a desiccator containing water in the lower portion. The water level shall be approximately 1-inch below the specimens. The lid of the desiccator shall be put in place and the desiccator placed in a circulating air oven having a temperature of 140°F (± 2°F) for a period of 14 days. At the end of the aging period, each specimen shall be removed from the desiccator, visually examined for colorfastness and then tested immediately hydrostatic resistance properties. The coating shall not become stiff and brittle nor soft and tacky, and there shall be no evidence of cracking or crazing under visual examination.
8/ ASTM D751, Hydrostatic Resistance, Procedure B (Pressure Application by Rising Column of Water), Procedure 2 using a fixed hydrostatic head of 50 centimeters held for 5 minutes; the water pressure applied to the uncoated side of the fabric. Leakage is defined as the appearance of water at three (3) or more places within the 4-1/2 inch diameter area.
9/ ASTM D751, Low-Temperature Crack Resistance. The test shall be conducted at – 25°F (± 5°F) after a minimum of 30 minutes at that temperature. The coating shall be on the outside of the fold.
10/ In addition to after-flame time and char length, any evidence of flaming melted or molten pieces dropping from the specimen at any time during the test shall be reported as a failure.
11/ Specimens shall be tested in warp direction only.
12/ Except the time shall be 1 hour.
13/ The specimen shall be placed between glass plates. The specimen/plate assembly and the test instrument shall be conditioned at -25°F for a minimum of 2 hours. The test shall be run at -25°F.
14/ Equal to or better than "3" rating on AATCC EP1 Gray Scale for Color Change.

TABLE IB. Physical requirements for water-resistant rain fly and carry bag fabric.

Characteristics, units	Requirements	Test Method
Weight, oz./sq. yd. (max.)	2.1	ASTM D3776/D3776M, Option C
Spray Rating (min.)	80, 80, 80	AATCC TM22 1/
Hydrostatic resistance, psi:		
Initial (min.)	125	ASTM D751 2/
After flexing, 100 cycles (min.)	35	ASTM F392 3/ and ASTM D751 2/
After abrasion, (min.)	35	ASTM D3886 4/ and ASTM D751 2/
After strength of coating (min.)	35	ASTM D751 2/, 5/
After high humidity (min.)	40	6/ and D751 2/
Flame resistance (max.)		
After flame, seconds:	2.0 Average	
Initial Warp and Fill	4.0 Individual	ASTM F3431
Char length, inches		
Initial Warp and Fill	7.5 Average	
	10.0 Individual	ASTM F3431

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

TABLE IB. Physical requirements for water-resistant rain fly and carry bag fabric. - Continued

Characteristics, units	Requirements	Test Method
Fungus Resistance	Certificate of Compliance	AATCC TM30, AATCC TM147

1/ The water shall be applied to the uncoated side of fabric.
2/ ASTM D751, Hydrostatic Resistance, Procedure A (Pressure Application by Mullen Type Hydrostatic Tester), Procedure 1 with water pressure applied to the uncoated side of the fabric.
3/ Test specimens shall be conditioned and tested as specified in ASTM F392 except that the specimens shall not be aged, the short edges shall not be heat sealed or otherwise joined, and the specimen shall be flexed for 100 flex cycles.
4/ The coated side of the coated fabric shall be abraded 1,000 multi-directional cycles using the coated side of the coated fabric as the abradant.
5/ Except that the load shall be 20 pounds.
6/ Three (3), 4-inch by 4-inch specimens shall be laid flat, coated side up on supporting plate, and the assembly placed in a containing water in the lower portion. The water level shall be approximately 1-inch below the specimens. The lid of the desiccator shall be put in place and the desiccator placed in a circulating air oven having a temperature of 140°F (± 2°F) for a period of 14 days. At the end of the aging period, each specimen shall be removed from the desiccator, visually examined for colorfastness and then tested immediately hydrostatic resistance properties. The coating shall not become stiff and brittle nor soft and tacky, and there shall be no evidence of cracking or crazing under visual examination.

TABLE II. Spectral reflectance (OCP).

Operational Camouflage Pattern (OCP) Reflectance values (percent)						
	Dark Cream 559 and Tan 525		Light Sage 560, Olive 527 and Brown 529		Dark Green 528 and Bark Brown 561	
Wavelength (nm)	MIN	MAX	MIN	MAX	MIN	MAX
600	22	44	12	30	3	12
620	24	45	12	30	3	12
640	24	45	12	32	4	12
660	25	45	12	32	4	13
680	28	45	14	34	4	18
700	28	48	14	36	6	25
720	30	52	16	39	6	27
740	32	55	18	41	10	29
760	36	56	20	43	14	33
780	38	57	22	45	18	36
800	40	57	22	45	20	37
820	44	58	24	46	20	38
840	46	59	26	47	21	39
860	48	60	28	48	21	40

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

3.4.1.1 Spectral reflectance test. Spectral reflectance data shall be obtained from 600 to 860 nanometers (nm) for Operational Camouflage Pattern (OCP) at 20 nm intervals on a spectrophotometer relative to the polytetrafluoroethylene (PTFE) family of compounds, the preferred white standard. Other white reference materials may be used provided they are calibrated to absolute white or vitrolite tiles. The spectral band width shall be less than 20 nm at 860 nm. Reflectance measurements shall be made by either the monochromatic or polychromatic mode of operation. When the polychromatic mode of operation is used, the spectrophotometer shall operate with the specimen diffusely illuminated with the full emission of a continuous source that simulates either CIE Source A or CIE Source D65. Measurements shall be taken on a minimum of two (2) different areas and the data averaged. The measured areas should be at least 6-inches away from the selvage. The Operational Camouflage Pattern (OCP) shall be measured as a single layer backed with four (4) layers of the same shade cut from the standard. The spectral reflectance on OCP shall be measured on the mostly solid color area not the tonal area. The specimen shall be viewed at an angle no greater than 10° from normal, with the specular component included. Specimens shall be oriented in different directions during testing. When possible, the specimens tested shall not contain the same warp or filling yarns when presented to the sample port. Camouflage materials should be measured with the appropriate aperture size to ensure that only one (1) color is measured at a time. Always use the largest aperture possible. Photometric accuracy of the spectrophotometer shall be within one (1) percent and wavelength accuracy within two (2) nm. Any color having spectral reflectance values falling outside the limits at four (4) or more of the wavelengths specified shall be considered a test failure.

3.4.2 Canopy netting. The material for the insect canopy netting on the front door and shelter vents shall be 40 Denier polyester knit mesh, Black, Coyote 498, Tan 499 or color as specified in the contract or solicitation.

3.5 Maintenance. The shelter shall be easy to clean and maintain. Maintenance will consist of cleaning and simple repair or replacement of components. Organizational will consist of replacement of poles, fasteners, and application of small patches.

3.6 Storage life. The shelter shall have a storage life of 5 years, minimum.

3.7 Instructions. A 'Care and Use' instruction pamphlet or sheet shall be provided with the shelter. It shall contain procedures for setup of the shelter in standard and minimum configurations, striking and packing, safety precautions, repair and care procedures, and a list of spare parts with National Stock Number (NSN) reference.

3.8 Labels.

3.8.1 Instruction labels/marking. Each shelter shall be permanently labeled with labels attached on the inside of the shelter and rain fly, and on the carry bag and repair kit bag. The labels shall be a printed cloth label, Coyote 498, Tan 499 or color as specified in the contract or solicitation. with permanent Black ink and sewn to the shelter or component. The shelter label shall contain the item nomenclature, contractor's name, contract number, National Stock Number (NSN) of the shelter system, fiber content, safety precautions, cleaning instructions

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

and a list of spare parts with NSN reference. Labels for the rain fly, carry bag and repair kit bag shall contain the item nomenclature, contractor's name, contract number, and National Stock Number (NSN).

3.8.2 Label/tag. Each shelter shall be individually bar-coded with the Type VIII, Class 17 label/tag of MIL-DTL-32075. This label/tag shall be located so that it is completely visible on the item when it is folded and packaged. The tag shall not damage the item.

3.9 Workmanship. The finished shelter shall conform to the quality of the product established in this document. The shelter shall be free from defects which would affect its serviceability, appearance, uniformity and quality assurance standards defined by the technical data in the procurement documents.

4. REGULATORY REQUIREMENTS. Unless otherwise specified, the offeror/contractor is encouraged to use recovered, recycled, bio based, and environmentally preferable materials to the maximum extent practicable, in accordance with paragraph 23.403, 23.404(b) of the Federal Acquisition Regulation (FAR), or the sustainable acquisition of EO 13693; as applicable. (see 7.1.2).

4.1 Toxicity. The finished cloths used in the construction of the shelter shall not present a dermal health hazard when the item is used as intended (see 5.3.1).

5. PRODUCT CONFORMANCE PROVISIONS.

5.1 Product conformance. The shelter shall meet the salient characteristics of this Commercial Item Description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance.

5.2 Market acceptability. The finished shelter offered must have been sold to the government or commercial market.

5.3 End item inspection procedures. Sampling for inspection shall be conducted in accordance with ANSI/ASQ Z1.4 - Sampling Procedures and Tables for Inspection of Attributes (see 7.2.2).

5.3.1 Toxicity assessment. The contractor must furnish information which certifies that the finished product is composed of materials which have been safely used commercially or provide sufficient toxicity data to show compatibility with prolonged, direct skin contact, (see 7.4).

5.3.2 Accelerated weathering procedure. The test procedure shall be in accordance with AATCC TM169 with the coated side of the coated fabric exposed to 100 Kilojoules energy and except that the deviations listed below shall apply. The coating shall not become stiff and brittle nor soft and tacky, and there shall be no evidence of cracking or crazing under visual examination.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

a. The test apparatus shall be either test chamber IA or 1B. Type 1B shall be equipped with a three-tiered inclined specimen rack. The apparatus shall be equipped with an automatic light monitor and shall be capable of automatically controlling irradiance, temperature, and humidity. The apparatus shall be maintained in accordance with the manufacturer's recommendations.
b. The weathering test cycle shall be 40 minutes of light, 20 minutes of light with water spray on the fabric face, 60 minutes of light, 60 minutes of darkness. The test cycle shall be repeated until the total energy exposure is equal to 100 kilojoules per square meter.
c. The irradiance level shall be 0.55 (± 0.01) watt/square meter/nanometer [W/m2/nm] bandpass at 340 nanometers.
d. The glass filter combination shall be a quartz inner filter and a borosilicate type "S" outer filter.
e. The relative humidity shall be 50 (± 5) percent during the light cycle and not lower than 95 percent during the dark cycle.
f. The control set points shall be as follows: 1/

	Dark Cycle	Light Cycle
Black panel	38 °C	77 °C
Conditioning water	40 °C	53 °C
Wet bulb depression	0 °C	10 °C

1/ as a guide only; adjust to achieve required relative humidity. [see e. above]

g. The test specimen shall fit the specimen rack of the apparatus with no wrinkles or gaps. The test specimen shall be mounted on the outside of the rack with the use of appropriate stainless steel spring clips. After the required exposure period, the specimens shall be removed from the apparatus and allowed to dry and condition at standard conditions. The test specimens for each required test shall be cut and tested appropriately.

NOTE: Monitoring of dry bulb temperature, wet bulb depression, irradiance, and black panel temperature is recommended using chart recorders.

5.3.3 Blocking procedure. ASTM D751, Blocking Resistance at Elevated Temperatures except that the test shall be performed at a temperature of 180 (±2)°F for 30 minutes. Evaluate the resistance of the specimen to blocking by the scale given below:

1 - No Blocking. Cloth surfaces are free and separate without any evidence of cohesion or adhesion.
2 - Trace Blocking. Cloth surfaces show slight cohesion or adhesion.
3 - Slight Blocking. Cloth surfaces must be lightly peeled to separate.
4 - Blocking. Cloth surfaces separate with difficulty or coating is removed during separation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

5.3.4 Seam leakage procedure. ASTM D751, Hydrostatic Resistance, Procedure B, Procedure 2 with a fixed hydrostatic head of 50-centimeters applied to the face side (side exposed to the weather or ground water) of the test specimen for 10 minutes. Five (5) test areas shall be tested on each of the shelter basic (weather-exposed shelter and ground water-exposed floor seams) and the rain fly (weather-exposed seams, except that the slide fastener welt seams shall not be tested). Leakage is defined as the appearance of one (1) or more droplets of water within the 4-1/2 inch diameter test area.

5.3.5 Operational test. Each shelter with rain fly shall be assembled, set up, struck, disassembled and packed to ensure operation of all moving parts and adjusting mechanisms.

5.4 Visual examination. Each finished shelter shall be examined for the defects listed in Table III as defined in ASTM D3990. The lot size shall be expressed in units of shelters. The sample unit shall be one (1) shelter.

TABLE III. Visual examination defects.

Material defects: Any hole, cut, tear, permanent fold, pleat, or crease; any spot or stain on outside, discoloration or color not as specified, any outwardly visible part shaded, any serious material defects or objectionable odor.
Stitches, seams and stitching: Loose or tight stitching tension, broken or skipped stitches, needle chew, any part caught in an unrelated operation or stitching, raw edge, open seams, thread ends not removed, or loose tension resulting in loose seams; any weather-exposed seam. Not seam sealed.
Workmanship: Any component part omitted, twisted, not specified size, missing, misplaced or distorted parts; poorly shaped, any dimension of item not as specified; design not as specified. Failure to meet product conformance; serviceability, reliability and quality of materials as defined by this document.
Labels: Label(s) missing, incorrect, or illegible; bar code or UPC code label omitted or not readable by scanner; human-readable interpretation (HRI) omitted or illegible; bar code not visible on folded packaged item, bar code label causes damage to the item.
Packaging: Not packaged in accordance with the contract or procurement documents.

5.5 Dimensional examination. The finished shelter shall conform to the dimensions specified in 3.3.1 when measured as stated. Any dimension that is not within the established tolerance shall be classified as a defect. The sample unit shall be one (1) shelter.

5.6 Acceptance criteria. Acceptance criteria shall be as specified in the contract or procurement documents (see 7.5).

6. PACKAGING. The preservation, packing and marking shall be as specified in the contract or order (see 7.5).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

7. NOTES.

7.1 Source of Government documents:

7.1.1 Copies of Government documents are available online at https://quicksearch.dla.mil.

7.1.2 EPA and EO 13693 information is available online at https://www.epa.gov.

7.1.3 Federal Acquisition Regulations (FAR) are available online at https://acquisition.gov.

7.1.4 Toxicity testing. If dermal toxicity testing is required, it will be conducted in accordance with Title 40, Protection of Environment, Code of Federal Regulations current edition and applicable sections, which are also consistent with the following Organisation for Economic Co-operation and Development (OECD) tests:

Skin Sensitization 406 and Dermal Irritation 404 (https://www.oecd-ilibrary.org/environment/oecd-guidelines-for-the-testing-of-chemicals-section-4-health-effects_20745788?page=1).

Dermal Sensitization (https://www.law.cornell.edu/cfr/text/40/798.4100).
Dermal Toxicity (https://www.law.cornell.edu/cfr/text/40/798.2250).

7.2 Source of non-Government documents.

7.2.1 AATCC Test Methods are available for purchase online at https://aatcc.org.

7.2.2 ASQ/ANSI Z1.4 – Sampling Procedures are available online at https://asq.org.

7.2.3 ASTM Standards are available for purchase online at https://www.astm.org.

7.3 Intended use. The Improved Combat Shelter (ICS) GEN II is intended to be used as single storage vestibule, one-person size, double-walled, free-standing, capable of setup in at least two (2) configurations used by the Army.

7.4 Certificate of compliance. The contracting activity may select to accept a certificate of compliance for a stated requirement.

7.5 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this CID.
b. Type, classes, and size required (see 2.).
c. Color required (see 3.3.1- 3.3.6).
d. When toxicity testing is required (see 4.1 and 5.3.1).
e. Product conformance (see 5.1).
f. Acceptance criteria (see 5.6).
g. Packaging requirements (see 6.).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.

7.6 Key words.

One-person
Single storage
Vestibule

MILITARY INTERESTS:

CIVIL AGENCY COORDINATING ACTVITY:
GSA-FAS

Custodians:
Army - GL

Preparing Activity
DLA-CT

(Project 8340-2025-002)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:33Z
Check the source to verify that this is the current version before use.