COMMERCIAL ITEM DESCRIPTION

CURETTE, EAR (House, Light, Angle)

The General Services Administration has authorized the use of this commercial item description.

This commercial item description covers a double ended ear currette of the House design with 15 degree angled cups.

Salient characteristics.

Material. The curette shall be manufactured from martensitic corrosion resistance steel in accordance with American Society for Testing and Materials (ASTM) Standard F899.

Hardness. The shank shall have a Rockwell hardness of HRC 40-45 for Type 410 or HRC 44-48 for Type 410X.

Style and design. The curette shall be in accordance with Figure 1.

Passivation. The curettes shall be properly passivated.

Finish. The finish of the currette shall be satin or matte. The finish shall be uniform and free from burrs, pits, scale, rough areas, or grind or tool marks.

Tests. Curettes shall be tested for Rockwell hardness and corrosion resistance as specified under Quality Assurance Provisions.

Markings. The curette shall be permanently and legibly marked with the manufacturer's name or registered trademark and the word "stainless." In addition, curettes of foreign manufacture shall bear the name of the country of manufacture.

AMSC N/A FSC 6515

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:20Z
Check the source to verify that this is the current version before use.

Workmanship. The curette shall be processed in such a manner as to be uniform and free from defects which affect life, utility, or appearance.

Product Quality Level

Visual and dimensional examination. Shall be examined to verify that design, construction and workmanship are in accordance with applicable requirements.

Materials. The supplier shall be responsible for performing tests to assure that materials are in accordance with requirements specified.

Unit. Each (EA). One curette, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Examination. Curettes shall be examined to determine compliance with specification requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:20Z
Check the source to verify that this is the current version before use.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as specified herein. The unit of product for test purposes shall be one curette. Sampling shall be as specified in the individual test methods below.

Tests.

Corrosion-resistance tests. Curettes shall be tested in accordance with Resistance to Copper Sulfate Test and the Resistance to Boil Test of Federal Specification GG-I-526. Sampling shall be level S-2 with an AQL of 1.0.

Hardness. Hardness shall be tested in accordance with ASTM Standard E18, or ASTM Standards E92 and E140. Sampling shall be level S-2 with an AQL of 1.0.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specification, standard, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practical.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:20Z
Check the source to verify that this is the current version before use.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document:

NSN	ITEM IDENTIFICATION
6515-01-113-4360	CURETTE, EAR, House, Double-Ended, Light Curve, 7 inch (17.78 cm)

Ordering data . Intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order.

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

Preparing Activity:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

Project No. 6515-4218

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:20Z
Check the source to verify that this is the current version before use.




FIGURE 1 CURETTE, EAR, HOUSE, DOUBLE-ENDED, LIGHT CURVE

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:20Z
Check the source to verify that this is the current version before use.