JAN-C-367

19 July 1946

JOINT ARMY-NAVVY SPECIFICATION

CLOTH, FUZE

Army Number	Navy Number
8-36B	27C64

This specification was approved by the War Department and the Navy Department for use of procurement services of the Army and the Navy and supersedes the following specifications:

U. S. Army	Navy Department
8-36A	Bureau of Ordnance
24 June 1935	O. S. 1347
	2 Sept. 1946

A. APPLICABLE SPECIFICATIONS AND OTHER PUBLICATION.

A–1. *Specifications.*— The following specifications, of the issue in effect on the date of invitation for bids, form a part of this specification:

U. S. ARMY SPECIFICATION

100–2—Standard Specification for Marking Shipments by Contractors.[1]

NAVY DEPARTMENT SPECIFICATION

General Specifications for Inspection of Material.[2]

FEDERAL SPECIFICATION

CCC–T–191—Textiles, General Specifications, Test Methods.

A–2. *Other publication.* The following publication, of the issue in effect on date of invitation for bids, forms a part of this specification:

BUREAU OF SUPPLIES AND ACCOUNTS PUBLICATION

Navy Shipment Marking Handbook.[2]

B. TYPE.

B–1. This specification covers one type of fuze cloth as hereinafter specified.

C. MATERIAL AND WORKMANSHIP.

C–1. The wool for both warp and filling shall be not lower in grade than 64s. It shall be of sufficient length and strength to meet the requirements as hereininafter described. The wool for both warp and filling shall be well carded, evenly spun, and of good workmanship. The woven cloth shall be uniform in weave, have a close nap, and be free from loading or doping materials.

D. GENERAL REQUIREMENTS.

D–1. See section E.

[1] Applicable only to Army purchases.
[2] Applicable only to Navy purchases.

707298—46—(34)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:06Z
Check the source to verify that this is the current version before use.

E. DETAIL REQUIREMENTS.

E–1. *Color.*—Natural (grayish-white).

E–2. *Width.*—Not less than 56 inches nor more than 58 inches, exclusive of the selvage.

E–3. *Thickness.*—0.033 ± 0.003 inch.

E–4. *Weight.*—13.50 ± 0.65 ounces per square yard.

E–5. *Weave.*—Broken four harness twill, two up and two down.

E–6. *Thread count.*—58 ± 2 threads per inch in each direction.

E–7. *Breaking strength.*—Warp direction, not less than 45 pounds. Filling direction, not less than 40 pounds.

E–8. *Wool content.*—100 percent.

E–9. *Acidity.*—Fuze cloth shall be free from inorganic acids. A water extract of the fuze cloth shall be neutral to litmus paper and the organic acidity shall not exceed 0.10 percent.

E–10. *Compression.*—When subjected to a pressure of 10,000 pounds per square inch, the cloth shall measure from 0.022 to 0.025 inch in thickness after being pressed.

F. METHODS OF SAMPLING, INSPECTION, AND TESTS.

F–1. *Size of lot.*—A lot shall consist of not more than 5,000 yards.

F–2. *Sampling.*—Remove approximately 1 yard from 10 percent, but not more than 10 of the rolls of cloth comprising the lot. Label each so that the roll from which it was taken can be identified. Make a composite sample of the lot consisting of approximately one-half yard of each of the primary samples. Make all acceptance tests on the composite sample, which is the official sample and shall be used by the inspector as the sample representative of the lot. Use as many pieces of the sample as possible in making the tests. Place all samples in securely closed containers, and label each container so as to show the name of the material, manufacturer, plant, purchase order, and the number of yards in the lot. The separate samples will be held by the inspector for possible future examination, should the composite sample show that the lot fails to meet the requirements.

F–3. *Inspection.*—The place of inspection shall be as specified in the contract or order. (See par. H–1.)

F–4. *Tests.*

F–4a. *Color.*—Determine the color by visual inspection.

F–4b. *Width.*—Determine the width as directed by Federal Specification CCC–T–191.

F–4c. *Thickness.*—Determine the thickness by means of a micrometer which presses upon a circle of felt 3/8 inches in diameter. The micrometer shall be equipped with a rachet stop, which exerts a pressure of approximately 6 ounces. Take at least 10 measurements of different portions of the sample and consider the average as the thickness of the cloth.

F–4d. *Weight.*—Determine the weight as directed by Federal Specification CCC–T–191.

F–4e. *Weave.*—Remove the nap from a portion of the sample

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:06Z
Check the source to verify that this is the current version before use.

by means of a razor blade and determine the type of weave by visual inspection.

F–4f. *Thread count.*—Determine the thread count as directed by Federal Specification CCC–T–191.

F–4g. *Breaking strength.*—Determine the breaking strength by the strip method as directed by Federal Specification CCC–T–191.

F–4h. *Wool content.*—Determine the wool content as directed by Federal Specification CCC–T–191.

F–4i. *Acidity.*—Place a weighed 5-gram portion of the sample in 150 ml of distilled water and boil for 30 to 45 minutes. Cool, dilute to 150 ml with distilled water and test the liquid with both blue and red litmus papers of such sensitiveness that their colors are completely changed in 1 minute by N/250 sulfuric acid and sodium hydroxide solutions respectively. No change in color of either papers should be apparent in 30 seconds. Add two drops of phenolphthalein indicator and titrate with N/10 sodium hydroxide. Calculate the organic acidity as percentage of acetic acid.

F–4j. *Compression.*—Cut pieces of the cloth exactly 1 inch square. Subject each to a pressure of 10,000 pounds for not more than 1 minute. Release the pressure and determine thickness immediately as directed in paragraph F–4c.

F–5. *Resubmission.*—If the composite sample representative of the lot fails to pass the inspection tests, the manufacturer shall have the option of having tests of each primary sample made at no further expense to the Government. The manufacturer may then remove or replace defective portions of the lot represented by the primary samples which fail to meet the requirements of this specification, and submit the lot for acceptance, provided that identification of the material is such that complete removal or replacement of defective portions of the lot can be made to the satisfaction of the Government inspector.

G. PACKAGING, PACKING, AND MARKING FOR SHIPMENT.

G–1. *Packaging.*—The subject commodity shall be furnished in rolls, full width, not folded, of about 50 yards each. Before rolling, the cloth shall be sprinkled with high-grade commercial flake naphthalene. Approximately 1 ounce of naphthalene shall be used for approximately 100 pounds of cloth. Each roll shall be wrapped with at least two layers of paper. One layer shall be of plain kraft paper and at least one layer shall be of water-proof kraft paper. After wrapping, each roll shall be sewed in burlap to insure delivery in good condition at destination.

G–2. *Packing.*—The rolls shall be packed for shipment in substantial wooden cases so constructed as to insure acceptance by common or other carriers for safe transportation at the lowest rate to the point of delivery. The gross weight of cases shall be not more than 250 pounds.

G–3. *Marking.*—In addition to any special marking required by the contract or order, shipments for the Army shall be marked in accordance with the requirements of U. S. Army Specification 100–2; for the Navy, in accordance with the requirements of the Navy Shipment Handbook.

[JAN-C-367]

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:06Z
Check the source to verify that this is the current version before use.

H. NOTES.

H–1. Requests, requisitions, schedules, and contracts or orders should contain the following features:

(a) Title, number, and date of the specification.
(b) Place of inspection. (See par. F–3.)

H–2. *Use.*—The material covered by this specification is intended for use in the manufacture of fuzes.

H–3. Copies of Joint Army-Navy specifications and Federal specifications (required for Army purchases) and U. S. Army specifications may be obtained as indicated in the "Index of United States Army, Joint Army-Navy, and Federal Specifications Used by the War Department". Copies of this Index may be obtained from the Superintendent of Documents, Government Printing Office, Washington 25, D. C. Agencies within the War Department will obtain copies of Joint Army-Navy, U. S. Army, and Federal specifications through established War Department channels. Both the title and identifying symbol number should be stipulated when requesting copies of specifications.

H–4. Copies of Joint Army-Navy specifications and Federal specifications (required for Navy purchases), Navy Department specifications and the Navy Shipment Marking Handbook may be obtained upon application to the Bureau of Supplies and Accounts, Navy Department, Washington 25, D. C., except that Naval activities should make application to the Supply Officer in Command, Naval Supply Depot, Bayonne, N. J. Both the title and identifying symbol number should be stipulated when requesting copies of specifications.

H–5. Copies of this Joint Army-Navy specification (required for Army purchases) may be obtained from the Office, Chief of Ordnance, War Department, Washington 25, D. C.

Notice. When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Army: O.
Navy: OS.

[JAN-C-367]

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:06Z
Check the source to verify that this is the current version before use.