MIL-C-342J
1 April 1988
SUPERSEDING
MIL-C-342H
30 April 1986

MILITARY SPECIFICATION

CLOTH, WIND RESISTANT, POPLIN, COTTON

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers rip stop poplin, wind resistant cotton cloth.

1.2 Classification. The cloth shall be of one type in the following classes as specified (see 6.2):

Class A - Plain finish (untreated)
Class B - Water repellent treated
Class C - Fire resistant treated

2. APPLICABLE DOCUMENTS

* 2.1 Government documents.

* 2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

* Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8305

* DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

V-T-276 - Thread, Cotton
PPP-P-1134 - Packaging of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics)

STANDARDS

FEDERAL

FED-STD-4 - Glossary of Fabric Imperfections
FED-STD-191 - Textile Test Methods

* MILITARY

* MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

* (Copies of specifications, standards, and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

* 2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of solicitation.

FEDERAL TRADE COMMISSION

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained from the Federal Trade Commission, Pennsylvania Avenue at Sixth Street, N.W., Washington, DC 20580.)

* (Copies of drawings, publications, and other Government documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

* 2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

Chromatic Transference Scale

(Copies may be obtained from the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, NC 27709-2215.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 1424 - Tear Resistance of Woven Fabrics by Falling Pendulum (Elmendorf) Apparatus

(Copies may be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

* (Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

* 2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Standard sample. The finished cloth shall match the standard sample for shade and appearance and unless otherwise indicated (see 3.4.3), shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.4).

3.2 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2 and 6.3).

3.3 Material. The cotton shall be carded, combed, drawn, spun and twisted into 2-ply yarn for the warp and 2-ply or single yarn for the filling (see 6.11).

3.4 Color. The color shall be as specified and shall match the standard sample (see 6.2, 6.4, and 6.5).

3.4.1 Labile sulfur. The use of dyes and compounds containing elementary sulfur capable of oxidation to sulfuric acid is prohibited. The dyes shall be chosen and applied so that the dyed and finished cloth shall contain no more labile sulfur than shown by the standard sample when tested as specified in 4.4.3. When a standard sample is not available, the dyed and finished cloth shall show no more than a slight trace of labile sulfur as defined in the test method when tested as specified in 4.4.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

* 3.4.2 Matching. The color of the finished cloth shall match the standard sample when viewed under filtered tungsten lamps which approximate artificial daylight having a correlated color temperature of 7500 ± 200 K, with illumination of 100 ± 20 foot candles and shall be a good match to the standard sample under incandescent lamplight at 2300 ± 200 K.

* 3.4.3 Colorfastness. The finished cloth shall show fastness to laundering (after 3 cycles), perspiration, wet dry-cleaning, and light equal to or better than the standard sample, or equal to or better than the rating of "good" when tested as specified in 4.4.3. The finished cloth shall show fastness to crocking equal to or better than the standard sample or shall have an AATCC Chromatic Transference Scale rating of 3.5, when tested as specified in 4.4.3.

3.5 Physical requirements. The finished cloth shall conform to the requirements specified in table I when tested as specified in 4.4.3.

TABLE I. Physical requirements

Class	Weight per sq.yd. (ounces) min	max	Yarns per inch, minimum Warp	Filling	Breaking strength, minimum Warp	Filling	Tearing strength, minimum Warp	Filling	Air permeability (cu.ft./minute/ sq. foot), max (avg)
A	5.7	7.0	104	52	110	68	4.0	4.0	18.0
B	5.7	7.2	104	52	100	60	4.0	4.0	15.0
C	7.0	8.0	104	52	90	60	2.0	3.0	15.0

3.5.1 Width. The width shall be as specified (see 6.2) and shall be the minimum acceptable width inclusive of selvage when fly shuttle looms or shuttleless looms with tuck-in selvage looms are used. For all other shuttleless looms, the width measurement shall be made between the last warp yarn on each side excluding the protruding fringe(s).

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

3.5.2 Weave. The weave shall be plain with reinforcement ribs uniformly spaced in the warp and filling. The warp repeat shall be two ends weaving as one followed by 23 single ends (total 25 ends per repeat). The filling repeat shall be two picks inserted into the same shed followed by 12 single picks (total 14 picks per repeat).

3.6 Finish. The cloth shall be singed, desized, mercerized and dyed. The use of resin pigments in the dyeing or finishing of the cloth is prohibited. The type and character of finish shall conform to that shown by the standard sample.

3.7 Nonfibrous material. The untreated cloth of classes A, B, and C shall contain not more than 2.0 percent starch and protein content (including chloroform-soluble and water-soluble material) when tested as specified in 4.4.3.

3.8 Dimensional stability. Unless otherwise specified (see 6.2), the finished cloth shall not shrink or elongate more than 2.0 percent in the direction of either the warp or the filling when tested as specified in 4.4.3. The preshrinking process used shall not be identified by name or trademark on either the cloth, ticket, or package.

3.9 Water repellency (class B).

3.9.1 Treatment. The cloth shall be given an approved Quarpel-type (see 6.6) water repellent treatment, and shall conform to the requirements of 3.9.1.1 and 3.9.1.2 when tested as specified in 4.4.3. The use of materials other than approved water repellents and sodium acetate buffer (and acetic acid), is prohibited.

3.9.1.1 Spray rating. The results of the three individual determinations on the sample unit for spray rating shall be equal to or better than ratings 90, 90, 80 when tested initially, and 70, 70, 70 after laundering as required by 3.8 when tested as specified in 4.4.3.

3.9.1.2 Resistance to organic liquid. The water repellent treated cloth shall not show wetting by n-dodecane initially when tested as specified in 4.4.3.

* 3.10 Flame resistance (class C). The cloth shall be given an approved flame-resistant treatment (see 6.7). The finished cloth shall have an average time for flaming of not more than 2.0 seconds, an after-glow of not more than 6.0 seconds, and an average char length of not more than 5.0 inches before and after 15 cycles of laundering when tested as specified in 4.4.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

3.11 pH. The pH value of the water extract of the finished cloth shall be no less than 5.0 nor more than 8.5 when tested as specified in 4.4.3.

3.12 Seam efficiency. Classes A and B finished cloths shall have a seam efficiency of not less than 80 percent when tested as specified in 4.4.3.

* 3.13 Length and put-up. For Government procurements only, unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths each not less than 40 yards. The cloth shall be put up on rolls as specified in 5.1.

3.14 Fiber identification. Each roll shall be labeled, ticketed, or invoiced for fiber content in accordance with the Textile Fiber Products Identification Act.

3.15 Marking. The face side of the cloth shall be identified by applying a stamping on that side of the cloth with the word "FACE" at each end of the piece.

* 3.16 Spectral reflectance for Camouflage Green 483. When Camouflage Green 483 is specified, the finished cloth shall meet the spectral reflectance factors (in percent) for the visible/near infrared wavelength range 600 to 860 nanometers (nm) as specified below, when tested as specified in 4.4.3.

Spectral reflectance requirements for Camouflage Green 483

Wavelength (nm)	Reflectance (%)		Wavelength (nm)	Reflectance (%)	
	Max	Min		Max	Min
600	10	4	740	40	14
620	10	4	760	49	18
640	11	4	780	55	23
660	13	4	800	60	29
680	15	4	820	64	34
700	20	6	840	67	39
720	30	9	860	69	45

* 3.17 Workmanship. The cloth shall conform to the quality established by this document. The demerit points per 100 square yards when calculated as specified in section 4 shall not exceed the established minimum point value.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicted or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3)
b. Quality conformance inspection (see 4.4)

* 4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for appearance, color and finish, and tested for the characteristics specified in 4.4.3. The presence of any defect or failure to pass any test shall be cause for rejection of the first article.

* 4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected and tested in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

* 4.4.2 End item visual examination.

4.4.2.1 Yard-by-yard examination. Each roll in the sample shall be examined on the face side only. When the total yardage in the roll does not exceed 100 yards, the entire yardage in the roll shall be examined. When the total yardage in the roll exceeds 100 yards, only 100 yards shall be examined. All defects, as defined in Section I of FED-STD-4, which are clearly noticeable at normal inspection distance (3 feet) shall be scored and assigned demerit points as listed in 4.4.2.1.1 except that: only those slubs and knots that exceed the limits shown on Sears Fabric Defect Scale (see 6.8) "D" or 3-1/2, as applicable, for slubs and "C" for knots shall be scored. No linear yard (increments of one yard on the measuring device of the inspection machine) from any one roll within the sample shall be penalized more than four points. The sample size shall be 20 rolls selected from 20 containers. For determination of acceptability on the average quality of the lot, the lot shall be unacceptable if the points per 100 square yards exceeds the following values:

30.0 points for dyed cloth
35.0 points for white cloth

For determination of acceptability on the individual roll quality basis, the lot shall be unacceptable if the points per 100 square yards of two or more individual rolls exceed the following values:

45.0 points for dyed cloth
53.0 points for white cloth

If one roll exceeds the point value per 100 square yards, a second sample of 20 rolls shall be examined for individual roll quality examination. If one or more rolls in the second sample exceeds the point value, the lot shall be rejected. Point computation for the lot quality and individual roll quality shall be as follows:

$$\frac{\text{Total points scored in sample} \times 3600}{\text{Contracted width of cloth (inches)} \times \text{total yards inspected}} = \text{Points per 100 square yards}$$

4.4.2.1.1 Demerit points. Demerit points shall be assigned as follows:

For defects 3 inches or less in any dimension	- one point
For defects exceeding 3 inches, but not exceeding 6 inches in any dimension	- two points
For defects exceeding 6 inches, but not exceeding 9 inches in any dimension	- three points
For defects exceeding 9 inches in any dimension	- four points

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

The following defects, when present, shall be scored four points for each yard in which they occur:

Baggy, ridgy, or wavy cloth
Width less than specified
Poor dye penetration, mottled, streaky or cloudy
Not singed
Excessive neppiness

4.4.2.2 Length examination. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified, or more than two yards less than the length marked on the ticket, shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length or if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the tickets.

4.4.2.3 Shade and appearance examination. During the yard-by-yard examination, each roll in the sample shall be examined for shade and appearance. Any roll in the sample off shade, shaded side to side, side to center, or end to end, shall be cause for rejection of the entire lot represented by the sample.

4.4.2.4 Roll identification examination. During the yard-to-yard examination, each roll in the sample shall be examined for the defects listed below. The lot shall be unacceptable if two or more rolls in the sample contain one or more of the following defects:

The preshrinking process is identified by name or trademark on the cloth, ticket, or package.
Not labeled or ticketed in accordance with the Textile Fiber Products Identification Act.
Face marking missing from either or both ends.

4.4.3 End item testing. The cloth shall be tested for characteristics listed in table II. The methods of testing specified in FED-STD-191, wherever applicable, and as listed in table II shall be followed. The physical and chemical values specified in section 3, except where otherwise specified, apply to the results of the determinations made on the sample unit for test purposes as specified in the applicable test method. The sample unit shall be 1/4-yard full width of the dyed cloth prior to application of the water repellent treatment for determination of the starch and protein content (including chloroform-soluble and water-soluble material), and 5 continuous yards full width of the finished cloth for all other physical and chemical tests. All test reports shall contain the individual values utilized in expressing the final result. The lot shall be unacceptable if one or more sample units fail to meet any requirement specified. The sample size shall be in accordance with the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

Lot size (yards)	Sample size (sample units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE II. End item tests

Characteristic	Requirement paragraph	Test method
Material		
Cotton identification	3.3	1200 1/
Yarn ply:		
Warp	3.3	Visual 1/ 2/
Filling	3.3	Visual 1/ 2/
Presence of labile sulfur	3.4.1	2020 1/
Colorfastness to:		
Laundering (after 3 cycles)	3.4.3	5610 3/ 4/
Crocking	3.4.3	5651
Wet drycleaning	3.4.3	5622
Perspiration	3.4.3	5680
Light	3.4.3	5660
Weight	3.5	5041
Yarns per inch	3.5	5050
Breaking strength	3.5	5100
Tearing strength	3.5	ASTM D 1424
Air permeability	3.5	5450
Weave and repeat	3.5.2	Visual 2/
Mercerization	3.6	Microscopic examination 2/
Presence of resin pigments	3.6	1/
Nonfibrous material	3.7	211
Dimensional stability	3.8	5550

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

TABLE II. End item tests (cont'd)

Characteristic	Requirement paragraph	Test method
Water repellent (class B)	3.9.1	5/
Spray rating (class B):		
Initial	3.9.1.1	5526
After laundering	3.9.1.1	5550 and 5526
Resistance to organic liquid (class B):		
Initial	3.9.1.2	4.5.1
Flame resistance (class C):		
Initial	3.10	5903
After laundering (15 cycles)	3.10	5556 3/ and 5903
pH	3.11	2811
Seam efficiency	3.12	5110 6/
* Spectral reflectance	3.16	4.5.2

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

2/ One determination shall be made from each sample unit and the result reported as "pass" or "fail".

3/ The specimens must be dried after each laundering cycle.

4/ On the color transfer cloth evaluation, only the stain on the cotton fibers of the color transfer cloth shall be evaluated.

5/ The contractor shall report the water repellent used, and certify that no other material (except the specified buffer and acetic acid) has been added.

6/ The needle shall measure 0.040 inch (± 0.001 inch) across the blade at the eye. The cotton thread shall be type IA1 conforming to V-T-276, ticket No. 40-3 ply in the needle and ticket No. 60-3 ply in the loopers.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

* 4.4.4 Packaging examination. The examination shall be in accordance with the quality assurance provisions of PPP-P-1134.

4.5 Methods of inspection.

4.5.1 Test for resistance to organic liquid. Place a small specimen of the cloth on a smooth horizontal surface, face up. Using a pipette or eye dropper, gently deposit one drop of n-dodecane on the surface of the specimen. After 1 minute, examine the specimen under light at an angle. Absence of light reflectance at the fabric-drop interface shall be taken as evidence of wetting. Three specimens (or areas) taken at various locations across the sample shall be tested. Evidence of wetting on one or more specimens shall be considered cause for rejection of the lot represented by the sample.

* 4.5.2 Spectral reflectance measurements in the visible/near infrared. Spectral reflectance data shall be obtained from 600 to 860 nanometers (nm), at 20 nm intervals on a spectrophotometer (see 6.9) relative to a barium sulfate standard, the preferred white reference standard. Other white reference materials may be used, provided they are calibrated to absolute white; e.g., Halon, magnesium oxide, or vitrolite tiles (see 6.10). The spectral bandwidth shall be less than 26 nm at 860 nm. Reflectance measurements may be made by either the monochromatic or polychromatic mode of operation. When the polychromatic mode is used, the spectrophotometer shall operate with the specimen diffusely illuminated with the full emission of a source that simulates either CIE Source A or CIE Source D65. The specimen shall be measured as a single layer, backed with four layers of the same fabric and shade. Measurements will be taken on a minimum of two different areas, and the data averaged. The specimen shall be viewed at an angle no greater than 10° from normal, with the specular component included. Photometric accuracy of the spectrophotometer shall be within 1 percent, and wavelength accuracy within 2 nm. The standard aperture size used in the color measurement device shall be 1.0 to 1.25 inches in diameter. When the measured reflectance values for any color at four or more wavelengths do not meet the limits specified in 3.16, it shall be a test failure.

5. PACKAGING

5.1 Put-up and preservation. Put-up and preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Levels A and Commercial. The cloth shall be put-up on rolls and preserved in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing. Packing shall be level A, B or Commercial as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

5.2.1 Levels A, B and Commercial . The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required by the contract or purchase order, shipments shall be marked in accordance with the requirements of PPP-P-1134.

6. NOTES

6.1 Intended use. The cloth is intended for use in the manufacture of clothing and equipage items. The class B cloth, although water repellent treated, will not provide rain protection due to its high air permeability. The class C cloth is intended to be used as a component of the 'CVC' face mask.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. Class required (see 1.2)
c. When a first article is required (see 3.2, 4.3, and 6.3).
d. Color required (see 3.4).
e. Width required (see 3.5.1).
f. When dimensional stability is other than specified (see 3.8).
g. When length is other than specified (see 3.13).
h. Selection of applicable levels of put-up, preservation, and packing (see 5.1 and 5.2).

* 6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

6.4 Standard sample. For access to a standard sample, address the contracting activity issuing the invitation for bids.

* 6.5 Dye combinations.

* 6.5.1 Olive Green 107. Satisfactory results in achieving the proper shade for Olive Green 107 and colorfastness have been obtained with an appropriate combination of the following dyes:

Vat Black 25, CI 69525
Vat Green 3, CI 69500/1
Vat Green 8, CI 71050

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

which are shaded with either or both of the following:

Vat Brown 3, CI 69015/6
Vat Yellow of suitable fastness

The redness of shade should result from the predominant use of the main colors and not from the shading colors.

* 6.5.2 Camouflage Green 483. A suggested but not mandatory dye combination for camouflage green 483 is as follows:

Vat Yellow 33
Vat Green 1
Vat Brown 57

* 6.6 Quarpel water repellent. The "Quarpel-type" water repellent treatment consists of the co-application of an emulsified fluorocarbon and a fluorocarbon extender. Approval of such components and combinations is the responsibility of the U.S. Army Natick Research, Development and Engineering Center, Natick, MA 01760-5014, and is based on extensive tests, including those for toxicity, which are not set forth in this document. Because of the time necessary to conduct full evaluation, only those chemical treatments already approved and so listed in the invitation for bid or request for proposal, shall be considered acceptable for the related procurement.

* 6.7 Approval of flame-resistant treatment formulas. Approval of formulas is the responsibility of the U.S. Army Natick Research, Development and Engineering Center, Natick, MA 01760-5014, and is based on extensive tests, including those for toxicity, which are not set forth in this document. Because of the time (approximately 6 months), only those formulas already approved will be considered acceptable for the related acquisition. Information pertaining to approval of new formulas should be obtained from the U.S. Army Natick Research, Development and Engineering Center. The list of approved formulas may be obtained from the contracting activity. As part of the approval testing of new flame-retardant treatments, the finished cloth should have an after-flame of not more than 2.0 seconds when tested in accordance with Method 5905 of FED-STD-191.

6.8 Fabric defect scales. Fabric Defect Replica Kits are available from Sears, Roebuck and Company, Department 817 (Attn: BSC 23-29), Sears Tower, Chicago, IL 60684.

* 6.9 Spectrophotometers. Suitable spectrophotometers for measuring spectral reflectance in the visible/near infrared are the Diano Hardy, Diano Match Scan, Hunter D54P-IR, and Macbeth 1500 with IR option.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

* 6.10 White standard. Barium sulfate of suitable quality for use as a white reference standard is available from the Eastman Kodak Company. The same source has available magnesium reagent (ribbon) and Halon. Suitable tiles can be obtained from the National Bureau of Standards or the instrument manufacturers.

* 6.11 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of this document (see 3.3).

* 6.12 Subject term (key word) listing.

Cloth
Cotton
Fabric
Poplin

6.13 Changes from previous issue. The margins of this document are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the previous issue.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Preparing activity:

Army - GL

Project No. 8305-0194

Review activities:

Army - MD
Air Force - 82
DLA - CT

User activity:

Navy - MC
* Air Force - 45

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

US ARMY NATICK RESEARCH
and DEVELOPMENT CENTER
ATTN STRNC-ES
Natick, MA 01760-5014

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON D C
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research
and Development Center
ATTN STRNC-ES
Natick, MA 01760-5014

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-C-342J	Cloth, Wind Resistant, Poplin, Cotton

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)* _____
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OP, 20 Nov 84

Source: https://assist.dla.mil - Downloaded: 2026-10-16T07:04Z
Check the source to verify that this is the current version before use.