MILITARY SPECIFICATION

TILE, ARMOR XM3, XM4, XM5, XM6 AND XM7, PARTS FOR

This Specification is approved for use within the U.S. Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers requirements and quality assurance provisions for parts for Tile, Armor XM3, XM4, XM5, XM6 and XM7.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shasll be those listed in the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

MILITARY

MIL-I-6866	- Inspection, Penetrant Method of
MIL-I-6868	- Inspection Process, Magnetic Particle
MIL-W-8611	- Welding, Metal Arc and Gas, Steels and Corrosion and Heat Resistant
MIL-A-48078	- Ammunition Standard Quality Assurance General Specification for

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, U.S. Army Armament, Munitions and Chemical Command, Attn. AMSMC-QA, Picatinny Arsenal, New Jersey 07806-5000 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 2350
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-171	- Finishing of Metal and Wood Surfaces
MIL-STD-1169	- Packaging, Packing and Marking for Shipment of Inert Ammunition Components

2.1.2 Other Government documents, drawings and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

US ARMY ARMAMENT RESEARCH, DEVELOPMENT AND ENGINEERING CENTER (ARDEC)

XM3, XM4, XM5, XM6 and XM7 PARTS (As applicable)

12556211	Box, Weldment
12556215	Plate
12556216	Seat, Rubber
12556217	Box - Sub-assembly
12556220	Spacer, Rubber
12556221	Clip
12556223	Plate
12556224	Plate
12556225	Bar
12556229	Channel
12556230	Box, Weldment
12556276	Box, Weldment
12556277	Grill, Weldment Assembly
12556279	Plate, Side
12556280	Plate, Bottom
12556281	Plate, Top
12556283	Plate, Back
12556384	Cover
12556285	Plate
12556286	Plate
12556287	Plate
12556288	Plate
12556289	Plate
12556290	Plate
12556291	Plate
12556292	Plate
12556293	Foam
12556294	Foam

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

XM3, XM4, XM5, XM6 and XM7, PARTS FOR

12556295	Foam
12556296	Foam
12556297	Foam
12556298	Foam
12556300	Angle, Bracket Assembly
12556308	Separator
12556309	Plate, Side
12556311	Plate
12556312	Plate
12576303	Box, Weldment
12576304	Box, Lower
12576305	Cover
12576306	Bracket, Box, Mounting
12576307	Box, Weldment
12576308	Box, Lower
12576309	Cover
12576310	Channel
12576311	Bracket
12576313	Plate
12576314	Plate
12576315	Plate
12576316	Plate
12576317	Plate
12576318	Plate
12576322	Bracket
12576323	Bracket
12576324	Foam
12576325	Foam
12576326	Foam
12576327	Foam
12576328	Foam
12576329	Plate
12576330	Plate
12576331	Plate
12576333	Plate
12576334	Plate
12576336	Bracket, Mounting
12576337	Foam
12576338	Foam
12576339	Foam
12576340	Foam
12576341	Foam
12576342	Bracket
12576343	Bracket
12576344	Nut, Special
12576345	Washer, Special

(Copies of specifications, standards, handbooks, drawings, and publications, and other Government documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

2.1.3 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues in effect of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIAL (ASTM)

ASTM A569 Carbon Steel, Commercial Quality, Sheet and Strip, Hot Rolled, Pickled and Oiled

(American Society for Testing and Material (ASTM) Standards for test methods are generally available in reference libraries. They are also distributed among technical groups and certain federal agencies. Application for copies should be addressed to the American Society Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19102).

2.1.4 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3 REQUIREMENTS

3.1 Materials. Materials shall be in accordance with the applicable drawings and specifications.

3.2 Parts. The parts shall comply with all requirements specified on the specified drawings (dwgs) and with all associated drawings and with all requirements specified in applicable specifications.

3.3 Welds. Welds shall be performed in accordance with specification MIL-W-8611 by qualified operators and operations.

3.3.1 Weld inspection. Welds shall be inspected for discontinuities, porosity, and cracks in accordance with specifications MIL-I-6866 or MIL-I-6868 as applicable.

3.4 Protective finish. Unless otherwise specified, the exterior and interior of parts that require finishing shall be prepared and finished in accordance with applicable drawings and Standard MIL-STD-171.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

3.5. Data requirements. The contractor shall generate data in accordance with the requirements of the data item description specified in 6.4).

3.6. First article inspection. This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples to be submitted by the contractor shall be specified in the contract.

3.7 Workmanship. All parts shall be fabricated in a thorough workmanlike manner. They shall be free of burrs, chips, sharp edges, cracks, unblended radii, surface defects, dirt, grease, rust, corrosion products and other foreign material. The cleaning method used shall not be injurious to any of the parts, nor shall the parts be contaminated by the cleaning agents. All marking shall be neat and sharply defined.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements. Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

4.1.1 Responsibility for compliance. All items must meet all requirements of section 3 and 5. The inspections set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.2 Classification of inspections. The following types of inspections shall be conducted:

a. First article inspection

b. Quality conformance inspection

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

4.3 First article inspection.

4.3.1 Submission. The contractor shall submit a first article sample for evaluation in accordance with the provisions 4.3.2. The first article sample shall consist of the sample quantities indicated in Table I, for the Tile, Armor, XM3, XM4, XM5, XM6 and XM7 (as applicable).

4.3.2 Inspections to be performed. See MIL-A-48078 and Table I specified herein.

4.3.3 Rejections. See MIL-A-48078.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

TABLE I First article inspection

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711 (AR)

PARAGRAPH	TITLE Tile, Armor: XM3, XM4, XM5, XM6 or XM7 (as applicable)		SHEET 1 OF 11		DRAWING NUMBER See Below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Box, Weldment (Dwg. 12556211) Examination for Defects	3		3.2	4.4.2.1
	Plate (Dwg. 12556215) Examination for Defects	3		3.2	4.4.2.2
	Seal, Rubber (Dwg. 12556216) Examination for Defects	3		3.2	4.4.2.3
	Box, Sub-assembly (dwg. 12556217) Examination for Defects	3		3.2	4.4.2.4
	Spacer, Rubber (dwg. 12556220) Examination for Defects	3		3.2	4.4.2.5
	Clip (Dwg. 12556221) Examination of Defects	3		3.2	4.4.2.6
	Plate (Dwg. 12556223) Examination of Defects	3		3.2	4.4.2.7
NOTES:					

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE Tile, Armor: XM3, XM5, XM5, XM6 or XM7 (as applicable)		SHEET 2 OF 11		DRAWING NUMBER See below
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Plate (Dwg. 12556224) Examination of Defects)	3		3.2	4.4.2.8
	Bar (Dwg. 12556225) Examination of Defects	3		3.2	4.4.2.9
	Channel (Dwg. 12556229) Examination of Defects	3		3.2	4.4.2.10
	Box, Weldment (Dwg. 12556230) Examination of Defects	3		3.2	4.4.2.11
	Box, Weldment (Dwg. 12556276) Examination of Defects	3		3.2	4.4.2.12
	Grill, Weldment Assembly (Dwg. 12556278) Examination of Defects	3		3.2	4.4.2.13
	Plate, Side (Dwg. 12556279) Examination of Defects	3		3.2	4.4.2.14

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE Tile, Armor, XM3, XM4, XM5, XM6 and XM7 (as applicable)		SHEET 3 OF 11		DRAWING NUMBER See below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Plate, Bottom (Dwg. 12556280) Examination of Defects	3		3.2	4.4.2.15
	Plate, Top (Dwg. 12556281) Examination of Defects	3		3.2	4.4.2.16
	Plate, Back (Dwg. 12556283) Examination of Defects	3		3.2	4.4.2.17
	Cover (Dwg. 12556284) Examination of Defects	3		3.2	4.4.2.18
	Plate (Dwg. 12556285) Examination of Defects	3		3.2	4.4.2.19
	Plate (Dwg. 12556286) Examination of Defects	3		3.2	4.4.2.20
	Plate (Dwg. 12556287) Examination of Defects	3		3.2	4.4.2.21

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE Tile, Armor, XM3, XM4, XM5, XM6 and XM7 (as applicable		SHEET 4 OF 11		DRAWING NUMBER See below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Plate (Dwg. 12556288) Examination of Defects	3		3.2	4.4.2.22
	Plate (Dwg. 12556289) Examination of Defects	3		3.2	4.4.2.23
	Plate (Dwg. 12556290) Examination of Defects	3		3.2	4.4.2.24
	Plate (Dwg. 12556291) Examination of Defects	3		3.2	4.4.2.25
	Plate (Dwg. 12556292) Examination of Defects	3		3.2	4.4.2.26
	Foam (Dwg. 12556293) Examination of Defects	3		3.2	4.4.2.27
	Foam (Dwg. 12556294) Examination of Defects	3		3.2	4.4.2.28

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE Tile, Armor, XM3, XM4, XM5, XM6 and XM7 (as applicable)		SHEET 5 OF 11		DRAWING NUMBER See below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Foam (Dwg. 12556295) Examination of Defects	3		3.2	4.4.2.29
	Foam (Dwg. 12556296) Examination of Defects	3		3.2	4.4.2.30
	Foam (Dwg. 12556297) Examination of Defects	3		3.2	4.4.2.31
	Foam (Dwg. 12556298) Examination of Defects	3		3.2	4.4.2.32
	Angle, Bracket Assembly (Dwg. 12556300) Examination of Defects	3		3.2	4.4.2.33
	Separator (Dwg. 12556308) Examination of Defects	3		3.2	4.4.2.34
	Plate, Side (Dwg. 12556309 Examination of Defects	3		3.2	4.4.2.35

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE Tile, Armor, XM3, XM4, XM5, XM6 and XM7 (as applicable)		SHEET 6 OF 11		DRAWING NUMBER See below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Plate (Dwg. 12556311) Examination of Defects	3		3.2	4.4.2.36
	Plate (Dwg. 12556312) Examination of Defects	3		3.2	4.4.2.37
	Box, Weldment (Dwg. 12576303) Examination of Defects	3		3.2	4.4.2.38
	Box, Lower (Dwg. 12576304) Examination of Defects	3		3.2	4.4.2.39
	Cover (Dwg. 12576305) Examination of Defects	3		3.2	4.4.2.40
	Bracket, Box, Mounting (Dwg. 12576306) Examination of Defects	3		3.2	4.4.2.41
	Box, Weldment (Dwg. 12576307) Examination of Defects	3		3.2	4.4.2.42
NOTES:					

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil-2 Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE: Tile, Armor, XM3, XM4, XM5, XM6 & XM7 (as applicable)		SHEET 7 OF 11		DRAWING NUMBER: See below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Box, Lower (Dwg. 12576308) Examination of Defects	3		3.2	4.4.2.43
	Cover (Dwg. 12576309) Examination of Defects	3		3.2	4.4.2.44
	Channel (Dwg. 12576310) (Examination of Defects	3		3.2	4.4.2.45
	Bracket (Dwg. 12576311) Examination of Defects	3		3.2	4.4.2.46
	Plate (Dwg. 12576313) Examination of Defects	3		3.2	4.4.2.47
	Plate (Dwg. 12576314) Examination of Defects	3		3.2	4.4.2.48
	Plate (Dwg. 12576315) Examination of Defects	3		3.2	4.4.2.49

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE Tile, Armor, XM3, XM4, XM5, XM6 and XM7 (as applicable)		SHEET 8 OF 11		DRAWING NUMBER See below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Plate (Dwg. 12576316) Examination of Defects	3		3.2	4.4.2.50
	Plate (Dwg. 12576317) Examination of Defects	3		3.2	4.4.2.51
	Plate (Dwg. 12576318) Examination of Defects	3		3.2	4.4.2.52
	Bracket (Dwg. 12576322) Examination of Defects	3		3.2	4.4.2.53
	Bracket (Dwg. 12576323) Examination of Defects	3		3.2	4.4.2.54
	Foam (Dwg. 12576324) Examination of Defects	3		3.2	4.4.2.55
	Foam (Dwg. 12576325) Examination of Defects	3		3.2	4.4.2.56

NOTES:

AMSMC Form 1570, 1 Feb 85 Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE Tile, Armor, XM3, XM4, XM5, XM6 and XM7 (as applicable)		SHEET 9 OF 11		DRAWING NUMBER See below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Foam (Dwg. 12576326) Examination of Defects	3		3.2	4.4.2.57
	Foam (Dwg. 12576327) Examination of Defects	3		3.2	4.4.2.58
	Form (Dwg. 12576328) Examination of Defects	3		3.2	4.4.2.59
	Plate (Dwg. 12576329) Examination of Defects	3		3.2	4.4.2.60
	Plate (Dwg. 12576330) Examination of Defects	3		3.2	4.4.2.61
	Plate (Dwg. 12576331) Examination of Defects	3		3.2	4.4.2.62
	Plate (Dwg. 12576333) Examination of Defects	3		3.2	4.4.2.63

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE Tile, Armor, XM3, XM4, XM5, XM6 and XM7 (as applicable)		SHEET 10 OF 11		DRAWING NUMBER See below NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
1	Plate (Dwg. 12576334) Examination of Defects	3		3.2	4.4.2.64
1	Bracket, Mounting (Dwg. 12576336) Examination of Defects	3		3.2	4.4.2.65
1	Foam (Dwg. 12576337) Examination of Defects	3		3.2	4.4.2.66
1	Foam (Dwg. 12576338) Examination of Defects	3		3.2	4.4.2.67
1	Foam (Dwg. 12576339) Examination of Defects	3		3.2	4.4.2.68
1	Foam (Dwg. 12576340 Examination of Defects	3		3.2	4.4.2.69
1	Foam (Dwg. 12576341) Examination of Defects	3		3.2	4.4.2.70

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE Tile, Armor, XM3, XM4, XM5, XM6 and XM7 (as applicable)		SHEET 11 OF 11		DRAWING NUMBER See below
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
	Bracket (Dwg. 12576342) Examination of Defects	3		3.2	4.4.2.71
	Bracket (Dwg. 12576343) Examination of Defects	3		3.2	4.4.2.72
	Nut, Special (Dwg. 12576344) Examination of Defects	3		3.2	4.4.2.73
	Washer, Special (Dwg. 12576345) Examination of Defects	3		3.2	4.4.2.74

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection.

4.4.1 Inspection lot formation. Inspection lots shall comply with the lot formation provisions of MIL-A-48078.

4.4.2 Examination. See MIL-A-48078.

a. Unless otherwise specified in the Classification of Defects and Test Tables, sampling plans and procedures for major and minor defects shall be in accordance with MIL-STD-105, Inspection Level II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.1	Box, Weldment	1 OF 1	12556211
			NEXT HIGHER ASSEMBLY: 12556217

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major					
101	Diameter of hole (4 places)		0.40%	3.2	Gage
102	Position of holes		0.40%	3.2	Gage
103	Location of weld stud (8 places)		0.40%	3.2	Gage
104	Weld stud missing		0.40%	3.2	Visual
105	Width of bar		0.40%	3.2	Gage
106	Position of bar (4 places)		0.40%	3.2	Gage
107	Weld penetrant inspection		100%	3.2	Test 4.5.2
108	Weld penetrant inspection incomplete or non-uniform		100%	3.2	Visual
109	Weld missing		0.40%	3.2	Visual
110	Length of box, max.		0.40%	3.2	Gage
111	Width of box, max.		0.40%	3.2	Gage
112	Component missing or loose		0.40%	3.2	Visual/Manual
113	Protective coating missing or loose		0.40%	3.2	Visual
Minor					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.2	Plate	1 OF 1	12556215
			NEXT HIGHER ASSEMBLY: 12556201

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of hole (4 places)		0.40%	3.2	Gage
102	Position of holes		0.40%	3.2	Gage
103	Depth of slot, min. (4 places)		0.40%	3.2	Gage
104	Width of slot, max.		0.40%	3.2	Gage
105	Material thickness, min.		0.40%	3.2	Gage
106	Length of plate		0.40%	3.2	Gage
107	Width of plate		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET	DRAWING NUMBER
4.4.2.3	Seal, Rubber		1 OF 1	12556216
				NEXT HIGHER ASSEMBLY: As applicable

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Thickness, min.		0.40%	3.2	Gage
102	Inside diameter, max.		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.4	Box, Subassembly	1 OF 1	12556217
			NEXT HIGHER ASSEMBLY: 12556201

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Perpendicularity of tubular post with inside surface		0.40%	3.2	Gage
102	Component missing or loose		0.40%	3.2	Gage
MINOR					
201	Excess sealant		0.65%	3.2	Visual
202	Evidence of poor workmanship		1.00%	3.7	Visuasl

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH 4.4.2.5	TITLE Spacer, Rubber		SHEET 1 OF 1		DRAWING NUMBER 12556220
					NEXT HIGHER ASSEMBLY 12556201
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length (3 locations)		0.40%	3.2	Gage
102	Thickness		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.6	Clip	1 OF 1	12556221
			NEXT HIGHER ASSEMBLY: 12556200

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL					
MAJOR					
101	Diameter of hole (2 places)		0.40%	3.2	Gage
102	Material thickness, min.		0.40%	3.2	Gage
103	Position of holes		0.40%	3.2	Gage
104	Inside width		0.40%	3.2	Gage
105	Component missing or loose		0.40%	3.2	Visual/Manual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - 74 - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.7	Plate	1 OF 1	12556223
			NEXT HIGHER ASSEMBLY: 12556202

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Thickness		0.40%	3.2	Gage
102	Length		0.40%	3.2	Gage
103	Diameter of hole, max. (4 places)		0.40%	3.2	Gage
104	Position of holes		0.40%	3.2	Gage
105	Flatness		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.8	Plate				12556224
					NEXT HIGHER ASSEMBLY 12556201
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Diameter of holes (4 places)		0.40%	3.2	Gage
103	Position of holes		0.40%	3.2	Gage
104	Depth of slot, min. (4 places)		0.40%	3.2	Gage
105	Width of slot, max.		0.40%	3.2	Gage
106	Width		0.40%	3.2	Gage
107	Length		0.40%	3.2	Gage
108	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.9	Bar				12556225
					NEXT HIGHER ASSEMBLY 12556211 & 12556230
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Thickness		0.40%	3.2	Gage
102	Width		0.40%	3.2	Gage
103	Length (as applicable)		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.2.10	Channel		12556229
			NEXT HIGHER ASSEMBLY 12556230

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of hole (2 places)		0.40%	3.2	Gage
102	Position of holes		0.40%	3.2	Gage
103	Inside width		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.11	Box Weldment	1 OF 1	12556230
			NEXT HIGHER ASSEMBLY 12556202

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of hole (11 places)		0.40%	3.2	Gage
102	Position of holes		0.40%	3.2	Gage
103	Material thickness, min.		0.40%	3.2	Gage
104	Position of bar (4 places)		0.40%	3.2	Gage
105	Weld penetrant inspection		100%	3.3	Test 4.5.2
106	Weld penetrant inspection missing or non-uniform		100%	3.3	Visual
107	Protective coating incomplete or inadequate		100%	3.2	Visual
108	Weld missing		0.40%	3.2	Visual
MINOR					
201	Serial number missing		0.65%	3.2	Visual
202	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.2.12	Box Weldment		12556276
			NEXT HIGHER ASSEMBLY 12556275

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Penetrant inspection of weld		100%	3.3	Test 4.5.2
102	Penetrant inspection missing or non-uniform		100%	3.3	Visual
103	Weld missing (where required)		0.40%	3.2	Visual
104	Component missing or loose		0.40%	3.2	Visual/Manual
105	Burrs or sharp edges		0.40%	3.2	Visual
MINOR					
201	Serial number missing		0.65%	3.2	Visual
202	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.13	Grill, Weldment Assembly	1 OF 1	12556278
			NEXT HIGHER ASSEMBLY: 12556277

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Penetrant inspection of welds		100%	3.3	Test 4.5.2
102	Penetrant inspection missing or non-uniform		100%	3.3	Visual
103	Weld missing		0.40%	3.2	Visual
104	Component missing		0.40%	3.2	Visual
MINOR					
101	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.14	Plate, Side	1 OF 1	12556279
			NEXT HIGHER ASSEMBLY 12556276

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of hole, max. (3 places)		0.40%	3.2	Gage
102	Position of hole (3 places)		0.40%	3.2	Gage
103	Angle incorrect		0.40%	3.2	Gage
104	Overall width		0.40%	3.2	Gage
105	Overall height		0.40%	3.2	Gage
106	Material thickness, min.		0.40%	3.2	Gage
107	Burrs or sharp edges		0.40%	3.2	Visual
108	Prime incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.15	Plate, Bottom				12556280
					NEXT HIGHER ASSEMBLY
					12556276
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of holes, max. (3 places		0.40%	3.2	Gage
102	Position of holes		0.40%	3.2	Gage
103	Overall height		0.40%	3.2	Gage
104	Thickness, min.		0.40%	3.2	Gage
105	Overall length including angle		0.40%	3.2	Gage
106	Short height		0.40%	3.2	Gage
107	Intermediate height		0.40%	3.2	Gage
108	Burrs or sharp edges		0.40%	3.2	Visual
109	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil/ - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.16	Plate, Top				12556281
					NEXT HIGHER ASSEMBLY 12556276
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of hole (3 places)		0.40%	3.2	Gage
102	Position of hole (3 places)		0.40%	3.2	Gage
103	Thickness, min.		0.40%	3.2	Gage
104	Total width, min.		0.40%	3.2	Gage
105	Intermediate width, min.		0.40%	3.2	Gage
106	Short width, min.		0.40%	3.2	Gage
107	Total height, min.		0.40%	3.2	Gage
108	Burrs or sharp edges		0.40%	3.2	Visual
109	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.17	Plate, Back	1 OF 1	12556283
			NEXT HIGHER ASSEMBLY: 12556276

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Total width, max.		0.40%	3.2	Gage
102	Height, max.		0.40%	3.2	Gage
103	Length, max.		0.40%	3.2	Gage
104	Thickness, min.		0.40%	3.2	Gage
105	Burrs or sharp edges		0.40%	3.2	Visual
106	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.18	Cover	1 OF 1	12556284
			NEXT HIGHER ASSEMBLY 12556275

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of holes end, max. (6 places)		0.40%	3.2	Gage
102	Position of end holes		0.40%	3.2	Gage
103	Material thickness, min.		0.40%	3.2	Gage
104	Diameter of top holes (6 places)		0.40%	3.2	Gage
105	Position of top holes		0.40%	3.2	Gage
106	Total length, min.		0.40%	3.2	Gage
107	Total height, min.		0.40%	3.2	Gage
108	Burrs or sharp edges		0.40%	3.2	Visual
109	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	OF	DRAWING NUMBER
4.4.2.19	Plate	1	1	12556285
				NEXT HIGHER ASSEMBLY: 12556277

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness min.		0.40%	3.2	Gage
102	Diameter of hole (2 places)		0.40%	3.2	Gage
103	Position of holes		0.40%	3.2	Gage
104	Overall length, min.		0.40%	3.2	Gage
105	Overall height, min.		0.40%	3.2	Gage
106	Burrs or sharp edges		0.40%	3.2	Gage
107	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.20	Plate				12556286
					NEXT HIGHER ASSEMBLY 12556270
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of hole (2 places)		0.40%	3.2	Gage
102	Position of hole		0.40%	3.2	Gage
103	Penetrant inspection of weld		100%	3.3	Test 4.5.2
104	Penetrant inspection missing or non-uniform		100%	3.3	Visual
105	Component missing or loose		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.21	Plate				12556287
					NEXT HIGHER ASSEMBLY 12556277
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Diameter of large hole (2 places)		0.40%	3.2	Gage
103	Position of large holes		0.40%	3.2	Gage
104	Diameter of small holes (2 places)		0.40%	3.2	Gage
105	Position of small holes		0.40%	3.2	Gage
106	Overall length		0.40%	3.2	Gage
107	Overall width		0.40%	3.2	Gage
108	Burrs or sharp edges		0.40%	3.2	Visual
109	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.22	Plate				12556288
					NEXT HIGHER ASSEMBLY 12556278
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Penetrant inspection of weld		100%	3.3	Test
102	Penetrant inspection missing or non-uniform		100%	3.3	Visual
103	Component missing or loose		0.40%	3.2	Visual/Manual
104	Location of bar (2 places)		0.40%	3.2	Gage
105	Weld missing		0.40%	3.2	Visual
106	Protective coating missing or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.23	Plate				12556289
					NEXT HIGHER ASSEMBLY 12556277
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Diameter of small hole (2 places)		0.40%	3.2	Gage
103	Position of small holes		0.40%	3.2	Gage
104	Diameter of large hole (2 places)		0.40%	3.2	Gage
105	Position of large holes		0.40%	3.2	Gage
106	Overall length		0.40%	3.2	Gage
107	Overall height		0.40%	3.2	Gage
108	Component missing or loose		0.40%	3.2	Visual/Manual
109	Burrs or sharp edges		0.40%	3.2	Visual
110	Protective finish incomplete or inadequate		1.00%	3.7	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85 Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil 4 Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.24	Plate				12556290
					NEXT HIGHER ASSEMBLY 12556278
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Penetrant inspection of weld		100%	3.3	Test 4.5.2
102	Penetrant inspection missing or non-uniform		100%	3.3	Visual
103	Component missing or loose		0.40%	3.2	Visual/Manual
104	Location of bar (2 places)		0.40%	3.2	Gage
105	Weld missing		0.40%	3.2	Visual
106	Protective coating missing or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.25	Plate	1 OF	12556291
			NEXT HIGHER ASSEMBLY: 12556278

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Penetrant inspection of weld		100%	3.3	Test 4.5.2
102	Penetrant inspection missing or non-uniform		100%	3.3	Visual
103	Component missing or loose		0.40%	3.2	Visual/Manual
104	Location of bar (2 places)		0.40%	3.2	Gage
105	Weld missing		0.40%	3.2	Visual
106	Protective coating missing or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	OF	DRAWING NUMBER
4.4.2.26	Plate	1	1	12556292
				NEXT HIGHER ASSEMBLY 12556277

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Diameter of hole (2 places)		0.40%	3.2	Gage
103	Position of holes		0.40%	3.2	Gage
104	Overall length		0.40%	3.2	Gage
105	Short length		0.40%	3.2	Gage
106	Intermediate length		0.40%	3.2	Gage
107	Overall width		0.40%	3.2	Gage
108	Angle improper (4 places)		0.40%	3.2	Gage
109	Burrs or sharp edges		0.40%	3.2	Visual
110	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	OF	DRAWING NUMBER
4.4.2.27	Foam	1	1	12556293
				NEXT HIGHER ASSEMBLY: 12556297

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Height, min.		0.40%	3.2	Gage
103	Gouges, max.		0.40%	3.2	Gage
104	Flaws, max.		0.40%	3.2	Gage
105	Surface inclusions, max.		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.28	Foam	1 OF 1	12556294
			NEXT HIGHER ASSEMBLY: 12556277

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Thickness, min.		0.40%	3.2	Gage
103	Surface inclusions		0.40%	3.2	Gage
104	Gouges		0.40%	3.2	Gage
105	Flaws		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.29	Foam	1 OF 1	12556295
			NEXT HIGHER ASSEMBLY: 12556277

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Thickness, min.		0.40%	3.2	Gage
103	Surface inclusions		0.40%	3.2	Gage
104	Gouges		0.40%	3.2	Gage
105	Flaws		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.30	Foam				12556296
					NEXT HIGHER ASSEMBLY 12556277
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Overall length, min.		0.40%	3.2	Gage
102	Overall width, min.		0.40%	3.2	Gage
103	Thickness, min.		0.40%	3.2	Gage
104	Gouges		0.40%	3.2	Gage
105	Flaws		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.31	Foam				12556297
					NEXT HIGHER ASSEMBLY 12556277
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Overall length, min.		0.40%	3.2	Gage
102	Thickness, min.		0.40%	3.2	Gage
103	Gouges		0.40%	3.2	Gage
104	Flaws		0.40%	3.2	Gage
105	Surface inclusions		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.32	Foam				12556298
					NEXT HIGHER ASSEMBLY 12556275
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Overall length, min.		0.40%	3.2	Gage
102	Width, min.		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	OF	DRAWING NUMBER
4.4.2.33	Angle, Bracket Assembly	1	1	12556300
				NEXT HIGHER ASSEMBLY: 12556276

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Length to tab		0.40%	3.2	Gage
103	Length of tab		0.40%	3.2	Gage
104	Width		0.40%	3.2	Gage
105	Diameter of hole		0.40%	3.2	Gage
106	Position of hole		0.40%	3.2	Gage
107	Penetrant inspection of weld		100%	3.3	Test 4.5.2
108	Penetrant inspection missing or non-uniform		100%	3.2	Visual
109	Protective coating incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	OF	DRAWING NUMBER
4.4.2.34	Separator	1	1	12556308

NEXT HIGHER ASSEMBLY: 12556275

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Thickness of bar (4 places)		0.40%	3.2	Gage
103	Total width of plate, min.		0.40%	3.2	Gage
104	Total length of plate, min.		0.40%	3.2	Gage
105	Location of weld		0.40%	3.2	Gage
106	Penetrant inspection of welds		100%	3.3	Test 4.5.2
107	Penetrant inspection missing or non-uniform		100%	3.2	Visual
108	Weld missing		0.40%	3.2	Visual
109	Burrs or sharp edges		0.40%	3.2	Visual
110	Protective coating incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil-2 Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.35	Plate, side				12556309
					NEXT HIGHER ASSEMBLY 12556278
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Total length, min.		0.40%	3.2	Gage
103	Overall width		0.40%	3.2	Gage
104	Burrs or sharp edges		0.40%	3.2	Visual
105	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.36	Plate				12556311
					NEXT HIGHER ASSEMBLY
					As applicable
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of hole (2 places)		0.40%	3.2	Gage
102	Position of holes		0.40%	3.2	Gage
103	Location of bar (2 places)		0.40%	3.2	Gage
104	Penetrant inspection of weld		100%	3.3	Test 4.5.2
105	Penetrant inspection missing or non-uniform		100%	3.2	Visual
106	Weld missing		0.40%	3.2	Visual
107	Component missing or loose		0.40%	3.2	Visual/Manual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil/ -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET	DRAWING NUMBER
4.4.2.37	Plate		1 OF 1	12556312
				NEXT HIGHER ASSEMBLY: 12556277

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Thickness of material, min.		0.40%	3.2	Gage
102	Diameter of hole (2 places)		0.40%	3.2	Gage
103	Position of holes		0.40%	3.2	Gage
104	Overall length, min.		0.40%	3.2	Gage
105	Overall width		0.40%	3.2	Gage
106	Burrs or sharp edges		0.40%	3.2	Visual
107	Protective coating incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.38	Box Weldment	1 OF 1	12576303
			NEXT HIGHER ASSEMBLY: 12576301

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Weld penetrant inspection		100%	3.3	Test 4.5.2
102	Weld penetrant inspection missing or non-uniform		100%	3.2	Visual
103	Weld missing		0.40%	3.2	Visual
104	Position of channel (10 places)		0.40%	3.2	Gage
105	Component missing or loose		0.40%	3.2	Visual/Manual
106	Protective coating incomplete or inadequate		0.40%	3.2	Visual
107	Angularity of channel (10 places)		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.39	Box, Lower				12576304
					NEXT HIGHER ASSEMBLY 12576303
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Diameter of small hole (12 places)		0.40%	3.2	Gage
103	Position of small holes (12 places)		0.40%	3.2	Gage
104	Diameter of large hole (3 places)		0.40%	3.2	Gage
105	Position of large holes		0.40%	3.2	Gage
106	Total length		0.40%	3.2	Gage
107	Total width		0.40%	3.2	Gage
108	Total height		0.40%	3.2	Gage
109	Penetrant inspection of welds		100%	3.31	Test 4.5.2
110	Penetrant inspection missing or non-uniform		100%	3.2	Visual
111	Burr or sharp edges		0.40%	3.2	Visual
112	Weld missing		0.40%	3.2	Visual
113	Protective coating incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85 Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.40	Cover				12576305
					NEXT HIGHER ASSEMBLY 12576301
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length		0.40%	3.2	Gage
102	Width		0.40%	3.2	Gage
103	Diameter of hole (12 places)		0.40%	3.2	Gage
104	Position of holes		0.40%	3.2	Gage
105	Penetrant inspection of welds		100%	3.3	ATest 4.5.2
106	Penetrant inspection missing or non-uniform		100%	3.2	Visual
107	Weld missing		0.40%	3.2	Visual
108	Burr or sharp edges		0.40%	3.2	Visual
109	Protective coating incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil-5-8-Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	OF	DRAWING NUMBER
4.4.2.41	Bracket, Box Mounting	1	1	12576306
				NEXT HIGHER ASSEMBLY: As applicable

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Width of hole (2 places)		0.40%	3.2	Gage
102	Length of hole (2 places)		0.40%	3.2	Gage
103	Position of holes		0.40%	3.2	Gage
104	Total height		0.40%	3.2	Gage
105	Large outside width		0.40%	3.2	Gage
106	Small outside width		0.40%	3.2	Gage
107	Material thickness, min.		0.40%	3.2	Gage
108	Width of notch (2 places)		0.40%	3.2	Gage
109	Depth of notch (2 places)		0.40%	3.2	Gage
110	Radius improper		0.40%	3.2	Gage
111	Burr or sharp edge		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	OF	DRAWING NUMBER
4.4.2.42	Box, Weldment	1	1	12576307
				NEXT HIGHER ASSEMBLY: 12576302

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Weld penetrant inspection		100%	3.3	Test 4.5.2
102	Weld penetrant inspection missing or non-uniform		100%	3.2	Visual
103	Position of channel (6 places)		0.40%	3.2	Gage
104	Angularity of channel (6 places)		0.40%	3.2	Gage
105	Component missing or loose		0.40%	3.2	Visual/Gage
106	Protective coating incomplete or inadequate		0.40%	3.2	Visual
107	Weld missing		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 12576308
4.4.2.43	Box, Lower				NEXT HIGHER ASSEMBLY 12576307
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Overall length		0.40%	3.2	Gage
102	Width		0.40%	3.2	Gage
103	Overall height		0.40%	3.2	Gage
104	Diameter of large hole (12 places)		0.40%	3.2	Gage
105	Position of large holes		0.40%	3.2	Gage
106	Diameter of intermediate holes (3 places)		0.40%	3.2	Gage
107	Position of intermediate holes		0.40%	3.2	Gage
108	Diameter of small holes (5 places)		0.40%	3.2	Gage
109	Position of small holes		0.40%	3.2	Gage
110	Penetrant inspection of welds		100%	3.3	Test
111	Penetrant inspection missing or non-uniform		100%	3.2	Visual
112	Weld missing		0.40%	3.2	Visual
113	Burr or sharp edge		0.40%	3.2	Visual
114	Protective coating missing or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.44	Cover	1 1 OF	12576309
			NEXT HIGHER ASSEMBLY 12576302

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Size of large square hole		0.40%	3.2	Gage
102	Position of large square holes		0.40%	3.2	Gage
103	Size of small square holes (3 places)		0.40%	3.2	Gage
104	Position of small square holes		0.40%	3.2	Gage
105	Diameter of hole (2 places		0.40%	3.2	Gage
106	Position of holes		0.40%	3.2	Gage
107	Overall width		0.40%	3.2	Gage
108	Overall height		0.40%	3.2	Gage
109	Diameter of hole (6 places)		0.40%	3.2	Gage
110	Position of holes (6 places)		0.40%	3.2	Gage
111	Overall length		0.40%	3.2	Gage
112	Weld missing (2 places)		0.40%	3.2	Visual
113	Burrs or sharp edges		0.40%	3.2	Visual
114	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.45	Channel	1 OF 1	12576310
			NEXT HIGHER ASSEMBLY: As applicable

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Thickness of material, min.		0.40%	3.2	Gage
102	Length (as applicable)		0.40%	3.2	Gage
103	Large inside width		0.40%	3.2	Gage
104	Small inside width		0.40%	3.2	Gage
105	Inside radius improper		0.40%	3.2	Gage
MAJOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE	SHEET	OF	DRAWING NUMBER
4.4.2.46	Bracket	1	1	12576311
				NEXT HIGHER ASSEMBLY: As applicable

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Length		0.40%	3.2	Gage
103	Width		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.47	Plate				12576313
					NEXT HIGHER ASSEMBLY: As applicable
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Position of bar (3 places)		0.40%	3.2	Gage
102	Material thickness, min.		0.40%	3.2	Gage
103	Height of bar from plate		0.40%	3.2	Gage
104	Penetrant inspection of weld		100%	3.3	Test 4.5.2
105	Penetrant inspection missing or non-uniform		100%	3.2	Visual
106	Protective coating incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil 6.5 Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER 12576314
4.4.2.48	Plate				NEXT HIGHER ASSEMBLY 12576319
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of hole (9 places)		0.40%	3.2	Gage
102	Position of holes		0.40%	3.2	Gage
103	Material thickness, min.		0.40%	3.2	Gage
104	Length		0.40%	3.2	Gage
105	Width		0.40%	3.2	Gage
106	Burrs or sharp edges		0.40%	3.2	Visual
107	Protective finish incomplete or inadequate		0.40%	3.7	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85 Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil/ - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.49	Plate				12576315
					NEXT HIGHER ASSEMBLY 12576320
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Position of bar (3 places)		0.40%	3.2	Gage
102	Diameter of hole (9 places)		0.40%	3.2	Gage
103	Material thickness, min.		0.40%	3.2	Gage
104	Height of bar above plate (3 places)		0.40%	3.2	Gage
105	Penetrant inspection of weld		100%	3.3	Test 4.5.2
106	Penetrant inspection missing or non-uniform		100%	3.2	Visual
107	Protective coating incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85 — Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.50	Plate				12576316
					NEXT HIGHER ASSEMBLY 12576320
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Diameter of hole (9 places)		0.40%	3.2	Gage
103	Position of holes		0.40%	3.2	Gage
104	Overall length		0.40%	3.2	Gage
105	Overall height		0.40%	3.2	Gage
106	Burrs or sharp edges		0.40%	3.2	Visual
107	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil/ - 6 - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.51	Plate	1 OF 1	12576317
			NEXT HIGHER ASSEMBLY: 12576321

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Position of bar (3 places)		0.40%	3.2	Gage
102	Diameter of hole (3 places)		0.40%	3.2	Gage
103	Position of holes		0.40%	3.2	Gage
104	Material thickness, min.		0.40%	3.2	Gage
105	Height of bar from plate		0.40%	3.2	Gage
106	Penetrant inspection of weld		0.40%	3.3	Test 4.5.2
107	Penetrant inspection missing or non-uniform		100%	3.2	Visual
108	Protective coating incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil/ - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.52	Plate	1 OF 1	12576318
			NEXT HIGHER ASSEMBLY 12576321

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of holes (3 places)		0.40%	3.2	Gage
102	Position of holes		0.40%	3.2	Gage
103	Material thickness (as applicable)		0.40%	3.2	Gage
104	Length		0.40%	3.2	Gage
105	Height		0.40%	3.2	Gage
106	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.53	Bracket				12576322
					NEXT HIGHER ASSEMBLY: As applicable
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Overall length		0.40%	3.2	Gage
103	Overall width		0.40%	3.2	Gage
104	Width of cut-out		0.40%	3.2	Gage
105	Angle of cut-out		0.40%	3.2	Gage
106	Short length		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.54	Bracket				12576323
					NEXT HIGHER ASSEMBLY 12576303
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Overall length		0.40%	3.2	Gage
103	Short length		0.40%	3.2	Gage
104	Angle incorrect (2 places)		0.40%	3.2	Gage
105	Location of cut-out		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85 Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.55	Foam				12576324
					NEXT HIGHER ASSEMBLY 12576301
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Width, min.		0.40%	3.2	Gage
103	Thickness, min.		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85 Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.56	Foam				12576325
					NEXT HIGHER ASSEMBLY: As applicable
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Width, min.		0.40%	3.2	Gage
103	Thickness, min.		0.40%	3.2	Gage
104	Angle incorrect		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.57	Foam				12576326
					NEXT HIGHER ASSEMBLY: As applicable
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Width, min.		0.40%	3.2	Gage
103	Thickness, min.		0.40%	3.2	Gage
104	Angle incorrect		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%		Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET	DRAWING NUMBER
4.4.2.58	Foam		1 OF	12576327
				NEXT HIGHER ASSEMBLY: As applicable

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Width, min.		0.40%	3.2	Gage
103	Thickness, min.		0.40%	3.2	Gage
104	Angle incorrect		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil-76 Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.59	Foam				12576328
					NEXT HIGHER ASSEMBLY 12576301
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Width, min.		0.40%	3.2	Gage
103	Thickness, min.		0.40%	3.2	Gage
104	Angle incorrect (2 places)		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.60	Plate				12576329
					NEXT HIGHER ASSEMBLY
					12576302
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Size of square hole (12 places)		0.40%	3.2	Gage
102	Position of square holes		0.40%	3.2	Gage
103	Material thickness of plate, min.		0.40%	3.2	Gage
104	Location of bar (3 places)		0.40%	3.2	Gage
105	Penetrant inspection of weld		100%	3.3	Test 4.5.2
106	Penetrant inspection missing or non-uniform		100%	3.2	Visual
107	Height of bar from plate, min.		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.61	Plate				12576330
					NEXT HIGHER ASSEMBLY 12576332
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of hole (9 places)		0.40%	3.2	Gage
102	Position of holes		0.40%	3.2	Gage
103	Position of bar (3 places)		0.40%	3.2	Gage
104	Material thickness, min.		0.40%	3.2	Gage
105	Height of bar above plate, min.		0.40%	3.2	Gage
106	Penetrant inspection of weld		100%	3.3	Test 4.5.2
107	Penetrant inspection missing or non-uniform		100%	3.2	Visual
108	Protective coating incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.62	Plate	1 OF 1	12576331
			NEXT HIGHER ASSEMBLY: 12576332

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Diameter of holes (6 places		0.40%	3.2	Gage
103	Position of holes		0.40%	3.2	Gage
104	Length		0.40%	3.2	Gage
105	Width		0.40%	3.2	Gage
106	Burrs or sharp edges		0.40%	3.2	Visual
107	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.63	Plate				12576333
					NEXT HIGHER ASSEMBLY
					12576335
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Location of bar (3 places)		0.40%	3.2	Gage
102	Diameter of hole (9 places)		0.40%	3.2	Gage
103	Position of holes		0.40%	3.2	Gage
104	Material thickness, min.		0.40%	3.2	Gage
105	Height of bar above plate, min.		0.40%	3.2	Gage
106	Penetrant inspection of weld		100%	3.3	Test 4.5.2
107	Penetrant inspection missing or non-uniform		100%	3.2	Visual
108	Protective coating incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.64	Plate				12576334
					NEXT HIGHER ASSEMBLY 12576335
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Diameter of hole (9 places)		0.40%	3.2	Gage
103	Position of holes		0.40%	3.2	Gage
104	Length		0.40%	3.2	Gage
105	Width		0.40%	3.2	Gage
106	Burrs or sharp edges		0.40%	3.2	Visual
107	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85 — Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.65	Bracket, Mounting				12576336
					NEXT HIGHER ASSEMBLY: As applicable
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Diameter of large hole (3 places		0.40%	3.2	Gage
102	Position of large holes		0.40%	3.2	Gage
103	Diameter of small hole (2 places)		0.40%	3.2	Gage
104	Position of small holes		0.40%	3.2	Gage
105	Total height		0.40%	3.2	Gage
106	Width at open end, max.		0.40%	3.2	Gage
107	Material thickness, min.		0.40%	3.2	Gage
108	Component missing or loose		0.40%	3.2	Visual/Manual
109	Burr or sharp edges		0.40%	3.2	Visual
110	Protective finish incomplete or inadequate		0.40%	3.2	Visual
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.66	Foam	1 OF 1	12576337
			NEXT HIGHER ASSEMBLY: 12576302

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Width, min.		0.40%	3.2	Gage
103	Width, min.		0.40%	3.2	Gage
104	Angle incorrect		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil/ - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.67	Foam				12576338
					NEXT HIGHER ASSEMBLY
					12576302
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Width, min.		0.40%	3.2	Gage
103	Angle incorrect		0.40%	3.2	Gage
104	Overall thickness, min.		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil - 5 Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.68	Foam	1 OF 1	12576339
			NEXT HIGHER ASSEMBLY: 12576302

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Width, min.		0.40%	3.2	Gage
103	Thickness, min.		0.40%	3.2	Gage
104	Angle incorrect		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE	SHEET	OF	DRAWING NUMBER
4.4.2.69	Foam	1	1	12576340

NEXT HIGHER ASSEMBLY: 12576302

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Width, min.		0.40%	3.2	Gage
103	Thickness, min.		0.40%	3.2	Gage
104	Angle incorrect		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.70	Foam				12576341
					NEXT HIGHER ASSEMBLY
					12576302
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length, min.		0.40%	3.2	Gage
102	Width, min.		0.40%	3.2	Gage
103	Thickness, min.		0.40%	3.2	Gage
104	Angle incorrect		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.71	Bracket				12576342
					NEXT HIGHER ASSEMBLY
					12576307
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Material thickness, min.		0.40%	3.2	Gage
102	Total length		0.40%	3.2	Gage
103	Height		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.72	Bracket				12576343
					NEXT HIGHER ASSEMBLY 12576302
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Size of large hole (3 places)		0.40%	3.2	Gage
102	Position of large holes		0.40%	3.2	Gage
103	Size of small hole (3 places)		0.40%	3.2	Gage
104	Position of small holes		0.40%	3.2	Gage
105	Material thickness, min.		0 40%	3.2	Gage
106	Length		0.40%	3.2	Gage
107	Height tab extends (3 places)		0.40%	3.2	Gage
108	Length from end to end of tab (3 places)		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85 Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

MIL-T-70711

CLASSIFICATION OF DEFECTS & TESTS

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.73	Nut, Special				12576344
					NEXT HIGHER ASSEMBLY
					12576336
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Pitch diameter of thread, max.		0.40%	3.2	Gage
102	Minor diameter of thread, max.		0.40%	3.2	Gage
103	Incomplete thread		0.40%	3.2	Gage
104	Snall outside diameter, min.		0.40%	3.2	Gage
105	Length of small outside diameter, min.		0.40%	3.2	Gage
MINOR					
201	Evidence of poor evidence		1.00%	3.7	Visual

NOTES:

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-T-70711

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.74	Washer, Special				12576345
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
CRITICAL	None defined				
MAJOR					
101	Length of small outside diameter		0.40%	3.2	Gage
102	Diameter of thru hole, max.		0.40%	3.2	Gage
MINOR					
201	Evidence of poor workmanship		1.00%	3.7	Visual

NOTES:

AMSMC Form 1570, 1 Feb 85

Replaces DRSMC-QA (D) Form 160, 1 Aug 83, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

4.4.3 Testing. Testing is described in the First Article and Quality Conformance Inspection tables.

4.4.4 Inspection equipment. The inspection equipment required to perform the examinations and tests prescribed herein is described in the "Paragraph Reference/Inspection Method" column in the tables starting with 4.4.2.1. The contractor shall submit for approval inspection equipment designs in accordance with the terms of the contract. See Section 6 of MIL-A-48078 and 6.3 herein.

4.5 Methods of inspection.

4.5.1 Materials, components and processes. Compliance with all requirements of Section 3 of this specification shall be ascertained by current and continuing examination of inspection and test data to determine that all components (parts and materials) have been inspected and tested and found to comply with their respective drawing and specification requirements, and that all specified manufacturing processes have been followed.

4.5.1.1 Visual and mechanical inspections. The visual, manual and mechanical inspections and tests shall verify compliance with the requirements of Sections 3 and 5 of this specification in accordance with 4.4.2 herein and Table I.

4.5.2 Penetrant inspection of welds. This test shall be performed as specified in specification MIL-I-6866.

5. PACKAGING

5.1 Packaging, packing, and marking. The parts shall be packaged and packed in accordance with the requirements of Level B of MIL-STD-1169.

5.2 Marking. Marking shall be in accordance with the requirements of Level B of MIL-STD-1169.

6. NOTES

6.1 Intended use. The components covered by this specification are intended for use in tile.

6.2 Ordering data. See MIL-A-48078.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.

6.3 Submission of inspection designs for approval. See 6.2.3 of MIL-A-480078. Submit designs as required to Commander, US Army Armament, Research Engineering and Development Center (ARDEC) ATTN:AMSMC-QAT-I, Picatinny Arsenal, NJ 07806-5000. This address will be specified on the Contract Data Requirements List, DD Form 1423 in the contract. Unless otherwise specified, data item DI-R-1714 will apply.

6.4 Data requirements. Deliverable data required by the specification cited as follows:

Data requirement	Applicable Data Item
Ammunition Data Card	DI-MISC-80043

6.5 Contractor. Unless otherwise specified, the word "Contractor," as used throughout this specification, shall mean any supplier or producer of items or material to the Government. This shall include commercial contractors, sub-contractors, Government-Owned, Contractor-Operated (GOCO) and Government-Owned, Government-Operated (GOGO) plants.

6.6 Drawings. Drawings listed in Section 2.1.2 of this specification under the heading U.S. Army Armament, Research, Development and Engineering Center (ARDEC) may also include drawings prepared by, and identified as ARDC, ARRADCOM, Picatinny Arsenal or Rock Island drawings. Technical data originally prepared by these activities is now under the cognizance of ARDEC.

6.7 Subject term (Key Word) listing.

Armor
Tiles
Bradley
Plate
Welds
Reactive

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 2350-A388)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:30Z
Check the source to verify that this is the current version before use.