METRIC

A-A-3139A
April 1, 2010
SUPERSEDING
A-A-3139
March 3, 1998

# COMMERCIAL ITEM DESCRIPTION

# ADHESIVE, RESILIENT FLOORING (WATER-BASED)

The General Services Administration has authorized the use of this commercial item description by all federal agencies.

**1.0 SCOPE.** This Commercial Item Description covers two types and three classes of adhesive suitable for the installation of resilient vinyl or other resilient flooring to on or above grade floors.

**2.0 CLASSIFICATION.** The adhesives shall conform to the following two types and three classes.

Type I - High viscosity for trowel application
Type II- Low viscosity for spray application

Class 1- For use on vinyl-backed sheet goods and tile
Class 2- For use on linoleum and linoleum title
Class 3- For use with commercial and residential felt-back sheet flooring, linoleum, cork sheet flooring, and most commercial carpeting, for bonding to concrete, underlayments, wood, terrazzo and existing resilient floors.

## 3. 0 SALIENT CHARACTERISTICS

3.1 Materials: The adhesive shall consist of a binder in a water-based suspension uniformly mixed with inorganic fillers and other additives to control odor and prohibit mold growth. It shall be homogeneous and free of lumps or foreign particles and shall not show evidence of separation or settling.

3.2 Viscosity: The viscosity of the Type I adhesive shall not be less than 80,000 nor more than 250,000 cps, and the viscosity of the Type II adhesive shall not be less than 40,000 nor more than 120,000 cps when tested in accordance with ASTM D 1084, method B using a Brookfield viscometer (or equivalent) and number 7 spindle at 10 rpm.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any other data which may improve this document should be sent to: General Services Administration, Heartland Supply Operations Center, 1500 Bannister Rd., Atrium, Kansas City, Missouri, 64131.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:30Z
Check the source to verify that this is the current version before use.

3.3 Drying time: The adhesive shall be dry to the touch in not more the 3 hours when tested as follows: Stir the adhesive until uniform. Spread a sample of the adhesive on an aluminum plate approximately 45 x 150 x 0.8mm (75 x 6 x 0.031 inches) using a Bird Film Applicator set or equivalent with a gap clearance of 0.25mm (0.010 inch). Allow the adhesive on the plate to dry in open air at standard conditions (23 +/- 2 deg. C) and 50 +/- 5% humidity for not longer the 3 hours. The film is dry if it does not transfer solvent to the finger under light pressure.

3.4 Peel strength: The peel strength of the cured adhesive shall not be less than 700 N/M (4 lb/in) tested in accordance with ASTM D 903. The test adherends shall be No. 1 white pine board, 9 cm x 15 cm x 1 cm (2.75 x 6 x 3/8 inches) panels and 627.4 g/sq meter (30 oz/sq yd) cotton duck. The pull angle shall be 90 degrees instead of 180 degrees, and the crosshead pull speed shall be 2.54 cm/min (1 inch/min) instead of 30 cm/min (12 inch/min).

3.5 Color: The color of the adhesive shall be white or other light color unless otherwise stated in the contract or purchase order and shall not bleed or migrate through the vinyl and linoleum floor covering.

## 4.0 REGULATORY REQUIREMENTS.

The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

## 5.0 QUALITY ASSURANCE PROVISIONS

5.1 The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards , and quality assurance practices, and is the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

5.2 Use the latest method in effect on the date of the solicitation or order. ASTM standards are available from the ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 - **http://www.astm.org/**

## 6.0 PACKAGING.

Packaging, preservation, packing, and marking shall be as specified in the contract or order.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:30Z
Check the source to verify that this is the current version before use.

**7.0 NOTES.**

7.1 National Stock Numbers (NSNs). The list of NSN assigned that correspond to this CID. The list may not be indicative of all possible NSNs associated with the CID.

| NSN | Type/Class |
|---|---|
| 8040-00-139-3674 | Type I |
| 8040-00-273-8713 | Type I / Class 1 |
| 8040-00-273-8714 | Type I / Class 2 |
| 8040-00-078-0737 | Type I / Class 3 |

MILITARY INTEREST:

Custodian
Air Force – 99

Preparing Activity:
GSA - FAS

Review Activity
Air Force – 84



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:30Z
Check the source to verify that this is the current version before use.