[INCH-POUND]
A-A-3157
April 13, 1998
SUPERSEDING
DDD-C-441C
September 7, 1972

COMMERCIAL ITEM DESCRIPTION

CLOTH, POLISHING

The General Services Administration has authorized the use of this commercial item description by all Federal agencies.

1. SCOPE

1.1 Scope. This commercial item description (CID) covers a soft cotton polishing cloth.

2. SALIENT CHARACTERISTICS

2.1 General. The cloth shall be 100% woven cotton meeting the requirements of table 1. The cloth shall have a soft finish and shall be lightly napped on both sides. The finished cloth edges, other than selvage edges, shall be bound, hemmed, or overedged with cotton sewing thread. The color shall be at the option of the contractor, however, any added color shall be permanent and non-bleeding.

Table 1, Cloth physical characteristics

Characteristic	Value	Test
Weight	3.3 oz/yd^2 (122 g/m^2) minimum	ASTM D 3776
Yarns per inch (per cm)		Visual
Warp	42 (17) minimum	
Filling	40 (16) minimum	
Breaking strength,		ASTM D 5034
Warp	25 lbs (111 N) minimum	
Filling	11 lbs (49 N) minimum	

2.2 Size. Unless otherwise specified, each cloth shall have a minimum area of 350 in^2 (2600 cm^2) with no side less than 17 inches (43 cm) long.

2.3 Workmanship. The cloth shall be clean, soft, free of hard particles, and free of any defects that may affect appearance, durability or serviceability.

2.4 Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within tolerances specified and all other requirements of this document are met.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: General Services Administration, Engineering Branch (7FXEE), 819 Taylor Street, Fort Worth, TX 76102

FSC 7920

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:30Z
Check the source to verify that this is the current version before use.

3. REGULATORY REQUIREMENTS

3.1 Regulatory requirements. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

4. QUALITY ASSURANCE PROVISIONS

4.1 Product conformance. The products provided shall meet the salient characteristics of this CID, shall conform to the producer's own drawings, specifications, standards, and quality assurance practices, and shall be the same product offered for sale in the commercial market. The government reserves the right to require proof of such conformance.

5. PACKAGING, PACKING AND MARKING

5.1 Packaging, packing and marking. The packaging, packing, and marking shall be as specified in the contract or order.

6. NOTES

6.1 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

a. Title, number, and date of this CID.
b. The packaging, packing and marking desired.

6.2 Referenced documents.

ASTM D 3776 - Standard Test Method for Mass Per Unit Area (Weight) of Fabric
ASTM D 5034 - Standard Test Method for Breaking Strength of Textile Fabrics (Grab Test)

Copies of ASTM standards are available from ASTM, 100 Barr Harbor Dr., West Conshohocken, PA 19428-2959, (610-832-9500).

6.3 National Stock Number. NSN 7920-00-205-1656 utilizes this document.

MILITARY INTERESTS

Preparing Activity:
GSA - FSS

Military coordinating activity:
Army - GL

Custodians:
Army - GL
Air Force - 99

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:30Z
Check the source to verify that this is the current version before use.