MIL-C-1726F
31 December 1985
SUPERSEDING
MIL-C-1726E
30 September 1977

MILITARY SPECIFICATION

CHEST, FIELD TABLEWARE OUTFIT

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers one type and size of fiber-covered, wood chest designed to hold field tableware.

2. APPLICABLE DOCUMENTS

* 2.1 Government documents. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this document to the extent specified herein.

SPECIFICATIONS

FEDERAL

KK-L-271	- Leather, Cattlehide, Strap, Vegetable Tanned
QQ-S-698	- Steel Sheet and Strip, Low Carbon
QQ-S-781	- Strapping, Steel, and Seals
QQ-W-461	- Wire, Steel, Carbon (Round, Bare, and Coated)

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to U.S. Army Natick Research and Development Center, Natick, MA 01760-5014, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 7360

AMSC N/A

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:41Z
Check the source to verify that this is the current version before use.

TT-C-490	- Cleaning Methods for Ferrous Surfaces and Pretreatments for Organic Coatings
TT-I-1795	- Ink, Marking, Stencil, Opaque (Porous and Non-Porous Surfaces)
TT-P-636	- Primer Coating, Alkyd, Wood and Ferrous Metal
TT-V-121	- Varnish, Spar, Water-Resisting
MMM-A-181	- Adhesives, Phenol, Resorcinol, or Melamine Base
MMM-A-1617	- Adhesive, Rubber Base, General Purpose
PPP-F-320	- Fiberboard: Corrugated and Solid, Sheet Stock (Container Grade), and Cut Shapes
PPP-S-760	- Strapping, Nonmetallic (and Connectors)

MILITARY

MIL-B-2505	- Buckles, Center-Bar With Tongue
MIL-R-3065	- Rubber, Fabricated Products
MIL-F-10336	- Fiber Sheet, Vulcanized
MIL-E-52798	- Enamel, Alkyd, Camouflage

STANDARDS

FEDERAL

FED-STD-595	- Colors

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	- Marking for Shipment and Storage
MIL-STD-147	- Palletized Unit Loads

DRAWINGS

U.S. ARMY NATICK RESEARCH AND DEVELOPMENT CENTER

5-13-12	- Chest, Field Tableware Outfit; Assembly and Details
5-13-13	- Chest, Field Tableware Outfit; Details
5-13-1951	- Chest, Field Tableware Outfit; Packing Of

(Copies of documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:41Z
Check the source to verify that this is the current version before use.

* 2.2 Other publications. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this document to the extent specified herein.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 1056 - Flexible Cellular Materials - Sponge or Expanded Rubber
D 2000 - Rubber Products in Automotive Applications
D 2016 - Standard Test Methods for Moisture Content Of Wood
D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

UNITED STATES DEPARTMENT OF COMMERCE

U.S. Product Standard PS 1 - Construction and Industrial Plywood

(Application for copies should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.)

AMERICAN NATIONAL STANDARDS INSTITUTE (ANSI)

ANSI/HPMA HP 1983 - Hardwood and Decorative Plywood

(Application for copies should be addressed to the American National Standards Institute, Inc., 1430 Broadway, New York, NY 10018.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

2.3 Order of precedence. In the event of conflict between the text of this document and the references cited herein, the text of this document shall take precedence.

3. REQUIREMENTS

3.1 First article. When specified, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:41Z
Check the source to verify that this is the current version before use.

3.2 Materials and components. The materials and components shall be as specified herein. Materials not definitely specified shall be of the quality normally used by the manufacturer in his standard commercial chest, provided the completed item complies with all of the provisions of this document. Unless otherwise specified, commercial tolerances shall apply to all metal thicknesses and diameters. Recycled materials may be used (see 6.4).

3.2.1 Plywood. Plywood shall be minimum 3-ply, of the following types:

a. Hardwood - Fully waterproof bond, grade 2 face and back, regular sanded, conforming to type I of ANSI/HPMA HP 1983.

b. Softwood - Softwood plywood shall conform to group 1, exterior type, grade B-B, sanded two sides of PS 1.

3.2.2 Lumber. Lumber shall be uniformly dried to an average moisture content of from 8 to 12 percent at time of fabrication (see 4.4.1.1). Lumber shall be free of defects, such as knots, splits, pitch pockets, warp, and wane. Any of the following species of wood may be used, except that only one species of wood may be used throughout any one chest.

Beech	Ponderosa pine	Short leaf pine	Birch
Sweet gum	Soft maple	Yellow poplar	

3.2.3 Vulcanized fiber. Vulcanized fiber shall conform to MIL-L-10336.

3.2.4 Steel sheet, strip, and wire. Steel sheet, strip, and wire used in the chest shall conform to the chemical composition of steel numbers C1008 through C1020 of QQ-S-698 or QQ-W-461, as applicable.

3.2.5 Rivets. Rivets shall be fabricated of steel, except as otherwise specified herein. Solid and tubular rivets may be used interchangeably. Rivets shall be 9/64 inch diameter except as shown on the drawings. Solid and tubular rivets shall be of sufficient length to provide a minimum of 1/16 inch clinch. Bifurcated rivets shall be of sufficient length to provide a minimum of 1/8 inch clinch.

3.2.6 Cut trunk tacks. Cut trunk tacks shall be oval or shot head with square shanks and shall be of sufficient length to provide a minimum of 1/8 inch clinch.

3.2.7 Center bar buckle. The center bar buckle shall conform to type II, class 2 of MIL-B-2505.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:41Z
Check the source to verify that this is the current version before use.

3.2.8 Leather. The leather for the lifting tab, billet, and buckle chape shall be natural conforming to any type, class 1 of KK-L-271.

3.2.9 Adhesives.

3.2.9.1 Rubber (synthetic and reclaimed base). Rubber adhesive for securing the gasket shall conform to type I of MMM-A-1617.

3.2.9.2 Resin. Resin adhesives shall conform to type I, II, or III of MMM-A-181, except that strength by compression loading and curing cycle requirements do not apply.

3.2.10 Primer. Primer shall conform to TT-P-636.

3.2.11 Enamel. Enamel shall conform to MIL-E-52798. Unless otherwise specified (see 6.2), the color shall be forest green as specified in MIL-E-52798.

3.2.12 Varnish. Varnish shall conform to TT-V-121.

3.2.13 Stencil ink. Stencil ink shall conform to TT-I-1795.

* 3.2.14 Rubber gasket. The rubber gasket shall conform to either one of the following:

a. Grade, type, class, and suffix letters 4AA315A13 of MIL-R-3065 and ASTM D 2000.

b. Type, style, and grade RO 14 of ASTM D 1056.

3.3 Design. The chest shall be fabricated of fiber-covered plywood. It shall consist of a body and lid, and shall be equipped with metal hardware and handles as shown on Drawings 5-13-12 and 5-13-13. A removable wood compartment divider shall be located in the body.

3.4 Construction. The construction of all components and assemblies covered by this document shall conform to the requirements specified herein and on Drawings 5-13-12 and 5-13-13.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:41Z
Check the source to verify that this is the current version before use.

3.4.1 Fiber covering. The vulcanized fiber specified in 3.2.3 shall be bonded with adhesive specified in 3.2.9.2 to both surfaces of the plywood for the body and lid. Each plywood surface shall be completely covered with a single sheet of vulcanized fiber. The plywood-fiber bond shall be clean, smooth surfaced, and free from waves or irregularities. The adhesive bond of fiber to plywood shall show no delamination when tested as specified in 4.5.1. The fiber-covered plywood panels shall be fabricated by either one of the following processes:

a. Unit process - The vulcanized fiber and wood veneers shall be glued with the same adhesive, and assembled, pressed, and cured in one operation.

b. Two-step process - The vulcanized fiber shall be bonded to the plywood specified in 3.2.1 with an adhesive specified in 3.2.9.2.

3.4.2 Fiber binding. The fiber binding shall be set tightly to the edges. Cut trunk tacks specified in 3.2.6 or bifurcated rivets specified in 3.2.5 shall be used for attaching the fiber binding.

3.4.3 Joints. All joints of the body, lid, compartment divider, and box shall be fastened with the adhesive specified in 3.2.9.2. Application of the adhesive shall be uniform and in quantities recommended by the manufacturer. The adhesive shall be in addition to nailing shown on drawings. Clamping or pressing time, and pressure shall be in accordance with the manufacturer's recommendation.

3.4.4 Driving of nails, cut trunk tacks, and rivets. All solid and tubular rivets shall be driven through predrilled holes with the heads flush against hardware or fiber surface and shall have the ends headed or set. All bifurcated rivets, trunk tacks, and box nails shall be driven with heads flush against hardware or fiber. Rivets and tacks shall be clinched on the interior of the chest so as not to protrude from the wood.

3.4.5 Assembly. The chest lid shall be so aligned that the lid valance and body mate. The lid and body shall be glued and nailed as specified herein. The compartment dividers and box, in addition to being glued, shall be nailed, except that the 1/4 inch dividers in the box shall be glued only.

3.5 Finish. Rough or sharp edges, burrs, and slivers shall be removed.

3.5.1 Metal surface preparation. The surfaces of steel parts, excluding nails, shall be given a cleaning and surface preparation treatment conforming to type I or II of TT-C-490.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:41Z
Check the source to verify that this is the current version before use.

3.5.2 Priming.

3.5.2.1 Lid and body. Prior to attachment of hardware, a coat of the primer specified in 3.2.10 shall be applied to all inside and outside surfaces of the lid and body. The primer coat shall level out and be dry before further assembly. All surfaces and edges of the fiber binding and fiber quarter circles shall be primed separately before attachment. Forced drying is permitted, provided a surface temperature of 140°F is not exceeded and the relative humidity of surrounding air is maintained between 30 and 50 percent.

3.5.2.2 Metal parts. All metal parts excluding tacks, nails, and escutcheon pins shall be given a coat of primer specified in 3.2.10.

3.5.3 Enameling. After attachment of hardware and binding, the complete chest, excluding compartments and hinged box, shall be given a coat of enamel specified in 3.2.11. The enamel on the lid and body shall be dry before stacking or packing. Hinges, hooks and eyes, and clamps of the hinged box and compartment shall be coated with enamel prior to installation and varnishing of the hinged box and compartment. There shall be no scratches, area of thin film, runs, or foreign matter embedded in the finish.

3.5.4 Varnishing. All edges and surfaces of the compartments and hinged box shall be finished with two coats of varnish specified in 3.2.12 and shall be completely dry before final assembly. There shall be no scratches, area of thin film, runs, or foreign matter embedded in the finish.

3.6 Marking for identification. On the outside of the chest, in the size and location shown on Drawing 5-13-12, there shall be stenciled, with the ink specified in 3.2.13, the following information:

a. Nomenclature
b. Contract or order number
c. Manufacturer's identification name or trademark
d. "US"

3.7 Workmanship. The end item shall have clean, smooth surfaces and be free from waves.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:41Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be inspected in accordance with the quality assurance provisions of this document and evaluated for overall appearance. Any failure to conform to the quality assurance provisions of this document or any appearance failure shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

4.4.1.1 Moisture content test of lumber. A test shall be performed on each lot of lumber at the time of fabrication for moisture content in accordance with ASTM D 2016 to determine conformance to 3.2.2. The sample unit shall be one piece of lumber. Three determinations shall be taken on each sample unit and the results shall be the average of the three determinations. The inspection level shall be S-3, and the acceptable quality level (AQL) shall be 2.5, expressed in terms of defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 20260-16T13:41Z
Check the source to verify that this is the current version before use.

contracting offices. preproduction sample. The contractor shall submit for the

4.4.2 In-process inspection. Examination shall be made during the manufacturing process for the requirements specified in table I to establish that no deviation is made from indicated requirements. Whenever nonconformance is noted, correction shall be made to the affected items and process.

TABLE I. In-process inspection

Requirement	Paragraph
Application of adhesive to joints of the body, lid, compartment dividers and box; clamping or pressing time and pressures as recommended by the adhesive manufacturer	3.4.3
Preparation of steel component surfaces	3.5.1
Priming of lid and body, fiber bindings, and fiber quarter circles	3.5.2.1
Force drying of primer coat (if applicable)	3.5.2.1
Enameling of hinges, hooks and eyes, and clamps of the hinged box and compartment prior to installation	3.5.3
Application of varnish	3.5.4

4.4.3 In-process testing.

4.4.3.1 Vulcanized fiber adhesion test. The test specified in 4.5.1 shall be performed on five (5) samples of 4-inch square, fiber-covered plywood to determine compliance with 3.4.1. Each sample shall be from a different piece of fiber-covered plywood. The inspection lot shall be all the fiber-covered plywood offered for inspection at one time. Any sample failing to meet the specified requirements shall be cause for rejection of the lot.

Source: https://assist.dla.mil -- Downloaded: 202610-16T13:41Z
Check the source to verify that this is the current version before use.

4.4.4 End item inspection. The end item shall be examined for visual defects and proper dimensions. The lot shall consist of all complete chests offered for inspection at one time. The sample unit for this inspection shall be one completely fabricated chest.

* 4.4.4.1 Visual examination. Examination of the chest shall be in accordance with the defects in table II. The inspection level shall be II and the AQL shall be 2.5 for major defects and 10.0 for total defects, expressed in terms of defects per hundred units.

TABLE II. Classification of defects

Examine	Defect	Classification	
		Major	Minor
Finish	Not type specified	101	
	Not specified color		201
	Scratch or gouge through coating to base material	102	
	Scratches visible at 5 feet		202
	Area of no coating on exterior surfaces	103	
	Area of no coating on interior surfaces		203
	Dirt, grit, or foreign matter embedded in finish		204
	Rough or sharp edge, burr, or sliver	104	
	Area of thin coat over an area 6 square inches or more	105	
	Area of thin coat over an area less than 6 square inches		205
Design	Any characteristic not in accordance with specified requirements	106	
Construction and workmanship (general)	Component missing (except rivets, tacks, burrs, or escutcheon pins) or not type specified	107	
	Component fractured, cracked, split, dented, creased, malformed, or deteriorated	108	

Source: https://assist.dla.mil -- Downloaded: 202610-16T13:41Z
Check the source to verify that this is the current version before use.

TABLE II. Classification of defects - Continued

Examine	Defect	Classification	
		Major	Minor
Construction and workmanship (general) (continued)	Component not securely attached or joined		206
	Lid does not fit evenly when in a closed position		207
	Draw bolt does not draw lid tight	109	
Fastening devices	Rivets or pin not properly set, peened, or clinched		208
	One rivet, trunk, tack, burr, screw or escutcheon pin missing		209
	More than one rivet, trunk tack, screw or escutcheon pin missing	110	
	Screw not set tight		210
	Two or more rivet or screw heads broken off		211
	Two or more rivets or trunk tracks cocked over 1/32 inch		212
	Nail protrudes from wood	111	
Identification marking	Missing, illegible, incorrect, wrong size, wrong location, or not applied as specified	112	

4.4.4.2 Dimensional examination. Inspection shall be made of the completed chests for compliance with specified dimensions. Any dimension that is not within the specified requirements shall be classified as a defect. The inspection level shall be S-3, and the AQL shall be 4.0, expressed in terms of defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:41Z
Check the source to verify that this is the current version before use.

4.4.5 Packaging inspection. An examination shall be made to determine that preservation, packing, and marking are in compliance with section 5. Defects shall be scored as specified in table III. The lot shall be the number of containers offered for inspection at one time. The sample unit shall be one chest fully packaged. The inspection level shall be S-3, and the AQL shall be 6.5, expressed in terms of defects per hundred units.

TABLE III. Packaging inspection

Examine	Defect
Markings	Omitted, incorrect, illegible or of improper size, location, sequence, or method of application
Materials	Component missing, damaged, or otherwise defective
Workmanship	Inadequate application of components such as loose strapping, strap protector inadequate or missing Interior components inadequately immobilized Lid not secured

4.4.6 Examination of palletization. An examination shall be made to determine that palletization is in compliance with section 5. Defects shall be scored as specified in table IV. The lot shall be the number of palletized unit loads submitted for inspection at one time. The sample unit for this examination shall be one palletized unit load, ready for shipment. The inspection level shall be S-1, and the AQL shall be 6.5, expressed in terms of defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:41Z
Check the source to verify that this is the current version before use.

TABLE IV. Examination of palletization

Examination	Defect
Finished dimension	Length, width, or height exceeds specified maximum requirement
Palletization	Not as specified Pallet pattern not as specified Interlocking of loads not as specified Load not bonded with required straps as specified
Weight	Exceeds maximum load limit
Marking	Omitted, incorrect, illegible, or of improper size, location, sequence, or method of application

4.5 Test methods.

4.5.1 Adhesion of vulcanized fiber to plywood test. Samples of the fiber-covered plywood, as specified in 4.4.3.1, shall be immersed in boiling water for 3 hours. The sample shall be cooled in 70°F water, ± 5°F, for a period of 10 minutes and immediately examined while wet for delamination or weakness of the bond at the glue line.

5. PACKAGING

5.1 Preservation. Preservation shall be level A.

5.1.1 Level A. Interior components shall be immobilized in place within each chest in a manner as to preclude movement or damage while in transit. Each chest shall be closed and the lid secured with the drawbolts provided.

5.2 Packing. Packing shall be level A, B, or Commercial, as specified (see 6.2).

5.2.1 Level A packing. Each chest, preserved as specified in 5.1.1, shall be protected with a solid fiberboard cap tray completely covering the top and extending down not less than 6 inches as shown on Drawing 5-13-1951. The cap tray shall be fabricated from fiberboard conforming to type SF, class

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:41Z
Check the source to verify that this is the current version before use.

weather-resistant, grade W5s of PPP-F-320. The cap tray shall be secured to the chest with flat steel strapping, 3/8 inch wide by 0.015 inch thick, conforming to class I, type 1, regular duty, finish A or B, of QQ-S-781 or type II or III nonmetallic strapping of PPP-S-760, having a minimum breaking strength of 390 pounds. The bottom edges of the chest shall be protected from indentation by the steel strapping at each point of contact with strap protectors as shown on Drawing 5-13-1951. The strap protectors may be eliminated when nonmetallic strapping is used. Positioning of nonmetallic strapping shall be the same as shown for steel strapping on Drawing 5-13-1951.

5.2.2 Level B packing. Level B packing shall be the same as level A packing with the exception that the cap tray shall be fabricated from fiberboard conforming to type SF, class domestic, grade 200 of PPP-F-320.

* 5.2.3 Commercial packing. Chests, preserved as specified in 5.1.1, shall be packed in accordance with ASTM D 3951.

5.3 Palletization. When specified (see 6.2), chests packed as specified in 5.2 shall be palletized in accordance with load type I of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K or L or with bonding means O or P. Pallet pattern shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course. If the container is of a size that does not conform to any of the pallet patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer.

5.4 Marking. In addition to any special marking required by the contract or purchase order, each chest and palletized unit load shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable. All markings shall be printed or stenciled on the fiberboard cap tray. Markings shall not be applied directly to the surfaces of the chest.

6. NOTES

6.1 Intended use. The chest is intended to be used for storing and transporting the components of the field tableware outfit in MIL-T-1748.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. When a first article is required (see 3.1).
c. Color, if other than specified (see 3.2.11).
d. Selection of the applicable levels of packing (see 5.2).
e. When palletization is required (see 5.3).

Source: https://assist.dla.mil -- Downloaded: 202610-16T13:41Z
Check the source to verify that this is the currentversion before use.

* 6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The first article should consist of one unit. The contracting officer should include specific instructions in all procurement instruments regarding arrangements for inspection and approval of the first article.

* 6.4 Recycled material. The contractor is encouraged to use recycled material when practical, provided that it meets the requirements of this document (see 3.2).

6.5 Changes from previous issue. The margins of this document are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only, and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodian:

Army - GL
Navy - MC

Review activities:

Army - MD
DLA - GS

Preparing activity:

Army - GL

Project No. 7360-0154

Source: https://assist.dla.mil -- Downloaded: 202640-16T13:41Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:41Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY
US Army Natick Research and Development Center
Natick, Massachusetts 01760

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development Center
ATTN: STRNC-ES
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 202640-16T13:41Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-C-1726F	Chest, Field Tableware Outfit

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*: _____
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OP 1 Apr 84

Source: https://assist.dla.mil -- Downloaded: 202610-16T13:41Z
Check the source to verify that this is the current version before use.