INCH-POUND

MIL-H-1679F
13 January 1992
SUPERSEDING
MIL-H-1679E
24 May 1974

MILITARY SPECIFICATION

HOOK, TENT; WITH THIMBLE, FOR GUY LINE, ASSEMBLY TENT

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Classification. This specification covers one type of assembly tent hook with thimble, for guy lines.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

FF-T-276 - Thimbles, Rope
TT-E-485 - Enamel, Semi-Gloss, Rust-Inhibiting

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5017 by using the Standardization Documents Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A

FSC 8340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-16T13:36Z
Check the source to verify that this is the current version before use.

PPP-B-601 - Boxes, Wood, Cleated-Plywood
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner
PPP-B-636 - Boxes, Shipping, Fiberboard
PPP-B-640 - Boxes, Fiberboard, Corrugated, Triple-Wall

MILITARY

MIL-T-1547 - Thimbles, Rope (Solid)
MIL-L-35078 - Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage, General Specification For

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads
MIL-STD-731 - Quality of Wood Members for Containers and Pallets

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWING

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

4-1-72 - Hook and Thimble, Guy Line, Tent, Assembly

(Copies of the drawing are available from the U.S. Army Natick Research, Development, and Engineering Center, ATTN: STRNC-UX, Natick, MA 01760-5017.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:36Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

A 47 - Malleable Iron Castings
A 108 - Steel Bars, Carbon, Cold-Finished, Standard Quality
A 153 - Zinc Coating (Hot-Dip) on Iron and Steel Hardware
B 633 - Electrodeposited Coatings of Zinc on Iron and Steel
D 2092 - Preparation of Zinc-Coated Steel Surfaces For Painting
D 3951 - Standard Practice for Commercial Packing

(Applications for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.

3.2 Materials. Materials shall conform to the applicable referenced specifications and requirements specified herein. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.2.1 Steel bar, carbon. The carbon steel bar shall conform to grade disgnation 1015-1025, cold finished, standard quality, condition cold drawn of ASTM A 108.

3.2.2 Enamel. The enamel shall conform to type I or II, composition G or L, as applicable, Olive Drab Color No. 24087 of TT-E-485.

3.3 Construction. The construction of the hook and assembly to thimble shall conform to Drawing 4-1-72 and as specified herein. The hook shall be assembled, at the option of the supplier, to either a steel thimble or malleable iron thimble. The hook and thimble shall be assembled after zinc coating and phosphate treatment but prior to application of enamel (see 3.4).

3.3.1 Hook. The hook shall be fabricated of steel specified in 3.2.1.

3.3.2 Thimble, steel. The steel thimble shall conform to type II, size 1/2-inch of FF-T-276, except that galvanizing requirements shall be waived.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:36Z
Check the source to verify that this is the current version before use.

3.3.3 Thimble, malleable iron. The malleable iron thimble shall conform to size 2-1/2 inches of MIL-T-1547, except that the castings shall conform to grade 35018 of ASTM A 47.

3.4 Finish. Prior to assembly, the hook and thimble shall be given a zinc coating with supplementary chromate treatment conforming to either type II of ASTM B 633 or ASTM A 153 with preparation for painting in accordance with method A-crystalline zinc phosphate treatment of ASTM D 2092. After assembly, the hook with thimble shall be coated with enamel specified in 3.2.2.

3.5 Workmanship. Components shall be free of burrs, slivers, rough or sharp edges, and shall not be broken, cracked or malformed. Enamel shall level out to a uniform dry film thickness without runs, drops, streaks or areas of no film. The coating shall be free from imbedded foreign matter, gouge, scratch, scuff and shall show no evidence of peeling, flaking or blistering. The end items shall conform to the quality of product established by this specification and the occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to ensure compliance with all dimensional requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:36Z
Check the source to verify that this is the current version before use.

METRIC

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.3 and 4.4.4. Any nonconformance shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.2 In-process inspection. Examination shall be made during the manufacturing process for zinc coating and phosphate treatment specified in 3.3 and 3.4 to establish that no deviation is made from the indicated requirements. Whenever nonconformance is noted, correction shall be made to the affected items and to the process. Items that cannot be corrected shall be removed from production.

4.4.3 End item visual examination. The end items shall be examined for the defects listed in table I. The lot size shall be expressed in units of complete hooks with thimbles. The sample shall be one complete hook and thimble. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5 for major defects and 6.5 for total (major and minor combined) defects.

TABLE I. End item visual defects

Examine	Defect	Classification Major	Classification Minor
Finish	Not finished as specified	101	
	Not color specified		201
	Area of no film	102	
	Not continuous, or is not smooth		202
	Contains runs, drops or streaks		203
	Foreign matter imbedded		204
	Gouge, scratch or scuff:		
	(a) Exposing bare metal	103	
	(b) Exposing phosphate treated zinc plate		205
	Evidence of peeling, flaking or blistering	104	

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:36Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Construction and workmanship	Burrs, slivers, rough or sharp edges	105	
	Hook or thimble broken, cracked or malformed	106	
	Eye of hook not fully closed	107	
	Evidence of red rust	108	
	Incorrect type or size thimble	109	
	Hook or thimble missing	110	

4.4.4 End item dimensional examination. The end items shall be examined for conformance to the dimensions specified on the drawing(s). Only those dimensions that can be evaluated without damaging or disassembling the end items shall be examined. Any dimension not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of complete hook assemblies. The sample unit shall be one complete hook assembly. The inspection shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

4.4.5 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as: incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling
	Bulged or distorted container
Contents	Number per container is more or less than required

4.4.6 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:36Z
Check the source to verify that this is the current version before use.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial, as specified (see 6.2).

5.1.1 Level A preservation. Twenty-five hooks with thimbles shall be packaged in snug-fitting fiberboard box conforming to style RSC, either type CF, class domestic, grade 200 of PPP-B-636. Inside dimensions of the box shall be approximately 13 inches in length, 6 inches in width, and 7-1/2 inches in depth. Each box shall be agitated during filling to assure a well-filled box. Closure shall be in accordance with the appendix of the box specification.

5.1.2 Commercial preservation. Hooks with thimbles shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial, as specified (see 6.2).

5.2.1 Level A packing. One hundred hooks with thimbles preserved as specified in 5.1, shall be packed in a shipping container. The shipping container shall be a fiberboard box conforming to overseas type, style A, B or I, grade B of PPP-B-601 or class 2, style 2 or 4 of PPP-B-621. Inside dimensions of the box shall be approximately 13-1/2 inches in length, 12-1/2 inches in width, and 15-1/2 inches in depth. Each box shall be closed, waterproofed, and reinforced with strapping or tape banding in accordance with the appendix of PPP-B-636. Boxes shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.2.2 Level B packing. One hundred hooks with thimbles preserved as specified in 5.1, shall be packed in a shipping container. The shipping container shall be a fiberboard box conforming to either class 1, style E of PPP-B-640; domestic type, style A, B or I, grade A or B of PPP-B-601; or

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:36Z
Check the source to verify that this is the current version before use.

class 1, style 2 or 4 of PPP-B-621. Inside dimensions of the box shall be approximately 13-1/2 inches in length, 12-1/2 inches in width, and 15-1/2 inches in depth. Each box shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

5.2.2.1 Weather-resistant shipping container. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of PPP-B-636.

5.2.3 Commercial packing. Hooks with thimbles preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Palletization. When specified (see 6.2), hooks with thimbles packed as specified in 5.2.2 and 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet types shall be type I (4-way entry), type IV or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means C and D or film bonding means F or G. Pallet pattern shall be number 11 in accordance with the appendix of MIL-STD-147.

5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The tent hooks with thimbles are intended for use with guy lines in the erection of tents.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
c. When a first article is required (see 3.1, 4.3, and 6.3).
d. Levels of preservation and packing (see 5.1 and 5.2).
e. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
f. When palletization is required (see 5.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:36Z
Check the source to verify that this is the current version before use.

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of Federal Acquisition Regulation (FAR) 52.209-4. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4 Subject term (key word) listing.

Anchor
Erection
Ground
Shelter

6.5 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Preparing activity:

Army - GL

(Project 8340-0540)

Review activities:

Air Force - 82
DLA - CT

User activity:

Navy - YD

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:36Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-H-1679F	1992 January 13

3. DOCUMENT TITLE

HOOK, TENT; WITH THIMBLE, FOR GUY LINE, ASSEMBLY TENT

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON/DSN
U.S. Army Natick RD&E Center	508-651-4531	256-4531
c. ADDRESS (Include Zip Code) Commander, U.S. Army Natick RD&E Center ATTN: STRNC-UXT Natick, MA 01760-5017	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T13:36Z
Check the source to verify that this is the current version before use.