MIL-B-82647(OS)
26 March 1976

SUPERSEDING
WS11555
25 February 1969

MILITARY SPECIFICATION

BAG, CONDUCTIVE PLASTIC, HEAT-SEALABLE, FLEXIBLE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1 SCOPE

1.1 This specification covers the requirements for a flexible, heat-sealable, conductive plastic bag.

2 APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein:

SPECIFICATIONS

Military

MIL-P-82646	Plastic Film, Conductive, Heat-sealable, Flexible

STANDARDS

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	Marking for Shipment and Storage

(Copies of specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procurement activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

FSC 8105

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:19Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM D 882 Tensile Properties of Thin Plastic Sheeting

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N.W., Washington, DC 20036.)

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification

(Application for copies should be addressed to Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies)

3 REQUIREMENTS

3.1 Material. The bags shall be fabricated from flexible, heat-sealable, conductive plastic film meeting the requirements of MIL-P-82646.

3.2 Construction. Bags shall be formed of tubular stock or by folding one sheet or from two sheets. Bags formed from tubular stock shall consist of a bottom seal. Bags formed by folding one sheet shall consist of two side seals or one side seal and a bottom seal. Bags formed from two sheets shall consist of two side seals and a bottom seal. Seal width, method of sealing, and seal strength shall meet the requirements of MIL-P-82646.

3.3 Dimensions. The width, length, and thickness of the bag shall be as specified by the procuring activity. Bag dimensions shall be inside measurements, exclusive of seals or seams. The opening of the bag shall be the first dimension specified. Width and length dimensions of the bag are in layflat condition and the thickness is the material thickness. Unless otherwise specified by the procuring activity, tolerances of width shall be minus 0 plus 3/8 inch, and of length, minus 0 plus 1 inch.

3.4 Identification. Identification marking on each bag shall be in accordance with MIL-P-82646.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:19Z
Check the source to verify that this is the current version before use.

3.5 Continuity of seam and seam strength. The seam breaking strength shall be in accordance with MIL-P-82646. The seals or seams shall be of high integrity and continuous.

3.6 Workmanship. The bags shall be uniformly constructed, free of pinholes, tears, cuts, sharp creases, wrinkles, or other imperfections which might impair usefulness. Bags shall not adhere to the extent that tearing of the material occurs when the bag is opened. The bags shall not leak when examined in accordance with 4.4.1

4 QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Quality conformance inspection. The quality conformance inspection shall consist of the examination of 4.4 and the test of 4.5.

4.3 Sampling for lot acceptance.

4.3.1 Lot. A lot shall consist of all bags made from one lot of material, by the same process, by one manufacturer, at one plant and offered for delivery at one time.

4.3.2 Sampling for examination. Sampling for examination shall be in accordance with MIL-STD-105, inspection level II, table II, single sampling, normal inspection.

4.3.3 Sampling for test. Sampling for test shall be in accordance with MIL-STD-105, inspection level S-3, table II, single sampling, normal inspection.

4.4 Examination. Sample bags shall be visually inspected to verify conformance with this specification. The Acceptable Quality Level (AQL) shall be 2.5% defective. Defect classification shall be in accordance with Table I.

4.4.1 Examination for leaks. Each bag selected in accordance with 4.3.2 shall be examined for leaks. The bag shall be supported on a flat surface and filled to 50% capacity (up to 5 gallons maximum) with water. Each leak detected within 5 minutes shall be counted as one defect.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:19Z
Check the source to verify that this is the current version before use.

Table I Types of Defects

Examine	Defects
Material	Bags not fabricated from material conforming to MIL-P-82646.
Workmanship	Not uniformly constructed - Any pinhole, leak (see 4.4.1) Any tear, cut, or sharp crease Excessive wrinkles. Bags sticking together to the extent that opening causes tearing or injury to inner surface.
Construction	Required seams not sealed. Seal not continuous. Edges of seams not parallel with each other.
Identification markings	Illegible, incorrect, or incomplete. Marking on bags not in compliance with those specified in MIL-P-82646.
Size of bags	Width, length or thickness not as specified. Width or length tolerance not as specified.

4.5 Test. Each bag selected in accordance with 4.3.3 shall be subjected to the following test:

4.5.1 Seam breaking test. Two speciments from each seam or seal comprising the sample bag shall be tested in accordance with ASTM D 882 with the following exceptions.

(a) The width of the specimen shall be 1 inch.
(b) The initial jaw separation shall be 2 inches and the seam shall be equidistant from each jaw of the testing machine.
(c) The crosshead speed shall be 2 inches per minute. Failure of any specimen to meet the requirement of 3.5 shall be cause for rejection of the lot.

4.6 Rejection and retest. Lots which have been rejected may be reworked or replaced to correct the defects and resubmitted for acceptance. Before resubmitting, full particulars concerning previous rejection and the action taken to correct the defects found in the original shall be furnished the inspector in writing. Bags rejected after retest shall not be resubmitted without the specific approval of the procuring activity.

5 PACKAGING

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:19Z
Check the source to verify that this is the current version before use.

5.1 Packaging. Unless otherwise specified, packaging shall be Level C. (See 6.2).

5.1.1 Level C. Packaging shall conform to manufacturer's commercial practice.

5.2 Packing. Unless otherwise specified, packing shall be Level C.

5.2.1 Level C. Bags shall be packed in a manner to insure safe delivery and acceptance upon arrival. Containers and methods of shipment shall comply with the Uniform Freight Classification or other carrier regulations applicable to the mode of transportation.

5.3 Marking. Unit packages and shipping containers shall be marked for shipment in accordance with MIL-STD-129 and as follows:

"Bags, Conductive Plastic, for Ordnance Packaging Applications
KEEP COOL AND DRY"

6 NOTES

6.1 Intended use. Conductive plastic bags in accordance with this specification are intended to be used for the protection and handling of special ordnance material, propellants and explosives, where conductive properties, protection from solids contamination, resistance to nitroglycerine, and waterproofing characteristics are of paramount importance.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification
(b) Quantity required.
(c) Size of bag (inside dimensions) and thickness of film material (See 3.3).
(d) Levels of packaging and packing desired (See 5.1 and 5.2).

Custodian
Navy - OS

Preparing Activity
Navy - OS
Project No. 8105-N264

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:19Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil - Downloaded: 2025-12-28T07:19Z
Check the source to verify that this is the current version before use.