MIL-C-82128(MC)
8 June 1966
SUPERSEDING
(see 6.4)

MILITARY SPECIFICATION

CLOTH, SATIN, RAYON: CUPRAMMONIUM, SCARLET

1. SCOPE

1.1 Scope. - This specification covers the requirements for one type of rayon satin cloth.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

CCC-T-191	- Textile Test Methods
PPP-P-51	- Packaging, Packing, And Marking Of Textile Fabrics (Woolens, Worsteds, Cottons, Silks, And Synthetics).

STANDARDS

FEDERAL

FED. STD. NO. 4	- Glossary Of Fabric Imperfections

MILITARY

MIL-STD-105	- Sampling Procedures And Tables For Inspection By Attributes

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. - The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations under the Textile Fiber Products Identification Act, effective March 3, 1960

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:43Z
Check the source to verify that this is the current version before use.

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D. C. 20580.)

3. REQUIREMENTS

3.1 Standard sample. - When a standard sample is available, the cloth shall match the standard sample for shade and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.2 Preproduction sample approval. - Unless otherwise specified (see 6.2), before production is commenced, a sample of the finished cloth shall be submitted, or made available, to the contracting officer or his authorized representative for approval. The approval of the preproduction sample authorizes the commencement of production but does not relieve the supplier of responsibility for compliance with all applicable provisions of the specification. The preproduction sample shall be manufactured by the supplier in the same facilities to be used for the manufacture of the production items.

3.3 Materials.

3.3.1 Yarns. - The warp and filling yarns shall be made of continuous filament, containing not less than 30 filaments each for warp and filling. The material used in the manufacture of the yarns shall be of the cuprammonium rayon process.

3.4 Physical requirements. - The finished cloth shall conform to the physical requirements listed below:

Width, inches (inclusive of selvages)	40-1/4 ± 1/8
Weave	5 harness warp satin counter of 2
Weight, oz/sq. yd.	4.2 min. 5.0 max.
Texture (threads per inch):	
-warp	240 minimum
-filling	88 minimum
Breaking strength, pounds (dry):	
-warp	100 minimum
-filling	65 minimum
Breaking strength, pounds (wet):	
-warp	50 minimum
-filling	35 minimum

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:43Z
Check the source to verify that this is the current version before use.

3.5 Color. - The color shall be Marine Corps scarlet, shade M-2504, yarn dyed, and shall match an approved shade standard (see 6.3). The use of sulphur dyes is prohibited.

3.5.1 Matching. - The color shall match the approved standard shade under natural (north sky) daylight or artificial light having a color temperature of 7500° Kelvin and shall be a good approximation to the standard shade under incandescent lamplight at 2800° Kelvin.

3.5.2 Colorfastness.- The dyed material shall show good fastness to laundering, wet (dry) cleaning, water and perspiration and fair fastness to crocking when tested as specified in Table I.

3.6 Finish. - The finish shall be equal to standard sample.

3.7 Roll length and identification ticket. - The minimum length acceptable at contract price will be 40 yards in one continuous piece (see 6.2). The pieces shall be put into rolls and ticketed as specified in PPP-P-51.

3.8 Fiber identification. - Each roll shall be labeled, ticketed, or invoiced for fiber content in accordance with the rules and regulations of the Textile Fiber Product Identification Act effective March 3, 1960.

3.9 Workmanship. - The finished cloth shall conform to the quality and grade of product established by this specification. The demerit points per 100 square yards when calculated as specified in section 4 shall not exceed the established maximum point value.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. - Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Inspection. - Except when otherwise specified, inspection shall be in accordance with the provisions of MIL-STD-105.

4.2.1 Preproduction sample inspection. - When required, the preproduction sample, submitted in accordance with 3.2, shall be visually examined for appearance, color and finish. In addition, the sample shall be tested for physical and chemical characteristics specified in Table I in accordance with the referenced test methods.

4.2.2 Examination of the end item. - Defects found during examination shall be classified in accordance with 4.2.2.1 through 4.2.2.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:43Z
Check the source to verify that this is the current version before use.

4.2.2.1 Yard-by-yard examination. - Thirty yards from each roll in the sample shall be examined on the face side. The number of rolls from which the sample yardage shall be extracted shall be in accordance with the following:

Lot size (yards)	Sample size (rolls) 1/
3200 or less	10
3201 up to and incl. 10,000	15
10,001 and over	25

1/ No more than one roll shall be taken from any shipping container unless the number of shipping containers in the lot is less than the required number of rolls, in which case all shipping containers shall be present in the sample. All defects as defined in Section III of FED. STD. NO. 4, which are clearly noticeable at normal inspection distance (3 feet), shall be scored and assigned demerit points as listed in 4.2.2.1.1. No linear yard (increment of one yard on the measuring device of the inspection machine) shall be penalized more than 4 points. The lot shall be unacceptable if the points per 100 square yards exceed 5.0 points. Point computation shall be as follows:

$$\frac{\text{Total points scored in sample size} \times 3,600}{\text{Contracted width of cloth (inches)} \times \text{sample size (yards)}} = \text{Points per 100 sq. yds.}$$

4.2.2.1.1 Demerit points. - Demerit points shall be assigned as follows:

For defects 3 inches or less in any direction - one point

For defects exceeding 3 inches, but not exceeding 6 inches in any dimension - two points

For defects exceeding 6 inches, but not exceeding 9 inches in any dimension - three points

For defects exceeding 9 inches in any dimension - four points

Note: The following defects when present shall be scored four points for each yard in which they occur:

Baggy, ridgy, or wavy cloth.
Objectionable odor.
Width of cloth not within specified tolerance.
Poor dye penetration, mottled, streaky or cloudy.

4.2.2.2 Examination for length. -

4.2.2.2.1 Individual rolls. - During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than two yards below the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:43Z
Check the source to verify that this is the current version before use.

4.2.2.2.2 Total yardage in sample. - The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of lengths marked on the ticket.

4.2.2.3 Examination for shade. - During the yard-by-yard examination, each roll in the sample shall be examined for shade. Any roll in the sample off-shade, shaded side to side, side to center, or end to end shall be cause for rejection of the entire lot represented by the sample.

4.2.2.4 Examination for identification of preshrinkage process and compliance with Textile Fiber Products Identification Act. - During the yard-by-yard examination, each roll in the sample shall be examined for these defects. The lot shall be unacceptable if two or more rolls in the sample contain identification of the preshrinkage process by name or trademark on the cloth or ticket, or are not labeled or ticketed in accordance with the Textile Fiber Products Identification Act.

4.3 Examination of preparation for delivery requirements. - An examination shall be made in accordance with the provisions of PPP-P-51 to determine that packaging, packing and marking requirements of section 5 of this specification are complied with.

4.4 Testing of the end item. - The method of testing specified in CCC-T-191, wherever applicable and as listed in Table I, shall be followed. The physical and chemical values specified in section 3 apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test method. All test reports shall contain the individual values utilized in expressing the final result. The sample unit shall be 2 continuous yards full width of the finished cloth. The sample size (number of sample units) shall be as shown in the table below. The lot size shall be expressed in units of 1 yard. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified.

Lot size (yards)	Sample size (units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:43Z
Check the source to verify that this is the current version before use.

Table I. - Test methods

Characteristic	Rqmt. para.	Test method	No. of deter. per Individual Unit	Results reported as:
Identification of				
-cuprammonium rayon	3.3.1	1520	1	Pass or fail
-filaments	3.3.1	Visual	1	Pass or fail
Weave	3.4	Visual	1	Pass or fail
Weight (oz. per sq. yd.)	3.4	5041	5	Avg. of the 5 det. to nearest 0.1 oz.
Texture (yarns per inch)				
-warp	3.4	5050	5	Avg. of the 5 det. to nearest whole number.
-filling	3.4	5050	5	
Breaking strength (dry)				
-warp	3.4	5100	5	Avg. of the 5 det. to nearest 1.0 lb.
-filling	3.4	5100	5	
Breaking strength (wet)				
-warp	3.4	5100	5	Avg. of the 5 det. to nearest 1.0 lb.
-filling	3.4	5100	5	
Colorfastness				
-laundering	3.5.2	5616	1	Good, fair or poor
-wet(dry) cleaning	3.5.2	5622	1	Good, fair or poor
-water	3.5.2	5630	1	Good, fair or poor
-crocking	3.5.2	5650	1	Good, fair or poor
-perspiration	3.5.2	5682	1	Good, fair or poor

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:43Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. - Packaging shall be level A or C, as specified (see 6.2).

5.1.1 Level A and C. - The cloth shall be put up on rolls and packaged in accordance with the requirements for class 2 fabrics of PPP-P-51.

5.2 Packing. - Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A, B or C. - The cloth shall be packed in accordance with requirements for class 2 fabrics of PPP-P-51.

5.3 Marking. - In addition to any special markings, specified in the contract or order, the shipping containers shall be marked in accordance with the requirements of PPP-P-51.

5.3.1 Nomenclature. - The nomenclature for item identification marking on the shipping container shall be as follows:

Cloth, Satin, Rayon: 5.0 oz. max. wt. per sq. yd.;
40-1/4 in. w; Marine Corps scarlet, M-2504.

6. NOTES

6.1 Intended use. - The cloth is intended for use in the manufacture of the evening dress jacket and cummerbund, worn by officers of the Marine Corps.

6.2 Ordering data. - Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Availability of the standard sample (see 3.1).
(c) Whether preproduction sample approval is required (see 3.2).
(d) Acceptance of short pieces (see 3.7).
(e) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 Samples. - For information regarding the availability of standard shade sample specified, address inquiry to the procuring activity issuing the invitation for bids.

6.4 Supersession data. - This specification includes the requirements for Marine Corps Purchase Description PD-31 (MCCD) dated 8 October 1956, for Cloth, Cuprammonium Rayon, Satin: Scarlet.

Custodian:
Navy-MC

Preparing Activity:
Navy-MC

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:43Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

SPECIFICATION

ORGANIZATION *(Of submitter)* | CITY AND STATE

CONTRACT NO. | QUANTITY OF ITEMS PROCURED | DOLLAR AMOUNT $

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)* | DATE

DD FORM 1 APR 63 1426

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:43Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY

POSTAGE AND FEES PAID
NAVY DEPARTMENT

Marine Corps Supply Activity
1100 South Broad Street
Philadelphia, Penna. 19146

OFFICIAL BUSINESS

Commanding General (826)
Marine Corps Supply Activity
1100 South Broad Street
Philadelphia, Pennsylvania 19146

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:43Z
Check the source to verify that this is the current version before use.