INCH-POUND

MIL-DTL-85361A
14 July 2010
SUPERSEDING
MIL-C-85361(AS)
20 February 1980

DETAIL SPECIFICATION

# CARRYING CASE ASSEMBLIES, INFLATABLE LIFE RAFT

This specification is approved for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 Scope. This specification covers the requirements for seven types of inflatable life raft carrying case assemblies.

1.2 Classification. Inflatable life raft carrying case assemblies will be of the following types, as specified (see 6.2):

| | | |
|---|---|---|
| Type I | - | Carrying Case Assembly, LRU-12/A Life Raft |
| Type II | - | Carrying Case Assembly, LRU-1/P Life Raft |
| Type III | - | Carrying Case Assembly, LRU-13/A Life Raft |
| Type IV | - | Carrying Case Assembly, LRU-14/A Life Raft |
| Type V | - | Carrying Case Assembly, For Droppable LRU-15/A and F-2B Life Rafts |
| Type VI | - | Carrying Case Assembly, For Wing installation of Twenty Man Life Rafts LRU-15/A |
| Type VII | - | Cover/Carrying Case Assembly, Twenty Man Life Raft (C-130 Aircraft) LRU-15/A |

Comments, suggestions, or questions on this document should be addressed to Defense Supply Center Philadelphia, ATTN: DSCP-NASA, 700 Robbins Avenue, Philadelphia, PA 19111-5096 or email to dscpg&ispecomments@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.daps.dla.mil.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

## 2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this standard or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in section 3 and section 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

MILITARY STANDARDS

| | |
|---|---|
| MIL-STD-130 | - Identification Marking of U.S. Military Property |
| MIL-STD-889 | - Dissimilar Metals |

(Copies of these documents are available online at https://assist.daps.dla.mil or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.2.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

NAVAIR DRAWINGS

| | |
|---|---|
| 62A82H5 | - Carrying Case Assembly, LRU-12/A Life Raft |
| 62A82H6 | - Carrying Case Assembly, LRU-1/P Life Raft |
| 62A82H601 | - Carrying Case Assembly, LRU-13/A Life Raft |
| 62A96H4 | - Carrying Case Assembly, LRU-14/A Life Raft |
| 63A80H6 | - Carrying Case Assembly, For Droppable LRU-15/A and F-2B Life Rafts |
| 63A80H13 | - Carrying Case Assembly, For Wing Installation of Twenty Man Life Rafts LRU-15/A |
| CL214D2 | - Cover Carrying Case Assembly, Twenty Man Life Raft (C-130 Aircraft) LRU-15/A |

(Copies of drawings are available from Naval Air Systems Command, 47123 Buse Rd STE IPT, Patuxent River, MD 20670-1547.)

2.3 Non-Government publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

AMERICAN SOCIETY FOR QUALITY (ASQ)



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

ASQ Z1.4 - Sampling Procedures and Tables for Inspection by Attributes

(Copies of this document are available from www.asq.org or the American Society for Quality, 611 East Wisconsin Avenue, Milwaukee, WI 53202.)

ASTM INTERNATIONAL

ASTM D6193 - Standard Practice for Stitches and Seams

(Copies of this document are available from www.astm.org or ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959.)

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained

## 3.REQUIREMENTS

3.1 First article. Unless otherwise specified, the carrying case assemblies furnished under this specification shall be products which have been inspected and passed the first article inspection specified in 4.2.

3.2 Material and components. The material and components shall conform to applicable specifications, standards, and drawings as listed or required herein (see 6.2). Materials and components which are not covered by applicable specifications, standards, or drawings, or are not specifically described herein, shall be of the lightest practicable, weight and entirely suitable for the purpose intended. Unless otherwise specified, the material and components, except for the metallic parts used in the fabrication of the carrying cases, shall have been manufactured not more than eighteen months prior to the date of delivery of the carrying case (see 6.2).

3.2.1 Metal parts. All metal parts shall be of a corrosion resistant material or treated in a manner to render them adequately resistant to corrosion.

3.2.2 Dissimilar metals: Unless suitably protected against electrolytic corrosion, dissimilar metals shall not be used in intimate contact with each other. Dissimilar metals are defined in MIL-STD-889.

3.3 Design.

3.3.1 Carrying case assemblies. The carrying case assemblies furnished under this specification shall conform to drawings 62A82H5, 62A82H6, 62A82H601, 62A96H4, 63A80H6, 63A80HS3, or CL214D2, as applicable (see 6.2).

3.3.2 Pull cable assemblies. Unless otherwise specified, the carrying cases conforming to drawings 62A82H5, 62A82H6, 62A82H601, 62A96H4, and 63A80H6, shall be provided with a pull cable assembly conforming to applicable drawing requirements.

3.4 Construction.

3.4.1 Cut edges. All the cut edges of the uncoated nylon fibrous materials, except for the base cloths which are to be coated, shall be seared prior to fabrication to prevent fraying. No sharp edges shall be formed by the searing process.

3.4.2 Use of the adhesive. In all the cementing operations, the surface to which the adhesive is applied shall be thoroughly cleaned with a suitable solvent in such a manner that the dusting material (talc) and



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

any other surface contaminant is removed. The surface shall be clean prior to cementing. Care should be exercised to insure that the coating and the base undercloth are not damaged, and the adhesion between both is not impaired in any way, or by prolonged exposure to the solvent. The solvent used shall evaporate completely prior to the application of the adhesive, and shall leave no residue. Cemented areas shall not contain trapped air, channels, or excessive wrinkling. The adhesive shall be controlled to insure that old adhesive, or adhesive that has partly or completely polymerized is not used. A fresh batch of the adhesive shall be used at least every eight hours during the course of manufacturing (see 4.3.1.1.2). Containers for the adhesive shall be free from congealed adhesive before being refilled.

3.4.3 Cementing of the seams, seam tapes, patches, and attachments. Seam construction and seam tape, patch, and attachment applications shall be in accordance with applicable drawing requirements. The techniques and precautions outlined in 3.4.2 shall be used in order to effect optimum bonding properties, and to ensure compliance with the requirements of this specification. The adhesive shall not be applied in a straight line parallel to the edges of the seam, seam tape; patch, or attachment; and shall extend from just being visible to a maximum of one inch beyond the applicable edge. The adhesive shall not be allowed to remain in clots or permitted to extend in such a manner as to result in localized stiffness. There shall be no spots or stains resulting from the cementing operation. The cemented areas shall not contain any trapped air, channels, edge lifts, or excessive wrinkling.

3.4.4 Seams and stitching. Unless otherwise specified, all the seams and stitching used in fabrication shall conform to applicable drawing requirements; and shall be accomplished with Stitch Type 301 conforming to ASTM D6193, with 6 to 10 stitches per inch. All the seam edges shall be properly forced out and shall not contain any folds. No seam shall be twisted, puckered, or pleated, and no part of the container shall be caught in an unrelated operation or seam. All the thread ends shall be trimmed to a length of 1/4 to 3/8 inch. Each row of stitching shall be straight and parallel to the seam edge. The straightness of the stitching, in any row, shall be maintained within a tolerance of 1/32 inch. The ends of the stitching that are not caught in other seams or stitching shall be securely backstitched, by overlapping on itself for at least 1/2 inch. Thread breaks, skips, and run-offs shall be overstitched not less than one inch. The thread tension shall be maintained so that there shall not be any loose or overly tight stitching, and the lock shall be imbedded in the materials sewn together. There shall be no spots or stains resulting from the sewing operation.

3.4.4.1 Bartacking. Unless otherwise specified, the number of stitches per bartack shall be based proportionally upon 7/8 inch long barracking containing a minimum of 49 stitches. The length and location of each bartack shall be as specified in applicable drawings.

3.5 Color. The color of the carrying case and components shall be as specified in applicable drawings.

3.6 Markings. Markings shall be in accordance with MIL-STD-130. Ink, color, size, and location of markings shall be as specified in applicable drawings. Letters and numerals 1/4 inch or less in height shall not be stenciled. Serial number for containers shall be in accordance with 3.6.1. All markings shall be thoroughly dry prior to packing or packaging. Markings may be applied directly to the specified area, or to a patch securely adhered to the specified area. Material and color of the patch, if used, shall be the same as the carrying case to which applied.

3.6.1 Serial numbers. Unless otherwise specified, each container shall be identified by a serial number which shall be assigned by the manufacturer. Serialization shall be by a block of consecutive number to cover the entire acquisition quantity.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

3.7 Visual. When inspected as specified in 4.4.1, the carrying case assemblies, including components, shall conform to the requirements of Paragraphs 3.2 through 3.6. The Classification of Defects for the Visual Examination of the Carrying Case Assemblies, Table II, shall be used to classify and enumerate the defects found.

3.8 Dimensional. When inspected as specified in 4.4.2, the dimensions of the carrying cases, including components; shall conform to applicable drawing requirements. The list of defects for finished dimensions of the carrying case assemblies, Table III, shall be used to classify and enumerate the defects found.

3.9 Performance inspections.

3.9.1 Strength of attachment of the pull cable assembly. When inspected as specified in 4.5.1, each locking pin, ball, swage, and loop shall withstand a pull of 100 pounds without slippage or deformation.

3.9.1.1 Permanent set of the locking pins. When inspected as specified in 4.5.1.1, each locking pin shall withstand a load of 8 pounds, without taking a permanent set.

3.9.2 Strength of attachment of the carrying case handles. When inspected as specified in 4.5.2, each handle shall withstand a pull of 250 pounds without tearing or separation.

3.10 Workmanship. After completion of the final assembly the carrying cases shall be thoroughly cleaned and all loose thread, lint, and foreign matter shall be removed. The grommets and snap fasteners shall be clinched without distortion, damage, splitting, or cutting of the cloth, webbing, or tape, as applicable. The metal components shall not be misaligned, nor shall they contain any sharp edge, crack, dent, burr, nick, or sliver. The carrying cases shall not contain any nonspecified hole, abraded area, tear, cut, mend, needle chew, spot, or stain. The carrying cases and components, furnished under this specification, shall conform to the quality and grade of the product as set forth in the specification. The occurrence of defects shall not exceed the acceptance criteria established herein.

4. VERIFICATION.

4.1 Classification of inspection. The examination and testing of the assemblies shall be classified as follows:

(a) First article inspection. First article inspection consists of examinations and tests performed on samples which are representative of the production item after award of a contract to determine that the production item conforms to the requirement of this specification (see 3.1, 4.2, 4.2.1, and 4.2.1.1).

(b) Conformance inspection. Conformance inspection consists of examinations and tests performed on individual products or lots to determine conformance of the products or lots with the requirements set forth in this specification (see 4.3 through 4.3.1.2).

4.2 First article inspection. The first article inspection of the carrying case assemblies shall consist of all the examination and tests for all the requirements of this specification.

4.2.1 First article samples. Unless otherwise specified, as soon as practicable after the award of the contract or order, the manufacturer shall submit two carrying case assemblies of the type specified in the contract or order. The samples shall be representative of the construction, workmanship, components, and materials to be used during production. When a contractor is in continuous production of the type specified, from contract to contract, submission of additional first article samples on the new contract may be waived at the discretion of the procuring activity (see 6.2). Approval of the first article inspection samples or the waiving of the first article inspection does not preclude the requirements for performing the conformance inspection. The first article inspection samples shall be furnished to the Government as directed by the contracting officer (see 6.2).



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

4.2.1.1 First article sample disposition. Upon completion of the first article inspection, recommendations and comments pertinent for use in monitoring production will be forwarded by the Government activity responsible for the inspection program (see 6.2) to the contracting officer. One of the approved first article samples will be returned to the manufacturer for reference in monitoring production. The other sample will be consumed or destroyed in the inspection program, and shall not be considered as a part of the quantity to be delivered under the contract.

4.3 Conformance inspection. The sampling and inspection levels shall conform to ASQ Z1.4. The conformance inspection shall consist of the following:

Pull cable assembly strength of attachment and permanent set

Visual examination of the carrying case assemblies

Dimensional examination of the carrying case assemblies

4.3.1 Sampling.

4.3.1.1 Inspection lot.

4.3.1.1.1 Carrying case assembly. An inspection lot size shall be expressed in units of one carrying case assembly and components of one type made essentially under the same conditions and from the same materials. The sample unit shall be one carrying case assembly and components of one specific type.

4.3.1.1.2 Adhesive. An inspection lot shall be expressed in units of one batch of adhesive. An inspection lot shall consist of all the batches of the adhesive used by the manufacturer during one day's production of the carrying case assemblies (see 3.4.2). The sample unit shall be one batch of the adhesive used during one day's production of the carrying case assemblies.

4.3.1.2 Sampling for examinations and tests of the carrying case assemblies and components. The sample size, examinations and tests required for the carrying case assemblies and components shall be as specified in Table 1. However, the Acceptance Quality Limit (AQL) shall be as specified in the contract.

4.4 Inspection methods.

4.4.1 Visual examination. Each carrying case assembly, including components, shall be visually examined for conformance to the requirements of paragraph 3.7.

4.4.2 Dimensional examination. Each carrying case assembly including components, shall be dimensionally checked for conformance to the requirements of paragraph 3.8.

4.5 Performance.

4.5.1 Strength of attachment of the pull cable assembly. The strength of attachment of each locking pin, ball, swage, and loop to the cable shall be determined by means of a suitable testing apparatus containing a fixed and movable jaw. The speed of the movable jaw, under no load, shall be 12 +1/2 inches per minute. To determine the strength of attachment of the locking pins, ball, and swage, insert the cable in the fixed jaw and the item being tested in the movable jaw and apply a load of 100 pounds. When testing the loop, insert a metal rod through the loop prior to attachment to the movable-jaw. The items tested shall conform to the requirements of paragraph 3.9.1.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

TABLE I. Sample size, examinations and tests of the carrying case assemblies.

| Inspection | Paragraph | | Sample size 1/ |
|---|---|---|---|
| | Requirement | Method | |
| Pull cable assembly, strength of attachments and permanent set | 3.9.1 and 3.9.1.1 | 4.5.1 and 4.5.1.1 | Inspection Level S-1 |
| Visual examination | 3.2 through 3.7 and applicable drawings | 4.4.1 | Inspection Level II |
| Dimensional check | 3.8 and applicable drawings | 4.4.2 | Inspection Level S-3 |

1/ This inspection may be performed either at the contractor's or subcontractor's plant.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

TABLE II. Classification of defects for the visual examination of the carrying case assemblies.

| Defects | Major | Minor |
|---|---|---|
| a. Any weakening defect such as smash, multiple float, loose slub, needle chew, or abraded area: | | |
| (1) Seriously affecting serviceability or appearance | X | |
| (2) Not seriously affecting serviceability or appearance | | X |
| b. Color of any component not as specified or contains one or more shade bars | | X |
| c. Any thread end not trimmed to a length of 1/4 to 3/8 inch or loose thread ends | | X |
| d. Any spot or stain: | | |
| (1) Seriously affecting serviceability or appearance | X | |
| (2) Not seriously affecting serviceability or appearance | | X |
| e. Any non-specified hole, cut, tear, mend or burn. | X | |
| f. Any cut edge of the uncoated nylon fibrous materials not seared or contains sharp edges | X | |
| Metallic components. | | |
| a. Any surface rough, misaligned, or contains any crack, nick, burr, sharp edge, dent, or sliver | X | |
| b. Any surface unclean or contains embedded foreign matter | | X |
| c. Any loose, detached, or otherwise not securely retained | X | |



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

TABLE II (Continued)

| Defects | Major | Minor |
|---|---|---|
| Metallic components (cont'd) | | |
| d. Any malformed, corroded, fractured, broken, chipped, bent, or distorted | X | |
| e. Any improperly finished: | | |
| (1) Affecting serviceability or appearance | X | |
| (2) Not affecting serviceability or appearance | | X |
| f. Any snap fastener or grommet misplaced or improperly clinched resulting in cutting of the cloth, tape, or webbing, as applicable | X | |
| g. Any snap fastener mismated or failing to function properly when snapped closed and unsnapping each of the snap fasteners at least three times | X | |
| h. Any part of the slide fastener assembly bent, broken, or the movement of the slider interfered with when checked for proper function by opening and closing the slide fastener at least three times, along its entire length | X | |
| Components and assembly | | |
| a. Any component not as specified or any defect of a component or defect of assembly not herein classified: | | |
| (1) Affecting serviceability or appearance | X | |
| (2) Not affecting serviceability or appearance | | X |
| b. Any component, component part, or required operation omitted or any operation improperly performed not herein classified: | | |
| (1) Affecting serviceability or appearance | X | |
| (2) Not affecting serviceability or appearance | | X |



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

TABLE II (Continued)

| Defects | Major | Minor |
|---|---|---|
| Seams and stitching | | |
| a. Accuracy of seaming: | | |
| (1) Any seam, hem, or attachment of any component twisted, puckered, pleated, or caught in an unrelated operation or stitching any seam edge not properly forced out or contains any fold | | X |
| (2) Ends of stitching that are not caught in other seams or stitching: | | |
| (a) Not securely back stitched | X | |
| (b) Secure but backstitched for a distance less than 1/2 inch or the backstitching is not overlapped on itself | | X |
| (3) Thread breaks: | | |
| (a) Not securely over stitched | X | |
| (b) Secure but overstitched for a distance less than one inch | | X |
| b. Gage of stitching: | | |
| (1) Any stitching irregular, unevenly gaged or various stitching not uniform when observed on major portion of the seam | | X |
| c. Open seams 1/: | | |
| (1) 1/2 inch or less | | X |
| (2) More than 1/2 inch | X | |
| d. Raw edges 2/: | | |
| (1) More than 1/4 inch but not more than one inch | | X |
| (2) More than one inch | X | |



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

TABLE II (Continued)

| Defects | Major | Minor |
|---|---|---|
| Seams and stitching (cont'd) | | |
| e. Seam and stitch type: | | |
| (1) Not specified seam or stitch type | X | |
| f. Stitch tension 3/: | | |
| (1) Loose tension resulting in a loose seam or tight tension resulting in breaking of stitches when normal pull is applied | X | |
| g. Stitches per inch (only when condition exists on the major portion of the seam): | | |
| (1) Stitches more or less than specified: | | |
| (a) One or two stitches | | X |
| (b) More than two stitches | X | |
| Cementing operations | | |
| a. Any cementing operation not in accordance with requirements: | | |
| (1) Seriously affecting serviceability or appearance. | X | |
| (2) Not seriously affecting serviceability or appearance | | X |
| b. Any void or channel in any cementing operation: | | |
| (1) Seriously affecting serviceability or appearance | X | |
| (2) Not seriously affecting serviceability or appearance | | X |
| c. Excessive wrinkling in any cementing operation | | X |
| Markings | | |
| a. Missing, incomplete, incorrect, illegible, or improperly located | | X |
| b. Ink not adhere to surface or easily flakes off" | X | |

1/ A seam shall be classified as open, when one or more stitches joining a seam are broken or when two or more continuous skipped stitches or runoffs occur. On double stitched seams, a seam is considered open, when either one or both sides of the seam is open.

2/ Any edge that should be turned under and is not, but is securely caught in the stitching, shall be classified as a raw edge. Any raw edge not securely caught in the stitching shall be classified as an open seam.

3/ Puckering is evidence of tight tension or gathering of the material. When puckering is evident, other than the gathering of the material, the seam or hem, as applicable shall be tested by exerting normal pull in



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

the lengthwise direction of the seam, hem, or stitching. Gathering of the material shall be recorded as a puckered seam or hem, as applicable.

TABLE III. List of defects for finished dimensions of the carrying case assemblies.

| Examine | Defect |
|---|---|
| Measure the container, and all the visible components, as applicable. | Any measurement deviating from the dimensions and tolerances as specified in 3.8, 4.4.2, and applicable drawings shall be enumerated as a dimensional defect. |

4.5.1.1 Permanent set of the locking pins. The permanent set of the locking pins shall be determined in accordance with Figure 1. Under a load of 8 pounds, the locking pins shall be observed for conformance to the requirements of paragraph 3.9.1.1.

4.5.2 Strength of attachment of the carrying case handles. The attachment of the handles to the carrying case shall be inspected for strength of attachment in a suitable testing apparatus having a fixed jaw and a movable jaw. The speed of the movable jaw, under no load, shall be 12 ±1/2 inches per minute. The direction of pull shall be perpendicular to the point of attachment. The handle being tested shall be subjected to a load of 250 pounds and observed for conformance to the requirements of paragraph 3.9.2.

## 5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the military service's System Commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

## 6. NOTES

6.1 Intended use. The carrying case assemblies covered by this specification are intended to be used as a convenient means of protecting and carrying multi-place inflatable life rafts that are used by aircrewmen to enhance their chances of survival in the event of ditching at sea.

6.2 Ordering data. Acquisition documents should specify the following:

(a) Title, number, and date of this specification, including any revisions or amendments

(b) Type, Government part number, and quantity desired.

(c) Applicable drawings, including revisions (see 3.3).

(d) Whether First Article Inspection is waived (see 4.2.1).



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.

(e) Name and address of First Article Inspection Laboratory (see 4.2.1), and the name of the Government activity responsible for conducting the First Article Inspection Program (see 4.2.1.1).

(f) Packaging requirement (see 5.1).

(g) Certificate of compliance for:

(1) Material and components conforming o applicable Specifications, standards, and drawings (see 3.2).

(2) The age of the materials and components (see 3.2).

6.3. Data. For the information of Contractors and Contracting Officers, any of the data specified in applicable documents listed in Section 2 of this specification, or referenced lower-tier documents need not be prepared for the Government, and will not be furnished to the Government unless specified in the contract or order. The data to be furnished will be listed on DD Form 1423 (Contractor Data Requirements List), which will be attached to, and made a part of, the contract or order.

6.4 First article. When a first article is required (see 6.2), it should be inspected and approved under the appropriate provisions of Federal Acquisition Regulation (FAR) 52.209. The first article should be a preproduction sample. The contracting officer should include specific instructions in all acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.5 Subject term (key word) listing.

Seams
Stitching
Survival equipment

6.5 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.





FIGURE 1. Inspection procedure for permanent set of locking pins

Custodian:
Navy - AS

Preparing activity:
DLA - IS

(Project 4220-2010-002)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST online database at https://assist.daps.dla.mil.



Source: https://assist.dla.mil -- Downloaded: 2026-10-23T10:44Z
Check the source to verify that this is the current version before use.