INCH-POUND
MIL-R-24730
27 April 1990

MILITARY SPECIFICATION

ROPE, FIBROUS POLYESTER, EIGHT STRAND PLAITED

This specification is approved for use by the Naval Sea Systems Command, Department of the Navy, and is available for use by all departments and agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements of eight strand plaited polyester rope.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards and handbooks. The following specifications, standards and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

PPP-F-320	Fiberboard: Corrugated and Solid, Sheet Stock (Container Grade), and Cut Shapes
UU-T-81	Tags, Shipping, and Stock

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, Naval Sea Systems Command, SEA 55Z3, Department of the Navy, Washington, DC 20362-5101 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 4020

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202640-20T01:32Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-C-3131	Cordage, Packaging of
MIL-L-17331	Lubricating Oil, Steam Turbine and Gear, Moderate Service
MIL-L-19140	Lumber and Plywood, Fire-Retardant Treated

STANDARDS

FEDERAL

FED-STD-191	Textile Test Methods

MILITARY

MIL-STD-105	Sampling Procedure and Tables for Inspection by Attributes

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, BLDG 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.2 Non-Government publications. The following document(s) forms a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 885	Standard Methods of Testing of Tire Cords, Tire Cord Fabrics, and Industrial Filament Yarns Made from Man-Made Organic-Based Fibers
D 1141	Standard Specification for Substitute Ocean Water; (DOD adopted)
D 1577	Standard Test Method for Linear Density of Textile Fibers
D 2257	Standard Test Method for Extractable Matter in Yarns; (DOD adopted)
D 2258	Standard Practice for Sampling Yarn for Testing
D 4268	Standard Methods of Testing Fiber Ropes

Source: https://assist.dla.mil -- Downloaded: 202610-20T01:32Z
Check the source to verify that this is the currentversion before use.

(Applications for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.4), in accordance with 4.3.

3.2 Materials. The material used in the rope shall be bright, virgin, continuous filament polyester fiber of at least 8.0 grams per denier tenacity, and not less than 4 but not more than 20 denier per filament. Polyester fiber is a long chain synthetic polymer composed of at least 85 percent by weight of an ester of a substituted aromatic carboxylic acid, including but not restricted to substituted terephthalate units and para-substituted hydroxy-bensoate units. Mixture of polyester fiber types shall not be employed in any one rope.

3.3 Construction. The ropes shall be made of eight strands arranged in four pairs, where one individual strand shall be laid adjacent to the second strand in each pair and shall conform to the requirements specified herein. Sizes 3/4 through 4-1/2 inch circumference, inclusive, may be made with single yarn construction; sizes 5-inch and larger shall be made with three-ply yarn construction. Individual strands shall be made of one size yarn and shall have an equal number of yarns. The single yarns shall be made from group filaments conforming to the sizes specified in table I for the respective sizes of rope.

TABLE I. *Construction*

Rope size (circumference) (inches)	Turns per feet (ft) (minimum)	Denier of single yarns
3/4 to 4-1/2	8	5,000 – 35,000
5 to 8	11	15,000 – 35,000
9 to 16	11	18,000, minimum

3.3.1 Preparation. In the preparation of the constituent rope strands, the "SZS" pattern shall be employed in the twisting of the singles yarns, the three-ply yarns and the individual strands of two pairs, while components of the remaining pairs shall be twisted in the "ZSZ" pattern. For single yarn construction the pattern shall be "ZS" and "SZ".

Source: https://assist.dla.mil -- Downloaded: 20260-20T01:32Z
Check the source to verify that this is the currentversion before use.

3.3.2 Finished rope. The finished rope shall be so constructed that in the interweaving procedure, pairs of strands of the former structure shall be twisted in the "Z" direction, while alternating pairs of the latter structure shall be twisted simultaneously in the "S" direction. Heat setting of the rope or any of its twisted components (with the exception of fibers) shall not be permitted (see 6.3).

3.4 Physical requirements. The finished rope shall conform to the physical properties specified in table II. The circumference shall be as specified (see 6.2) and in accordance with table II.

TABLE II. *Physical properties.*

Nominal Cir. at load P (inches)	Tolerance plus or minus (inches)	Nominal diameter (inches)	Load P 200 D^2 (pounds)	Hardness (minimum)	Linear density +5 percent −0 percent (pounds/100 ft)	Minimum breaking strength (pounds)
3/4	1/16	1/4	13	5	2.0	2,000
1	1/16	5/16	20	5	3.1	3,100
1-1/8	1/16	3/8	28	5	4.5	4,500
1-5/16	1/16	7/16	38	5	6.2	6,000
1-1/2	1/16	1/2	50	5	8.0	7,700
1-3/4	1/16	9/16	63	5	10.2	9,700
2	1/8	5/8	78	5	13.0	12,100
2-1/4	1/8	3/4	113	5	17.5	15,200
2-1/2	1/8	13/16	132	5	20.6	18,800
2-3/4	1/8	7/8	153	5	25.0	21,800
3	3/16	1	200	20	30.4	26,700
3-1/2	3/16	1-1/8	253	20	40.0	35,900
3-3/4	3/16	1-1/4	313	20	46.4	40,200
4	3/16	1-5/16	345	20	52.5	45,600
4-1/2	1/4	1-1/2	450	20	67.0	56,900
5	1/4	1-5/8	528	20	82.0	69,500
5-1/2	1/4	1-3/4	613	20	98.0	82,000
6	5/16	2	800	20	118	97,200
6-1/2	5/16	2-1/8	903	20	135	112,000
7	3/8	2-1/4	1,013	20	157	129,000
7-1/2	3/8	2-1/2	1,250	20	181	149,000
8	7/16	2-5/8	1,378	20	204	167,000
9	7/16	3	1,800	20	258	208,000
10	1/2	3-1/4	2,113	20	318	255,000
11	9/16	3-1/2	2,450	20	384	306,000
12	5/8	4	3,200	20	454	365,000
13	3/4	4-1/4	3,613	20	540	429,000
14	3/4	4-1/2	4,050	20	630	496,000
15	3/4	5	5,000	20	720	570,000
16	3/4	5-1/4	5,513	20	820	638,000

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:32Z
Check the source to verify that this is the current version before use.

3.4.1 Elongation. The elongation of the ropes shall not exceed 45 percent at the breaking strength (see 4.6.5). The load elongation curve, drawn autographically, shall not exhibit evidence of sudden changes in load applications greater than 5 percent of the load weighed at the instant of change. Changes due to splice slippage shall not be considered in this determination.

3.4.2 Hardness. The finished rope shall meet the minimum hardness specified in table II (see 4.6.10).

3.5 Finish. No extraneous material shall be added for the purpose of weighing the rope. The extractable matter of the finished rope shall not exceed 4.0 percent (see 4.6.6).

3.6. Moisture content. The moisture content of the rope shall not exceed 4.0 percent (see 4.6.8).

3.7 Spliceability. The finished ropes shall be spliceable and shall not develop yarn displacement or strand cockles (distortion formed by a back twist in the strand), when spliced in accordance with 4.6.9.

3.8 Identification marker. The manufacturer shall identify his product by inserting a kraft paper or water repellent cotton marker within one strand in all ropes 2 1/4 inches in circumference and larger. The marker shall be completely enveloped by the cover yarns in the strand in which enclosed. Unless otherwise specified (see 6.2), the manufacturer's name, year of manufacture, and type fiber (polyester), shall be clearly printed on the marker. Italic or script type shall not be used. The printing shall not be affected upon exposure to water or mineral oil (see 4.6.7).

3.9 Identification ticket. In addition to the requirements specified in 3.8, a ticket (identification tag), shall be attached to each package unit. The ticket shall be in accordance with type B, class 1, size 4 or 5, and 15 CSU grade designator of UU-T-81. The ticket shall be legibly printed, stamped, or typed with water insoluble ink. The ticket shall contain the following information:

a. Stock number
b. Nomenclature
c. Specification
d. Length
e. Contract number and date
f. Contractor's name
g. Year of manufacture

Source: https://assist.dla.mil -- Downloaded: 202610-20T01:32Z
Check the source to verify that this is the currentversion before use.

3.10 Put-up. Unless otherwise specified (see 6.2), the rope shall be furnished without strand or rope knots or splices on nonreturnable reels (spools) not larger than 7 ft in diameter in the lengths specified in table III. Multiple lengths will be permitted but no piece shall be less than 600 ft when measured in the relaxed condition (see 6.2). The rope shall be ordered by weight as specified (see 6.2). Delivered weight per reel shall be within plus 10 percent, minus 0 percent of weight specified in table III. The weight for lengths other than standard shall be determined in accordance with table III with the proper length ratio applied. The ends of all rope shall be cut off squarely and be securely whipped, taped or heat sealed to prevent fraying and untwisting. The reel (spools) shall be wound so that each turn and layer is free from entanglement.

TABLE III. *Put-up.*

Circumference (inches)	Standard length (ft)	Weight (pounds)
3/4	1,200	26
1	1,200	41
1-1/8	1,200	60
1-5/16	1,200	82
1-1/2	1,200	106
1-3/4	1,200	136
2	1,200	172
2-1/4	1,200	231
2-1/2	1,200	273
2-3/4	1,200	331
3	1,200	402
3-1/2	1,200	529
3-3/4	600	307
4	600	348
4-1/2	600	443
5	600	543
5-1/2	600	648
6	600	780
6-1/2	600	893
7	600	1,039
7-1/2	600	1,197
8	600	1,349
9	600	1,706
10	600	2,103
11	600	2,540
12	600	3,663
13	600	3,572
14	600	4,160
15	600	4,763
16	600	5,424

Source: https://assist.dla.mil -- Downloaded: 202640-20T01:32Z
Check the source to verify that this is the currenversion before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

(a) First article inspection (see 4.3)
(b) Quality conformance inspection (see 4.4).

4.3 First article inspection. First article inspection shall consist of the examinations specified in 4.5.1 and 4.5.2 and the test specified in 4.6 (see 6.3).

4.3.1 First article sample. The first article sample for ropes shall be a continuous finished length of 70 ft.

4.4 Quality conformance inspection. Quality conformance inspection shall consist of the examinations specified in 4.5.1 and 4.5.2 and the tests specified in 4.4.1 and 4.6 (Unless otherwise specified herein, the sample size shall be in accordance with MIL-STD-105).

4.4.1 Material and component inspection. Determination shall be made for all characteristics specified in table IV, except material. Results shall be either pass or fail (see 6.3). The linear density per filament and the tenacity of the fiber shall be determined in accordance with ASTM D 885, D 1577, and D 2258.

Source: https://assist.dla.mil -- Downloaded: 202610-20T01:32Z
Check the source to verify that this is the current version before use.

TABLE IV. *Component test.*

Characteristics	Requirement
Material	3.2
Denier per filament	3.2
Tenacity (grams per denier)	3.2
Denier (single yarns)	3.3
Turns per foot (single yarns)	3.3
Direction of twist (single yarns)	3.3.1
Direction of twist (plied yarns)	3.3.1
Direction of twist (strand)	3.3.2

4.5 Examinations.

4.5.1 Examination of the end item for visual defects. A lot size for examination for visual defects specified in table V shall be expressed in units of reels or spools each. Ten percent of the gross length contained on each unit of product, but not less than 100 ft shall be subjected to the visual examination. The inspection level shall be level I in accordance with MIL-STD-105. Any sample unit having one or more defects specified in table V shall be rejected. If any defects are noted in the original sample units, additional units shall be randomly selected and if any defects specified in table V are noted, the entire lot shall be rejected.

TABLE V. *Classification of defects.*

Categories	Defects
Critical: None defined	
	Appearance and workmanship
101	Cut, chafed or damaged affecting serviceability
102	Kinks, darting yarns[1], broken or loose ends, bulged strands, strands knots
103	Other than eight strands (four pair)
104	Ends not securely whipped, taped or heat sealed to prevent fraying or untwisting
	Identification marker[2]
105	Omitted, incorrect, illegible
106	Italic or script type used
107	Not completely covered by cover yarns
108	Not as specified

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:32Z
Check the source to verify that this is the current version before use.

TABLE V. Classification of defects – *Continued.*

Categories	Defects
Critical: None defined	
	Identification ticket
109	Omitted, incorrect, illegible, insecurely attached
110	Not as specified (hand written entries)
	Cleanliness
111	Spot or stain, clearly visible[3]
112	Objectionable odor

[1]Darting yarns are internal yarns which project through the cover yarns of the strand at intervals along the rope.
[2]Identification marker for 2 1/4 inches in circumference and larger.
[3]At normal inspection distance (approximately 3 ft).

4.5.2 Examination for length and winding. The sample unit for this examination shall be one reel or spool. The inspection level shall be 0 percent defective. The lot size shall be the number of units in the inspection lot. Defects shall be listed as specified in 4.5.2.1 and 4.5.2.2.

4.5.2.1 Defects with regard to length shall be considered to exist if any of the following are determined during inspection:

a. Length of unit less than specified (see 3.10)

b. Length of unit less than marked on ticket

c. Any piece less than 600 feet in length for sizes up to and including ropes of 16-inch circumference.

4.5.2.2 Defects with regard to winding shall be considered to exist if any of the following are determined during inspection:

a. Improperly or not firmly wound resulting in kinks, knots, entangling, or slippage during unwinding or otherwise affecting free unhampered unwinding of rope.

b. Knot, splice, or otherwise joining of ends to make a continuous length, except as noted in 3.10.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:32Z
Check the source to verify that this is the current version before use.

4.6 Testing of the end item. Testing of the end item shall be as specified in table VI and 4.6.2 through 4.6.10 (see 6.3). The physical and chemical values specified herein, apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The sample size shall be in accordance with inspection level I of MIL-STD-105 and shall be 0 percent defective. The unit for testing shall be 70 feet of rope. The lot size shall be expressed in units of reels or spools.

TABLE VI. *Test methods*[1]

Characteristics	Requirement	Test method	Number of determinations per individual unit of product	Results reported as:
Yarns per strand	3.3	Visual	1	Pass or fail
Direction of strand twist	3.3.1	4.4.1	1	Pass or fail
Circumference	3.4	4.6.2	3	Average of 3 determinations to nearest 1/16 inch
Linear density	3.4	4.6.3	1	See 4.6.3
Breaking strength	3.4	4.6.4	3	An accuracy of 1 percent
Elongation	3.4.1	4.6.5	3	Average of 3 determinations to nearest 0.1 percent
Hardness	3.4.2	4.6.10	3	Average of 3 determinations to nearest 1.0 ft
Extractable matter	3.5	4.6.6.	2	Average of 2 determinations to nearest 0.1 percent
Moisture content	3.6	4.6.8	2	Reported to nearest 0.1 percent
Spliceability	3.7	4.6.9	1	Pass or fail
Identification marker				
–Material	3.8	4.6.7		
–Fastness to oil and water	3.8	4.6.7	1	Pass or fail
Identification ticket				
–Material	3.9	(see 6.3)	1	Pass or fail

[1]Tests to determine compliance with specification requirements including quantity of delivery may be made under prevailing atmospheric conditions except in settlement of dispute in which case the tests shall be made upon material which has reached equilibrium under standard conditions as defined in ASTM D 4268.

Source: https://assist.dla.mil -- Downloaded: 202610-20T01:32Z
Check the source to verify that this is the current version before use.

4.6.1 Specimen preparation. The designated length and the number of test specimens shall be removed from the selected test reels in accordance with ASTM D 4268.

4.6.2 Determination of circumference. The circumference shall be measured in accordance with ASTM D 4268. Results shall be of three determinations to the nearest 1/16-inch.

4.6.3 Linear density. The linear density shall be determined in accordance with ASTM D 4268. Results shall be as follows:

Circumference (inches)	Degree of accuracy (Pounds per 100 feet)
Less than 1 3/4	Nearest 0.01
2 to 6	Nearest 0.10
6 1/2 to 12	Nearest 1.0
More than 12	Nearest 10.0

4.6.4 Breaking strength. Breaking strength determinations shall be conducted in accordance with ASTM D 4268. Results shall be the average to an accuracy of 1 percent. The load applied need not cause a failure provided that all individual tests exceed the specified minimum breaking strength specified in table II.

4.6.5 Elongation. The elongation at the minimum breaking strength shall be determined in accordance with the initial single loading procedure as specified in ASTM D 4268. The results shall be the average of the determination to the nearest 0.1 percent.

4.6.6 Extractable matter. The extractable content shall be determined in accordance with ASTM D 2257, using a Soxhlet apparatus in the procedure. Results shall be the average of two determinations to the nearest 0.1 percent.

4.6.7 Identification marker. Three lengths of the identification marker shall be used to determine the fastness of the printed matter of the identification marker to saltwater and mineral oil. Each length shall be approximately 1-1/2 feet. One length shall be retained as a control, one length shall be immersed for 2 hours in synthetic seawater conforming to ASTM D 1141, stock solution number 1, 2, or 3, and one length shall be soaked for 2 hours in mineral oil conforming to symbol 2190-TEP specified in MIL-L-17331. Following removal from the respective environments, the two exposed specimens shall be visually compared with the control specimen. The fastness of the printed matter shall be considered satisfactory when no perceptible change in color or legibility is observed.

4.6.8 Moisture content. The moisture content shall be determined in accordance with method 2600 specified in FED-STD-191. Results shall be the average of two determinations to the nearest 0.1 percent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:32Z
Check the source to verify that this is the current version before use.

4.6.9 Determination of spliceability. A breaking strength specimen shall be prepared and spliced at each end with four full double strand tucks. The specimen shall then be allowed to rest for 24 hours. Three of the tucks shall then be backed out of the rope. The portion of the rope from which the tucks are removed shall be examined for yarn displacement and strand cockles.

4.6.10 Hardness. The length of rope previously used in the weight determination shall be taped off each end. The tip of the 14-inch marlinspike, conforming to method 6020 specified in FED-STD-191, shall be started through the center of the rope so that two pairs of strands shall be visible on each side thereof. With the spike inserted, the rope shall be placed in a compression type testing machine in such a manner that the force necessary to push the spike through the rope will be measured with the rope in a relaxed state without tension and completely free to absorb the force of the penetrating spike. The rate of loading shall be 6 plus or minus (±) 1 inch per minute. Care shall be taken to ensure that the spike shall not be inserted less than 5 feet from an end and not less than 4 feet from an area which has been subjected to a previous hardness test. The load necessary to force to the nearest one pound the spike to the 1/2-inch diameter mark shall be measured on ropes up to and including 2-3/4 inch circumference and to the 1-inch diameter mark for larger size ropes. The marks shall be considered to be reached when the respective mark just disappears behind two pairs of strands.

4.7 Inspection of packaging. Sample packages, and the inspection of the preservation, packing, and marking for shipment, stowage, and storage shall be in accordance with the requirements of section 5 and the documents specified therein.

5. PACKAGING

(The packaging requirements specified herein apply only for direct Government acquisition. For the extent of applicability of the packaging requirements of referenced documents listed in section 2, see 6.8.)

5.1 General.

5.1.1 Navy fire-retardant requirements.

a. *Treated lumber and plywood.* When specified (see 6.2), all lumber and plywood including laminated veneer material used in shipping container, reel (spools), and pallet construction, members, blocking, bracing, and reinforcing shall be fire-retardant treated material conforming to MIL-L-19140 as follows:

Levels A and B	–	Type II – weather resistant Category 1 – general use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:32Z
Check the source to verify that this is the current version before use.

Level C	–	Type I – non-weather resistant Category 1 – general use

b. *Fiberboard.* When specified (see 6.2), fiberboard used in the construction of class-domestic, non-weather resistant fiberboard and cleated fiberboard boxes including interior packaging forms shall meet the flamespread index and the specific optic density requirements of PPP-F-320.

5.2 Packaging requirements. The packaging (preservation, packing and marking) requirements shall be in accordance with MIL-C-3131 for the level (A, C, or commercial) of preservation except as specified herein for 13 through 16-inch circumference rope; level (A, B, C, or commercial) of packing; and marking including packaging acquisitioning options as specified (see 6.2). For level A preservation of 13 through 16-inch circumference, rope, reels shall be constructed in accordance with the wood and plywood requirements specified in MIL-C-3131 and the following:

a. *Wood.*

(1) The thickness of the reel head boards shall be minimum 1-inch, two or three ply.

(2) The barrel shall consist of minimum 1 1/2 inch thick wood staves mortised into the reel heads.

(3) The reel shall be assembled with a minimum of five, 1/2-or 3/4-inch diameter steel bolts having cup washers on each end.

b. *Plywood.*

(1) 1-1/4 inch, two sheets of 3/4-inch, thick for net weights 700 through 1675 pounds; in addition, minimum of five 1/2-inch nuts and bolts shall be used for the flange and barrel assembly.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The rope covered by this specification is intended for use where relative freedom from torque deformation is required in addition to high strength and high elongation.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification

Source: https://assist.dla.mil -- Downloaded: 202640-20T01:32Z
Check the source to verify that this is the currentversion before use.

b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2)

c. When first article inspection is required (see 3.1)

d. Circumference size required (see 3.4)

e. When information on identification marker is other than specified (see 3.8)

f. Put-up and length when other than specified (see 3.10)

g. When multiple lengths per unit are not allowed (see 3.10)

h. Nominal continuous lengths of each unit (see 3.10)

i. When fire-retardant materials are required (see 5.1.1)

j. Levels of preservation, packing, and marking required (see 5.2)

k. That the purchaser will accept at original weight any unit which has been shortened or cut for test specimens, if in complete compliance with this specification. Reel shall be marked as to actual length.

l. That plaited polyester will be purchased on a price-per-pound basis-net weight.

6.3 Consideration of data requirements. The following data requirements should be considered when this specification is applied on a contract. The applicable Data Item Descriptions (DIDs) should be reviewed in conjunction with the specific acquisition to ensure that only essential data are requested/provided and that the DIDs are tailored to reflect the requirements of the specific acquisition. To ensure correct contractual application of the data requirements, a Contract Data Requirements List (DD Form 1423) must be prepared to obtain the data, except where DOD FAR Supplement 27.475-1 exempts the requirement for a DD Form 1423.

Reference Paragraph	DID Number	DID Title	Suggested Tailoring
3.2, 3.3.2, 3.10 and table VI	DI-E-2121	Certificate of compliance	–
4.3	DI-T-4902	First article inspection report	–
4.4.1 and 4.6	DI-R-5329	Inspection test reports	–

The above DIDs were those cleared as of the date of this specification. The current issue of DOD 5010.12-L, Acquisition Management Systems and Data Requirements Control List (AMSDL), must be researched to ensure that only current, cleared DIDs are cited on the DD Form 1423.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T01:32Z
Check the source to verify that this is the current version before use.

6.4 First article. When first article inspection is required, the contracting officer should provide specific guidance to offerors whether the item(s) should be a preproduction sample, a first article sample, a first production item, a sample selected from the first production items, a standard production item from the contractor's current inventory (see 3.1), and the number of items to be tested as specified in 4.3.1. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for examinations, approval of first article test results, and disposition of first articles. Invitations for bids should provide that the Government reserves the right to waive the requirement for samples for first article inspection to those bidders offering a product which has been previously acquired or tested by the Government, and that bidders offering such products, who wish to rely on such production or test, must furnish evidence with the bid that prior Government approval is presently appropriate for the pending contract. Bidders should not submit alternate bids unless specifically requested to do so in the solicitation.

6.5 Adjustment for high moisture content. Material furnished containing an excess of moisture will be accepted by an adjustment in weight to the 5-percent moisture basis.

6.6 Certificate of compliance. When a certificate of compliance is prepared, the following information should be included:

a. Conformance of material characteristics to the requirements specified herein (see 3.2)

b. Conformance to the requirement for heat setting of yarns or finished rope (see 3.3.2)

c. Conformance to the requirement for the mixing of fiber types, fiber grades, or fibers of different manufacturers within the rope (see 3.2).

6.7 Government or supplier purchases. The requirements specified in 3.8 and 3.9 apply only to plaited polyester rope purchased directly by the Government. All other requirements apply to plaited polyester rope purchased as a component for an end item by a supplier and to plaited polyester rope purchased directly by the Government.

6.8 Sub-contracted material and parts. The packaging or preparation for delivery referenced documents listed in section 2 do not apply when material and parts are acquired by the contractor for incorporation into the equipment and lose their separate identity when the equipment is shipped.

6.9 Subject term (key word) listing.

Splices
Strands
Yarns

Source: https://assist.dla.mil -- Downloaded: 202610-20T01:32Z
Check the source to verify that this is the current version before use.

Custodians:
Army – GL
Navy – SH
Air Force – 99

Review activities:
Navy – AS
Air Force – 82
DLA–DISC–ESA

User activities:
Navy – MC

Preparing activity:
Navy – SH
(Project 4020-0310)

☆U.S. GOVERNMENT PRINTING OFFICE: 1990 - 704-034/30611

Source: https://assist.dla.mil -- Downloaded: 202640-20T01:32Z
Check the source to verify that this is the current version before use.