MIL-H-9896C
12 August 1988
SUPERSEDING
MIL-H-9896B
31 March 1967

MILITARY SPECIFICATION

HARDWARE, UNIVERSAL LOAD CARRYING SLING

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers hardware for the universal, individual load carrying sling.

1.2 Classification. Hardware shall be of the following types as specified (see 6.2).

Type I - Buckle, quick adjustable slide, 1-3/4 inches
Type II - Buckle, quick adjustable slide, 1-3/4 inches, with eye and attached snap
Type III - Loop, slide, 1-3/4 inches
Type IV - Ring, V, with bar, 1-3/4 inches

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 5340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

QQ-A-250/8 - Aluminum Alloy 5052, Plate and Sheet
QQ-W-470 - Wire, Steel, Carbon, Spring, Music
TT-C-490 - Cleaning Methods for Ferrous Surfaces and Pretreatment for Organic Coatings
TT-P-1757 - Primer Coating, Zinc Chromate, Low-Moisture-Sensitivity
PPP-B-566 - Boxes, Folding, Paperboard
PPP-B-601 - Boxes, Wood, Cleated-Plywood
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner
PPP-B-636 - Boxes, Shipping, Fiberboard
PPP-B-665 - Boxes: Paperboard, Metal Edged and Components
PPP-B-676 - Boxes, Setup

MILITARY

MIL-M-3171 - Magnesium Alloy, Processes for Pretreatment and Prevention of Corrosion On
MIL-C-5541 - Chemical Conversion Coatings on Aluminum and Aluminum Alloys
MIL-R-5674 - Rivets, Structural, Aluminum Alloy, Titanium Columbium Alloy, General Specification For

STANDARDS

FEDERAL

FED-STD-141 - Paint, Varnish, Lacquer and Related Materials: Methods of Inspection, Sampling and Testing

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage

(Copies of specifications, standards, and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

4-1-190	- Hardware, Universal Load Carrying Sling; buckle, Quick Adjustable, Slide 1-3/4 Inches with Eye and Attached Snap, Buckle, Quick Adjustable Slide, 1-3/4 Inches
4-1-191	- Hardware, Universal Load Carrying Sling, Slide, Quick Adjustable, 1-3/4 Inches (Magnesium)
4-1-192	- Hardware, Universal Load Carrying Sling; Ring "V" with Bar, 1-3/4 Inches, Loop Slide, 1-3/4 Inches
4-1-193	- Hardware, Universal Load Carrying Sling; Snap, Round Eye, 1/2 Inch Diameter for Type II Buckle
4-1-194	- Hardware, Universal Load Carrying Sling, Method of Testing
4-1-435	- Hardware, Universal Load Carrying Sling, Alternate Type I and Type II Buckle Assembly. 1-3/4 Inch, Aluminum Slide

(Copies of drawings, publications, and other Government documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

B 94 - Specification for Magnesium-Alloy Die Castings

B 117 - Salt Spray (Fog) Testing

D 822 - Recommended Practice for Operating Light- and Water-Exposure Apparatus (Carbon - Arc Type) for Testing Paint, Varnish, Lacquer, and Related Products

D 3951 - Standard Practice for Commercial Packaging

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

G 23 - Recommended Practice for Operating Light- and Water-Exposure Apparatus (Carbon-Arc Type) for Testing Paint, Varnish, Lacquer, and Related Products

(Copies should be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.3).

3.2 Material. The material specified shall conform to the referenced documents and requirements specified hereinafter.

3.2.1 Magnesium alloy die-castings. Magnesium alloy die-castings shall conform to alloy AZ91B of ASTM B 94.

3.2.2 Aluminum alloy sheet. Aluminum alloy sheet shall conform to temper 5052-H32 of QQ-A-250/8.

3.2.3 Wire, steel. The steel wire shall be carbon, spring, music, conforming to QQ-W-470.

3.2.4 Rivets, aluminum alloy. The aluminum alloy rivets shall conform to composition 5056, condition H-32 of MIL-R-5674.

3.2.5 Primer. The primer shall conform to composition G or L, as applicable, color Y of TT-P-1757.

3.2.6 Enamel. The enamel shall be baked urea resin modified epoxy type, pigmented with carbon black and ultra-fine silica (see 6.4).

3.2.6.1 Resistance to abrasion. The abrasion loss shall not be more than 25 milligrams when calibrase wheels apply a pressure of 1000 grams against the film for 500 cycles as specified in 4.5.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

3.3 Construction. The construction of the hardware shall conform to the requirements specified herein, and to the design, size, and dimensions specified on Drawings 4-1-190, 4-1-191, 4-1-192, and 4-1-193. At the option of the contractor, for types I and II hardware, an alternate one-piece aluminum slide conforming to 3.3.3 may be substituted for the magnesium slide specified on Drawing 4-1-191.

3.3.1 Types I, III, and IV hardware. The types I, III, and IV hardware shall be cast from magnesium specified in 3.2.1, except for aluminum slide when applicable (see 3.3 and 3.3.3).

3.3.2 Type II hardware. The type II hardware, shall be cast from magnesium specified in 3.2.1 except for the snap tongue (see 3.3.2.1), snap spring (see 3.3.2.2), and aluminum slide when applicable (see 3.3 and 3.3.3).

3.3.2.1 Snap tongue for type II hardware. The snap tongue for type II hardware shall be fabricated from aluminum specified in 3.2.2.

3.3.2.2 Snap spring for type II hardware. The snap spring for type II hardware shall be fabricated from material specified in 3.2.3.

3.3.3 Alternate aluminum slide. When supplied (see 3.3), the alternate slide shall be fabricated from aluminum alloy sheet specified in 3.2.2, except that the temper shall be temper 0. The aluminum slide shall be of one-piece construction conforming to the size and dimensions of Drawing 4-1-435. The slide shall not be detachable after final assembly to buckle body.

3.3.4 Rivets. Rivets shall conform to the aluminum specified in 3.2.4 and shall be of the size and style specified on drawings. All rivets shall be spun and smoothly headed. The rivets shall not split, crack, or fracture the castings.

3.3.5 Castings. All castings shall be of uniform quality, free from blowholes, porosity, hardspots, shrinkage defects, and cracks. All castings shall be smooth, clean and free from burrs or sharp edges.

3.3.6 Die ejector pins for slide cap, and slide base for type I and II buckles. When internal ejector pins are used to release the slide cap and slide base from the die, the centerline of the ejector pins shall be located equidistant between the centerline of the rivet holes in the slide. The ejector pin marks shall be flush with the surface of the casting to a maximum of 0.005 inch in depth.

3.3.7 Proof load of hardware of types I, II, III, and IV. The hardware types I, II, III, and IV shall not fracture nor permanently distort under a 375-pound load when tested as specified in 4.5.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

3.4 Finish.

3.4.1 Surface preparation.

3.4.1.1 Type I buckle, type III loop, and type IV ring. The type I buckle body with magnesium slide, type III loop, and type IV ring shall be given a treatment conforming to type III of MIL-M-3171. The treatment shall be applied at any stage of assembly of the buckle. When the buckle is supplied with an aluminum slide (see 3.3), the slide shall be given a treatment conforming to class 1A of MIL-C-5541, prior to assembly.

3.4.1.2 Type II buckle with eye and snap.

3.4.1.2.1 Buckle, eye and snap body. The type II buckle body with magnesium slide, eye, and snap body shall be given a treatment conforming to type III of MIL-M-3171. This treatment shall be applied at any stage of assembly. When the buckle is supplied with an aluminum slide (see 3.3), the slide shall be given a treatment conforming to class 1A of MIL-C-5541, prior to assembly.

3.4.1.2.2 Rivets and tongue. Before assembly, the aluminum rivets and tongue of the snap shall be given a treatment conforming to class 1A of MIL-C-5541.

3.4.1.2.3 Spring. Before assembly, the steel spring shall be given a treatment conforming to any method, type I or II of TT-C-490.

3.4.2 Priming. Surfaces of all types of hardware, after surface preparation specified in 3.4.1, shall be coated with primer specified in 3.2.5. Application of primer to snap tongue, spring, and tongue rivet of type II buckle shall be made before assembly. Application of primer to other components may be made during any stage of assembly. Rivets joining the eye to type II buckle and rivets of the slide need not be primed.

3.4.3 Enameling. Surfaces of all types of hardware, after priming, shall be coated with the enamel specified in 3.2.6 and then baked. Application of enamel to snap tongue, spring, and tongue rivet of type II buckle shall be made before assembly. Application of enamel to other components may be made at any stage of assembly. Rivets joining the eye to type II buckle and rivets of the slide need not be enameled prior to spinning. After spinning, rivet heads of completed hardware, shall be cleaned and coated with the enamel specified in 3.2.6 and then baked, or shall be cleaned and coated with an adherent air drying black enamel or lacquer. Coating weight of primer and enamel combined shall be a minimum of 20 milligrams per square inch of surface when tested as specified in 4.5.3.

3.4.3.1 Gloss. Gloss of enamel shall be 40 maximum, when tested as specified in 4.5.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

3.4.3.2 Resistance to accelerated weathering. The enamel shall show no more than slight chalking when tested for resistance to accelerated weathering as specified in 4.5.5.

3.4.3.3 Resistance to salt spray. The enamel shall be tested for resistance to salt spray as specified in 4.5.6. The enamel shall show no wrinkling or blistering when examined immediately upon removal of the hardware from the salt spray chamber; nor shall there be any evidence of corrosion of the base metal. Upon air drying for 24 hours after removal from salt spray, the enamel shall be no softer than an unexposed enamel prepared in the same manner.

3.4.3.4 Resistance to scoring. A film of the enamel shall be difficult to score through to the metal. The score produced in the enamel film shall not have the jagged edge characteristic of brittle films when tested as specified in 4.5.7.

3.5 Marking for identification. Each type of hardware shall have the manufacturer's name or trademark integrally cast in the location identified on Drawings 4-1-190 and 4-1-192.

3.6 Workmanship. The hardware shall conform to the quality of product established by this document and the occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirement in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in table IV and dimensions specified in 4.4.4, and shall be tested as specified in 4.4.5. The presence of any defect or failure of any test shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

4.4.1.1 Enamel tests. The enamel shall be tested for the characteristics in table I. The inspection level shall be S-1 and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 6.5.

TABLE I. Enamel tests

Material and lot expressed in terms of	Characteristic	Requirement para.	Test method	Requirement appl. to ind. unit	No. of deter. per unit	Results reported as	Sample unit
Baking enamel (1 gal.)	Resistance to abrasion	3.2.6.1	4.5.1	X	2	Average of 2 deter. to the nearest milligram	Two 4 in. by 4 in. unprimed magnesium panels

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

TABLE I. Enamel tests (cont'd)

Material and lot expressed in terms of	Characteristic	Requirement para.	Test method	Requirement appl. to ind. unit	No. of deter. per unit	Results reported as	Sample unit
Baking enamel (1 gal.) (cont'd)	Material identification	3.2.6	Std. commercial	X	1	Pass or fail	Two 1 pint containers

4.4.2 In-process inspection. Inspection of sub-assemblies shall be made to ascertain that construction details which cannot be examined in the finished product are in accordance with specified requirements. The Government reserves the right to exclude from consideration for acceptance any material or service for which in-process inspection has indicated nonconformance.

4.4.2.1 In-process examination. Examination shall be made during the manufacturing process for the requirements specified in table II. Whenever nonconformance is noted, correction shall be made to affected items and process.

TABLE II. In-process examination

Requirements	Requirement paragraph
Riveting (spinning of heads)	3.3.4
Prepaint treatment	3.4.1
Priming	3.4.2

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

4.4.2.2 Visual examination of castings. The castings shall be examined for the defects listed in table III, prior to assembly and surface preparation. The lot size shall be expressed in units of castings of one type. The sample unit shall be one casting. The inspection level shall be S-3 and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5.

TABLE III. Casting defects

Examine	Defect
Workmanship	Blowhole(s) Not uniform, i.e., any porosity, hard spots, shrinkage defects, cracks Not smooth Not clean Holes not countersunk when required

4.4.3 End item visual examination. The end item shall be examined for the defects listed in table IV. The lot size shall be expressed in units of completed buckles, slide loops, or V-rings, as applicable. The sample unit shall be one buckle, slide loop, or V-ring, as applicable. The inspection level shall be II and the AQL, expressed in terms of defects per hundred units, shall be 2.5 for major defects and 10.0 for total defects.

TABLE IV. End item visual defects

Examine	Defect	Classification Major	Minor
Finish of magnesium, aluminum and steel hardware	Color not black	101	
	Area of no film	102	
	Rivet head not coated with enamel	103	
	Finish not continuous, smooth, and adherent, i.e., has run, creep, peel, streaked, wrinkled, or blistered	104	
	Finish is rough, i.e., appreciable lint, dust or other matter embedded in finish		201

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

TABLE IV. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Construction, assembly, and workmanship	Part or component missing from the assembly	105	
	Part or component broken, fractured, cracked, twisted, warped, misaligned, or malformed	106	
	Any sharp edge, projections, burr, or metal sliver	107	
	Pronounced tool or forming marks clearly noticeable, except for ejector marks on castings		202
	Any functioning part that cannot be operated, or requires abnormal force to operate	108	
	Open joint between mating faces of slide		203
	Knurling omitted from adjustable slide	109	
	Knurling not coarse, cross-diamond design		204
	Knurling incomplete		205
	Die ejector pin marks not located equidistant between center line of rivet holes in slides		206
	Die ejector pin mark not approximately flush with surface of casting		207
	Rivet insufficiently headed, not smoothly headed, not concentric with hole, or is loose	110	
	Rivet head on wrong side of assembly		208
Aluminum slide, when applicable	Slide can be detached by hand from buckle body	111	
	Slide assembled backwards	112	
Identification marking	Manufacturer's name or trademark and stock number missing, incorrect, illegible; of improper size, location, or method of application		209

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

4.4.4 End item dimensional examination. The end items shall be examined for conformance to the dimensions specified, and those dimensions annotated with an asterisk on the drawings shall be subject to end item inspection. Any dimension not within the specified tolerance shall constitute a defect. The lot size shall be expressed in units of completed buckles, slide loops, or V-rings, as applicable. The sample unit shall be one completed buckle, slide loop, or V-ring, as applicable. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 4.0

4.4.5 End item testing. The end items shall be tested for the characteristics listed in table V. The lot size shall be expressed in units of complete buckles, slide loops, or V-rings, as applicable. The sample unit shall be 6 complete buckles, slide loops, or V rings, as applicable. The inspection level for all tests shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

TABLE V. End item tests

Characteristic	Requirement para.	Test method	Number of determinations per sample unit	Results reported as
Proof load test on hardware types I, II, III, and IV	3.3.7	4.5.2	1	Pass or fail
Coating weight of primer and enamel combined	3.4.3	4.5.3	1	To the nearest milligram per square inch
Gloss of enamel	3.4.3.1	4.5.4	1	Pass or fail
Resistance to accelerated weathering	3.4.3.2	4.5.5	2	Pass or fail
Resistance to salt spray	3.4.3.3	4.5.6	1	Pass or fail
Resistance to scoring	3.4.3.4	4.5.7	1	Pass or fail

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

4.4.6 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling Bulged or distorted container
Content	Number per container is more or less than required

4.5 Methods of inspection.

4.5.1 Abrasion test. Resistance to abrasion shall be tested by method 6192 of FED-STD-141. The enamel shall be applied on 4-inch square, clean, unprimed magnesium panels. The thickness shall be 1.0 ± 0.1 mil and shall be measured at four places equidistant from the center of the panel. The enamel shall be baked as specified by the supplier and aged at least 24 hours prior to testing. At least two panels shall be used and the results averaged. The CA-17 calibrase wheels are to be used to apply a pressure of 1000 grams against the test film for 500 cycles on each panel to determine conformance with 3.2.6.1.

4.5.2 Proof load test on hardware type I, II, III, and IV. The hardware types I, II, III, and IV shall be subjected to a 375-pound load applied as indicated on Drawing 4-1-194 and at a rate not to exceed 1000 pounds per minute to determine conformance with 3.3.7.

4.5.3 Coating weight of finish test. The test specimen shall be a piece of finished hardware, or a portion thereof, and shall be weighed to the nearest milligram. The coated area shall be measured in square inches (the area may be subdivided into component simple geometric shapes and then combined). The enamel shall then be stripped completely from the metal using a chemical stripper of a type that does not dissolve the base metal. The stripped metal shall be dried and weighed again. Coating weight shall be calculated by

Source: https://assist.dla.mil -- Downloaded: 202640-17T13:10Z
Check the source to verify that this is the currentversion before use.

dividing the change in weight in milligrams by the coated area in square inches, and reported in milligrams per square inch to determine compliance with 3.4.3.

4.5.4 Gloss test. Gloss shall be estimated visually by examination of finished hardware against a black panel whose gloss is 40, as determined by method 6101 of FED-STD-141. Highlight effects due to sharp curvatures of the hardware will be ignored as enamel is examined to determine conformance with 3.4.3.1.

4.5.5 Accelerated weathering test. The test specimen shall be a finished piece of hardware. The specimen shall be exposed for 168 hours to accelerated weathering in accordance with ASTM D 822 or ASTM G 23. The exposed surface shall be examined for chalking, by rubbing with a piece of light colored velvet or cheese cloth wrapped around the finger using moderate pressure, to determine compliance with 3.4.3.2.

4.5.6 Salt spray test. Test specimen shall be a finished piece of hardware. The specimen shall be exposed to salt spray for 200 hours in accordance with ASTM B 117 to determine compliance with 3.4.3.3. The thumbnail or knife shall be used to determine evidence of softening.

4.5.7 Resistance to scoring test. A cut shall be made in the enamel film on a portion of the hardware by a knife blade held at 30 degrees to the surface being tested. A narrow band (about 1/8 inch) of exposed metal shall be produced to determine compliance with 3.4.3.4.

5. PACKAGING

5.1 Preservation. Preservation shall be level A, B, or Commercial, as specified (see 6.2).

5.1.1 Level A. Unless quantities are specified otherwise (see 6.2), 400 type I buckles; 200 type II buckles; 500 type III loops; or 400 type IV V-rings, shall be unit packed in a fiberboard box conforming to style RSC, V2s or V3c of PPP-B-636. Boxes shall be well-filled and compact. If quantities are other than as specified above, the gross weight of boxes shall not exceed 70 pounds.

5.1.2 Level B (see 6.5). Unless quantities are specified otherwise (see 6.2), the same quantities as specified in level A shall be unit packed in a fiberboard box conforming to style RSC, type CF, variety SW or type SF, class domestic, grade 200 of PPP-B-636. If quantities are other than as specified above, buckles, loops, or V-rings may be packaged in boxes conforming to PPP-B-566, PPP-B-665, PPP-B-676, in lieu of PPP-B-636, provided the gross weight does not exceed the weight limitation of the box document. Closure shall be in accordance with the appendix of the box document.

Source: https://assist.dla.mil -- Downloaded: 202640-17T13:10Z
Check the source to verify that this is the current version before use.

5.1.3 Commercial. Hardware shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing. Unless quantities are specified otherwise, 2400 type I buckles; 1200 type II buckles; 3000 type III loops; or 2400 type IV V-rings, preserved as specified in 5.1, shall be packed in a snug-fitting cleated-plywood box conforming to PPP-B-601, overseas type.

5.2.2 Level B packing. Unless quantities are specified otherwise (see 6.2), 2400 type I buckles; 1200 type II buckles, 3000 type III loops, or 2400 type IV V-rings, preserved as specified in 5.1, shall be packed in a snug-fitting, cleated-plywood box conforming to PPP-B-601, domestic type or in a snug-fitting nailed wood box conforming to PPP-B-621.

5.2.3 Commercial packing. Hardware, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Marking. In addition to any special marking required by the contract or purchase order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. The hardware is intended for use with the sling, universal, individual load carrying (MIL-S-43013).

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. Type of hardware required (see 1.2).
c. When a first article is required (see 3.1, 4.3, and 6.3).
d. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
e. When quantity per unit pack or packing is other than specified (see 5.1.1, 5.2.1, and 5.2.2).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

Source: https://assist.dla.mil -- Downloaded: 202610-17T13:10Z
Check the source to verify that this is the current version before use.

6.4 Enamel requirements. The enamel requirements of this document have been met by an enamel of the following formulation:

	Parts by weight
Xylol	286.1
Epon 1007 (Shell Chemical Co.)	226.0
Diacetone Alcohol	187.0
Beckamine P-138 (Reichold)	161.2
Cyclohexanone	97.5
Ultrafine Silica Syloid 244	30.7
Elf-1 Channel Black (Godfrey L. Cabot Co.)	8.4
Bentonite, Bentone 18-C	3.0
Silicon, SF-69 (10% Toluol)	0.1
Total	1000.0

6.5 Subject term (key word) listing.

Buckle, quick adjustable slide
Hardware
Sling, universal, individual load carrying

6.6 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - MC
Air Force - 99

Review activities:

Army - AV
Air Force - 69
DLA - IS

Preparing activity:

Army - GL

Project No. 5340-1872

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-H-9896C	Hardware, Universal Load Carrying Sling

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)* _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OF 1 APR 84

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:10Z
Check the source to verify that this is the current version before use.