INCH-POUND

MIL-T-9918C(USAF)
5 JUNE 1989
SUPERSEDING
MIL-T-9918B
27 June 1973

MILITARY SPECIFICATION

TOW TARGET, AERIAL DART, GUNNERY TYPE
TDU-10/B and TDU-10B/B

1. SCOPE

1.1 This specification establishes the requirements for manufacture and Government acceptance of the TDU-10/B and TDU-10B/B Tow Target, which is used for air-to-air gunnery training of fighter pilots.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbook. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Ogden ALC/MMDSA Hill Air Force Base, Utah 84056-5609 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

SPECIFICATIONS

Federal

QQ-S-781 Strapping, Steel, Flat and Seals

AMSC N/A FSC 6920

DISTRIBUTION STATEMENT A: Approved for public release, distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:12Z
Check the source to verify that this is the current version before use.

PPP-B-35	Bags, Textile-Shipping, Burlap, Cotton and WaterProof
PPP-T-97	Tape, Pressure-Sensitive Adhesive, Filament Reinforced

Military

MIL-P-116	Preservation-Packaging, Methods of
MIL-B-121	Barrier Material, Greaseproofed, Waterproofed, Flexible, Heat-Sealed
MIL-B-131	Barrier Materials, Watervaporproof, Flexible, Heat Sealable
MIL-P-17667	Paper, Wrapping, Chemically Neutral (Non-Corrosive)
MIL-A-83377	Adhesive Bonding for Aerospace Systems, Guidelines for

STANDARDS

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	Marking for Shipment and Storage
MIL-STD-130	Identification Marking of US Military Property
MIL-STD-401	Sandwich Contructions and Core Materials; General Test Methods
MIL-STD-794	Parts and Equipment, Procedure for Packaging and Packing of
MIL-STD-831	Test Reports, Preparation of

MILITARY HANDBOOK

MIL-HDBK-106	Multi-Level Continuous Sampling Procedure and Tables for Inspection by Attributes

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

DRAWINGS

Air Force

59B90714	Lug Adapter
59C90718	Counter Weight-Adjusting
59D90724	Base Assembly-Reflection
59D90711	Rail-Keel Assy
59D90717	Nose Angle
59D90721	Nose Assy
59D90722	Fairing
59D90727	Reflector Assembly
59D90728	Bridle Assembly

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:12Z
Check the source to verify that this is the current version before use.

59H90730	Target Assembly
64H30383	Wing Panel, Specification Control Drawing
8121564	Target Assy, Type TDU-10B/B
8121565	Adapter Assy, Type TDU-10B/B

TRANSPORTATION PACKAGING ORDER (TPO)

Air Force

TPO 6920-613-0312	TDU-10/B Tow Target TDU-10B/B Tow Target

'(Copies of specifications, standards, handbooks, drawings, publications, and other government documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)'

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.'

3. REQUIREMENTS

3.1 Classification of requirements. The requirements for the TDU-10/B and TDU-10B/B Tow Target are classified herein as follows:

REQUIREMENTS	PARAGRAPHS
Preproduction	3.2
First Article	3.3
Material	3.4
Design and Construction	3.5
Performance Characteristics	3.6
Identification	3.7
Workmanship	3.8
Bridle Strength	3.9

3.2 Preproduction requirements. The preproduction requirements for the TDU-10/B and TDU-10B/B Tow Target are classified herein as follows:

REQUIREMENTS	PARAGRAPHS
Process Specification	3.2.1
Testing	3.2.2 and 4.3
Test Report	4.3.6

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:12Z
Check the source to verify that this is the current version before use.

3.2.1 Process specification. A process specification in accordance with MIL-A-83377 shall be prepared by the contractor covering all details of the wing panel bonding operation. This document shall be submitted to the Air Force for acceptance concurrent with the delivery of the first article wing panels. The acceptance of the process specification does not relieve the contractor from assuring that the wing panels meet the required performance characteristics (see 3.6).

3.2.1.2 Brand names data sheets. All brand names, data sheets, and other required information shall be included in the process specification. All deviations (during production) to the approved contractor's process specification must have prior approval by the cognizant Air Force engineering agency. Such deviation shall be granted only if sufficient test data is submitted to assure the Air Force that no degradation of the target shall occur. Any documents containing proprietary information and labeled as such, will be handled in accordance with applicable directions for these documents.

3.2.2 Testing. Initial contractor testing shall consist of peel strength tests. These tests shall determine the peel strength of the adhesive bond between both the facing/core and facing/wood frame of the wing panels. Minimum peel strength requirements are specified in Table I with peel strength testing listed in Table II. Failure to achieve minimum peel strength requirements will preclude first article testing by the Air Force.

3.3 First article. The contractor shall submit four wing panels, in accordance with 64H30383 and 8121564, to the Air Force for first article testing. The wing shall be representative of the production item and produced using the same material, processes, and equipment that will be used during production. The wing panels will be consumed in testing. All fabrication and shipping expenses shall be borne by the prospective contractor. (See 4.3 and 6.3)

3.3.1 First article tests. These tests shall consist of detailed inspection of the four wing panels submitted and such additional peel strength tests as deemed necessary by the Air Force to assure that the panels meet specification requirements.

3.3.2 Acceptance or rejection. Acceptance or rejection of the first article panels shall be determined by the Air Force. The Air Force shall furnish a report to the contractor concerning the results of the first article tests. The engineering decisions within the report will be final, unless otherwise stipulated. Production of targets shall not begin until both contractors process specification (see 3.2.1) and test report (see 4.3.6) have been accepted.

3.3.3 Prior approval. First article submission will not be required if the prospective contractor has built the TDU-10/B and TDU-10B/B Target within the preceding 24 months and submits a letter attesting there has been no change in materials, processes, or equipment used in fabrication of the target.

Source: https://assist.dla.mil -- Downloaded: 20260-17T13:12Z
Check the source to verify that this is the current version before use.

3.3.4 Requalification. Change in adhesive, bonding, procedures, plant locations, and critical manufacturing equipment shall require a complete re-evaluation of the contractor's capability to produce an acceptable target. If any of the above changes occur (or any other change that the Government considers potentially detremental), the contractor shall be required to fulfill the requirements of 3.2.*

3.4 *Material. The use of reclaimed materials shall be encouraged to the maximum extent possible. The contractor will notify the procuring activity as to what type reclaimed material is proposed for usage.*

3.4.1 General. Material used in construction of the TDU-10/B and TDU-10B/B Target shall be as specified on the applicable drawings. No deviation from the specified material shall be allowed without prior approval by the Air Force.

3.4.2 Adhesive. Any adhesive which employs a scrim cloth may be used providing the minimum peel strength requirements are achieved throughout the temperature spectrum noted in Table I.

3.5 Design and Construction. The TDU-10/B, TDU-10A/B and TDU-10B/B Tow Targets consist of four triangle-shaped wing panels with a keel, assembled in accordance with Drawing 59H90730 (TDU-10/B), and Drawing 8121564 (TDU-10B/B) to form a cruciform dart.*

3.5.1 Components. The Tow Targets shall consist of the following major components:

ITEM NO.	P/N	DESCRIPTION	APPLICATION	QUANTITY
1	59D90711	Rail	TDU-10/B, TDU-10B/B	1
2	64H30383	Wings	TDU-10/B, TDU-10B/B	4
3	59D90727	Radar Reflector	TDU-10/B, TDU-10B/B	1
4	59D90722	Flairing	TDU-10/B, TDU-10B/B	4
5	59D90717	Nose Angles	TDU-10/B, TDU-10B/B	4
6	59D90721	Nose Casting	TDU-10/B, TDU-10B/B	1
7	59C90718	Counter Weight	TDU-10/B, TDU-10B/B	1
8	59D90728	Bridle	TDU-10/B, TDU-10B/B	1
9	8121565	Adapter Assy	TDU-10/B	1

3.5.2 Balance. The tow targets, when assembled shall be balanced in accordance with Drawing 59H90730 (TDU-10/B), and Drawing 8121564 (TDU-10B/B).*

3.6 Performance characteristics. The peel strength of the adhesive bond shall conform to the requirements specified in Table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:12Z
Check the source to verify that this is the current version before use.

TABLE I - PEEL STRENGTH OF BONDED PANELS

BOND	TEST TEMPERATURE (±5°F)	MINIMUM PEEL STRENGTH VALUE
1. Facing/core (without artificial aging)	-60°F	1.5 in-lb/in
	60°F	5.0 in-lb/in
	150°F	1.5 in-lb/in
2. Facing/core for preproduction testing (with artificial aging)	60°F	5.0 in-lb/in
3. Facing/frame for preproduction testing (without artificial aging)	-60°F	1.5 in-lb/in
	60°F	5.0 in-lb/in
	150°F	1.5 in-lb/in

3.7 Identification. Equipment, assemblies, and parts shall be marked for identification in accordance with MIL-STD-130.

3.8 Workmanship. The tow target shall be fabricated and finished in a thoroughly workmanlike manner such that the item is suitable for the purposed intended.

Bridle strength. Bridle assemblies, 59D90728, shall have a minimum breaking strength of 2300 pounds when tested in accordance with 4.4.3.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:12Z
Check the source to verify that this is the current version before use.

4.2 Classification of examinations and tests. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements, except first article tests, as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2.1 Preproduction testing (see 4.3).

4.2.2 Production testing (see 4.4).

4.2.3 Quality Conformance inspection (see 4.5).

4.3 Preproduction testing. Preproduction testing will consist of peel strength tests on both facing/core and facing/frame samples. The peel test specimens shall be cut from a wing panel(s) that has been manufactured using the same material, processes, and equipment as a production panel.

4.3.1 Preparation of facing/core samples. Forty 3 x 12-inch samples will be cut from a wing panel (P/N 64H30383) for peel testing by the contractor. Specimens shall be cut so the 'L' direction of the core is the 12-inch dimension as specified in MIL-STD-401. Ten of these samples shall be artificially aged in accordance with 4.3.2. The paper core shall be left exposed during the artificial aging. All samples shall be identified with the area of the wing panels from which they were taken.

TABLE II - PREPRODUCTION TESTING

TESTS	REQUIREMENT PARAGRAPH	TEST PARAGRAPH	QTY (UNAGED)	(ARTIFIC-IALLY AGED)	TEMPER. (±5°F)
Peel Strength Test					
a. Facing/core bond	3.2.2	4.3	4	3	-60°F
			4	-	-30°F
			4	-	0°F
			3	-	30°F
			4	4	60°F
			3	-	90°F
			4	-	120°F
			4	3	150°F
b. Facing/frame bond	3.2.2	4.3	3	-	-60°F
			3	-	60°F
			3	-	150°F

Source: https://assist.dla.mil -- Downloaded: 202640-17T13:12Z
Check the source to verify that this is the current version before use.

4.3.2 Artificial aging. The samples chosen for artificial aging shall be subjected to the following procedures and in the sequence stipulated:

a. Immersed in water at 120°F ± 3°F for one hour.

b. Sprayed with steam and water vapor at 200°F ± 5°F for three hours.

c. Stored at 10°F ± 5°F for twenty hours.

d. Heated in dry air at 210°F ± 3°F for three hours.

e. Sprayed again with steam and water vapor at 200°F ± 5°F for three hours.

f. Heated again in dry air at 210°F ± 3°F for eighteen hours.

4.3.3 Preparation of facing/frame samples. Nine samples of the facing/frame (2 by 10 inches) shall be cut from the wing panel(s) fabricated for the preproduction testing.

4.3.4 Test procedures. The peel strength tests on the facing/core bond and the facing/frame bond shall be conducted in accordance with paragraph 5.2.6 of MIL-STD-401, except that the measurement of resisting torque shall include the force required to bend the facing material. The requirements of MIL-STD-401, paragraph 4.3, shall apply.

4.3.5 Test conditions. Unless otherwise specified, all tests required by this specification shall be made at atmospheric pressure and a relative humidity of 80 percent or less. All peel test specimens shall be stabilized at required temperature for a minimum of 5 minutes prior to testing.

4.3.6 Test report. Three copies of a test report in accordance with MIL-STD-831 shall be submitted to the Air Force concurrent with the delivery of the first article panels. This report shall cover all the tests performed under 4.3 of this specification.

4.4 Production testing. Production testing shall consist of those tests specified below:

a. Peel strength tests (see 4.4.1).

b. Balance test (see 4.4.2).

c. Bridle strength tests (see 4.4.3).

4.4.1 Peel strength tests. During production, peel strength tests will be conducted on the facing/core bond only. The tests will be performed in accordance with paragraph 4.3.4 and Table I. The tests will be conducted at room temperature on samples without artificial aging. One wing panel will be selected at random from each 25 wing panels. From this sample panel one 3x12 inch sample (12 inch "L" direction, see 4.3.1), shall be cut at random for peel

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:12Z
Check the source to verify that this is the current version before use.

strength testing. Testing at other than room temperature will be at the discretion of the Government Quality Assurance representative.

4.4.1.1 Rejection and retest. If the test sample fails to meet the minimum peel strength requirements of 3.6 the entire lot of 25 panels shall be rejected. Each wing panel in the rejected lot shall be tested, and panels that fail to meet minimum peel strength requirement shall be rejected. If one or more panels fail to meet the peel test requirement, the contractor shall explain fully in writing to the Government representative the cause of failure and the action taken to preclude recurrence. The peel test shall be repeated on the first wing panel produced after corrective action has been taken, and on subsequent wing panels until the production process is agian in order.

4.4.1.2 Test report. The contractor shall submit a report of testing performed per 4.4.1. The report shall be prepared after every 20 peel tests (125 targets). The report shall be informal in format and contain a listing of the peel strengths obtained in the 20 tests. Individual data sheets, recordings, graphs, etc, need not be submitted. The report shall be submitted for the life of the contract.

4.4.1.3 Repair of wing panels. All wing panels shall be repaired using the following procedure:

a. Cut a piece of honeycomb slightly larger than 3 x 12-inches.

b. Compress honeycomb by hand and fit into hole.

c. Assure that exposed area of the honeycomb patching piece is reasonably level.

d. Cover entire area with one layer of 3-inch adhesive backed aluminum tape, using Nr 11 Permacel Aluminum Foil, Permacel Tape Corporation, New Brunswick, New Jersey, or equivalent.

e. Allow approximately 1-inch of tape to cover skin on all sides of patched area.

f. Press tape firmly down over entire area.

4.4.2 Balance test. One out of every one hundred tow targets shall be assembled to determine compliance with 3.5.2. When a target does not balance, the lot shall be rejected. The contracter shall take immediate action to correct the deficiencies by changing the balancing weight length in accordance with Drawing 59C90718. Prior to production approval of the balancing weight change by the Government representative, another target shall be assembled and balanced to verify the new balance weight length.

4.4.3 Bridle strength test. Bridle assemblies, P/N 59D90728, shall be tested to determine adequacy of the swaging operation. Sampling shall be done in accordance with MIL-STD-105. Special Inspection Level S-4, and an AQL of 1.5. The bridle assembly shall be mounted in a tensile tester and pulled until

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:12Z
Check the source to verify that this is the current version before use.

failure occurs (1760 lbs. for MIL-C-5424 Cable and 2000 lbs. for MIL-C-1511 Cables). If either cable of the bridle fails to meet the test requirements due to improperly swaged sleeves, the entire lot shall be rejected and shall be resubmitted for inspection only after all defective units are removed or defects corrected. If either cable of the bridle fails to meet the test requirements due to cable failure, the entire lot shall be rejected.

4.5 Quality Conformance Inspection.

4.5.1 General. The target components shall be inspected per MIL-HDBK-106.

4.5.2 Lot formation. Items fabricated by the contractor shall be inspected on a continuous sampling basis. Items purchased from a subcontractor shall be inspected on a lot basis. The lot shall be defined as all items recieved in a shipment.

4.5.3 Sampling and acceptance criteria. The components shall be inspected per MIL-HDBK-106, multi-level continuous sampling plans for f=1/3. Characteristics identified in 4.5.4 shall have an AOQL of 2.0%. All other characteristics shall have an AOQL of 5%. In no instance shall inspection proceed below the fourth level.

4.5.4 Characteristics. The characteristics to be inspected with an AOQL of 2.0% shall be as follows:

4.5.4.1 Rail (Drawing 59D90711).

Characteristic	Method
a. Internal width of Extrusion Legs	Gage (1)
b. Hole pattern for .3438 Dia Holes	Gage (2)

4.5.4.2 Lug Adapter (Drawing 59B90714).

Characteristic	Method
Internal thread depth	Gage

4.5.4.3 Nose Angle (Drawing 59D90717).

Characteristic	Method
Hole location	Gage (3)

4.5.4.4 Base Assembly (Drawing 59C90724).

Characteristic	Method
Swaging of clinch nuts	Visual/feel

Source: https://assist.dla.mil -- Downloaded: 20260-17T13:12Z
Check the source to verify that this is the current version before use.

4.5.4.5 Target Assembly (Drawing 59H90730 and 8121564).

Characteristic	Method
Location of balance markings	Gage

4.5.4.6 Wing Panel (Drawing 64H30383).

Characteristic	Method
Thickness of wing panel	Gage (4)
Hole pattern for seven 1/2" holes on base	Gage (2)
Panel flatness	Gage (5)

a. Internal width is 1.270±.010. Minimum width (1.260) shall be inspection dimension.

b. Hole pattern in keel shall match hole pattern in wing (reference Note 3, Drawing 59D90711 and Notes 9 and 16, Drawing 64H30383).

c. One inch dimensions on location from edge shall be inspection dimensions.

d. Thickness on base shall be inspection dimension.

e. Criteria per Note 13, Drawing 64H30383.

4.6 Inspection of preparation for delivery. Sample items or packs, and the inspection of the preservation, packaging, packing and marking for shipment and storage shall be in accordance with the requirements of Section 5.

5. PREPARATION FOR DELIVERY

5.1 Preservation and packaging. Preservation and packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A. Tow targets shall be preserved in accordance with Specification MIL-P-116, Method III. Two complete targets shall be disassembled and arranged within a single exterior container typical of the arrangement shown in Transportation Packaging Order (TPO) 6920-613-0312. Four wing panels of one target shall be placed in one direction, and four wing panels of a second target shall be placed in opposite direction. A strip of wrapping paper conforming to Specification MIL-P-17667 shall be used to separate each panel to prevent damage to the metal foil skins. Positioning of the two keels in the container is the prerogative of the contractor, providing there is no increase in the dimensions and cube of the container as illustrated in TPO 6920-613-0312. Reflector fins, reflector bases, and fairings shall be protected with paper conforming to Specification MIL-B-121. Hardware shall be packaged in closth bags conforming to Specification PPP-B-35 or aluminum foil bags MIL-B-131. Counter weights, nose castings, and angles

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:12Z
Check the source to verify that this is the current version before use.

shall require no wrapping and shall be positioned within the container at the prerogative of the contractor providing they are secured in such a manner that will prevent any movement and consequent damage to the wing panels. The bridle shall be coiled separately and secured with tape conforming to Specification PPP-T-27. Contact preservative is not required on cadmium plated items. The bagged hardware shall be packaged and stowed in separate packs so the unit quantities will be sufficient in number to assemble one complete target.

5.1.2 Level C. TDU-10/B and TDU-10B/B Tow Targets shall be preserved and packaged in accordance with the requirements of the contract.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A - B. Two complete tow targets packaged in accordance with paragraph 5.1.1 shall be packed in exterior containers as illustrated in TPO 6920-613-0312. Paper conforming to Specification MIL-P-17667 or single-faced corrugated fiberboard will be placed in the wooden container to prevent the plywood floor and the cover from damaging the metal foil of the top and bottom wing panels. The gross weight of each container shall be approximately 600 pounds. Containers shall be closed and strapped with steel strapping conforming to Specification QQ-S-781.

5.2.2 Level C. Packages which require packing for acceptance by the carrier shall be packed in exterior type shipping containers in a manner that will insure safe transportation at the lowest rate to the point of delivery. Containers shall meet Consolidated Freight Classification rules or regulations of common carrier as applicable to the mode of transporation.

5.3 Physical protection. Cushioning, blocking, bracing, bolting and testing shall be in accordance with applicable requirements of MIL-STD-794. The drop tests of MIL-STD-794 are not required when the level of packing is C.

5.4 Marking. In addition to any special marking required by the contract or purchase order (see 6.2), interior and exterior containers shall be marked in accordance with MIL-STD-129. The shipment marking nomenclature and stock number shall be as follows:

Tow Target, Aerial Dart, Gunnery, Type TDU-10/B
Tow Target, Aerial Dart, Gunnery, Type TDU-10B/B
FSN 6920-613-0312

6. NOTES

6.1 Intended use. The TDU-10/B and TDU-10B/B Tow Target covered by this specification is intended for use as a high speed, highly maneuverable, aerial tow target for air-to-air gunnery training.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and the date of this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:12Z
Check the source to verify that this is the current version before use.

b. Selection of applicable levels of preservation, packaging and packing (see 5.1 and 5.2).

c. Whether special marking is required (see 5.4).

6.3 Data. Data generated by this document is not deliverable unless specified on the Contract Data Requirements List (DD Form 1423), referencing the appropriate data item description in the military departments Authorized Data List (ADL). The data produced by this standard are as follows:

a. Process specification (3.2.1).

b. Test report (4.3.6) and (4.4.1.2).

6.4 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodian:
Air Force - 99

Preparing Acitivity:
Air Force - 70

Project No. 6920-0064

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:12Z
Check the source to verify that this is the current version before use.