T-T-871E
INT. AMENDMENT-2
February 15, 1977

FEDERAL SPECIFICATION

TWINE, COTTON, WRAPPING

This interim amendment was developed by the General Services Administration, Federal Supply Service, Washington, DC 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to Federal Specification T-T-871E, dated June 18, 1970, and Amendment-1 dated May 20, 1975.

PAGE 3

3.2 Delete entire paragraph and substitute the following:

"3.2 Material. Except for ply sizes A and B, the twine shall be constructed from cotton of suitable grade and staple to meet the requirements of this specification. Ply sizes A and B shall be made from cotton, polyester staple fiber, or a combination of cotton and polyester staple fiber."

3.3, second sentence. Delete "Z twist" and substitute "S twist."

Table I delete in its entirety and substitute the following:

TABLE I. Physical requirements

Ply (size)	Length per pound, feet (minimum)	Length per pound, feet (maximum)	Breaking strength, pounds (minimum)
3	6000	-------	5.5
4	4500	-------	8
5	3600	-------	10
6	3000	-------	12
8	2250	-------	16
12	1500	-------	24
16	1125	-------	32
20	900	-------	40
24	750	-------	48
A 1/	1150	1600	40
B 1/	2300	3300	20.5

1/ Ply is not standard with manufacturers. In no instance shall twine be less than 2 ply."

3.6.1 In last sentence delete "cotton material, is required" and substitute, "fiber used."

PAGE 4

3.7 Delete in its entirety.

PAGE 5

4.2 Paragraph title. Delete "Inspection" and substitute "Quality Conformance Inspection".

FSC 4020

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

PAGE 8

Table V. test methods. Delete section of table V that is on page 8 and pubstitute the following:

TABLE V. Test methods

Characteristics	Requirement Paragraph	Test method	Number of determinations per individual sample unit	Results
Material identification:				
Cotton	3.2	1200 1/ 1/	1	Pass or fail
Polyester	3.2	AATCC 20-1972 1/	1	Pass or fail
Direction of twist	3.3	4050	1	Pass or fail

PAGE 9

Table V. Test method column; for Breaking strength characteristic. Delete "4102" and substitute "6016", for Elongation characteristic. Delete "4102" and substitute: "6016".

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:20Z
Check the source to verify that this is the current version before use.