U-I-00552b (DSA-DM)
October 26, 1971
Interim Revision of
Fed. Spec. U-I-552a
April 25, 1952

INTERIM FEDERAL SPECIFICATION

INVESTMENT, SOLDERING, DENTAL

This interim Federal specification was developed by the Defense Personnel Support Center, 2800 South 20th Street, Philadelphia, Pennsylvania 19101, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above. The General Services Administration has authorized the use of this interim Federal specification as a valid exception to Federal Specification U-I-552a.

1. SCOPE

1.1 Scope. This specification covers an investment suitable for holding dental prosthetic appliances in proper alignment during soldering procedures.

1.2 Classification. Dental soldering investment shall be of one type and size.

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein:

FSC 6520

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

Federal

RR-S-366	Sieve, Standard for Testing Purposes.
PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-corner.
PPP-B-636	Box, Fiberboard.
PPP-C-96	Can, Metal, 28 Gage And Lighter.

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D. C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Auburn, Washington, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

SPECIFICATIONS

Military

MIL-L-10547	Liners, Case, and Sheet, Overwrap; Water-Vaporproof Or Waterproof, Flexible.

STANDARDS

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

(Copies of Military specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material. The soldering investment shall be a powder, composed essentially of plaster of paris (gypsum) and quartz (silica) with necessary chemical modifiers. The ingredients shall be uniformly distributed throughout the investment. Investment shall be free of any foreign material and set or caked lumps.

3.2 Description. The dental investment powder when mixed with water according to manufacturer's directions, shall be suitable for holding dental prosthetic appliances in proper alignment during soldering procedures.

3.3 Physical properties.

3.3.1 Consistency. The average of the minimum and maximum diameters of the slumped mixture shall be not less than 2 1/4 inches and not more than 3 1/2 inches, when tested as specified in 4.4.1.2.

3.3.2 Setting time. The setting time shall be 9 $\pm$ 4 minutes, when tested as specified in 4.4.2. The setting time shall not vary more than 20 percent from the manufacturer's stated values.

3.3.3 Setting expansion. The setting expansion shall be not less than 0.05 percent and not more than 0.35 percent at the end of 24 hours, when tested as specified in 4.4.3.

3.3.4 Thermal expansion. The thermal expansion shall be not less than 0.50 percent nor more than 1.00 percent, when tested as specified in 4.4.4. The specimen shall not at any temperature above 200° C. (392° F.), show a length shorter than the original length of the specimen at standard test conditions (see 4.4.1.1).

3.3.5 Compressive strength. The compressive strength shall be no less than 900 pounds per square inch (p.s.i.), when tested as specified in 4.4.5.

3.3.6 Fineness. The powder shall be of such fineness that 100 percent shall pass through a No. 30 sieve, when tested as specified in 4.4.6.

3.3.7 Heat reaction. The mixed investment shall not crack nor give off poisonous or offensive odors when heated to a minimum of 850° C. (1562° F.), when tested as specified in 4.4.7.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

3.4 Net weight. The net weight shall be 5 pounds minimum, when tested as specified in 4.4.8.

3.5 Shelf life. The investment shall conform to the requirements of this specification for no less than 1 year from date of delivery to the Government, when stored at a controlled room temperature of 59° F. to 86° F.

3.6 Delivery schedule. No more than three months shall have elapsed from date of manufacture of the investment to date of delivery to the Government.

3.7 Instructions. Adequate and accurate instructions for proportioning and manipulating dental investment shall be furnished with each unit package. These instructions shall include:

1. Water to powder ratio (mixing consistency).

2. Setting time.

3. Setting expansion after 24 hours.

4. Thermal expansion at 1300 degrees Fahrenheit (°F.).

5. The statement:

"Heavy ingredients settle to bottom.
Mix thoroughly before dispensing."

Two copies of instructions shall be forwarded to the contracting officer for information purposes.

3.8 Workmanship. Workmanship shall be first class in every respect. Material shall be dry, free from set or caked particles, uniform in texture, and free of impurities which may impair the satisfactory performance of the investment. Coloring matter, as such, shall not be regarded as an impurity.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties).

4.2 Quality conformance inspection. The examinations and tests required to assure conformance of those items or lots of items to be offered for acceptance are classified as specified in tables I and III (see 4.2.1 and 4.3) and table II (see 4.2.2).

4.2.1 Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105. The inspection levels and acceptable quality levels (AQL's) shall be as indicated in table I. Unit of product for examination purposes shall be unit of issue.

Table I. Examination Criteria

Type defect	Inspection level	AQL (Percent defective)
Major	II	1.0
Minor	II	2.5

4.2.2 Sampling for tests. Sampling for tests shall be conducted in accordance with table II. Unit of product for tests purposes shall be one unit of issue from each lot or control number.

Table II. Tests

Characteristic	Requirement	Test procedure	Number of determinations per lot or batch number
Consistency	3.3.1	4.4.1.2	2 2/
Setting time	3.3.2	4.4.2	3 2/
Setting expansion	3.3.3	4.4.3	2 2/
Thermal expansion	3.3.4	4.4.4	2 2/
Compressive strength	3.3.5	4.4.5	5 2/
Fineness	3.3.6	4.4.6	2 1/
Heat test	3.3.7	4.4.7	5 1/
Net weight	3.4	4.4.8	1 1/

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

4.2.2 (cont'd.)

1/ A lot shall be rejected if any of the determinations per unit of product fails the test.
2/ A lot shall be rejected if the average of the determinations per unit of product fails the test.

4.2.3 Sample unit usage. Where feasible, the same sample unit shall be used for the determination of two or more test characteristics.

4.3 Examination. The investment shall be examined for defects including, but not limited to, those listed in table III.

Table III. Classification of Defects

Categories	Defects
Major	
101	Investment not dry.
102	Foreign material present in investment.
103	Set or caked lumps present in investment.
104	Investment not uniform in texture.
105	Instructions missing, incomplete, incorrect or illegible.
Minor	
201	Packaging and packing not as specified.
202	Marking not as specified.

4.4 Tests.

4.4.1 Test conditions, consistency and mixing procedure.

4.4.1.1 Test conditions. Unless otherwise specified, tests shall be at room temperature of 23.0° ± 2.0° C. (73.4° ± 3.6° F.). Equipment and material shall be conditioned at this temperature for at least 10 hours prior to testing. Distilled water at a temperature of 23.0° ± 1.0° C. (73.4° ± 1.8° F.) shall be used in conducting the pertinent tests.

4.4.1.2 Consistency. Before testing for physical properties with the exception of fineness, the mixing consistency shall be determined. To determine the water-powder ratio, at least a 100-gram sample of investment shall be mixed with a sufficient quantity of distilled water to give a slump spread in accordance with the requirement specified in 3.3.1. The following procedure shall be observed in determining the normal mixing consistency:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

4.4.1.2 (cont'd.)

a. The powder shall be added to the water in a suitable mixing bowl and immediately hand spatulated for 20 seconds. The time of initial contact of powder with water shall be considered the start of mix.

b. After hand spatulation, mixes shall be spatulated mechanically by 100 turns of a stiff blade in 15 seconds.

c. A cylindrical mold 2 inches long with an internal diameter of 1-3/8 inches shall be placed on a dry glass plate and filled immediately after spatulation of the mix.

d. Two minutes from the time of starting the mix, the mold shall be lifted and the mixture allowed to slump or spread over the plate on a vibration-free bench.

e. One minute after the mold is lifted, the major and minor diameters of the slumped mixture shall be determined.

f. The average of at least two tests shall be reported for determination of mixing consistency.

4.4.1.3 Mixing procedure. Specimens for determining setting time, compressive strength, setting expansion, and thermal expansion shall be prepared by using the water-powder ratio determined in 4.4.1.2 and the mixing procedure described in instructions a and b of 4.4.1.2.

4.4.2 Setting time.

4.4.2.1 Vicat apparatus. The Vicat apparatus shall consist of a frame bearing a movable rod weighing 300 grams; one end being 1 centimeter (cm.) in diameter for a distance of at least 5 cm., the other end having a removable needle 1 millimeter (mm.) in diameter and 5 cm. in length. The rod shall be reversible and able to be held in any desired position by a screw, and shall have an adjustable indicator which moves over a scale (graduated in millimeters) attached to the frame. The mixture shall be held in a rigid conical ring, or as an alternate, in a cylindrical mold, resting on a glass plate. Not less than 100 grams of powder shall be used for determining the setting time when using a cylindrical mold (2.5 ± 0.1 cm.). Not less than 200 grams of powder shall be used for determining the setting time when using a rigid conical ring (7 by 6 by 4 cm.). The ring shall be made of a noncorrosive, nonabsorbent material such as hard rubber, and shall conform to the following dimensions:

Inside diameter of ring at base:
7.0 ± 0.3 cm. (2.75 ± 0.12 inches).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

4.4.2.1 (cont'd.).

Inside diameter of ring at top:
6.0 ± 0.3 cm. (2.36 ± 0.12 inches).

Height of ring:
4.0 ± 0.1 cm. (1.57 ± 0.04 inches).

The cylindrical mold shall be 2.5 ± 0.1 cm. (1.00 ± 0.04 in.) both in diameter and length. The Vicat apparatus shall conform to the following requirements:

Weight of plunger:
300.0 ± 0.5 gram (0.661 ± 8 grains).

Diameter of needle:
1.00 ± 0.05 mm. (0.039 ± 0.002 inch).

4.4.2.2 Procedure. A thin coating of vaseline shall be applied to the inside surface of the ring before filling it with the mixture. The mixture, when prepared as specified in instructions a and b of 4.4.1.2, shall be placed in the ring or mold, worked slightly to remove air bubbles, struck off flush with the top of ring or mold, and shall then be tested for setting time with a Vicat needle. The needle should not touch surface of mixture while in stationary position. The needle shall be allowed to sink into the mixture from a height not exceeding 1 mm. above the surface of the mixture. After each penetration, the needle shall be wiped clean and the ring or mold moved so that the needle will not strike the same place twice. The mixture shall be tested at such intervals as is necessary to determine compliance with the requirements for setting time. The mixture shall not be tested with the Vicat needle unitl it shows evidence of setting, such as gloss disappearing, since excessive penetration of the mixture with the needle tends to accelerate the setting. Setting shall be considered complete when the needle no longer penetrates to the bottom of the mixture. The elapsed time in minutes, from the time when the powder was first added to the water to the time when setting is complete, shall be recorded to the nearest one-half minute, and the average of three tests shall be reported to the nearest minute.

4.4.3 Setting expansion. The setting expansion shall be determined by observing the change in length with a micrometer microscope comparator, or with equipment of equal accuracy. The comparator consists of a V-shaped support for the mixture, and two micrometer microscopes attached to a common base. Not less than a 100-gram sample shall be used for each setting expansion determination. The powder shall be mixed and poured into the V-shaped support lined with a rubber dam or strips of waxed paper overlapped

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

to prevent the mixture from adhering to the walls. Two small metal plates of noncorrosive material with ruled reference lines shall be placed in position, one at each end of the sample. These plates are provided with short projections which are imbedded in the mixture to prevent motion of the plates relative to the sample. The change in dimension on setting shall be determined on a 30 cm. specimen. The markers shall be placed as soon after pouring as possible. Hygroscopic expansion specimens shall be immersed 5 minutes after the start of the mix. The initial reading shall be taken 3 minutes before the setting time as determined in 4.4.2, and the final reading shall be taken 2 hours after the start of mix. The change in length of the test specimen shall be determined by observing the difference in dimensions developed between the initial and final readings. The change in length as a percentage of the original length shall be reported as the setting expanison. The value reported shall be the average of the values for two specimens, provided they are within ± 20 percent of the average value or within ± 0.1 percent expansion, whichever is greater. If the results are not within this range, two additional specimens shall be tested and the average of all four shall be reported.

4.4.4 Thermal expansion. A 100-gram sample shall be used in preparing each specimen. The thermal expansion shall be measured on 1.2 centimeters in diameter and 20 centimeters in length by the "Fused Quartz Expansion Apparatus" method, or by the use of equipment of equal accuracy. The specimen shall be gradually heated from room temperature at a rate which shall closely follow the schedule given in table IV. The initial observation shall be taken 120 minutes after the beginning of the mix. Subsequent observations shall be taken at 10-minute intervals. The value reported shall be the average of the values for two specimens, provided they are within ± 0.1 percent expansion of the average value at 700° C. If the results are not within this range, two additional specimens shall be tested and the average of all four shall be reported.

Table IV. Heating Schedule

Time Minutes	Temperature °C.	Temperature °F.
0	Room	Room
60	200	392
120	500	932
180	700	1,292

4.4.5 Compressive strength. Specimens for compressive strength shall be cylinders 1.0 to 1.3 inches in diameter by 2 inches in height, 20 mm. in diameter by 40 mm. in height, or 2-inch split cube mold specimens. A 100-gram sample shall be used for preparing each specimen with cylindrical mold. The amount of sample used with the split mold will depend on the number of 2-inch cube compartments in the mold.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

4.4.5.1 Apparatus. The mold for making the test specimens shall be made of noncorrosive material sufficiently rigid to prevent spreading during molding. The cylindrical mold shall be tubing slotted to facilitate removal of the specimen and precision machined to provide a dimensionally accurate test specimen. The parts of the 2-inch split cube mold, when assembled, shall be firmly held together. The dimensions shall conform to the following requirements: interior faces shall be plane surfaces with a maximum variation of 0.001 inch for new molds, and 0.002 inch for old molds; distance between opposite faces and height of the molds, measured separately for each cube compartment, shall be 2.000 ± 0.005 inches for new molds or 2.000 ± 0.020 inches for old molds. Angle between adjacent interior faces and between interior faces and top and bottom planes of the mold shall be 90.00 ± 0.05 degrees, measured at points slightly removed from the intersection of the faces. The 2-inch split cube mold shall have no more than three cube compartments and shall be separable into no more than two parts.

4.4.5.2 Procedure. When the sample is prepared as described in 4.4.1.2, the mixture shall be poured into the mold, resting on a flat polished glass plate and slightly overfilled with the mixture. The mixture shall be gently vibrated while being filled. A second, flat, polished glass shall be pressed on top of the mold to remove the excess from the mixture. The specimen shall be removed from the mold 15 minutes after the reported setting time as determined in 4.4.2, and stored in air at 23 ± 3° C. and a relative humidity of 100 percent. When the specimens are two hours old, the compressive strength shall be measured in a suitable testing machine. The specimens shall be crushed at a loading rate of 400 pounds per square inch per minute. The compressive strength shall be determined on five specimens and the average value shall be reported, except that any value departing more than 15 percent from the average shall be discarded. If less than three values remain to be averaged, the test shall be repeated.

4.4.6 Fineness. A weighed 100-gram sample shall be spread uniformly over the face of a No. 30 sieve conforming to the requirements of RR-S-366. Using a swirling motion on the sieve, apply a soft stream of water through a 5/8 inch inside diameter rubber hose and rapidly wash the sample through the screen. The water temperature shall be 65 to 75° F., and the washing operation shall be completed in 30 seconds. The sieve and remaining sample shall be dried to constant weight in a 125° F. oven or screen drier. The amount of material retained on the sieve shall be weighed, and this result shall be expressed as a percentage of the weight of the original dried sample. Two tests shall be conducted.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

4.4.7 Heat test. Five specimens of approximately 0.5 by 1.5 by 2.0 inches each shall be prepared for subjection to heat testing. After pouring the specimens, they shall be stored in air at room temperature for 1 hour. Immediately thereafter the specimens shall be subjected to the following heat cycle:

a. Place in furnace at 427° ± 10° C. (800° F.) and raise the furnace temperature to 850° ± 10° C. in 45 minutes.

b. Hold at 850° C. for 5 minutes.

c. Remove specimen to room temperature for 1 minute.

d. Replace in furnace at 850° C. for 5 minutes.

e. Remove specimen from furnace and immediately examine visually for cracks.

4.4.8 Net weight. The net weight of the investment shall be determined using a balance or scale suitable for the intended purpose.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue. One can containing five pounds of investment, as specified, constitutes one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in Table V shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Table V. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	Not required	12 units

5.1.2.1 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be over-packed in an exterior container, such units may be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

5.1.3 Level A.

5.1.3.1 Unit package. Five pounds of investment shall be packaged in a hermetically sealed metal container conforming to PPP-C-96, type III, plan A. Leakage test as specified in 3.7 of PPP-C-96 shall apply.

5.1.4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing.

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant, grade V3c. Closure and strapping shall be as specified in the appendix of the applicable box specification.

5.2.1.2 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes. Each fiberboard box shall be waterproofed in accordance with 30.4 of PPP-B-636.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification. Fiberboard box shall be closed by method II of PPP-B-636.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Unit packages. Each unit package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.2 Federal Stock Number (FSN) coverage. This specification covers the following item appearing in the Federal Supply Catalog:

Federal Stock Number	Item Identification
6520-536-8050	INVESTMENT, DENTAL, Soldering, 5 lb:Crown and Bridge

6.3 Specification changes. Because of the extensiveness of changes to this document, the margins have not been marked with an asterisk to indicate where changes from the previous issue have been made.

6.4 Limitations. This specification does not cover all types, classes, grades, styles, or sizes of the commodity indicated by the title of this specification, or those which are commercially available, but is intended to cover those items which are normally procured to meet Federal Government requirements.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Project No. 6520-1302

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER ON ANY CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM SINCE ANY CHANGES OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER NON-RESPONSIVE IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

Fold

FENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

DEFENSE SUPPLY AGENCY
OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

Fold

SC FORM 2418
MAR 68

EDITION AUG 66, WILL BE USED UNTIL EXHAUSTED

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

ORGANIZATION U-I-00552b (DSA-DM)

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64, WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.