U-P-00401F(DLA-DM)
March 14, 1978
Interim Revision of
Fec. Spec. U-P-401E
September 16, 1975

INTERIM FEDERAL SPECIFICATION

TAPE, ADHESIVE, SURGICAL

This interim Federal specification was developed by the Defense Personnel Support Center, 2800 South 20th Street, Philadelphia, PA 19101, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim Federal specification as a valid exception to Federal Specification U-P-401E, dated September 16, 1975.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers adhesive tape made of suitable cotton, synthetic, or combination thereof, fabric with an adhesive on one side for use in medical or surgical procedures.

1.2 Classification. The surgical tapes shall be of the following types of backing, sizes, colors, methods, and cut or uncut, as specified (see 6.2).

1.2.1 Types.

Type I - Standard base fabric, non-water-repellent.
Type II - Waterproof-back fabric.
Type III - Napped cotton-back cloth (Moleskin).

1.2.2 Sizes.

	Width-Inches		Length-Yards
Size 1	1/2	by	5
Size 2	1/2	by	10
Size 3	1	by	1
Size 4	1	by	5
Size 5	1	by	10
Size 6	2	by	5
Size 7	2	by	10
Size 8	3	by	5
Size 9	3	by	10
Size 10	12	by	5
Size 11	12	by	10

FSC 6510

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

1.2.3 Colors.

Color a - White
Color b - White or flesh colored
Color c - Camouflaged

1.2.4 Methods. Surgical tapes shall be supplied in rolls, spools, boxes or packages as specified (see 6.3).

1.2.5 Cut or uncut. Surgical tapes shall be provided uncut or cut into a specified number of tapes of specified widths (see 6.3).

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposals, form a part of the specification to the extent specified herein:

Federal Specifications:

CCC-C-665 - Crinoline; Surgical.
PPP-B-566 - Boxes, Folding, Paperboard.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-B-676 - Boxes, Set-Up.

Federal Standards:

Fed. Std. No. 123 - Marking for Shipment (Civil Agencies).
Fed. Test. Method Std. No. 191 - Textile Test Methods.
Fed. Std. No. 595 - Colors.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, US Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, WA.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply.

U.S. PHARMACOPEIAL CONVENTION INC.

Pharmacopeia of the United States (USP)

(Application for copies should be addressed to the Mack Publishing Company, Easton, PA 18042.)

3. REQUIREMENTS

3.1 Material.

3.1.2 Backing.

3.1.2.1 Type I. The backing of type I surgical adhesive tape shall be a plain weave, white, bleached-cotton, synthetic or combination thereof having not less than 96 yarns per square inch, when tested as specified in 4.5.4, and shall weigh not less than 1.7 ounces per square yard. It shall have a breaking strength not less than 35 pounds (in the warp) per inch of width, when tested as specified in 4.5.3. The running length of the fabric shall be in the warp direction.

3.1.2.2 Type II. The fabric, plus the water-repellent material forming the backing of type II surgical adhesive tape, shall weigh not less than 2.9 ounces per square yard and shall have a breaking strength of not less than 35 pounds (in the warp) per inch of width when tested as specified in 4.5.3. Base fabric shall be white, bleached cotton, synthetic or combination thereof, of plain weave having a minimum thread count of 96 threads per square inch and minimum weight of 1.7 ounces per square yard.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

3.1.2.3 Type III. The fabric forming the backing of type III, surgical adhesive tape shall be a thick, soft, napped, cotton backing, white or tinted (moleskin). The backing shall weigh not less than 9 nor more than 10.5 ounces per square yard and shall have a breaking strength of not less than 40 pounds (in the warp) per inch of width when tested as specified in 4.5.3. The running length of the fabric shall be in the warp direction.

3.1.3 Facing. Facing shall be polyethylene, crinoline, silicone treated release paper, or continuous organic film embossed or unembossed. If crinoline is used, it shall conform to the requirements of CCC-C-665, except that the basic fabric shall be type I, plain gauze.

3.2 Construction and design. Surgical adhesive tape shall consist of a backing fabric coated on one side with an adhesive mass. In addition, the type II backing shall be coated with a washable substance on the outer surface. The adhesive mass and method of application of the adhesive shall be as specified in 3.2.1. The adhesive shall comply with 3.2.1.4 and 3.2.1.5. A facing material, as specified in 3.1.3, shall be applied to the type III backing on the adhesive side. The facing shall be removable from the adhesive surface without excessive pull. The tape shall be supplied in rolls, uncut or cut into a specified number of widths, or in spools, boxes, or packages as indicated for the method specified (see 6.2).

3.2.1 Adhesive.

3.2.1.1 Type I coating. Type I backing shall be evenly coated on one side with a pressure sensitive adhesive mass. The base of the adhesive mass shall be natural rubber, synthetic rubber, or rubber substitutes. As an alternate to evenly coating, the adhesive mass shall be spread (calendered) in such a manner that numerous discrete open areas in the adhesive are present in a uniform pattern. Such a pattern may be lines (spaces) approximately 1/64 inch wide, 1/4 inch apart running at a 45° angle with the length of the tape.

3.2.1.2 Type II coating. Type II backing shall be coated on the outer surface with resins, esters of cellulose, or a similar water repellent and easily washable coating. The inner surface shall be calender spread with an adhesive mass as specified in 3.2.1.1.

3.2.1.3 Type III coating. Type III backing shall be calender spread with an adhesive mass as specified in 3.2.1.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

requirements.

3.2.1.4 Weight of adhesive mass. The minimum weight of the adhesive mass, when tested as specified in 4.5.1, shall be as follows:

Type I - 3.5 ounces per square yard
Type II - 3 ounces per square yard
Type III - 3 ounces per square yard

3.2.1.5 Adhesive quality. The adhesive quality of surgical adhesive tape shall be not less than 35 pounds when tested as specified in 4.5.2.

3.2.2 Dimensions. Surgical adhesive tape shall be furnished in the size specified and shall be uncut or cut into selected or assorted widths as specified (see 6.2). The actual length of each tape shall be not less than 98 percent of the specified length. The width of the tape shall be within ± 1/16 inch of the specified width. With the exception of type II, size 3, color c and type II, size 6, color a, five percent of the lot of tape of each size may be furnished in two pieces. Otherwise, the tape shall be of one continuous length.

3.2.3 Color. The surgical adhesive tape shall be white, flesh colored, or camouflaged (dyed brown) as specified (see 6.2). The camouflaged dye shall be colorfast when tested as specified in 4.5.5.

3.3 Workmanship. The adhesive tape shall be free from imperfections which might affect the appearance or serviceability of the tape. The adhesive mass and water-repellent substances shall be homogeneous and uniformly spread. Each size shall be evenly cut, free from ravels, extraneous matter, and excessive bumps. No residual film of adhesive shall cover the threads at the open areas, and the threads of the cloth shall not be damaged. The tape shall be wound on the rolls, spools, or cores with uniform pressure in such a manner as to prevent excessive sticking of the layers as the tape is unwound. Tape edges shall be straight or pinked, and the tape shall be evenly wound on the core.

3.4 Inspection/test dating period. The inspection test dating period shall be 24 months.

3.4.1 Delivery. Not more than 6 months shall have elapsed from the date of manufacture of the adhesive tape to the date of delivery to the Government.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:20Z
Check the source to verify that this is the currentversion before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual and auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of quality. Certificates of quality, supplied by the manufacturer of the materials may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the Item Identification, the name of the component/material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Inspection lot.

4.2.1 Raw materials. An inspection lot for raw material inspection shall be all material produced under the same conditions and controlled to the degree that uniformity of product within the designated lot can be assured. Lot identification of the raw material by the manufacturer is one method of control, as cited above, which is considered acceptable.

4.2.2 End product. An inspection lot for inspection of end product shall consist of all tapes of the same type produced under essentially the same conditions and offered for inspection at one time.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:20Z
Check the source to verify that this is the currentversion before use.

4.3 Sampling.

4.3.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, and table I. The unit of product for sampling purposes shall be a roll, spool, or core, as applicable.

TABLE I. Sampling for examination

	Inspection level	AQL (percent defective)
For visual examination		
Major A defects	S-2	1.0
Major B defects	S-1	1.0
Minor A defects	S-2	4.0
For dimensional examination	S-1	2.5

4.3.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and table II, for an Inspection level of S-1 and AQL of zero. The unit of product for sampling purposes shall be roll, spool, or core as applicable.

TABLE II. Sampling for tests

Characteristic	Requirement	Test procedure
Weight of backing	3.1.2	4.5.1
Weight, adhesive mass	3.2.1.4	4.5.1
Adhesive quality	3.2.1.5	4.5.2
Breaking strength	3.1.2	4.5.3
Thread count	3.1.2	4.5.4
Colorfast	3.2.3	4.5.5

4.4 Examination. The adhesive tape shall be examined to determine compliance with all requirements contained in this specification.

4.4.1 Classification of defects. Examination shall be conducted in accordance with the classification of defects listed in table III. Examination shall not be restricted to the classified possible defects listed below.

TABLE III. Classification of defects

Major A	
101	Tape rolls or spools not uniformly and smoothly wound.
102	Sides of tape rolls or spools not free of cuts or deformed areas.
Major B	
151	Adhesive separates from backing upon unwinding.
152	Tape, roll or spool, more than two pieces.
153	Tape in roll or spool not free from holes, tears, breaks, cuts, or splits.
154	Adhesive coating on roll or spool not uniform and free of breaks.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:20Z
Check the source to verify that this is the current version before use.

TABLE III. Classification of defects (Continued)

Minor A	
201	Tape roll or spool crushed to the extent of presenting an oval rather than a round profile.
202	Color not as specified.

4.4.2 Dimensional examination. The tape shall be examined for defects in dimensions. Any dimension not within the tolerances specified herein shall be classified as a defect. Measure the width of the plaster at five points evenly spaced throughout the length of the roll or spool; the average of the five measurements shall be the width of the tape. Length of surgical adhesive tape shall be measured under only sufficient tension to straighten the tape and prevent wrinkles.

4.4.3 Examination of preparation for delivery. An examination shall be made to determine compliance with the packaging, packing and marking requirements of section 5. Defects shall be scored as specified in table IV. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 with AQL of 4.0 expressed in terms of percent defective.

TABLE IV. Examination of preparation for delivery

Examine	Defect
Contents	Not as specified.
Container	Not as specified.
Marking	Omitted; incorrect; illegible; improper size, location, sequence or method of application.
Material	Component missing or damaged.
Workmanship	Bulging or discoloration of containers.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:20Z
Check the source to verify that this is the currentversion before use.

4.4.3.1 Examination of closure, waterproofing and banding of containers. When the containers are required to comply with PPP-B-566, PPP-B-636, or PPP-B-676 the examination for defects in closure, waterproofing or banding shall be in accordance with the appendix of the box specification.

4.5 Tests.

4.5.1 Weight, backing, and adhesive mass. The weight of a sample measuring 20 square inches shall be determined. The sample shall be placed mass side down on a glass plate and the backing wetted with Petroleum Ether, USP. After 30 seconds, the backing shall be stripped from the glass plate leaving the bulk of the mass behind. The remaining mass shall be removed from the sample by repeated immersion in Petroleum Ether. The fabric backing shall then be air dried and the weight determined. The weight of the adhesive mass is the original weight of the adhesive tape, minus the determined weight of the backing. This factor multiplied by a factor of 2.28 will convert the actual mass weight into ounces per square yard. Where necessary, the sample for the test may be taken before slitting, cutting, rolling to specified end product design.

4.5.2 Adhesive quality. The adhesive quality of all types of tape shall be determined by cutting strips 1 inch wide and approximately 6 inches long from each sample unit selected for test. Two square inches (1 by 2 inches) of these strips shall be applied to a bakelite surface by means of a rubber roller under pressure of 30 ounces. The rubber roller shall have a durometer hardness of 70-80. The roller shall pass over the tape twice at the rate of 12 inches per minute. The temperature of the bakelite surface and the tape shall be conditioned to approximately 37° centigrade, and immediately tested. The tape shall be pulled (sheared) from the board by means of the machine specified in method 5100 of Fed. Test Method Std. No. 191, the jaws separating at the rate of 12 $\pm$ 0.5 inches per minute. The adhesive quality shall be the average of the results obtained from not less than five specimens from each sample roll.

4.5.3 Breaking strength of cloth backing. Each sample unit shall be tested to determine the breaking strength of the cloth backing as specified in method 5102 of Fed. Test Method Std. No. 191. Test shall be conducted without the removal of the adhesive mass or other soluble material(s). The breaking strength of the cloth backing shall be the average of the results obtained from not less than five specimens from each sample roll.

4.5.4 Thread count of cloth backing. The total number of yarns per square inch (warp and filling) shall be counted on five specimens from each sample roll. The average of the results obtained on the five specimens shall be the thread count for the sample roll.

4.5.5 Colorfastness. The camouflage tape shall be tested for colorfastness as specified in Fed. Test Method Std. No. 191.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:20Z
Check the source to verify that this is the currentversion before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, or C (commercial), as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Unit package.

5.1.1.1.1 Size 1, 2, 4, 5, 7, 8 and 9. Tape of one type and size only shall wound on a metal spool and the spool inserted into a metal sleeve so designed tha the spool may be easily removed and returned to the sleeve. Spools and sleeves containing camouflaged tape shall have the exterior surfaces coated with a luste olive drab color, comparable to color number 34097 shown in Fed. Std. No. 595.

5.1.1.1.2 Size 11. Tape shall be evenly wound on a suitable paperboard tube Uniform pressure shall be used to prevent excessive sticking of the tape in unwinding for use. The twelve inch roll shall be slit to give the number of roll of tape and the dimensions as specified in 6.3. The cut rolls shall be assemble on a suitable spiral wound paperboard core or other suitable material. The core shall be approximately 1/2 inch longer than the entire roll. The diameter of th core shall be such as to permit ready dispensing of each roll of tape. A suitab disk separator shall be placed between adjacent cut rolls and on the outer ends the roll to prevent adhesion of the rolls. Rolls assembled on the core shall be packaged in a cylindrical paperboard container fitted with metal ends or in a folding box fabricated of not less than 30-point solid kraft board and having a minimum bursting strength of not less than 175 pounds. The container shall include interior fittings to center the rolls within the container to prevent the rolls from contacting the interor side walls. Closure shall be secured with tape by other suitable means.

5.1.1.1.3 Size 10. Each twelve inch by five yards of tape shall be formed i a roll and packaged in a cylindrical spiral wound fiber container with ends of metal or other suitable material.

5.1.1.1.4 Size 6. Each two inch by five yards of tape shall be wound on a m spool and inserted into a metal sleeve as specified in 5.1.1.1.1. Thirty-six spools shall be further packaged in a box conforming to PPP-B-636, class domesti Closure shall be as specified in the appendix of the box specification.

5.1.1.1.5 Size 3. Each one inch by one yard of tape shall be evenly wound o a flat waxed cardboard core. The core may be first wound with one turn of crino or other suitable material in order that the tape may be stripped completely and cleanly from the core. Each wound strip shall be packaged in an extruded, lay flat 100 percent, virgin polyethylene tubing having a minimum thickness of 0.00225 inches, a maximum of 1-3/8 inches + 1/8 inch in width and 2-5/8 inches i length. Closure shall be effected by heat sealing. The maximum dimension of th package tape with end of the bag folded back on the flattened tape and core unit shall be 2 inches in length, 1/4 inch in thickness and 1 + 1/16 inch in width. One hundred individually packaged wound strips of adhesive shall be further pack in a snug fitting box constructed in accordance with PPP-B-566 or PPP-B-676. Closure of the box shall be as specified in the appendix of the applicable box specification.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:20Z
Check the source to verify that this is the current version before use.

5.1.1.2 Intermediate package.

5.1.1.2.1 Size 1, 2, 4, 5, and 11. Twelve unit packages shall be packaged in a box conforming to PPP-B-566, or PPP-B-676. Closure shall be as specified in the appendix of the applicable box specification.

5.1.1.2.2 Size 7, 8 and 9. Six unit packages shall be packaged as specified in 5.1.1.2.1.

5.1.1.2.3 Size 3, 6 and 10. An intermediate package shall not be required.

5.1.2 Level C (commercial).

5.1.2.1 Sizes 1, 2, 4, 5, 7, 8 and 9. Tape shall be clean, dry and packaged as specified in 5.1.1.1.1.

5.1.2.2 Size 3. Each one inch by one yard tape shall be clean, dry wound and packaged in a polyethylene bag as specified in 5.1.1.1.5. One hundred bags shall be further packaged in a manner that will afford adequate protection against deterioration and physical damage during shipment from the supply source to the first receiving activity.

5.1.2.3 Size 10. Each twelve inch by five yards shall be packaged as specified in 5.1.1.1.3.

5.1.2.4 Size 6. Each two inch by five yards of tape shall be packaged as specified in 5.1.1.1. Thirty-six spools shall be further packaged in the same manner as specified for the one hundred bags specified in 5.1.2.2.

5.1.2.5 Size 11. Each twelve inch by ten yards of tape wound on a tube, slit and assembled on a core as specified in 5.1.1.1.2 shall be packaged in a manner that will afford adequate protection against deterioration and physical damage as specified in 5.1.2.2.

5.2 Packing. Packing shall be level A, B or C (commercial) as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Size 3, 6 and 10. Twenty-four unit packages containing size 3, four unit packages containing size 6 or twelve unit packages containing size 10 shall be packaged in a shipping container designed for a type 2 load and conforming to PPP-B-636 class weather-resistant. Closure, banding and waterproofing shall be as specified in the appendix of the box specification.

5.2.1.2 Size 1, 2, 5 and 9. Twelve intermediate packages containing tape of one size only shall be packed in a shipping container as specified in 5.2.1.1.

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:20Z
Check the source to verify that this is the currentversion before use.

5.2.1.3 Size 4, 7 and 9. Twenty-four intermediate packages containing tape of one size only shall be packed in a shipping container as specified in 5.2.1.1.

5.2.1.4 Size 11. Two intermediate packages containing size 11 tapes shall be packaged in a vertical position in a shipping container as specified in 5.2.2.

5.2.2 Level B. Tapes of the size specified shall be packed in shipping containers as specified in 5.2.1 except that the shipping container shall conform to PPP-B-636, class domestic and waterproofing and banding shall not be required.

5.2.3 Level C (commercial). The packaged tapes shall be packed in shipping containers in a manner that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the carriers rules and regulations.

5.3 Marking.

5.3.1 Civil agencies. Marking shall be as specified in Fed. Std. No. 123.

5.3.2 Military activities.

5.3.2.1 Individual container.

5.3.2.1.1 Size 3 and 6. Marking is not required for polyethylene bags containing size 3 tape. Each spool or sleeve containing size 6 tape shall be marked in accordance with the requirements of the Federal Food, Drug and Cosmetic Act and the contractors commercial practice. In addition, the lot or control number and date of manufacture shall be shown.

5.3.2.2 Unit package. Each unit package shall be marked as specified in MIL-STD-129 and the requirements of the Federal Food, Drug and Cosmetic Act. In addition, the name and address of the manufacturer, lot or control number, and date of manufacture shall be shown. The date of manufacture may be shown on the unit package or on the tape. If the date of manufacture is placed on the tape, it shall be located as to be readily visible upon removal of the spool or roll from the unit package. Type II shelf life marking as specified in MIL-STD-129 shall also be shown. Marking shall include the legend: "STORE AT CONTROLLED ROOM TEMPERATURE 15° - 30° C. (59° - 86° F.)".

5.3.2.3 Intermediate package. Each intermediate package shall be marked as specified in MIL-STD-129. The lot or control number and type II shelf life marking as specified in MIL-STD-129 shall also be shown. Marking shall include the legend: "STORE AT CONTROLLED ROOM TEMPERATURE 15° - 30° C. (59° - 86° F.)".

5.3.2.4 Shipping container. Shipping containers shall be marked as specified in MIL-STD-129. The lot or control number and type II shelf life marking, as specified in MIL-STD-129, shall be shown. Marking shall include the legend: "STORE AT CONTROLLED ROOM TEMPERATURE 15° - 30° C. (59° - 86° F.)".

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:20Z
Check the source to verify that this is the current version before use.

5.3.2.5 Special marking.

5.3.2.5.1 Size 11. The unit package shall be marked with the legend: "STORE ON END" and the intermediate and shipping container shall be marked with arrows and the word "UP" as specified in MIL-STD-129.

6. NOTES

6.1 Intended use. Shall be suitable for use in medical and surgical procedures.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents.

a. Title, number and date of this specification.
b. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
c. Required type, size, color, method of packaging, uncut or cut into a specific number of specific widths (see 1.2).

6.3 This specification covers the following items appearing in the Federal Supply Catalog:

NSN	Item Identification	Type	Size	Color	Uncut/ cut	Method of Packaging
6510-00-203-5000	ADHESIVE TAPE, SURGICAL, 3 inches by 5 yards	I	8	a	Uncut	Spool
6510-00-203-5500	ADHESIVE TAPE, SURGICAL, 12 inches by 10 yards	I	11	a	4 ea - 1/2" 3 ea - 1" 2 ea - 2" 1 ea - 3"	Roll
6510-00-203-6010	ADHESIVE TAPE, SURGICAL, 12 inches by 5 yards: Moleskin	III	10	b	Uncut	Roll
6510-00-512-4570	ADHESIVE TAPE, SURGICAL, 2 inches by 5 yards, 36s	II	6	a	Uncut	Package
6510-00-526-0162	ADHESIVE TAPE, SURGICAL, CAMOUFLAGED, 1 inch by 5 yards	I	4	c	Uncut	Spool
6510-00-550-8501	ADHESIVE TAPE, SURGICAL, 2 inches by 10 yards	I	7	a	Uncut	Spool
6510-00-782-6426	ADHESIVE TAPE, SURGICAL, CAMOUFLAGED, 1 inch by 1 yard, 100s	I	3	c	Uncut	Box

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:20Z
Check the source to verify that this is the currentversion before use.

6.4 Surgical adhesive tapes are available from the industry in a wide variety of widths and lengths and in a wide variety of combinations of widths.

Preparing activity:
DLA-DM

Project No. 6510-0630

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS. This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE. This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

U-P-00401F(DLA-DM) TAPE, ADHESIVE, SURGICAL

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1426 1 OCT 76

Replaces edition of 1 Jan 72 which may be used.

S/N 0102-LF-001-4260

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:20Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID
DEPARTMENT OF THE NAVY
DoD-316



OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

DEFENSE PERSONNEL SUPPORT CENTER
DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:20Z
Check the source to verify that this is the current version before use.