INCH-POUND

MIL-C-71165 (AR)
15 June 1993

MILITARY SPECIFICATION

CONTAINER, AMMUNITION, LIGHTWEIGHT METAL FOR
TOW 2A GUIDED MISSILE, SURFACE ATTACK: BGM - 71E - 5B WEAPON SYSTEM

This specification is approved for use by the U.S. Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers requirements and quality assurance provisions for the manufacture of a metal container used for packing TOW 2A 71E - 5B Weapon System (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

TT-C-490 - Cleaning Methods for ferrous Surfaces and Pretreatments for Organic Coatings

MILITARY

MIL-W-12332 - Welding Resistance, Spot, Seam and Projection, for Fabricating Assemblies of Low-Carbon Steel

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document, should be addressed to: Commander, U.S. Army ARDEC, ATTN: SMCAR-BAC-S, Picatinny Arsenal, NJ 07806-5000 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8140

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

MIL-A-48078 - Ammunition, Standard Quality Assurance Provisions, General Specification for
MIL-A-70625 - Automated Acceptance Inspection Equipment Design, Testing and Approval of

STANDARDS

MILITARY

MIL-STD-171 - Finishing of Metal and Wood Surfaces
MIL-STD-1235 - Single and Multilevel Continuous Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-1261 - Arc Welding Procedures for Constructional Steel

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the DODSSP - Customer Service, Standardization Documents Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWINGS

U.S. ARMY ARMAMENTS RESEARCH, DEVELOPMENT AND ENGINEERING CENTER (ARDEC)

12953476 - Container, Ammo, Metal TOW 2A

(Copies of other Government documents, drawings, and publications required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Non-Government publications. The following document(s) form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM-D3951 - Standard Practice for Commercial Packaging (DOD adopted)

(Applications for copies for ASTM publications should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein (except for related associated detail specifications, specification sheets or MS standards), the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Materials. Materials and parts shall be in accordance with applicable drawings and specifications.

3.2 Containers. The containers (container assemblies) shall comply with all requirements specified on Drawing 12953476 as applicable and associated drawings and with all requirements specified in applicable specifications and standards.

3.3 Welding. The welding shall comply with the requirements of MIL-W-12332 or MIL-STD-1261.

3.3.1 Tensile strength of body weld. The tensile strength of the longitudinal body weld shall not be less than 65 percent of the tensile strength of body material.

3.3.2 Tensile strength of body material. The tensile strength of the body material shall not be less than 60,000 pounds per square inch (psi).

3.4 Painted surface. The painted surfaces of the container shall comply with the requirements of TT-C-490. However, the film thickness and salt spray requirements of TT-C-490 shall not apply to the interior surfaces, exterior surface welded spots and exterior surface sharp corners of the container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

3.5 Cover assembly. Upon assembly of the cover assembly to the body assembly (body weldment), the cover assembly shall freely engage and rotate within the body assembly. As the cover assembly is rotated with the "D" handle in the open position, the "D" handle shaft ends shall freely engage into the respective bayonet slots of the rim. Rotation of the cover assembly will permit disengagement from the body assembly when the spring clip is disengaged.

3.6 Air pressure test.

3.6.1 Air pressure of unpainted cover assembly. The unpainted cover assembly shall withstand an internal air pressure of three psi for five (5) seconds minimum. A leak rate in excess of 5 cc/min shall be cause for rejection.

3.6.2 Air pressure of unpainted body assembly. The unpainted body assembly shall withstand an internal air pressure of three psi for five (5) seconds minimum. A leak rate in excess of 5 cc/min shall be cause for rejection.

3.7 First article inspection. This specification contains technical provisions for first article inspection. Requirements for the submission of first article samples by the contractor shall be as specified in the contract.

3.8 Workmanship.

3.8.1 Containers. The containers shall be regular, smooth, and free from wrinkles, pin holes, cracks, rough spots, burrs, sharp edges and any other defect that might affect the serviceability, durability, and safety of the container.

3.8.2 Paint coating. The paint coating shall be in accordance with applicable drawings and comply with instructions in MIL-STD-171.

3.8.3 Parts. All parts shall be free of chips, dirt, grease, rust and foreign material. The cleaning method used shall not be injurious to any of the parts nor shall any of the parts be contaminated by the cleaning agents used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of Sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2. General provisions. Unless otherwise specified herein, the provisions of MIL-A-48078 apply and form a part of this specification. Reference shall be made to MIL-STD-109 to define quality assurance terms used herein.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).

b. Quality conformance inspection (see 4.4).

4.3 First article inspection.

4.3.1 Submission. The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article sample shall consist of the assemblies, components and test specimens listed below in the quantities indicated.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

4.3.2 Inspections to be performed. As determined by the Government, the first article assemblies, components and test specimens may be subjected to any or all of the examinations and tests specified in this detail specification and be inspected for compliance with any or all requirements of the applicable drawings.

4.3.3 Rejection. If any assembly, component or test specimen fails to comply with any of the applicable requirements, the first article sample shall be rejected. The Government reserves the right to terminate inspection upon any failure of an assembly, component or test specimen to comply with any of the requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE Assemblies and Components	SHEET 1 OF 2	DRAWING NUMBER See below
			NEXT HIGHER ASSEMBLY

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
	Container assemblies, painted (Dwg. 12953476 as applicable)			
	Examination for defects	5	3.2	4.4.2.17
	Air pressure	15	3.6	4.5.4.2
	Painted surface 1/	3	3.4	4.5.5
	Body assembly (weldment), unpainted (Dwg. 12944493)			
	Examination for defects	10	3.2	4.4.2.16
	Air pressure	5	3.6.2	4.5.4.1
	Weld strength of rim to body 1/	5	3.3	4.5.2
	Cover assembly, unpainted (Dwg. 12944491)			
	Air pressure	5	3.6.1	4.5.4.1
	Examination for defects	5	3.2	4.4.2.10
	Cover assembly, painted (Dwg. 12944491)			
	Examination for defects	5	3.2	4.4.2.11

NOTES

1/ The weld security inspections and painted surface shall be performed after the other inspections have been performed on the applicable samples.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

TABLE I - First article inspection

CLASSIFICATION OF CHARACTERISTICS

MIL-C-71165 (AR)

PARAGRAPH	TITLE	SHEET 2 OF 2	DRAWING NUMBER
	Assemblies and Components		See below
			NEXT HIGHER ASSEMBLY

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
	Body, Unpainted (Dwg. 12944487)			
	Examination for defects	10	3.2	4.4.2.16
	Tensile strength 1/	5	3.3.1	4.5.1
	Cover, Weldment (Dwg. 12944492)			
	Examination for defects	10	3.2	4.4.2.9
	Spring Clip (Dwg. 12934837)			
	Examination for defects	10	3.2	4.4.2.1
	Gasket (Dwg. 12944489)			
	Examination for defects	10	3.2	4.4.2.8
	Hardness	5	3.2	4.5.3
	Remaining Subassemblies and Components			
	Examination for defects	10	3.2	Applicable subparagraph of 4.4.2
	Rim (Dwg. 12944480)	10	3.2	4.4.2.12

NOTES 1/ The weld security inspections and painted surface shall be performed after the other inspections have been performed on the applicable samples.

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection.

4.4.1 Inspection lot formation. The term "inspection lot" is defined as a homogeneous collection of units of product from which a representative sample is drawn or which is inspected 100 percent to determine conformance with applicable requirements. Units of product selected for inspection shall represent only the inspection lot from which they are drawn and shall not be construed to represent any prior or subsequent quantities presented for inspection. Homogeneity shall be considered to exist provided the inspection lot has been produced by one manufacturer, in one unchanged process, using the same materials and methods, in accordance with the same drawings, same drawing revisions, same specifications and same specification revisions. All material submitted for inspection in accordance with this specification shall comply with the homogeneity criteria specified herein, regardless of the type of inspection procedure which is being applied to determine conformance with requirements.

4.4.2 Examinations and tests.

a. Classification of characteristics. Quality conformance examinations and tests are specified in the following Classification of Characteristics paragraphs. The contractor's quality program or detailed inspection system shall provide assurance of compliance of all characteristics with the applicable drawing and specification requirements utilizing as a minimum the conformance criteria specified. When cited herein, attributes sampling inspection shall be conducted in accordance with Table II below, using the inspection levels stated in the Classification of Characteristics paragraphs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

TABLE II. Attributes sampling inspection

Lot Size	Inspection Levels					
	I	II	III	IV	V	VI
2 to 8	*	*	*	*	5	3
9 to 15	*	*	*	13	5	3
16 to 25	*	*	*	13	5	3
26 to 50	*	*	32	13	5	3
51 to 90	*	*	32	13	12	4
91 to 150	*	125	32	13	12	5
151 to 280	*	125	32	30	14	6
281 to 500	*	125	32	30	17	7
501 to 1200	*	125	74	35	20	9
1201 to 3200	1250	125	74	43	24	10
3201 to 10000	1250	125	87	50	30	10
10001 to 35000	1250	296	109	61	36	10
35001 to 150000	1250	296	124	74	40	10
150001 to 500000	1250	346	156	91	40	10
500001 and over	1250	431	187	102	40	10

Numbers under inspection levels indicate sample size; asterisks (*) indicate one hundred percent inspection. If sample size exceeds lot size, perform one hundred percent inspection. Accept on zero and reject on one or more for all inspection levels.

b. Alternative quality conformance provisions. Unless otherwise specified herein or provided for in the contract, alternative quality conformance procedures, methods or equipment, such as statistical process control, tool control, other types of sampling plans, etc., may be used by the contractor when they provide, as a minimum, the level of quality assurance required by the provisions herein. Prior to applying such alternative procedures, methods or equipment, the contractor shall describe them in a written proposal submitted to the Government for evaluation (see 6.5). When required, the contractor shall demonstrate that the effectiveness of each proposed alternative is equal to or better than the specified quality conformance provision(s) herein. In case of dispute as to whether the contractor's proposed alternative(s) provides equivalent assurance, the provisions of this specification shall apply. All approved alternative provisions shall be specifically incorporated into the contractor's quality program or inspection system, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.1	Spring Clip, Hairpin	1 OF 1	12934837
			NEXT HIGHER ASSEMBLY 12953476

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	True position of holes	Level III	3.2	Gage
102	Radius of bend	Level III	3.2	Gage
103	Length from end to lower edge of bend	Level III	3.2	Gage
104	Thickness	Level III	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

MIL-C-71165 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.2	Support, Shaft	1 OF 1	12960992
			NEXT HIGHER ASSEMBLY 12944491

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Diameter of large hole, maximum (max.)	Level III	3.2	Gage
102	True position of large hole	Level III	3.2	Gage
103	True position of slot	Level III	3.2	Gage
104	True position of holes located on side (used for assembly of spring and clamp)	Level III	3.2	Gage
105	Distance between shaft support uprights	Level III	3.2	Gage
106	Material thickness	Level IV	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

AMSMC Form 1570b, 1 Jul 89 Replaces 1570, 1 Feb 85, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION
CLASSIFICATION OF CHARACTERISTICS

MIL-C-71165 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.3	Handle, Square	1 OF 1	12944482
			NEXT HIGHER ASSEMBLY 12944491

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Width of hexhole, max. (three readings, 60 degrees apart)	Level III	3.2	Gage
102	True position of small hole (two places)	Level III	3.2	Gage
103	Width of spring slot	Level III	3.2	Gage
104	Length of spring slot (Dim B)	Level III	3.2	Gage
105	Material thickness	Level IV	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.4	Shaft	1 OF 1	12944484
			NEXT HIGHER ASSEMBLY 12944491

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Width across flats of hexagon segment minimum (min.) (three readings, 60 degrees apart)	Level III	3.2	Gage
102	Length of hexagon segment of shaft	Level III	3.2	Gage
103	Length of small diameter segment (two places)	Level III	3.2	Gage
104	Large diameter (two places)	Level III	3.2	Gage
105	Small diameter (two places)	Level III	3.2	Gage
106	Total length of large diameters and hexagon segments (Dim B)	Level III	3.2	Gage
107	Small diameter segment not tangent to large diameter segment and side of hexagon segment	Level III	3.2	Visual
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

AMSMC Form 1570b, 1 Jul 89 — Replaces 1570, 1 Feb 85, which may not be used

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.5	Washer	1 OF 1	9344038
			NEXT HIGHER ASSEMBLY 12944491

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	Washer			
Major				
101	Inside diameter	Level III	3.2	Gage
102	Height, min.	Level III	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

AMSMC Form 1570b, 1 Jul 89

Replaces 1570, 1 Feb 85, which may not be used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

MIL-C-71165 (AR)

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.6	Retainer, Washer	1 OF 1	9344041
			NEXT HIGHER ASSEMBLY 12944491

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Height	Level III	3.2	Gage
102	Diameter of hole	Level III	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

AMSMC Form 1570b, 1 Jul 89

Replaces 1570, 1 Feb 85, which may not be used

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION
CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.7	Cover	1 OF 1	12944485
			NEXT HIGHER ASSEMBLY 12944491

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Outside diameter, max.	Level III	3.2	Gage
102	Width of groove	Level III	3.2	Gage
103	Depth from top cover to recess	Level III	3.2	Gage
104	Height of threads, min., when applicable 1/	Level III	3.2	Gage
105	Flatness of bottom surface inner annular ring and surrounding air test hole	Level III	3.2	Gage
106	Material thickness	Level IV	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES 1/ Threads may be formed on cover (instead of cover assembly)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION
CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.8	Gasket	1 OF 1	12944489
			NEXT HIGHER ASSEMBLY 12944491

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Inside diameter, max. (Dim A)	Level III	3.2	Gage
102	Large width	Level III	3.2	Gage
103	Middle width	Level III	3.2	Gage
104	Height of rectangular cross section	Level III	3.2	Gage
105	Material certification		3.2	Certification
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION
CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.9	Cover Weldment	1 OF 1	12944492
			NEXT HIGHER ASSEMBLY 12944491

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	True position of shaft support	Level III	3.2	Gage
102	Weld missing, incomplete or visually inadequate	Level III	3.2	Visual/Manual
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION
CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.10	Cover Assembly, Prior to Painting	1 OF 1	12944491
			NEXT HIGHER ASSEMBLY 12953476

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	.725 Distance from top of shaft (in closed position) to inside surface of the gasket retainer section of cover	Level II	3.2	Gage
102	Component missing or inadequately assembled	Level III	3.2	Visual
103	Rotating of shaft inadequate after crimping	Level III	3.2	Manual
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.11	Cover Assembly, Painted	1 of 1	12944491
			NEXT HIGHER ASSEMBLY 12953476

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major 101	Gasket not secured or secured improperly to cover	Level III	3.2	Visual/Manual
Minor 201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.12	Rim	1 OF 1	12944480
			NEXT HIGHER ASSEMBLY 12944493

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of larger slot (on side of rim), max.	Level III	3.2	Gage
102	Width of larger slot (on side of rim), max.	Level III	3.2	Gage
103	Location of bayonet slot, four places 1/	Level III	3.2	Gage
104	Inside diameter of rim, two places (Dim E)	Level III	3.2	Gage
105	Outside dimension across flats, two places (Dim A)	Level III	3.2	Gage
106	Outside dimension across corners, two places (Dim D)	Level III	3.2	Gage
107	Radius at beginning of locking edge of bayonet slot missing 1/	Level IV	3.2	Visual
Minor				
201	Drainage hole missing	Level IV	3.2	Visual
202	Step at inside of locking edge of bayonet slot missing 1/	Level IV	3.2	Visual
203	Evidence of poor workmanship	Level V	3.8	Visual

NOTES 1/ Inspections 103, 107 and 202 may be done on the next higher assembly (Dwg. 12944493)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION
CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.13	Bottom	1 OF 1	12944486
			NEXT HIGHER ASSEMBLY 12944493

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Height, minimum (min.)	Level III	3.2	Gage
102	Material thickness	Level IV	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

AMSMC Form 1570b, 1 Jul 89

Replaces 1570, 1 Feb 85, which may not be used

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION
CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.14	Body	1 OF 1	12944487
			NEXT HIGHER ASSEMBLY 12944493

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length, min.	Level III	3.2	Gage
102	Inside diameter, min. 1/	Level III	3.2	Gage
103	Flatness of body end 1/	Level III	3.2	Gage
104	Material thickness	Level IV	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.15	Plug, Stacking	1 OF 1	9386837
			NEXT HIGHER ASSEMBLY

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Length of plug, min.	Level III	3.2	Gage
102	Width of plug, min.	Level III	3.2	Gage
Minor				
201	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION
CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.16	Body Assembly (Weldment)	1 OF 1	12944493
			NEXT HIGHER ASSEMBLY 12953476

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	True position of slots of rims to each other	Level III	3.2	Gage
102	True position of stacking plugs of rims to each other	Level III	3.2	Gage
103	Perpendicularity of rim with datum A	Level III	3.2	Gage
104	Inside diameter of body, min.	Level III	3.2	Gage
105	Body (seam) weld (if applicable) or rim or bottom to body missing, incomplete or visually inadequate	Level III	3.2	Visual
106	Paint thickness, min.	Level IV	3.2	Gage
107	Shear load min. between stacking plug and rim 1/	Level V	3.2	Gage
108	Shear load min. between stacking plug and ring 1/	Level V	3.2	Gage
Minor				
201	Marking missing, illegible or incorrect	Level V	3.2	5.3/Visual
202	Evidence of poor workmanship	Level V	3.8	Visual

NOTES 1/ These shear load inspections may be performed on the subassembly.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.17	Container Assembly	1 OF 1	12953476
			NEXT HIGHER ASSEMBLY

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Cover assembly assembled to body assembly	Level III	3.5	Visual
Minor				
201	Protective finish damaged, bare spots exposing metal, etc.	Level IV	3.2	Visual
202	Evidence of poor workmanship	Level V	3.8	Visual

NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

4.4.3 Testing.

4.4.3.1 Tensile strength of body material and weld (see 3.3), Major defect. During the first half of a production shift and during the last half of a production shift, a body shall be selected for this test. From each body, three (3) specimens shall be selected at random for determination of body material tensile strength. Also from each body, four (4) specimens, approximately equally spaces along the axis, shall be taken at right angles to the weld and the tensile strength of their welds shall be determined. Each of these values shall be compared with the lowest determined value of the body material tensile strength for compliance with the requirement of 3.3.1. If one or more specimens (longitudinal body weld or body material) fail to comply with 3.3.1 or 3.3.2, the quantity of bodies which were welded during this shift and the earlier strength test (if applicable) shall be rejected. The test shall be performed as specified in 4.5.1.

4.4.3.2 Weld strength of rim to body (see Dwg. 12944480), Major defect. During the first half of a production shift and during the last half of a production shift, a body assembly shall be randomly selected for this test. From each body assembly, two (2) specimens of welded rim to body segments shall be taken at random. If any specimen fails to meet the requirement when tested in accordance with 4.5.2, the quantity of body assemblies which were welded during this shift between this weld strength test and the earlier weld strength test and (if applicable) shall be rejected.

4.4.3.3 Hardness of gasket (see Dwg. 12944489), Major defect. Five (5) gaskets shall be randomly selected from each lot for this test. If any gasket fails to meet the requirement, the lot shall be rejected. The test shall be performed as specified in 4.5.3.

4.4.3.4 Air pressure.

4.4.3.4.1 Air pressure of unpainted cover assembly (see 3.6.1), Major defect. The cover assemblies shall be checked 100 percent. If any cover assembly fails to comply with the requirement, the cover assembly shall be rejected. The test shall be performed as specified in 4.5.4.1.

4.4.3.4.2 Air pressure of unpainted body assembly (body weldment) (see 3.6.2), Major defect. The body assemblies shall be checked 100 percent. If the body assembly fails to comply with the requirement, the body assembly shall be rejected. The test shall be performed as specified in 4.5.4.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

4.4.3.4.3 Air pressure of painted container assembly (see Dwg. 12953476 as applicable), Major defect. The test shall be performed as specified in 4.5.4.2. The container assemblies shall be checked 100 percent. If the container assembly fails to comply with the requirement, the container assembly shall be rejected.

4.5.3.5 Painted surface (see 3.4), Major defect. Sampling shall be in accordance with TT-C-490 and testing shall be in accordance with 4.5.5.

4.4.4. Inspection equipment. The inspection equipment required to perform the examinations and tests prescribed herein is described in the "Paragraph Reference/Inspection Method" column in the tables starting with paragraph 4.4.2.1 and in 4.5. When Automated Acceptance Inspection Equipment is to be used, the provisions of MIL-A-70625 shall apply. The contractor shall submit for approval inspection equipment designs in accordance with the terms of the contract. See section 6 of MIL-A-48078 and 6.3 herein.

4.5 Methods of inspection. (see 6.4)

4.5.1 Tensile strength of body material and weld. The tensile strength shall be determined in accordance with ASTM-E8.

4.5.2 Weld strength of rim to body. The strength of the weld shall be determined in accordance with ASTM-E8.

4.5.3 Hardness of gasket. The hardness shall be determined in accordance with ASTM-D2240.

4.5.4 Air pressure test.

4.5.4.1 Air pressure of unpainted cover assembly and unpainted body assembly. (Water immersion method) Subject the cover assembly and container body to the specified internal air pressure for the test time specified. For the cover assembly, apply the pressure when the cover assembly is assembled to a master body assembly (or its equivalent) equipped with a gasket. For the body assembly, apply the pressure when the body assembly is assembled to master cover (or equivalent) and gasket. The master cover and the master body assembly shall be provided with satisfactory means for applying and maintaining the pressure during the test and for showing evidence of leakage. Observation shall be made for the presence of bubbles. No bubbles (other than surface bubbles) shall be permitted. A cover assembly or body assembly which does not meet the requirements, shall be classed defective.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

4.5.4.2 Air pressure of painted container assembly. Subject the painted container assembly to an air pressure test as specified in the applicable container assembly drawing. A container assembly which does not meet the requirement, shall be classed defective. When cover assemblies or body weldments (container bodies) are procured separately, the contractor shall submit for Government (SMCAR-QAT-B) approval, the test procedure that will be followed to meet the applicable test requirement.

4.5.5. Painted surface. The painted container assembly shall be tested in accordance with TT-C-490.

5. PACKAGING

5.1 Packaging requirements. None required.

5.2 Packing. Packing shall be commercial. Missile containers shall be prepared in accordance with ASTM-D3951.

5.3 Marking. Shipping marking shall comply with ASTM-D3951 and the following additional instructions. No shipping markings shall be placed directly on the containers. Commercial shipping tags attached with wire shall be used unless otherwise specified. The following information shall be shown: Item name and model number, part number and revision, contract number, lot number and date, name and address of manufacturer. If containers are bundles, boxed or palletized, the gross weight and quantity shall be included. The above information may be placed on pallets or boxes by labelling or stenciling.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. This lightweight metal ammunition container is used for packing TOW 2A 71E - 5B Weapon System.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number and date of this specification.

b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

6.3 Submission of contractor inspection equipment designs for approval. Submit copies of designs as required to: Commander, U.S. Army ARDEC, ATTN: SMCAR-QAT-I, Picatinny Arsenal, NJ 07806-5000. This address will be specified on the Contract Data Requirements List, DD Form 1423 in the contract.

6.4 Equivalent test methods. Prior approval of the Contracting Officer is required for use of equivalent test methods. A description of the proposed method should be submitted through the Contracting Officer to: Commander, U.S. Army Armament Research, Development and Engineering Center, ATTN: SMCAR-QAT-B, Picatinny Arsenal, NJ 07806-5000. This description should include but not be limited to the accuracy and precision of the method, test data demonstrating the accuracy and precision and drawings of any special equipment required.

6.5 Submission of alternative quality conformance provisions. All contractor proposed alternative quality conformance provisions will be submitted to the Government for evaluation/approval by the technical activity responsible for the preparation of this specification.

6.6 Subject term (key word) listing.

Cover
Packing
Pallet

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 8140-A987)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarif requirements on current contracts. Comments submitted on this form do not constitute or imply auth waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1 DOCUMENT NUMBER MIL-C-71165 (AR)	2 DOCUMENT DATE (YYMMDD) 930615

3 DOCUMENT TITLE: CONTAINER, AMMUNITION, LIGHTWEIGHT METAL FOR TOW 2A GUIDED

4 NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets if needed.)*

5 REASON FOR RECOMMENDATION

6 SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8 PREPARING ACTIVITY

a. NAME U.S ARMY ARDEC STANDARDIZATION OFFICE	b. TELEPHONE (Include Area Code) (1) Commercial: 201-724-6675 (2) AUTOVON: DSN-880-667
c. ADDRESS (Include Zip Code) ATTN: SMCAR-BAC-S PICATINNY ARSENAL, NJ 07806-5000	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTAC Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-346 Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil - Downloaded: 2026-10-26T04:34:3
Check the source to verify that this is the current version before use.