INCH - POUND

MIL-W-71125(AR)
16 March 1992

MILITARY SPECIFICATION

WOOD PRESERVATIVES: WATERBORNE OR WATER REDUCIBLE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers ready-to-use aqueous solutions, dispersions or emulsions for preservative treatment of wood by nonpressure methods (see 6.1).

1.2 Classification. The waterborne wood preservatives covered by this specification shall be of the following compositions:

Composition E - Zn naphthenate
Composition F - Cu naphthenate
Composition G - Copper-8-quinolinolate

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in this specification. (see 6.2)

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, U.S. Army ARDEC, ATTN: SMCAR-BAC-S, Picatinny Arsenal, New Jersey 07806-5000 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8030

DISTRIBUTION STATEMENT A. Approved for public release: distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-C-96 - Can, Metal, 28 Gage and Lighter.
PPP-D-729 - Drums, Shipping and Storage, Steel, 55-Gallon (208 Liters).
PPP-P-704 - Pails, Metal: (Shipping, Steel, 1 through 12 Gallon).
TT-P-25 - Primer Coating, Exterior Undercoat for Wood, Ready-mixed, White and Tints.

MILITARY

MIL-B-2427 - Box, Ammunition Packing: Wood, Nailed.
MIL B-46506 - Boxes, Ammunition Packing Wood, Wirebound.

STANDARDS

FEDERAL

FED-STD-123 - Marking for Shipment (Civil Agencies).
FED-STD-141 - Paint, Varnish, Lacquer and Related Materials, Methods of Inspection, Sampling and Testing.
FED-STD-313 - Material Safety Data Sheets, Preparation and the Submission of.

MILITARY

MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-731 - Quality of Wood Members for Containers and Pallets.

(Unless otherwise indicated, copies of federal and military specifications are available from the Naval Publications and Forms Center, Standardization Document Order Desk, Bldg. 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

CFR 49, PART 107 et al.

(Copies of the CFR are available from the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 02402-0001)

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:31Z
Check the source to verify that this is the currentversion before use.

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)
ASTM D775-1980 - Drop Test for Loaded Boxes, Test Method for.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1137.)

AMERICAN WOOD-PRESERVERS' ASSOCIATION (AWPA) STANDARDS

A4 - Standard Methods for Sampling Wood Preservatives.
A5 - Standard Methods for Analysis of Oil-Borne Preservatives.
A9 - Standard Method for Analysis of Treated Wood and Treating Solutions by X-ray Spectroscopy.
A11 - Standard Method for Analysis of Treated Wood and Treating Solutions by Atomic Absorption Spectroscopy.

(Application for copies should be addressed to the American Wood-Preservers' Association, P.O. Box 849, Stephensville, MD 21666.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INCORPORATED AGENT
National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Association, Inc., Tariff Order Section, 1616 P Street, N.W. Washington, DC 20036.)

UNIFORM CLASSIFICATION COMMITTEE, AGENT
Uniform Freight Classification.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Qualification. Wood preservatives furnished under this specification shall be products which are authorized by the qualifying activity for listing on the applicable qualified products list at the time of the award of contract (see 4.2 and 6.4).

3.1.1 Requalification. Any changes in the formulation or processing of a qualified product will necessitate its requalification. Wood preservatives supplied under contract shall be identical, within manufacturing tolerances, to the approved qualification sample. The Qualifying activity, may at its discretion, request complete requalification testing or require only partial requalification in order to determine the significance, impact and acceptability of any proposed formulation change, manufacturing process or change in manufacturing location.

3.2 Preservative effectiveness. In a single application, all compositions shall provide wood packaging materials a minimum of two years protection during uncontrolled exposure, out of ground contact, in temperate and tropical environments (see 4.6.1).

3.3 Homogeneity and stability. The treating mixture shall be sufficiently stable to maintain during the treating operation, a concentration of active ingredient that does not vary more than 10° from top 1/10 to bottom 1/10 of a given manufacturing batch.

3.4 Color. Solutions shall not unduly change the color of the wood to which they are applied. It is recognized that Compositions F and G impart a green color to the wood (see 4.6.2).

3.5 Solvents. The principle carrier for treating solutions shall be water. Where emulsions or dispersions of organic materials in water are used, the "organic solvent" is defined as the solvent for the organic wood preservative. A "dispersing agent" is defined as the substance, when mixed with the preservative concentrate, causes the preservative concentrate to disperse easily when mixed with water. Organic solvents shall be sufficiently pure so that contaminates do not cause objectionable odors or irritation.

3.6 Preservative chemicals.

3.6.1 Registration. All preservatives shall be registered with the Environmental Protection Agency (EPA) and must be used in accordance with the EPA - label.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

3.6.2 Composition E. The treating solution containing Zn naphthenate shall be an emulsion of Zn naphthenate and shall contain not less than 3 %, by weight, of Zn as determined by methods described in 4.6.3.1.

3.6.3 Composition F. The treating solution containing Cu naphthenate shall be either an aqueous solution, dispersion or emulsion of Cu naphthenate and shall contain not less than 2 %, by weight, of Cu as determined by methods described in 4.6.3.2.

3.6.4 Composition G. The treating solution containing Cu-8-quinolinolate shall be an aqueous solution of dodecylbenzene sulfonic acid (DDBSA)-solubilized Cu-8-quinolinolate and shall contain not less than 1.8 % copper-8-quinolinolate, by weight, as determined by methods described in 4.6.3.3.

3.7 Paintability. The treating solution shall pass the test for drying and adhesion of paints described in 4.6.4.

3.8 Drying time. When tested in accordance with 4.6.4, the surface of the treated wood shall be free from tack within 72 hours after treatment.

3.9 Corrosion. Wood preservatives shall have no adverse effect, such as pitting or oxidation on hardware utilized in packaging design.

3.10 Odor. Wood preservatives shall be free of disagreeable or offensive odors.

3.11 Toxicity. The material shall have no adverse effect on the health of personnel when used for its intended purpose. Questions pertinent to this effect shall be referred by the contracting activity to the appropriate departmental medical service who will act as adviser to the contracting agency. The contractor shall furnish the qualifying activity (see 6.4) with all the information necessary to evaluate the safety of the product (see 4.8). This shall include safety data sheets in accordance with FED-STD-313.

4. QUALITY ASSURANCE PROVISIONS

4..1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to the prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become part of the contractor's overall inspection system or quality program. The absence of inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission to known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.2 Classification of inspection. The inspection requirements specified herein are as follows:

a. Qualification inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 Qualification inspections. Qualification inspection shall consists of tests for all of the requirements specified in section 3.

4.3.1 Qualification samples. The qualification sample shall consist of two one-gallon containers of the finished product. The product sample shall be accompanied by data response to 4.8. Additional sampling procedures will be in accordance with AWPA A4. Unless otherwise specified, sample and data shall be furnished to the activity identified in 6.4.

4.3.2 Inspection of packaging. An inspection shall be made to determine that the preservative, packaging and packing, conforms to the requirements of Section 5 of this specification. Defects shall be scored in accordance with Table II. For examination of interior packaging the sample unit shall be one shipping container fully prepared for delivery, selected at random just prior to the closing operations. Defects of closure listed shall be examined on shipping container fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot.

4.4 Quality conformance inspection. Quality conformance inspection shall be performed in accordance with the provisions set forth herein. The characteristics shown in Table I and requirements for packaging and marking set forth in Section 5 shall constitute minimum inspections to be performed by contractor prior to Government acceptance or rejection by item or lot.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

Table I. Conformance certifications

Characteristic	Certification paragraph
Homogeneity	3.3
Solvents	3.5
Registration	3.6.1
Corrosion	3.9
Odor	3.10

Table II. Conformance inspection.

Inspection	Requirement Paragraph	Test Paragraph
Color	3.4	4.6.2
Preservative chemicals	3.6	4.6.3
Composition E	3.6.2	4.6.3.1
Composition F	3.6.3	4.6.3.2
Composition G	3.6.4	4.6.3.3
Paintability	3.7	4.6.4
Drying Time	3.8	4.6.4
Toxicity	3.11	4.8

4.4.1 Certifications. Certifications for characteristics specified in Table I shall include test data and results as applicable. Certification shall be provided prior to performing inspections in accordance with Table II and shall suffice for Government acceptance throughout a contract, providing the materials, manufacturing processes, and techniques used to produce the items for which certification was issued have not been changed or revised. Any and all changes will require a new certification from the contractor. Certification does not relieve the contractor of the responsibility for inspection of characteristics, and recording data and results therefrom. Recorded data results shall be made available to the Government upon request. When defects or inferior quality is detected, and the Government deems a material analysis necessary, the contractor will be required to submit data, samples, or specimens to the contracting officer for analysis and approval.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

4.5 Toxicological product formulations. The contractor shall have the toxicological product formulations and associated information available for review by the contracting activity to evaluate the safety of the material for the proposed use.

4.6 Tests.

4.6.1 Preservative effectiveness. (qualification only) Treated boxes comprised of softwoods, hardwoods or composite, wood-based materials, after the equivalent of two years exposure under tropical rainforest conditions, (see 6.5.6) shall be able to withstand damage which can be caused by dropping as evidenced by surviving a 3 foot drop test without damage and a 7 foot drop test without spillage of contents when tested in accordance with ASTM D775, Objective A, modified to the extent that drop testing can be performed under actual conditions of field exposure. Packaging materials chosen for the test shall be representative of materials and designs used for packaging ammunition. As a minimum, field evaluations shall include wirebound packaging fabricated in accordance with MIL-B-46506 and nailed packaging fabricated in accordance with MIL-B-2427 or equivalent. A minimum of two species of hardwood and softwood included within each Group I through Group IV categories of wood in accordance with MIL-STD-731 other than white oak, black locust, and orange osage must be represented in the field evaluations. Southern pine black/red gum and red oak must be included within the above selection. Any package design included within MIL-B-2427 or MIL-B-46506 is acceptable for this evaluation provided procedures prescribed in ASTM D775 are followed.

4.6.2 Color. The solution shall be tested in accordance with test method 4248 of FED-STD-141.

4.6.3 Preservative chemicals. All preservatives shall be certified as registered with the EPA.

4.6.3.1 Composition E, zinc naphthenate. The determination of zinc shall be made in accordance with AWPA A9 or AWPA A11.

4.6.3.2 Composition F, copper naphthenate. The determination of copper shall be in accordance with either AWPA A5, AWPA A9 or AWPA A11.

4.6.3.3 Composition G, copper-8-quinolinolate. The determination of copper shall be made in accordance with either AWPA A5, AWPA A9 or AWPA A11.

4.6.4 Paintability and drying time. Unless otherwise specified, the wood species for these tests shall be ponderosa pine and the test paint shall conform to the requirements of TT-P-25. (see 6.5.5)

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:31Z
Check the source to verify that this is the current version before use.

4.6.4.1 Test procedure. Prepare three pairs of wood test specimens, 2 1/2 inches wide and 12 inches long, with a thickness of from 1/2 to 1 inch. The specimen shall be of flat-grain material, containing significant proportions of sapwood and heartwood, dried to a moisture content not to exceed 20%, and surfaced four sides. Each pair shall consist of two end-matched specimens from the same board, and each of three pairs shall be cut from different boards. One end-matched specimen from each pair shall be used as a control and painted without treatment. The matching specimen from each pair shall be immersed in the treating solution for 3 minutes. The three treated specimens shall then be set in a flat position supported on glass rods and allowed to dry for 72 hours at room temperature in circulating air. The treated specimens shall then be examined for compliance with 3.8. To the entire top surface of the three treated and the three matching untreated control specimens, apply one brush coating (3 wet mils) of the primer selected to that conforming to the requirements of TT-P-25. Allow the coating to dry in a sunlit location, preferably exterior, free of dew or rainfall for 48 hours. The treated and untreated specimens shall be observed and compared for paint drying, discoloration and adhesion. When subjected to a cheese cloth covered thumbprint, twist, (approximately 180°) under pressure of approximately 10 pounds (this can be determined with a 10 pound weight on torsion balance or platform scales), the tackiness and adhesion of the paint coating on the treated specimens shall compare favorably with that applied to the matching untreated control specimens. The color and appearance of the coatings and the treated surfaces shall also compare favorably with those on the untreated controls.

4.7 Lot.

4.7.1 Production lot. A production lot shall consist of an indefinite quantity of a homogeneous mixture of product offered for acceptance in a single, isolated container, or manufactured in a single paint run, through the same processing equipment, with no change in the ingredient materials in a 24 hour period.

4.7.2 Packaged lot. A packaged lot shall consist of an indefinite number of unit containers of identical size and type, ordered for acceptance at one time, and filled with a homogeneous mixture of product manufactured in a single plant run, through the same processing equipment, in a 24 hour period.

4.8 Toxicity. The contractor shall furnish the qualifying activity (see 6.4) safety data sheets conforming to FED-STD-313 along with all the information necessary to evaluate the safety of the product. At the discretion of the qualifying activity, such information shall be furnished in one of the following forms:

a. A complete listing of the constituent materials, including an infra-red profile giving percentage of composition and using standard chemical nomenclature. (This is the simplest and most direct method. In most instances, it will completely satisfy the requirement for information.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

b. The results of toxicological testing of a scope and quality acceptable to the qualifying activity.

c. Some other form acceptable to the contractor and the qualifying activity.

All information furnished by the contractor in connection with the evaluation of toxicity shall be signed by a responsible official of the contracting firm. Such information shall be held in strict confidence by the qualifying activity and shall not be divulged to other contractors.

5. PACKAGING

5.1 Packaging requirements. Packaging shall be Level B or C, as specified in the acquisition documents (see 6.2) and shall comply with Department of Transportation (DOT) regulations as described in 49 CFR, PART 107 et al.

5.1.1 Level A. Not applicable.

5.1.2 Level B. The preservative shall be furnished in 1-gallon cans conforming to PPP-C-96, Type V, Class 2; 5-gallon steel containers conforming to PPP-P-704, Type I, Class 1, 2, 3, 4, 5, or 8; or in 55-gallon steel drums conforming to PPP-D-729, Type I or II (see 6.2); or in 55-gallon molded polyethylene drums conforming to 49 CFR 178.19, Specification 34. The 5-gallon pails shall be furnished with pour spouts.

5.1.3 Level C. The preservative shall be furnished in 1-gallon cans, 5-gallon steel containers or in 55-gallon steel or molded polyethylene drums normally furnished for commercial practice (see 6.2). Bulk quantities of the preservative shall be furnished by truck in a 397 stainless steel tank.

5.2 Packing. Packing shall be Levels B or C, as specified in the acquisition documents (see 6.2) and shall comply with Department of Transportation (DOT) regulations as described in 49 CFR, PART 107 et al.

5.2.1 Level A. Not applicable.

5.2.2 Level B. The filled 1-gallon cans shall be packed in quantities of 4 in a close-fitting box conforming to PPP-B-636, class weather-resistant. Closure shall be in accordance with the appendix of the box specification. The 5 and 55-gallon containers do not require over-packing.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

5.2.3 Level C. The preservative shall be packed in a manner which will insure arrival at destination in satisfactory condition and which will be acceptable to the carrier at the lowest rates. Containers and packing shall comply with National Freight Classification or Uniform Freight Classification. The preservative shall be furnished in 1-gallon cans, 5-gallon steel pails, or 55-gallon steel drums, as specified (see 6.2). Bulk shipments, by tank truck, shall be transported in a manner which will ensure arrival in satisfactory condition.

5.3 Marking.

5.3.1 Civil agencies. In addition to any special markings required by the contract order, shipping containers shall be marked in accordance with FED-STD-123.

5.3.2 Military agencies. In addition to any special markings required by the contract order, shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful but is not mandatory.)

6.1 Intended use.

6.1.1 Treatments. The solutions covered by this specification are intended primarily for the treatment of wood pallets, containers and packing materials. Such treatments provide a moderate degree of resistance to fungi when applied to wood products that are exposed intermittently to rain wetting. They do not provide adequate protection to wood under severe exposure conditions such as those entailing ground contact or prevalent, extensive periods of wetting.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Composition desired (see 1.2).
c. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
d. Selection of applicable levels of packaging and packing required (see 5.1 and 5.2).
e. Size of container required (see 5.2.1. 5.2.2 and 5.2.3).
f. Ordering data must state sampling plan at the time of contract. The suggested inspection level is S-2 with an AQL of 4.0 defects per hundred units.
g. Paintability (see 3.7, 4.6.4 and 6.5.5)

6.3 Basis of purchase. The material should be purchased by volume, the unit being a U.S. gallon at 60° F. or by weight, the unit being one pound avoirdupois. For the purpose of awarding contract, comparisons of cost should be made on the basis of the treating solution prepared for use according to the directions of the contractor.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

6.4 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified, for inclusion in the Qualified Products List QPL 71125, whether or not such products have actually been so listed by that date. The intention of the contractors is called to those requirements, and manufacturers are urged to arrange to have the products that they propose to offer the Federal Government tested for qualification in order that they may be eligible to be awarded contracts of purchase orders for the products covered by this specification. The activity responsible for the Qualified Products List is the U.S. Army Armament Research, Development and Engineering Center, ATTN: SMCAR-BAC-S, Picatinny Arsenal, NJ 07806-5000 and information pertaining to qualification may be obtained from that activity.

6.4.1 Qualification of chemicals. Additional chemicals will be considered qualified upon verification by a US Government laboratory, or by any commercial laboratory acceptable to the US Government, that they have field effectiveness described in 4.6.1, upon demonstration that they meet the health and safety criteria defined by the Army Environmental Hygiene Agency (AEHA), and upon demonstration that they do not adversely effect strength of fasteners. Preliminary assessment of candidate preservatives may be accomplished through use of small wood samples that represent the wood species used in packaging if those samples are exposed in environments and in test configurations which stimulate the exposure hazards that occur with full-size packages. Such experimentation should allow statistical comparison to candidate systems with preservatives that are already qualified.

6.5 Precautionary measures.

6.5.1 Work environment. Workers should read, become familiar with, and follow instructions on EPA-approved label. Workers should use the protective clothing and devices as required by the label.

6.5.2 Freezing. Protect treating solutions from freezing. Freezing and thawing may deteriorate the stability of some waterbased preservatives.

6.5.3 Stirring. Before use, it may be necessary to thoroughly agitate water-repellent preservatives.

6.5.4 Corrosivity. Preservative solutions vary in corrosivity to metals. Follow manufacturer's recommendations for choice of materials to use in treating facilities.

6.5.5 Paintability. Since paintability of a treated wood surface will vary with different species of wood, paint systems, and conditions related to specific products, users are urged to modify paint requirements for acceptability to specific needs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

6.5.6 Tropical rainforest. The most severe biological hazards for these wood items will occur in tropical rainforests, that is, forest ecosystems that occur in humid tropics where rainfall is abundant and distributed throughout the year to the extent that the canopy is continuous throughout the year. There is no pronounced dry season with canopies opened by deciduous trees. The forest is comprised of numerous tree species, numerous species or epiphytic plants and large wood climbers. Plant species are concentrated in the canopy and a high proportion of mammals and reptiles are arboreal. The entire year is frost-free, (a 365 day growing season), mean annual rainfall is in excess of 90 inches mean annual temperature is in excess of 75° F, and the mean annual relative humidity is in excess of 70%. Actual testing may be accomplished through environmental chamber or at actual rainforest geographic location. Environmental chamber utilization or choice of geographic location is subject to the review and approval of the qualifying activity.

6.6 Subject term (key word) listing.

Dispersion
Emulsion
Hardwoods
Softwoods
Solution, Aqueous
Solvent, organic

Custodians
Army - AR

Preparing activity:
Army - AR

(Project 8030-0557)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:31Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-W-71125	2. DOCUMENT DATE (YYMMDD) 16 March 1992

3. DOCUMENT TITLE
WOOD PRESERVATIVES: WATERBORNE OR WATER REDUCIBLE

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets if needed.)

5. REASON FOR RECOMMENDATION

[redacted]

6. PREPARING ACTIVITY

a. NAME
PAUL TREMBLAY

b. TELEPHONE (Include Area Code)
(1) Commercial: 201-724 6671
(2) AUTOVON: DSN 880-6671

c. ADDRESS (Include Zip Code)
Commander
U. S. Army ARDEC
ATTN: SMCAR-BAC-S
Picatinny Arsenal, N. J. 07806-5000

IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:
Defense Quality and Standardization Office
5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466
Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:31Z
Check the source to verify that this is the current version before use.