A-A-54419
28 June 1991

COMMERCIAL ITEM DESCRIPTION

GAUZE, PETROLATUM

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for Federal Specification DDD-G-138B, which is cancelled.

Salient Characteristics:

Shall be sterile, petrolatum impregnated gauze dressings suitable for medical and surgical use. The dressings shall be sterile when tested in accordance with the USP.

The impregnated dressings shall be of the following sizes and shall contain the following minimum weight of petrolatum after removal of the dressings from their immediate container when determined in accordance with Petrolatum Gauze, USP.

SIZE	UNFOLDED DRESSING (INCHES) LENGTH	WIDTH	MINIMUM WEIGHT OF PETROLATUM (GRAMS)
1	36 ± 3	3 $^{+1/8}_{-1/8}$	9.0
2	18 + 3 1-1/2	3 ± 1/8	4.5

Gauze shall be Absorbent Gauze, USP, Type I. Petrolatum shall be White Petrolatum, USP, except that the melting point shall be 125° to 140°F (51° to 60°C), and the consistency shall be 150 to 240 as determined by a penetrometer. Petrolatum shall be evenly and uniformly distributed throughout the gauze. Impregnated gauze strips shall be accordian pleated in a stepped-backed style with approximate 1 1/2 inch folds stepped back approximately 1/8 inch each step to permit easy dispensing of the dressing. The dressings shall be substantially free of lint and ravelings and the edges of the gauze shall be substantially even.

AMSC\NA FSC 6510

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Residual Ethylene Oxide. If ethylene oxide is used as a sterilization agent, the finished gauze shall contain not more than 250 ppm of Ethylene Oxide, 250 ppm, Ethylene Chlorohydrine and 5000 ppm Ethylene Glycol. Petrolatum Gauze shall be tested by methods 54, 55, or 56 published in the Federal Register, Volume 43, No. 122, Part V, 22 June 1978, Ethylene Oxide, Ethylene Chlorohydrine, and Ethylene Glycol, Proposed Maximum Limits and Maximum Levels of Exposure. Contractor shall satisfactorily demonstrate that he has the capability to meet specification requirements for residual testing for the product. A satisfactory test report from a recognized independent testing laboratory shall be considered as an acceptable means for demonstrating his capability. Note: A manufacturer who has demonstrated his ability to use Ethylene Oxide sterilization without excessive residuals present in the final product may confirm his sterilization method on the basis of an approved auditing schedule in lieu of lot-by-lot testing. Prior approval shall be obtained from the contracting officer.

Workmanship. The dressings shall be free from defects which detract from their appearance or impair their serviceability.

Unit. Package (PG). Each dressing shall be individually packaged in a peel-open type container capable of maintaining sterility of contents unless package is damaged or opened. One package containing 12 individually packaged dressings of one size only, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as specified herein. Unit of product for examination purposes shall be one dressing. Sampling shall be Inpsection level II with an acceptable quality level (AQL) of 2.5 (percent defective).

Examination. Examination shall be conducted to determine compliance with specification requirements.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as specified herein. Unit of product for test purposes shall be one dressing. Sampling shall be Inspection level S-1 with an AQL of 2.5 (percent defective).

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Metric Products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerance specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerance specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document:

NSN	ITEM IDENTIFICATION	SIZE
6510-00-202-0800	GAUZE, PETROLATUM, 3 By 18 Inches, 12s	2
6510-01-112-6414	GAUZE, PETROLATUM, 3 By 36 Inches, 12s	1

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Ordering data. Intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order.

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

PREPARING ACTIVITY:
DoD - MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITY:

VA-OSS
PHS
FDA-MPQAS

PGC 05087

Project No. 6510-0777

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	A-A-54419	28 JUN 91

3. DOCUMENT TITLE: GAUZE, PETROLATUM

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON
Defense Personnel Support Center	(215)737-2870	444-2870
ADDRESS (Include Zip Code) ATTN: DPSC-MSE 2800 S. 20th Street Philadelphia, PA 19101	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89 — Previous editions are obsolete. — 198-290

Source: https://assist.dla.mil - Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.