COMMERCIAL ITEM DESCRIPTION

ABRASIVE, DENTAL (Paste, Aluminum Oxide)

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for Federal Specification P-A-0086b (DSA-DM).

This commercial item description covers a dental abrasive paste suitable for use as an abrading and polishing agent for plastic teeth and cast metal restorations.

Salient characteristics:

Material. The paste shall consist essentially of aluminum oxide and zinc oxide, incorporated in a water-insoluble base such as petrolatum. The base may contain modifiers, preservatives, color and flavor additives.

The paste shall contain no harmful ingredients, and shall be pleasant to the taste. The color of the paste shall be light gray. Materials shall be of the highest quality throughout and suitable in all respects for the intended purpose. Any ingredients in the paste which are not included in the Pharmacopeia of the United States (USP) or National Formulary (NF) shall be of a quality suitable for pharmaceutical use.

The paste shall be an all purpose paste for intra-oral and extra-oral milling, finishing, and polishing of plastic teeth and cast metal restorations. The paste shall be removable by brushing with soap and warm water.

Net weight. The net weight of paste in the tube shall be a minimum of 3.0 ounces (85 grams) when tested as specified below.

Particle size. The particle size of aluminum oxide in the paste shall be 150 mesh when tested as specified below.

Consistency. The paste shall not flow or spread more than 1/64 inch under compression when tested as specified below.

AMSC N/A FSC 6520
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Instructions for use. Adequate and accurate instructions for specific uses and technique for use of the abrasive paste shall be furnished with each unit of issue.

Immediate container. The immediate container for the paste shall be a collapsible metal tube with screw cap closure.

Marking. The lot number and date of manufacture shall be marked on the immediate container and on the unit package (box). The legend "STORE AT CONTROLLED ROOM TEMPERATURE (59°-86°F)" shall be marked on the immediate container and unit package.

Delivery schedule. Not more than 3 months shall have elapsed from the date of manufacture of the paste to the date of delivery to the Government.

Workmanship. The paste and the immediate container shall be clean and free from defects which detract from their appearance or impair their serviceability.

Unit. Tube (TU). One tube containing 3.0 ounces of abrasive paste constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after the delivery of the supplies to which such records relate.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Sampling for inspection. Sampling for inspection shall be conducted in accordance with MIL-STD-105. Where feasible, the same sample shall be used for the determination of two or more inspection characteristics. The unit of product for inspection purposes shall be one tube of abrasive paste. Unless otherwise specified, sampling for examination shall be conducted at inspection level II, AQL 2.5, and sampling for tests shall be conducted at inspection level S-1, AQL 1.0.

Examination. The abrasive paste shall be examined to determine compliance with specification requirements.

Tests. Tests shall be conducted to determine compliance with specification requirements.

Net weight. The net weight of paste in the tube shall be determined using a suitable balance.

Particle size. The particle size of aluminum oxide in the paste shall be determined in accordance with Table 2 of ANSI Standard B74.12-1976.

Consistency. The consistency test shall be conducted at a temperature of 23.0°C ± 2°C and a relative humidity of 50 ± 10 percent. Materials and test equipment shall be conditioned in the test room for not less than 10 hours prior to testing. Aluminum oxide paste (0.60 ml ± 0.02 ml) shall be dispensed onto a glass plate with a level surface. Place a quarter on top of the paste and compress the paste. After 5 minutes observe if the paste has spread more than 1/64 inch beyond the coin.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch/pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met. If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable. The contracting officer has the option of accepting or rejecting the product.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Number is covered by this document:

National Stock Number	Item Identification
6520-00-500-0400	ABRASIVE, DENTAL, PASTE Aluminum Oxide, 3 ounces (85 grams)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Ordering data. Intermediate/exterior package quantities, labeling, and marking must be as specified in the contract and/or order.

MILITARY INTERESTS:

Custodians:

Army-MD
Navy-MS
Air Force-03

Preparing Activity:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

Project No. 6520-2479
Location: PL/Abrasive

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I. RECOMMEND A CHANGE:	1. DOCUMENT NUMBER A-A-54426	2. DOCUMENT DATE (YYMMDD) 17 June 1991

3. DOCUMENT TITLE
ABRASIVE, DENTAL (Paste, Aluminum Oxide)

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	e. DATE SUBMITTED (YYMMDD)

7. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON
Defense Personnel Support Center	(215)737-2870	444-2870
c. ADDRESS (Include Zip Code) ATTN: DPSC-MSTE 2800 S. 20th Street Philadelphia, PA 19101	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT Defense Quality and Standardization Office 5203 Leesburg Pike Suite 1403 Falls Church VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89 — Previous editions are obsolete — 98/290

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.