A-A-30018A
April 30, 1982
SUPERSEDING
A-A-30018
September 8, 1981

Commercial Item Description

Prosthetic Socks

The General Services Administration has authorized the use of this Commercial Item Description.

Salient Characteristics. Prosthetic socks (stump socks) shall be knitted in a circular (tubular) fashion, with a smooth graduation of diameter (or width) from toe to top. The socks shall possess all the characteristics that contribute to comfort and durability having adequate elasticity and allowable shrinkage. Within the limits of suppliers equipment, the socks shall be manufactured free of hard ends, knots, square pockets and open stitches.

Size of Sock. Except for Type IV, size of socks shall be determined by laying socks flat for length, for width at top and the width at approximately two (2) inches from the end of the toe, (or approximately 1/2 of the toe width from end of toe). Leg sock sizes 0-6 are increased by 1" in width at the top per each additional size, and toe width by increments of 1/2" to 2" per size depending on sock length, and length 10-34" are increased by 2" increments. Arm sock sizes 0-1 are increased by 1-1/2" increment in width at the top, and 1/2" increment in toe width. In both sizes, lengths 6-22" are increased by 2" increments. VA sizes are standard among all manufacturers and offers are solicited per VA size.

Type I - Cotton socks shall be of domestic spun yarn carded or carded and combed, 100% cotton with 1/2% tolerance. To the greatest degree possible, socks shall have adequate stretch and/or elasticity and allowable shrinkage (maximum 10% in length and 5% in width) when laundered in accordance with manufacturer's instructions.

Type II - Virgin wool socks shall be 100% wool with 1/2% tolerance. Socks shall be of strands of 64's, or finer quality fibers. Socks shall be knitted using 3, 4, 5, 6 and/or 7 strands with yarn sizes not larger than 16 nor smaller than 18 (worsted method) or other to provide comparable weight or thickness. To the greatest degree possible, socks shall have adequate stretch and/or elasticity and allowable shrinkage (maximum 10% in length and 5% in width) when laundered in accordance with manufacturer's instructions.

Type III - Blend socks to be of virgin wool and synthetic fibers. Socks shall be knitted using 3, 4, 5, 6 and/or 7 strands with yarn sizes not larger than 16 nor smaller than 18, (worsted method) or other to provide comparable weight or thickness. To the greatest degree possible, socks shall have adequate stretch and/or elasticity and allowable shrinkage (maximum 5% in length and 5% in width) when laundered in accordance with manufacturer's instructions.

Type IV - Orlon Acrylic/Lycra Spandex socks are to be white, fleeced inside and out, and suitable for immediate post-operative use. Fiber composition shall be 95% ± 2% acrylic and 5% ± 2% spandex.

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description, and that the product conforms to the producer's own drawings, specifications, standards and quality assurance practices and is the same product sold in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

FSC 6515

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:35Z
Check the source to verify that this is the current version before use.

Regulatory Requirements.

Recovered Materials. Offerors/contractors are encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practical.

Federal Food, Drug and Cosmetic Act. The offeror/contractor shall comply, and be responsible for compliance by their subcontractors/suppliers, with the requirements of cited Act and regulations promulgated thereunder, and the requirements of all other applicable Federal and State statutes and regulations, as appropriate.

Packaging and Marking. Except for Type IV, stump socks are to be packaged individually or three to a package. Six individually packaged socks or two packages of three socks, each of the same size and ply, shall be tied with suitable string or rubber bands encircling both width and length. Each package will be labeled or noted to indicate the size number, length in inches, width in inches at the top and the toe, the ply and type material (cotton, wool, synthetic yarns). Instructions for proper care and laundering of the socks will be included in or on each package. The flap of each package will be secured in such a manner as to permit inspection of contents and resealing without damage to the contents or destroying the package. Type IV stump socks shall be packaged in a manner appropriate for storage, handling, and use.

Test Methods. Test methods include: ASTM D 231, ASTM D 1059, AATCC 20, AATCC 150, AATCC 135 1A and 2A.

MILITARY INTERESTS:

Military Coordinating Activity:

DoD-MB

Agent:

DLA-DM

Custodians:

Army-MD
Navy-MS
Air Force-03

REVIEW ACTIVITY:

DMSSO-SD

PREPARING ACTIVITY:

VA-OSS VAMKC (904C)
Agent VA-OSS VACO (93C)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:35Z
Check the source to verify that this is the current version before use.