MIL-R-45036D(MR)
AMENDMENT 1
3 August 1983

MILITARY SPECIFICATION

RUBBER, HARD (EBONITE), NATURAL OR SYNTHETIC, SHEET, STRIP, ROD, TUBING, AND MOLDED PARTS

This amendment forms a part of Military Specification MIL-R-45036(MR), dated 3 August 1983, and is approved for use by the Army Materials and Mechanics Research Center, Department of the Army and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

Para 2.1, after line 9: Add "MIL-STD-810 - Environmental Test Methods".

PAGE 2

Para 2.2, line 7: Delete "of Electrical" and substitute "of Solid Electrical".

Para 2.2, line 14: Delete "Under Load" and substitute "Under Flexural Load".

Para 2.2, line 15: Delete title and substitute: "Test for Durometer Hardness - Rubber Property".

After contents of paragraph 2.2, add the following paragraph: "2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence."

Para 3.1, Delete contents of paragraph and substitute: "The material shall be natural or synthetic rubber or a mixture thereof, or recycled or reclaimed rubber. Material shall be suitably cross-linked to produce the physical properties in accordance with this specification."

PAGE 10 AND 11

Delete paragraphs 4.6.2.1.1 and 4.6.2.1.2 and substitute: "4.6.2.1.1 Solar radiation. Solar radiation (sunshine) shall be conducted in accordance with MIL-STD-810, Method 505.1 - procedure 1, for 200 hours at room temperature [23 $\pm$ 2°C (73.4 $\pm$ 3.6°F)]."

Custodian:
Army - MR

Preparing activity:
Army - MR

Review activities:
Army - AT, AV, MI, ME
DLA - GS

Project No. 9320-A428

User activities:
Army - ER

/ FSC 9320 /

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:15Z
Check the source to verify that this is the current version before use.