INCH-POUND

MIL-B-85667/12
AMENDMENT 1
31 AUGUST 1998

MILITARY SPECIFICATION SHEET

BOLT, SLEEVE, 100° PROTRUDING FLUSH HEAD, STRAIGHT SHANK,
CRES 304 SLEEVE, TITANIUM ALLOY PIN, 95 KSI Fsu, 160 KSI Ftu

This amendment forms a part of Military Specification MIL-B-85667/12, dated 28 January 1991, and is approved for use by all Departments and Agencies of the Department of Defense.

Page 1

5.2 Sleeve. Delete entire paragraph and substitute: "Sleeve material shall be corrosion resistant steel, AISI 304 (UNS S30400), in accordance with MIL-T-8504 (chemistry only) or ASTM A269 (chemistry only)."

Page 3

9. Lubricants. End of last sentence, add "or equivalent." after "...with MIL-L-87132."

Page 5

TABLE II. Mechanical Properties.

Delete: Values under column headings for Ultimate Tensile Strength, Thread Area, and Fatigue Test Loading, and substitute the following:

Dia Dash Number	Ultimate Tensile Strength Lbs-Min (b)	Thread Area In^2 (b)		Fatigue Test Loading Lbs +/- 2% (c)	
				Max	Min
-3	3,620	.0226		1,450	145
-4	6,470	.0404		2,590	259
-5	10,200	.0640		4,080	408
-6	15,200	.0951		6,080	608
-7	20,600	.1288		8,240	824
-8	27,500	.1717		11,000	1100
-9	34,800	.2176		13,920	1392
-10	43,600	.2724		17,440	1744
-12	63,200	.3953		25,280	2528

Table II, Note c. Delete entire note. Substitute: "Maximum fatigue load is based on 40% of the ultimate tensile strength. Minimum fatigue load is 10% of maximum fatigue load."

Custodians:
Army - AV
Navy - AS
Air Force - 99

Preparing Activity:
DLA-IS

(Project 5306-2054)

AMSC N/A

FSC 5306

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:20Z
Check the source to verify that this is the current version before use.