MIL-S-83315(USAF)
AMENDMENT 2
14 December 1984
SUPERSEDING
AMENDMENT 1
17 October 1972

MILITARY SPECIFICATION

SEALING COMPOUND, ALUMINUM STRUCTURE,
PRESSURE AND WEATHER SEALING, LOW DENSITY

This amendment forms a part of Military Specification MIL-S-83315(USAF), dated 31 March 1971, and is approved for use by the Department of the Air Force and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

Paragraph 2.1, under "SPECIFICATIONS, Military": Add

"MIL-S-7124 — Sealing Compound, Elastomeric, Accelerator Required, Aircraft Structure

MIL-S-8802 — Sealing Compound, Temperature-Resistant, Integral Fuel Tanks and Fuel Cell Cavities, High Adhesion".

PAGE 5

Paragraph 3.5.8, second line, delete "15" and substitute "12."

* Delete Table II in its entirety and substitute:

"TABLE II. Tensile strength, elongation and hardness.

Condition	Tensile strength psi (min)	Elongation percent (min)	Rex hardness points (min)
Control	150	125	45
30 days at 160°F	100	125	40
30 days at 200°F	100	125	40"

* Paragraph 3.5.12, second line, delete "2.0" and substitute "3.0."

Paragraph 3.5.13: Add at the end of first sentence, "and with materials qualified to MIL-S-7124 and MIL-S-8802."

* Paragraph 3.5.13, fourth line, change "15 pounds per inch of width" to "10 pounds per inch of width."

FSC 8030

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.

PAGE 8

Paragraph 4.4.4: Delete "h. Peel strength (Immerse for 3 days)," and substitute:

"h. Peel strength (Immerse for 3 days only and on one primer only that is required by this specification or on a primer that is specified by the procurer and is acceptable to the manufacturer)."

PAGE 12

Figure 1: Change the thickness dimension on the plunger (lower left hand corner of drawing) from ".200 ± .005" to ".250 ± .005."

PAGE 18

Paragraph 4.19: Insert the following after the second sentence: "In addition, six panels, 0.040 by 2.75 by 6 inches of aluminum alloy conforming to QQ-A-250/13 T6 shall be cleaned in accordance with 4.6.1. Two of these panels shall be coated with each of the following materials: A material qualified to MIL-S-7124, a dichromate cured material qualified to MIL-S-8802, and a manganese dioxide cured material qualified to MIL-S-8802. The sealants shall be applied as a continuous layer 0.125 ± 0.015 inch thick on 5 inches of the panels and cured at standard conditions (see 4.6.4) for 14 days."

* The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the intire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Air Force - 20

Preparing activity:
Air Force - 20

(Project 8030-F039)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:48Z
Check the source to verify that this is the current version before use.